INCH-POUND

MIL-W-22759/31
AMENDMENT 1
31 December 1990

MILITARY SPECIFICATION SHEET

WIRE, ELECTRICAL, FLUOROPOLYMER-INSULATED, EXTRUDED TFE, POLYIMIDE COATED, NICKEL-COATED HIGH STRENGTH COPPER ALLOY CONDUCTOR, 600 VOLT

This amendment forms a part of Military Specification MIL-W-22759/30, dated 15 June 1976, and is approved for use by all Departments and Agencies of the Department of Defense.

PAGE 1

Delete FSC 6145 and substitute FSC 6145

Add DISTRIBUTION STATEMENT A. at the bottom of page 1.

PAGE 2

Delete and substitute:

Under " Additional requirements"

Low temperature (cold bend):
Bend temperature: -65 ±2°C (-85 ±3.6°F)
Dielectric test, 3000 volts (rms), 60 Hz

Life cycle: Oven temperature, 275 ±2°C (527 ±3.6°F)
Dielectric test, 3000 volts (rms), 60 Hz

Dielectric test after immersion: 3000 volts (rms), 60 Hz

Acid resistance: Dielectric test, 3000 volts (rms), 60 Hz

Conductor strand adhesion - not applicable

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T13:48Z
Check the source to verify that this is the current version before use.

Custodians:
Navy - AS
Air Force - 85

Review activities:
Air Force, 80, 99

User activity:
Air Force - 11

Preparing activity:
Navy - AS

Agent:
DLA - IS

(Project 6145-1152-16)

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T13:48Z
Check the source to verify that this is the current version before use.