
MIL-W-22759/5B
19 July 1974
SUPERSEDING
MIL-W-22759/5A
29 June 1973
See also "Supersession Data" on Page 3

MILITARY SPECIFICATION SHEET

WIRE, ELECTRIC, FLUOROPOLYMER-INSULATED, ABRASION RESISTANT, EXTRUDED TFE, SILVER-COATED COPPER CONDUCTOR, 600-VOLT

This specification is approved for use by all Departments and Agencies of the Department of Defense.

The complete requirements for procuring the wire described herein shall consist of this document and the issue in effect of Specification MIL-W-22759.



TFE-Polytetrafluoroethylene

Note: Outer Surface Must be Smooth, Homogeneous, Virgin TFE With no Mineral Fillers Exposed.

TABLE I. CONSTRUCTION DETAILS

Part No. 1/	Wire size	Stranding (Number of strands X AWG gage of strands)	Diameter of stranded conductor (inches)		Finished wire		
			(min)	(max)	Resistance at 20°C (68°F) (ohms/1000 ft) (max)	Diameter (inches)	Weight (lbs/1000 ft) (max)
M22759/5-24-*	24	19 X 36	.023	.025	24.3	.075 ±.005	6.0
M22759/5-22-*	22	19 X 34	.029	.032	15.1	.085 ±.005	8.0
M22759/5-20-*	20	19 X 32	.037	.040	9.19	.095 ±.005	10.0
M22759/5-18-*	18	19 X 30	.046	.050	5.79	.110 ±.005	14.0
M22759/5-16-*	16	19 X 29	.052	.057	4.52	.125 ±.005	18.0
M22759/5-14-*	14	19 X 27	.065	.072	2.88	.143 ±.007	25.0
M22759/5-12-*	12	(B) 19 X 25	(B) .082	(B) .090	(B) 1.81	.160 ±.007	(B) 34.5
M22759/5-10-*	10	37 X 26	.106	.112	1.19	.179 ±.007	48.0
M22759/5-8-*	8	133 X 29	.158	.169	.658	.248 ±.007	83.7
M22759/5-6-*	6	133 X 27	.198	.213	.418	.300 ±.010	(B) 126.
M22759/5-4-*	4	133 X 25	.250	.268	.264	.355 ±.015	(B) 188.

1/ PART NO.: The asterisks in the part number column, Tables I through III, shall be replaced by color code designators in accordance with MIL-STD-681. Examples: Size 20, white - M22759/5-20-9; white with orange stripe - M22759/5-20-93.

(B) denotes changes

FSC 6145

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T13:44Z
Check the source to verify that this is the current version before use.

TABLE II. PERFORMANCE DETAILS

Part No.	Abrasion resistance (Procedure I)				Bend testing			
					Mandrel diameter (inches) (±3%)		Test load (lbs) (±3%)	
	Resistance (inches of tape) (min) (initial and after immersion)	Weight support bracket	Weight (lbs)	Tension load (lbs)	Life cycle (oven & bend tests) 1/	Cold bend test	Life cycle (oven & bend tests) 1/	Cold bend test
M22759/5-24-*	21	A	1.0	1.0	4.5	3.0	.75	2.0
M22759/5-22-*	24	A	1.0	1.0	4.5	3.0	.75	2.0
M22759/5-20-*	24	A	1.0	1.0	4.5	3.0	.75	2.0
M22759/5-18-*	28	A	1.0	1.0	4.5	3.0	1.00	2.0
M22759/5-16-*	30	A	1.0	2.0	6.5	3.0	1.00	3.0
M22759/5-14-*	24	B	3.0	2.0	6.5	6.0	1.00	3.0
M22759/5-12-*	24	B	3.0	2.0	6.5	6.0	3.00	3.0
M22759/5-10-*	24	B	3.0	2.0	10.0	6.0	3.00	5.0
M22759/5-8-*	34	B	3.0	2.0	10.0	6.0	3.00	5.0
M22759/5-6-*	36	C	3.0	2.0	10.0	6.0	6.00	10.0
M22759/5-4-*	36	C	4.25	2.0	10.0	10.0	6.00	10.0

1/ Also for bend tests after immersion.

ADDITIONAL REQUIREMENTS

TEMPERATURE RATING: 200°C (392°F) max conductor temperature
VOLTAGE RATING: 600 volts (rms) at sea level
SPARK TEST OF PRIMARY INSULATION: Not required
IMPULSE DIELECTRIC TEST: 8.0 kilovolts (peak) 100% test
INSULATION RESISTANCE: 50,000 megohms for 1000 ft (min)
WRAP TEST: "Wrap back" test required; no cracking
Oven temperature: 313 ±2°C (595.4 ±3.6°F)
BLOCKING: 260 ±2°C (500 ±3.6°F)
SHRINKAGE: 0.125 inch max at 313 ±2°C (595.4 ±3.6°F)
WICKING (PROCEDURE I): 1.0% (max) weight increase
LOW TEMPERATURE (COLD BEND):
Bend temperature: -65 ±2°C (-85 ±3.6°F)
Dielectric test, 2500 volts (rms), 60Hz
THERMAL SHOCK: Oven temperature, 200 ±2°C (392 ±3.6°F)
Max change in measurement Sizes 24 through 12: 0.060 inch
Sizes 10 through 8: 0.100 inch
Sizes 6 through 4: 0.125 inch
FLAMMABILITY: Post-flame dielectric test not required
LIFE CYCLE: Oven temperature 313 ±2°C (595.4 ±3.6°F)
Dielectric test, 2500 volts (rms), 60Hz
DIELECTRIC TEST AFTER IMMERSION: 2500 volts (rms), 60Hz
ABRASION RESISTANCE AFTER IMMERSION: Specimens after immersion shall meet the same abrasion requirements as initial specimens; this test to be a quality conformance test subject to the same inspection level and acceptable quality level as the test for initial abrasion resistance.
HUMIDITY RESISTANCE: 50,000 megohms for 1000 ft, min insulation resistance after humidity exposure
SURFACE RESISTANCE: 500 megohm-inches (min), initial and final readings
SMOKE: 313°C (595.4°F)
ACID RESISTANCE: Required
Dielectric test, 2500 volts (rms), 60Hz
COLOR: In accordance with MIL-STD-104, Class 1; white preferred

COLOR STRIPING OR BANDING DURABILITY: 250 cycles (500 strokes) (min), 500 grams weight

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T13:44Z
Check the source to verify that this is the current version before use.

ADDITIONAL REQUIREMENTS (Continued)

IDENTIFICATION DURABILITY: 125 cycles (250 strokes) (min), 500 grams weight
WIRE LENGTH REQUIREMENTS: Schedule A
SUPERSESSION DATA: The wire of this specification sheet, by part number, replaces and supersedes the wire of MS17411(AS) (canceled) in accordance with Table III.

TABLE III. SUPERSESSION BY PART NUMBER

Part number MS17411(AS)	Part number MIL-W-22759/5
MS17411-24	M22759/5-24-*
MS17411-22	M22759/5-22-*
MS17411-20	M22759/5-20-*
MS17411-18	M22759/5-18-*
MS17411-16	M22759/5-16-*
MS17411-14	M22759/5-14-*
MS17411-12	M22759/5-12-*
MS17411-10	M22759/5-10-*
MS17411-8	M22759/5-8-*
MS17411-6	M22759/5-6-*
MS17411-4	M22759/5-4-*

Custodians:
Navy - AS
Army - EL
Air Force - 80

Preparing activity:
Navy - AS
(Project No. 6145-0670-3)

Review activities:
Navy - EC, OS
Army - ME, MI, MU
Air Force -
DSA - IS
NSA

User activities:
Navy - MC
Army - AT, AV
Air Force - 11

Review/user information is current as of the date of this document. For future coordination of changes to this document, draft circulation should be based on the information in the current Federal Supply Classification Listing of DOD Standardization Documents.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T13:44Z
Check the source to verify that this is the current version before use.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T13:44Z
Check the source to verify that this is the current version before use.

FOLD

DEPARTMENT OF THE NAVY
Naval Air Engineering Center
Philadelphia, PA 19112

OFFICIAL BUSINESS

POSTAGE AND FEES PAID
DEPARTMENT OF THE NAVY
DOD 316

Engineering Specifications and Standards Department (Code ES)
Naval Air Engineering Center
Philadelphia, PA 19112

FOLD

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T13:44Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL	OMB Approval No. 22-R255

INSTRUCTIONS: The purpose of this form is to solicit beneficial comments which will help achieve procurement of suitable products at reasonable cost and minimum delay, or will otherwise enhance use of the document. DoD contractors, government activities, or manufacturers/vendors who are prospective suppliers of the product are invited to submit comments to the government. Fold on lines on reverse side, staple in corner, and send to preparing activity. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or to amend contractual requirements. Attach any pertinent data which may be of use in improving this document. If there are additional papers, attach to form and place both in an envelope addressed to preparing activity.

DOCUMENT IDENTIFIER AND TITLE MIL-W-22759/5B WIRE, ELECTRIC, FLUOROPOLYMER-INSULATED, ABRASION RESISTANT, EXTRUDED TFE, SILVER-COATED COPPER CONDUCTOR, 600-VOLT

NAME OF ORGANIZATION AND ADDRESS	CONTRACT NUMBER
	MATERIAL PROCURED UNDER A ☐ DIRECT GOVERNMENT CONTRACT ☐ SUBCONTRACT

1. HAS ANY PART OF THE DOCUMENT CREATED PROBLEMS OR REQUIRED INTERPRETATION IN PROCUREMENT USE?
   A. GIVE PARAGRAPH NUMBER AND WORDING.

   B. RECOMMENDATIONS FOR CORRECTING THE DEFICIENCIES

2. COMMENTS ON ANY DOCUMENT REQUIREMENT CONSIDERED TOO RIGID

3. IS THE DOCUMENT RESTRICTIVE?
   ☐ YES ☐ NO (If "Yes", in what way?)

4. REMARKS

SUBMITTED BY (Printed or typed name and address - Optional)	TELEPHONE NO.
	DATE

DD FORM 1 JAN 72 1426 REPLACES EDITION OF 1 JAN 66 WHICH MAY BE USED

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T13:44Z
Check the source to verify that this is the current version before use.

NOTICE
OF VALIDATION

MIL-W-22759/5B
NOTICE 1
8 September 1987

MILITARY SPECIFICATION SHEET

WIRE, ELECTRIC, FLUOROPOLYMER-INSULATED, ABRASION RESISTANT, EXTRUDED TFE, SILVER-COATED COPPER CONDUCTOR, 600-VOLT

MIL-W-22759/5B, dated 19 July 1974, has been reviewed and determined to be valid for use in acquisition.

Custodians:
Army - CR
Navy - AS
Air Force - 99

Preparing Activity:
Navy - AS

Review Activities:
Army - ME, MI, AR
Navy - EC, OS
DSA - IS

User Activities:
Army - AT, AV
Navy - MC
Air Force - 11

AMSC - N/A

FSC 6145

DISTRIBUTION STATEMENT: A Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T13:44Z
Check the source to verify that this is the current version before use.