NOT MEASUREMENT SENSITIVE

MIL-DTL-3628/298(IH)
25 March 2024

DETAIL SPECIFICATION SHEET


BADGE, IDENTIFICATION BADGE, DEFENSE MEDIA ACTIVITY

This specification is approved for use by all
Departments and Agencies of the Department of Defense

The requirements for acquiring the product described herein shall consist of this specification sheet and the latest issue of MIL-DTL-3628.



ASSEMBLED



BASE



DEVICE

DASH NO.
-1: Regular Size
-2: Miniature Size

MATERIAL: BASE and DEVICE: Red Brass 85/15 (UNS Alloy No. C-230)

FINISH: -1, -2: The base shall be Stoned Epoxy, 24K Gold and Nickel Plated, Mirror Like Polish and shall match TIOH Finish Chip #6.

DIMENSIONS:
BASE:
DIAMETER:
-1: 2 inches (REF)
-2: 1 1/2 inches (REF)

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T20:32Z
Check the source to verify that this is the current version before use.

THICKNESS (At rim):
-1: 0.070 ± 0.010 inch
-2: 0.065 ± 0.010 inch
DEVICE:
HEIGHT:
-1: 1 inch (REF)
-2: 3/4 inch (REF)
WIDTH:
-1: 5/8 inch (REF)
-2: 27/32 inch (REF)
THICKNESS (At rim):
-1: 0.070 ± 0.010 inch
-2: 0.070 ± 0.010 inch
ASSEMBLED THICKNESS:
-1: 0.140 ± 0.010 inch
-2: 0.135 ± 0.010 inch

ATTACHING DEVICE:
1. Attaching device shall be prong and flat ball type clutch.

2. For -1, three prongs shall be located on the reverse, on an approximate 1-3/4 inches diameter circle. Each prong shall be placed 120 degrees apart with the bottom prong located on the vertical centerline at the bottom of the badge. For -2, three prongs shall be located on the reverse, on an approximate 1-1/4-inch diameter circle. Each prong shall be placed 120 degrees apart with the bottom prong located on the vertical centerline at the bottom of the badge.

EPOXY: Epoxy resin shall be applied to the Badge Qualification as indicated above and shall match TIOH Hard Enamel Color Chip Numbers listed below. Hard cloisonné enamel may be used in lieu of epoxy. If hard cloisonné enamel is used, the required base material shall be Gilding Metal 95/5 (UNS Alloy C-210).

TIOH HARD ENAMEL COLOR CHIPS		
EPOXY COLOR	**CHIP #**	**LOCATION**
Purple	22	Outer Ring around Globe and Corners of Shield
Black	26	Inner Ring around Globe of Shield
White	28	Outside Ring of Base
Blue	33	Area around Shield, Stars, and Wreath

1. All epoxy on the base shall be stoned.
2. All epoxy on the device shall be stoned except for the three corners of the shield, which shall be floating.

NOTES:
1. The term (REF) refers to the measurements taken from the Government furnished hub or die.

2. The specification slash sheet for the lapel button is MIL-DTL-11484/450.

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T20:32Z
Check the source to verify that this is the current version before use.

Custodian:
Army - IH

Preparing activity:
Army - IH

Review activity:
DLA - CT

(Project No. 8455-2024-110)

NOTE: The activities listed above were interested in this document as of the date of this document. Since organizations and responsibilities can change, you should verify the currency of the information above using the ASSIST Online database at https://assist.dla.mil.

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T20:32Z
Check the source to verify that this is the current version before use.