INCH-POUND

A-A-55252
May 3 1994

# COMMERCIAL ITEM DESCRIPTION

## CLOTH, COATED, POLYESTER OR NYLON, WATERPROOF

The General Services Administration has authorized the use of this commercial item description in preference to MIL-C-20696.

Abstract. This commercial item description covers five types and four classes of coated nylon cloth. The cloth is intended for use in the manufacture of covers and shelters (types I, II, IV and V) and survival containers (type III).

Classification. The cloth shall be in the following types and classes:

Type I - Cloth, Polyester or Nylon, 2.3 oz/yd$^2$ uncoated
Type II - Cloth, Polyester or Nylon, 5.1 oz/yd$^2$ uncoated
Type III - Cloth, Polyester or Nylon, 7.25 oz/yd$^2$ uncoated
Type IV - Cloth, Polyester or Nylon, 4.8 oz/yd$^2$ uncoated
Type V - Cloth, Polyester or Nylon, 5.9 oz/yd$^2$ uncoated

Class 1 - Base cloth coated with chloroprene (both sides)
Class 2 - Base cloth coated with vinyl chloride polymer or copolymer containing a fire retardant (both sides)
Class 3 - Base cloth coated with chloroprene containing a fire retardant (both sides)
Class 5 - Base cloth coated with nitrile-butadiene rubber (NBR) (one side) (applicable to type III only)

Beneficial comments recommendations, additions, deletions, clarifications, etc. and any data which may improve this document should be sent to: HQ CASC,74 N. Washington Avenue, Battle Creek, MI 49017-3094

AMSC N/A FSC 8305

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:45Z
Check the source to verify that this is the current version before use.

Salient Characteristics.

Base cloth. All base cloths shall consist of either bright or clear, high-tenacity, filament polyester or nylon unless otherwise specified in the contract or order. Types I, II, III and V shall be woven and the weave shall be plain. Type IV shall be of weft inserted warp knit construction. The base cloths shall conform to the applicable requirements listed in Table I. Unless otherwise specified, the base cloth shall be a minimum of 60 inches exclusive of selvages or exclusive of tuck-in when woven on Sulzer-type looms. The cloth shall be scoured and heat-set prior to coating.

Table I Base cloth requirements

| Characteristics | Type I | Type II | Type III | Type IV | Type V 1/ |
|---|---|---|---|---|---|
| Weight oz/yd$^2$ | 2.3 ±0.2 | 5.1 ±0.3 | 7.25 (max) | 4.8 ±0.3 | 5.9 ±0.3 |
| Yarns/inch (min) | | | | | |
| Warp | 38 | 22 | 60 | 18 | 23 |
| Filling | 38 | 21 | 45 | 18 | 23 |
| Breaking Strength lbs. (min.) | | | | | |
| Warp | 115 | 225 | 325 | 225 | 300 |
| Filling | 115 | 225 | 275 | 225 | 240 |
| Tearing Strength lbs. (min.) | | | | | |
| Warp and Filling | - | - | 20 | - | - |

1/ Refer to paragraph on basic fabric information.

Coating compounds.

Class 1 - Chloroprene rubber. Up to 20 percent of other elastomers such as styrene-butadiene rubber (SBR) may be added to facilitate processing provided the coated cloth conforms to the Table II requirements.

Class 2 - Virgin polymer or copolymer of vinyl chloride resin plasticized with only phosphate or phthalate esters and containing and evenly dispersed fire inhibitor.

Class 3 - Chloroprene rubber containing an evenly dispersed fire inhibitor. Up to 20 percent of other elastomers such as styrene-butadiene rubber (SRB) may be added to facilitate processing provided the coated cloth conforms to the Table II requirements.

Class 5 - Nitrile-butadiene rubber.

Dusting powder - The dusting powder for application to classes 1, 3, and 5 coated cloths shall be whiting, talc or other finely divided mineral material which does not support mildew growth.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:45Z
Check the source to verify that this is the current version before use.

Coated cloth - The coating compound shall be applied to both sides of the base cloth, except for type III, class 5 which shall be coated on one side only. The face side shall be more heavily coated than the back except for type II, class 2, type IV, class 2 and type V, class 2, which shall have a balanced coating unless otherwise specified by the contracting agency. Classes 1, 3 and 5 cloths shall be fully vulcanized and dusted with the dusting powder specified herein before curing. The physical properties for the coated cloth shall conform to the requirements specified in Table II when tested as specified.

Color. The color of the finished cloth shall match the applicable color number of FED-STD-595 or shall match the approved color standard for the color specified where such a sample is applicable. The color of the finished coated cloth shall match the standard sample when viewed under filtered tungsten lamps that approximate artificial daylight and that have a correlated color temperature of 7500 (± 200) K, with illumination of 100 (± 20) footcandles and shall be a good match to the standard sample under incandescent lamplight at 2300 (± 200) K.

Physical requirements. The finished cloth shall conform to the requirements listed in Table II.

Table II Physical requirements of coated cloth

| Characteristic | Type I | | | Types II & IV | | | Type III | Type V |
|---|---|---|---|---|---|---|---|---|
| Class | 1 | 2 | 3 | 1 | 2 | 3 | 5 | 2 |
| Weight Oz/yd$^2$ (± 1.0 oz) | 8.0 | 9.0 | 10.5 | 16.0 | 18.0 | 18.0 | 12.0 | 20.0 |
| Breaking Strength, pounds (min) Initial: | | | | | | | | |
| Warp | 115 | 115 | 115 | 225 | 225 | 225 | 325 | 300 |
| Filling | 115 | 115 | 115 | 225 | 225 | 225 | 275 | 240 |
| Breaking strength after accelerated weathering, pounds (min) | | | | | | | | |
| Warp | 92 | 92 | 92 | 180 | 180 | 180 | 260 | 275 |
| Filling | 92 | 92 | 92 | 180 | 180 | 180 | 220 | 180 |
| Tearing Strength, pounds (min) | | | | | | | | |
| Warp | 12.0 | 12.0 | 12.0 | 45.0 | 45.0 | 45.0 | 20.0 | 50 |
| Filling | 10.0 | 10.0 | 10.0 | 38.0 | 38.0 | 38.0 | 20.0 | 50 |



Source: https://assist.dla.mil - Downloaded: 2026-10-26T09:45Z
Check the source to verify that this is the current version before use.

Table II Physical requirements of coated cloth

| Characteristic | Type I | | | Types II & IV | | | Type III | Type V |
|---|---|---|---|---|---|---|---|---|
| Class | 1 | 2 | 3 | 1 | 2 | 3 | 5 | 2 |
| Stiffness cm (max) (warp only) | | | | | | | | |
| at 70 ± 2°F | 10.0 | 10.0 | 10.0 | 14.5 | 16.5 | 14.5 | - | 16.5 |
| at 10 ± 5°F | - | 13.0 | - | - | 22.0 | - | - | 22.0 |
| at -40 ± 5°F | 12.0 | - | 12.0 | 20.0 | - | 20.0 | - | - |
| Adhesion of coating, pounds/2 inch width (min) | 10.0 | 10.0 | 10.0 | 15.0 | 15.0 | 15.0 | 12.0 | 20.0 |
| Blocking, scale rating (max) | 3 | 3 | 3 | 3 | 3 | 3 | 2 | 3 |
| Resistance to accelerated aging | 1/ | - | 1/ | 1/ | - | 1/ | 1/ | - |
| Flame Resistance: (max) | | | | | | | | |
| After flame sec | - | - | 10 | - | - | 10 | - | - |
| Char length In. | - | - | 3.5 | - | - | 3.5 | - | - |
| Dimensional stability % shrinkage (max) | | | | | | | | |
| Warp | - | - | - | - | 1.5 2/ | - | - | 1.0 |
| Filling | - | - | - | - | 1.0 2/ | - | - | 1.0 |

1/ The coating shall show no increase in softness, stiffness, tackiness or brittleness when compared with an unexposed specimen.

2/ Applicable only when required by the contract or order.

Marking. The back of the cloth shall be marked "BACK" at both ends of each roll with the letters not less than 1/2 inch (1.3 cm) in height. The marking shall be clearly legible in any indelible marking medium used commercially and shall not show through the face of the cloth.

Workmanship. The finished coated cloth shall conform to the quality of product established by this document. The occurrence of defects shall not exceed the applicable acceptable quality

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:45Z
Check the source to verify that this is the current version before use.

levels.

Width. The selvages may be trimmed after coating. The residual minimum width shall be 60 inches or as specified in the contract or purchase order.

Length and put-up. The coated cloth shall be put up in full width rolls in lengths of 80 to 125 yards. There shall be no more than two pieces in each roll and no piece shall be less than 25 yards in length. The ends of the pieces shall be overlapped and not joined by a seam. Acceptance of shorter lengths, if permitted, shall be based on the conditions stipulated in the contract or purchase order.

Component and material inspection. Components and materials shall be inspected in accordance with all the requirements of referenced documents, unless otherwise excluded, amended, modified or qualified in this document or applicable purchase document. In addition, testing shall be performed for the characteristics specified in Table III. All test reports shall contain the individual values utilized in expressing the final result. The sample unit shall be 1/2 yard full width of the base cloth. The lot size shall be expressed in units of 1 yard and the sample size shall be as specified below. The lot shall be unacceptable if one or more sample units fail to meet any requirement specified.

| Lot size - yards (meters) | Sample size (sample unit) |
|---|---|
| 800 (732) or less | 2 |
| 801 (732) up to and including 22,000 (20117) | 3 |
| 22,001 (20117) and over | 5 |

Table III Component testing

| Component | Characteristic | Test method |
|---|---|---|
| Base cloth | Weave | Visual 1/ |
| | Weight oz/yd$^2$ | ASTM-D-3776-Opt C |
| | Yarns/inch | ASTM-D-3775 |
| | Breaking strength, lbs. | ASTM-D-5035 2/ |
| | Tearing strength, lbs. | ASTM D-2261 3/ |

1/ One determination shall be made and the results reported as pass or fail.

2/ The test specimens shall be one inch wide raveled strip specimens; a constant-rate-of-extension (CRE) testing machine shall be used; the distance between clamps of the testing machine shall be 3 ± 0.05 inches and the test shall be conducted using a fixed rate of extension of 12 ± 0.5 inches per minute.

3/ The test shall be conducted using a fixed rate of extension



Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:45Z
Check the source to verify that this is the current version before use.

of 12 ± 0.5 inches per minute; the tearing strength of the test specimen shall be the average of the five highest peak loads of resistance registered during the separation of the tear.

Quality Assurance.

Certification. The contractor shall certify that the product offered meets the salient characteristics of this description and that the product conforms to the producer's own drawings, specifications, standards and quality assurance practices. The Government reserves the right to require proof of such conformance prior to the first delivery and thereafter as may be otherwise provided for, under the provisions of the contract. Reliance on contractor QA systems shall not relieve the contractor of the responsibility of ensuring that all products or supplies submitted to the government for acceptance comply with all requirements of the contract. A certificate of compliance shall be furnished with each shipment or lot for the following:

a. The yarn used in the base cloth is composed of either bright or clear, high-tenacity, filament polyester or nylon.
b. The classes 1 through 5 coatings are compounded as specified.
c. The dusting powder for application to classes 1, 3 and 5 coated cloths is whiting, talc or other finely divided mineral material which does not support mildew growth.

End item tests. The coated cloth shall be tested for the characteristics listed in Table IV. The methods of testing specified shall be followed. Unless otherwise specified, methods of testing of FED-STD-191, Textile Test Methods are specified as four digit numbers (i.e., 5204). The physical values specified apply to the average of determinations made on a sample unit for test purposes as specified in the applicable test methods. The sample unit shall be 3 (5 for Type V, Class 2), continuous yards full width of the coated cloth. The lot shall be unacceptable if one or more sample units fail to meet any test requirements specified. The lot size shall be expressed in units of one yard (0.91 m) each. All test reports shall contain the individual values utilized in expressing the final result. The sample size (number of sample units) shall be in accordance with the following:

| Lot size-yards- (meters) | Sample size |
|---|---|
| 800 (363) or less | 2 |
| 801 (363) up to and including 22,000 (9,988) | 3 |
| 22,001 (9,989) and over | 5 |

Standard test conditions. Results of physical tests obtained under testing conditions defined in FED-STD-191, ASTM-D-618 or FED-STD-601 will be acceptable except in cases of dispute. In dispute cases, tests shall be conducted with both the specimen and test apparatus under standard conditiions as defined in FED-STD-191.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:45Z
Check the source to verify that this is the current version before use.

Table IV End item tests

| Characteristics | Test method |
|---|---|
| Weight | ASTM-D-3776 Opt C |
| Breaking strength: | |
| Initial | ASTM-D-5035 1/ |
| After accelerated weathering | 2/ 10/ 11/ |
| Tearing Strength | ASTM-D-2261 3/ |
| Stiffness 4/ | |
| at 70° ± 2°F | 5204 |
| at 10° ± 5°F | 5204 |
| at -40° ± 5°F | 5204 |
| Adhesion of coating | 5970 |
| Blocking | 5872 |
| Accelerated aging 5/ | 5852 |
| Flame resistance: | |
| Flame time | 5903 |
| Char length | 5903 |
| Hydrostatic resistance | |
| Initial | 5516 6/ |
| After abrasion | 7/ |
| Oil resistance | 8/ |
| Resistance to aromatic hydrocarbon | 9/ |
| Resistance to accelerated weathering | 10/ 12/ |
| Resistance to low temperature | 13/ |
| Resistance to high temperature | 14/ |
| Flame retardency | 5903 15/ |
| Dimensional stability | 16/ |

1/ The test specimens shall be one inch wide cut strip specimens; a constant-rate-of-extension (CRE) testing machine shall be used; the distance between clamps of the testing machine shall be 3 ± 0.05 inches and the test shall be conducted using a fixed rate of extension of 12 ± 0.5 inches per minute.

2/ The specimens for test after accelerated weathering exposure shall be cut from each sample unit at the same time as specimens for original test and shall be marked to ensure proper

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:45Z
Check the source to verify that this is the current version before use.

identification.

3/ The test shall be conducted using a fixed rate of extension of 12 ± 0.5 inches per minute; the tearing strength of the test specimen shall be the average of the five highest peak loads of resistance registered during the separation of the tear. Specimens of type IV cloth (weft inserted warp knit) shall be 8 inches by 10 inches.

4/ The specimens and test equipment shall be conditioned at the specified temperature for a minimum of 4 hours before testing and test shall be conducted in still air.

5/ Only one specimen shall be tested.

6/ Except that the water will be in contact with the lightly coated side. The hydrostatic head shall be 20 inches and the time of exposure shall be 10 minutes. The coated cloth shall show no leakage.

7/ Hydrostatic resistance after abrasion test. A new specimen, 10 by 10 inches, shall be taken for test. The specimen shall be abraded by means of a 2-inch square piece of grade 1/0 garnet paper which shall be uniformly loaded with an 8 ± 0.1 ounce weight. The specimen shall be abraded on the heavily coated side by moving the weighted garnet paper filling-wise five times in each direction. The specimen shall then be turned over and abraded on the other side in such a manner that the center 2-inch square section is abraded on the other side, i.e., the specimen is abraded in a north-south direction on one side and an east-west direction on the other side. The abraded 2-inch square area shall then be placed face up across the center line of the clamping head so that the center of the abraded area will coincide with the center of the exposed part of the specimen. Hydrostatic resistance shall then be determined as specified in method 5516 of FED-STD-191. The hydrostatic head shall be 20 inches and the time of exposure shall be 10 minutes. The coated cloth shall show no leakage of water in either the abraded or unabraded portion of the test specimen after testing.

8/ Oil resistance test (applicable only to type I, type II type IV and type V). One 8 by 8 inch specimen of coated cloth shall be placed on a wood frame. The inside dimensions of the frame shall be 6 by 6 by 1 inches. The specimen shall be forced into the frame by a wood block 5-3/4 by 5-3/4 inches (with round corner) to form a basin of uniform depth. The edges of the cloth shall be tacked to the frame and the block removed. Lubricating oil, conforming to grade 1100 of MIL-L-6082 shall be rapidly poured into the basin to a 1/2 inch depth. After the oil has been in the basin for 1 hour, the bottom of the fabric specimen forming the basin shall be examined to determine if oil has permeated the coated cloth to cause leakage. The coated cloth

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:45Z
Check the source to verify that this is the current version before use.

shall show no evidence of seepage of oil through the material after testing.

9/ Resistance to aromatic hydrocarbons (applicable only to type I, type II type IV and type V). One, 1 by 6 inch specimen with the long dimension parallel to the warp shall be immersed for 5 minutes in aromatic hydrocarbon fluid conforming to Reference fuel D of ASTM D 471. The specimen shall be allowed to dry at room temperature for 2 hours (± 5 minutes) and shall be creased sharply on itself, face outward. A similar cut specimen with the long dimension parallel to the filling shall be tested in the same manner. The coated cloth shall not crack.

10/ Accelerated weathering procedure. One specimen, 8 by 6 inches minimum, with the short dimension warpwise and one specimen, 8 by 6 inches, minimum, with the short dimension filling wise shall be subjected to the procedure specified in Method 5804 of FED-STD-191. The procedure shall be performed with the heavily coated side exposed. The exposure times shall be as follows:

Types I, II, IV and V class 2 - 150 hours for all colors.
Types I, II, and IV classes 1 and 3 - 150 hours for olive green and black only, all other colors - 50 hours.
Type III, class 5 - 150 hours for all colors.

After exposure, the specimens shall be removed and allowed to condition for at least 24 hours.

NOTE: Attention is called to contractors who own equipment which operates at one revolution in two hours. This equipment may be used. However, the one revolution per minute shall be the standard procedure in the event of dispute and the laboratory reports shall state the procedure used.

11/ Breaking strength after accelerated weathering test. After completion of the accelerated weathering procedure, the two specimens shall be subjected to the following conditions:

a. 2 hours at $180^{\circ} \pm 5^{\circ}F$
b. 40 (± 8) hours at $70^{\circ} \pm 2^{\circ}F$ at a relative humidity of 65 ± 2%.

Each specimen shall then be tested for breaking strength as specified in ASTM-D-5035 1/.

12/ Resistance to accelerated weathering test. After completion of the accelerated weathering procedure, each specimen shall be folded by hand, face out, sharply upon itself and visually examined along the fold for cracking and crazing. Each specimen shall then be opened flat and examined for blooming, chalking or appreciable color change (An appreciable color change is one that is noticeable on first glance when comparing the tested specimen with the original). The presence of any cracking,



Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:45Z
Check the source to verify that this is the current version before use.

crazing, blooming, chalking or appreciable color change shall be considered a test failure.

13/ Resistance to low temperature test. A 1 by 4 inch specimen of the coated cloth with the long dimension warpwise and a 1 by 4 inch specimen of the coated cloth with the long dimension fillingwise shall be exposed for 4 hours at a temperature of minus 70 ± 5°F with the temperature recorded at the lowest point in the chamber. The sample, still in the test atmosphere, shall then be bent sharply (heavily coated side out) 180 degrees over a 1/8 inch steel rod that has been exposed in the test chamber with the test specimen. The coated cloth shall not crack or flake.

14/ Resistance to high temperature test. A 2 by 6 inch specimen of the coated cloth shall be exposed for a period of 6 hours in an electrically heated oven maintained at a temperature of 170° ± 2°F. At the end of this period, the specimen, still maintained at the test atmosphere shall be bent (heavily coated side out) 180 degrees over a 1/8 inch steel rod. The coated cloth shall show no evidence of tackiness, blistering or softening.

15/ Except that the specimen shall be observed for an additional 30 seconds after burner flame turn off. If the tip of the flame passes beyond the top edge of the specimen at any time during the 42 seconds after the burner is turned on, the specimen shall be reported as a test failure. Five specimens shall be tested in the warp direction and the results reported individually as "pass" or "fail". Failure of one or more specimens of coated cloth shall be considered a test failure.

16/ Dimensional stability. The test specimen shall be a strip of coated cloth, 6 inches wide by 50 inches long; the long dimension of the test specimen shall be parallel to the direction under test. The initial length of the test specimen shall be measured to the nearest 1/16 inch and recorded. The test specimen shall then be subjected successively to the following conditions:

a. 24 hours at minus 20 (± 5) degrees F.,
b. 24 hours at 150 (± 2) degrees F. (circulating hot air oven).
c. 15 minutes at 300 (± 2) degrees F. (circulating hot air oven).

The test specimen shall then be brought to equilibrium under standard conditions and the final length of the test specimen shall be measured to the nearest 1/16 inch and recorded. Dimensional stability (shrinkage) shall then be calculated as follows:

$$\text{Shrinkage, percent} = \frac{\text{Length (initial)} - \text{Length (final)}}{\text{Length (initial)}} \times 100$$

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:45Z
Check the source to verify that this is the current version before use.

any hole, cut, tear, scratch or abrasion mark that results in baring the base cloth; Any pinhole; Any surface scratch or abrasion mark that does not result in baring the base cloth; Any uncoated area; Any pit, blister, tunnel or delamination of coating; Any lump or heavily coated area; Any crease or wrinkle resulting in doubling or adhesion of surfaces that cannot be corrected by manual pressure; Uneven coating, thin area where coating is missing or noticeably thinner; Any light area or window due to absence or poor blending of pigmentation; Cloth edges rolled, curled, folded, doubled, scalloped, or wavy precluding a flat lay of the cloth; Any spot, stain or streak more than 1 inch in combined directions, clearly visible at normal inspection distance (3 feet); Trimmed width less than minimum specified; Any objectionable odor (odors of chemicals commonly used in coating compounds shall not be regarded as objectionable); Color not as specified, off shade, uneven or mottled; Any tackiness (coating will adhere and not unroll readily); Deposition of coating not as required, i.e. not balanced or unbalanced as specified.

NOTE: Specimens of classes 1,3 and 5 cloths which have been dusted with mineral powder shall be wiped with a wet cloth and allowed to dry before color matching.

Length examination. Each individual roll in the sample shall be examined for the defects listed below. If the total number of defects in the sample roll exceeds the maximum number of defects specified in Table V, the lot shall be rejected.

Any roll containing more than two pieces.
Any piece in roll less than 25 yards.
Any roll with a total length of less than 80 yards or more than 125 yards.
Any roll with a total length more than two yards less than that marked on ticket.
End of pieces in roll not overlapped.
End of pieces in roll joined by a seam.

Preservation, packing and marking. The preservation, packing and marking shall be as specified in the contract or order.

NOTE: Base fabric information. The Type V, class 2 coated cloth has been successfully produced using woven polyester fabric conforming to the requirements of Table I and the following properties:

| | |
|---|---|
| Free unloaded fabric shrinkage at 350 degrees F. for 30 min., % (ASTM-D-1204) | |
| Warp | 2.5 (max) |
| Filling | 2.5 (max) |



Source: https://assist.dla.mil Downloaded: 2026-10-26T09:45Z
Check the source to verify that this is the current version before use.

Examination for shade match and finish, individual rolls. Each roll in the lot shall be examined visually for shade match and finish. A roll shall be unacceptable if it fails to meet the requirements for shade match or finish. The sample unit shall be a 4 inch by 20 inch (10.2cm x50.8cm) swatch of the cloth. A sample unit shall be drawn from each roll in the lot.

Length examination. During the yard- by- yard examination, each roll in the sample shall be examined for length. Any lot found to be less than the minimum length specified in the basic cloth document or more than 2 yards less than the length marked on the ticket shall be scored as a defect. The lot shall be unacceptable if two or more rolls in the sample are defective in respect to the length. The lot shall be unacceptable if the total of the actual length of the rolls in the sample is less than the total of the lengths marked on the roll tickets.

Yard-by-yard examination. The required yardage of each roll in the sample shall be examined on one side only for the defects listed below, however the side shall be alternated for every other roll examined (except type III, class 5 cloth). The same yardage shall be given a through-light inspection for pinholes and thinly coated areas. The through-lighting inspection shall be performed in accordance with MIL-STD-1487. The defects found shall be counted regardless of their proximity to each other, except where two or more defects represent a single local condition of the cloth, in which case only the more serious defect shall be counted. A continuous defect shall be counted as one defect for each warpwise yard or fraction thereof in which it occurs. The sample unit shall be 1 linear yard. The inspection level shall be II and the acceptable quality level (AQL), expressed in terms of defects per hundred units, shall be 2.5 for major defects and 6.5 for total (major and minor combined defects) in accordance with ANSI/ASQC Z1.4. The number of rolls from which the sample yardage is to be selected shall be in accordance with Table V. The sample yardage shall be apportioned equally among the selected rolls.

Table V - Sample size and acceptance criteria

| Lot size (yards) | Sample size (rolls) | Maximum number of defects acceptable in sample 2/ |
|---|---|---|
| Up to 1200 inclusive 1/ | 3 | 0 |
| 1201 up to and including 3200 | 5 | 0 |
| 3201 up to and including 10,000 | 8 | 0 |
| 10,001 up to and including 35,000 | 13 | 0 |
| 35,001 up to and including 150,000 | 20 | 1 |
| 150,001 and over | 32 | 2 |

1/ If a lot contains fewer than three rolls, each roll in the lot shall be examined.
2/ Applicable to length examination only.

Defects. The cloth shall be examined for the following defects:

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:45Z
Check the source to verify that this is the current version before use.

Yarn twist, turns per inch (nominal) (ASTM-D-1423)

| | |
|---|---|
| Warp | 1.5 |
| Filling | 1.5 |

Source of Government Documents. Copies of Military and Federal documents are available from:

Standardization Documents Order Desk
Bldg. 4D
700 Robbins Avenue
Philadelphia, PA 19111-5094

Sources of Nongovernment Documents.

ANSI/ASQZ Z1.4 - Sampling Procedures and Tables For Inspection By Attributes

(Applications for copies should be addressed to the American national Standards Institute, 1430 Broadway, New York, NY 10018-3308.)

TECHNICAL MANUAL OF THE AMERICAN ASSOCIATION OF TEXTILE CHEMISTS AND COLORISTS

(Applications for copies should be addressed to AATCC, P.O. Box 12215, Research Triangle Park, N.C. 27709.)

AMERICAN SOCIETY FOR TESTING AND MATERIALS

D 471 - Rubber Property - Effect of Liquids
D 618 - Conditioning Plastics and Electrical Insulating Materials for Testing
D 2261 - Tearing Strength of Woven Fabrics By The Tongue (Single Rip) Method (Constant-Rate-Of-Extension Tensile Testing Machine)
D 5035 - Breaking Force and Elongation of Textile Fabrics (Strip Force)

(Applications for copies should be addressed to the American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.)

Custodian:
Army - GL
Navy - NU
Air Force - 99

Civil Agency Coordinating Activity:
GSA - FSS

Review Activities:
Army - ME, MI
Navy - MC
Air Force - 45, 82
DNA-DS

Preparing Activity:
DLA - CT

Project No. 8305-0489



Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:45Z
Check the source to verify that this is the current version before use.