
THE REQUIREMENTS FOR ACQUIRING THE PRODUCT(S) DESCRIBED HEREIN SHALL CONSIST OF THIS SPECIFICATION SHEET AND THE ISSUE OF THE FOLLOWING SPECIFICATION LISTED IN THAT ISSUE OF THE DODISS SPECIFIED IN THE SOLICITATION: MIL-B-81820

THIS SPECIFICATION IS APPROVED FOR USE BY ALL DEPARTMENTS AND AGENCIES OF THE DEPARTMENT OF DEFENSE.

FORM APPROVED
OMB NO. 0704-0188



DETAIL A

TABLE I. DIMENSIONS AND STRENGTHS

DASH NO.	B +.0000 -.0010	D +.0000 -.0005	H ±.005	Q MIN	W +.000 -.002	STATIC LIMIT LOAD		OSCILLATING LOAD LB	NO-LOAD ROTATIONAL BREAKAWAY TORQUE IN - LB		WT LB MAX
						RADIAL LB	AXIAL LB		STANDARD	* "K" TYPE	
-5	.3135	.6875	.317	14	.437	9250	1640	4450	1.0 - 15.0	0 - 1.0	.035
-6	.3760	.8125	.406	8	.500	13000	2630	6200			.060
-7	.4385	.9375	.442	10	.562	17250	3650	8250			.080
-8	.5010	1.0000	.505	9	.625	21400	4970	10600			.100
-9	.5635	1.1250	.536	10	.687	26600	5370	13200			.135
-10	.6260	1.1875	.567	12	.750	29000	6130	16150			.160
-12	.7510	1.3750	.630	13	.875	37000	7730	24800			.240
-14	.8760	1.6250	.755	6	.875	56000	10800	26750	1.0 - 25.0	0 - 2.0	.350
-16	1.0010	2.1250	1.005	12	1.375	103300	19300	49300			.970

* SEE REQUIREMENT 5 "NO-LOAD TORQUE" AND NOTE 5

REQUIREMENTS:

1. MATERIAL: BALL: PH13-8 Mo STEEL ALLOY PER AMS 5629, CONDITION H1000.
   OUTER RING: 17-4 PH STEEL ALLOY PER AMS 5643.
   LINER: POLYTETRAFLUOROETHYLENE (PTFE) SHALL BE INCLUDED IN THE LINER.

2. SURFACE TEXTURE: BALL DIA. Ra 8; BALL FACES Ra 16; OUTER RACE DIA Ra 32; ALL OTHER METALLIC SURFACES Ra 125. LINER SURFACES ARE EXEMPT FROM SURFACE TEXTURE MEASUREMENTS.

PREPARING ACTIVITY: NAVY — AS
CUSTODIANS: ARMY — AV NAVY —
AIR FORCE — 99 DLA —
REVIEW: DLA - IS
USER: ARMY - MI
PROJECT NUMBER: 3120 - 0693

MILITARY SPECIFICATION SHEET

TITLE
BEARING, PLAIN, SELF-ALIGNING, SELF-LUBRICATING, LINED BORE, LOW SPEED, WIDE, CHAMFERED OUTER RING, -65° TO 325° F

SPECIFICATION SHEET NUMBER 31 JAN 90
MIL-B-81820/2

SUPERSEDING

AMSC — N/A FSC 3120

DISTRIBUTION STATEMENT
A. APPROVED FOR PUBLIC RELEASE; DISTRIBUTION IS UNLIMITED.

DD FORM 1 MAY 88 672 PREVIOUS EDITIONS OF THIS FORM ARE OBSOLETE

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T06:13Z
Check the source to verify that this is the current version before use.

THE REQUIREMENTS FOR ACQUIRING THE PRODUCT(S) DESCRIBED HEREIN SHALL CONSIST OF THIS SPECIFICATION SHEET AND THE ISSUE OF THE FOLLOWING SPECIFICATION LISTED IN THAT ISSUE OF THE DODISS SPECIFIED IN THE SOLICITATION: MIL-B-81820

THIS SPECIFICATION IS APPROVED FOR USE BY ALL DEPARTMENTS AND AGENCIES OF THE DEPARTMENT OF DEFENSE.

FORM APPROVED
OMB NO. 0704-0188

3. SURFACE FINISH:

OUTER RACE: PLATING, WHEN SPECIFIED, SHALL BE CADMIUM PLATING PER QQ-P-416, TYPE II, CLASS 2.

PLATE ON THE OUTSIDE DIAMETER SURFACE AND ON THE CHAMFER.

PLATING RUNOUT SHALL OCCUR IN THE SIDE FACE AREA BETWEEN THE CHAMFER AND THE BALL.

THE PTFE LINER IN THE OUTER RACE INSIDE DIAMETER AND IN THE BALL BORE SHALL BE PROTECTED FROM EXPOSURE TO PLATING SOLUTIONS DURING PROCESSING.

BALL: PASSIVATE PER MIL-S-5002.

4. HARDNESS: BALL: Rc 43 MIN; OUTER RING: Rc 28 MIN, Rc 37 MAX BEFORE SWAGING.

5. NO-LOAD TORQUE: WHEN THE LETTER "K" IS PRESENT IN THE PART NUMBER LOWER VALUES OF NO-LOAD TORQUE ARE SPECIFIED PER TABLE I. IF THE MEASURED TORQUE OF A "K" TYPE BEARING IS LESS THAN 0.1 INCH-POUND. THE INTERNAL RADIAL CLEARANCE SHALL BE MEASURED AND SHALL NOT EXCEED THE VALUES IN TABLE II. THESE REQUIREMENTS APPLY TO THE TORQUE AND INTERNAL PLAY BETWEEN THE SPHERICAL BALL AND THE OUTER RING. THIS STANDARD DOES NOT DEFINE REQUIREMENTS FOR TORQUE OR INTERNAL PLAY BETWEEN THE BEARING BORE AND SHAFT.

TABLE II. INTERNAL CLEARANCE

DASH NO.	MAXIMUM RADIAL PLAY	MAXIMUM AXIAL PLAY
-5K THRU -12K	0.0007 INCH	0.0021 INCH
-14K THRU -16K	0.0010 INCH	0.0030 INCH

6. BREAK SHARP EDGES AND CORNERS AND REMOVE ALL BURRS AND SLIVERS.

7. DIMENSIONS ARE IN INCHES. UNLESS OTHERWISE SPECIFIED. TOLERANCES, DECIMALS ± .010, ANGLES ± 0.5.

NOTES:

1. WHEN TESTED TO THE FLUID CONTAMINATION AND SUB-ZERO TEMPERATURE REQUIREMENTS OF THE PROCUREMENT SPECIFICATION, THE OSCILLATING LOAD SHALL BE DECREASED TO 75% OF SPECIFIED LOAD.

2. WHEN FLUIDS AND ELEVATED TEMPERATURES (ABOVE 200°F) ARE BOTH PRESENT IN AN APPLICATION, THEN REDUCTIONS IN OPERATING LOADS OR BEARING LIFE MAY BE REQUIRED.

3. DASH NUMBER DESIGNATES NOMINAL BORE DIA IN SIXTEENTHS OF AN INCH.

4. DIMENSION "D" TO BE MET AFTER PLATING.

5. EXAMPLE OF PART NO.

M81820/2-6 P K = 3/8 NOMINAL BORE DIA, PH13-8 Mo BALL MATERIAL, CADMIUM PLATED, LOW TORQUE.

- ABSENCE OF LETTER INDICATES STANDARD BREAKAWAY TORQUE.
- LETTER "K" INDICATES LOW BREAKAWAY TORQUE (SEE TABLE I).
- ABSENCE OF LETTER INDICATES NO PLATING.
- LETTER "P" INDICATES CADMIUM PLATING (SEE REQUIREMENT 3).
- SIZE - BORE DIAMETER. (DASH NO. FROM TABLE I).
- MS NUMBER.

6. IN THE EVENT OF A CONFLICT BETWEEN THE TEXT OF THIS STANDARD AND THE REFERENCES CITED HEREIN, THE TEXT OF THIS STANDARD SHALL TAKE PRECEDENCE.

7. REFERENCED GOVERNMENT (OR NON-GOVERNMENT) DOCUMENTS OF THE ISSUE LISTED IN THAT ISSUE OF THE DEPARTMENT OF DEFENSE INDEX OF SPECIFICATIONS AND STANDARDS (DoDISS) SPECIFIED IN THE SOLICITATION FORM A PART OF THIS STANDARD TO THE EXTENT SPECIFIED HEREIN.

PREPARING ACTIVITY: NAVY — AS
CUSTODIANS: ARMY — AV NAVY —
AIR FORCE — 99 DLA —
REVIEW: DLA-IS
USER: ARMY-MI
PROJECT NUMBER: 3120-0693

MILITARY SPECIFICATION SHEET

TITLE
BEARING, PLAIN, SELF-ALIGNING, SELF-LUBRICATING, LINED BORE, LOW SPEED, WIDE, CHAMFERED OUTER RING, -65°F TO 325°F

SPECIFICATION SHEET NUMBER 31 JAN 90
MIL-B-81820/2

SUPERSEDING

AMSC — N/A FSC 3120

DISTRIBUTION STATEMENT
A. APPROVED FOR PUBLIC RELEASE; DISTRIBUTION IS UNLIMITED.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T06:13Z
Check the source to verify that this is the current version before use.