MILITARY SPECIFICATION SHEET

WIRE, ELECTRICAL, SOLDERLESS WRAP, EXTRUDED POLYVINYIDENE FLUORIDE (PVDF) INSULATION, SILVER COATED SOLID CONDUCTOR

This specification is approved for use by all Departments and Agencies of the Department of Defense.

The complete requirements for acquiring the wire described herein shall consist of this document and the issue in effect of Specification MIL-W-81822.




TABLE I. Construction and performance details.

	Part no. 1/	Wire size (AWG)	Finished wire diameter (inches)	Finished weight Ⓐ (lb/1,000 ft) (max)	Cut-through load (grams)	Bend testing			Insulation pull-off (lbs)
						Mandrel diameter (ins.)		Tension load (lbs)	
						Heat resistance	Cold bend	Cold bend	
	M81822/3-X30-*	30	0.0195 ± .0010	0.53	700 Ⓐ	1/16	1.0	0.25	0.4 to 2.5 Ⓐ
	M81822/3-X28-*	28	0.0265 ± .0015	0.91	900	5/64	1.0	0.50	0.5 to 2.5
Ⓐ	M81822/3-X28V*	28	0.0230 ± .0015	0.79	720	5/64	1.0	0.50	0.5 to 2.5
	M81822/3-X26-*	26	0.0295 ± .0015	1.26	950	3/32	1.0	0.50	1 to 4
Ⓐ	M81822/3-X26V*	26	0.0260 ± .0015	1.13	760	3/32	1.0	0.50	1 to 4
	M81822/3-X24-*	24	0.0340 ± .0015	1.84	1000	7/64	1.0	0.50	1 to 4
Ⓐ	M81822/3-X24V*	24	0.0300 ± .0015	1.67	800	7/64	1.0	0.50	1 to 4
	M81822/3-X22-*	22	0.0390 ± .0020	2.71	1100	1/8	1.0	0.75	1 to 6
	M81822/3-X20-*	20	0.0460 ± .0020	4.09	1200	9/64	1.0	0.75	1 to 6
	M81822/3-X18-*	18	0.0540 ± .0030	6.21	1300	11/64	1.0	1.00	1 to 6

1/ PART NO.: The "X" in the generalized part numbers of table I shall be replaced by the designator for the conductor type and the asterisk shall be replaced by the code designator for the insulation color. Example: Size 22 wire with type A (soft annealed copper) conductor and white insulation - M81822/3-A22-9.

Ⓐ Denotes changes.

FSC 6145

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T06:13Z
Check the source to verify that this is the current version before use.

WIRE RATINGS AND ADDITIONAL REQUIREMENTS

TEMPERATURE RATING: 135°C (275°F) max conductor temperature.
VOLTAGE RATING: 300 volts (rms).
INSULATION TENSILE STRENGTH: 2,500 psi (min).
INSULATION ELONGATION: Wire sizes 30 and 28 - 35 percent (min).
Wire sizes 26 through 18 - 50 percent (min).
Ⓐ COLOR: Colors listed in MIL-STD-104, as specified in contract or order. However, color limits of MIL-STD-104 are not applicable to wire of this specification sheet.
Ⓐ SPARK TEST: 2,000 volts (rms).
INSULATION RESISTANCE: 300 megohms-1,000 ft (min).
Ⓐ WET DIELECTRIC TEST: 1,000 volts (rms), 60 Hz.
COLD BEND CONDITIONING: 4 hrs at -65° ± 2°C (-85° ± 3.6°F).
DIELECTRIC TEST FOR CUT-THROUGH: 500 volts (rms), 60 Hz.
INSULATION HEAT RESISTANCE:
Conditioning, 96 hrs at 150° ± 2°C (302° ± 3.6°F).
Shrinkage, 0.062 inch (max).
Ⓐ DIELECTRIC CONSTANT: 8.50 max at 1 MHz.
Ⓐ POWER FACTOR: 0.250 max at 1 MHz.
Ⓐ RESISTANCE TO FLUIDS, APPLICABLE TEST FLUIDS:
Isopropyl alcohol, TT-I-735.
Hydraulic fluid, MIL-H-5606.
Trichlorotrifluoroethane, MIL-C-81302.
Trichloroethane, MIL-T-81533.
FLAMMABILITY: 30 sec (max) after-flame.
3.0 inches (max) flame travel.
No flaming of tissue paper.
SURFACE RESISTANCE: 5 megohms (min).
Ⓐ FUNGUS RESISTANCE: Wire constructed as specified in MIL-W-81822/3A shall be considered fungus resistant in accordance with Requirement 4 of MIL-STD-454 by virtue of the recognized inherent fungus resistance of all components. Fungus resistance test is not required.

Custodians:
Army - CR
Navy - AS
Air Force - 85

Preparing activity:
Navy - AS

(Project 6145-0683-4)

Review activities:
Navy - EC, SH
Air Force - 11, 99
DLA - ES, IS

User activities:
Navy - MC, OS
Air Force - 17

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T06:13Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

INSTRUCTIONS. This form is provided to solicit beneficial comments which may improve this document and enhance its use. DoD contractors, government activities, manufacturers, vendors, or other prospective users of the document are invited to submit comments to the government. Fold on lines on reverse side, staple in corner, and send to preparing activity. Attach any pertinent data which may be of use in improving this document. If there are additional papers, attach to form and place both in an envelope addressed to preparing activity. A response will be provided to the submitter, when name and address is provided, within 30 days indicating that the 1426 was received and when any appropriate action on it will be completed.

NOTE: This form shall not be used to submit requests for waivers, deviations or clarification of specification requirements on current contracts. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or to amend contractual requirements.

DOCUMENT IDENTIFIER *(Number)* AND TITLE
MIL-W-81822/3A WIRE, ELECTRICAL, SOLDERLESS WRAP, EXTRUDED POLYVINYLIDENE FLUORIDE (PVDF) INSULATION, SILVER COATED SOLID CONDUCTOR

NAME OF ORGANIZATION AND ADDRESS OF SUBMITTER

☐ VENDOR ☐ USER ☐ MANUFACTURER

1. ☐ HAS ANY PART OF THE DOCUMENT CREATED PROBLEMS OR REQUIRED INTERPRETATION IN PROCUREMENT USE? ☐ IS ANY PART OF IT TOO RIGID, RESTRICTIVE, LOOSE OR AMBIGUOUS? PLEASE EXPLAIN BELOW.

A. GIVE PARAGRAPH NUMBER AND WORDING

B. RECOMMENDED WORDING CHANGE

C. REASON FOR RECOMMENDED CHANGE(S)

2. REMARKS

SUBMITTED BY *(Printed or typed name and address — Optional)*

TELEPHONE NO.

DATE

DD FORM 1426
1 OCT 76

EDITION OF 1 JAN 72 WILL BE USED UNTIL EXHAUSTED.

Source: https://assist.dla.mil -- Downloaded: 202610-23T06:13Z
Check the source to verify that this is the current version before use.

FOLD

DEPARTMENT OF THE NAVY

OFFICIAL BUSINESS
PENALTY FOR PRIVATE USE $300

NO POSTAGE
NECESSARY
IF MAILED
IN THE
UNITED STATES

BUSINESS REPLY MAIL

FIRST CLASS PERMIT NO. 12503 WASHINGTON D. C.

POSTAGE WILL BE PAID BY THE DEPARTMENT OF THE NAVY

Engineering Specifications and Standards
Department (Code 93)
Naval Air Engineering Center
Lakehurst, NJ 08733

FOLD

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T06:13Z
Check the source to verify that this is the current version before use.