GGG-B-451d
January 31, 1968
SUPERSEDING
Fed. Spec. GGG-B-451c
April 11, 1960

FEDERAL SPECIFICATION

BLADE, HAND HACKSAW AND BLADE, POWER HACKSAW

This specification was approved by the Commissioner, Federal Supply Service, General Services Administration, for the use of all Federal agencies.

1. SCOPE AND CLASSIFICATION

1.1 Scope. This specification covers hand and power hacksaw blades.

1.1.1 Federal specification coverage. This Federal specification does not cover all types, grades, and classes of hacksaw blades which are commercially available, but only those generally used by the Federal Government.

1.2 Classification.

1.2.1 Types, grades, and classes. The hacksaw blades shall be of the following types, grades, and classes, as specified (see 6.2):

Type I. Hand.
  Grade A. High-speed steel.
    Class 1. All hard.
    Class 2. Flexible back.
  Grade B. High-carbon or low-tungsten steel.

Type II. Power.
  Grade A. High-speed steel.
    Class 1. One piece, all hard.
    Class 2. Welded composite, high-speed edge.

2. APPLICABLE DOCUMENTS

2.1 The following specifications and standards, of the issues in effect on date of invitation for bids or request for proposal, form a part of the specification to the extent specified herein:

Federal Specifications:

QQ-I-652 - Iron Castings, Gray.
QQ-S-633 - Steel Bars, Carbon, Cold Finished and Hot Rolled, (General Purpose).
QQ-S-763 - Steel Bars, Shapes and Forgings, Corrosion-Resisting.
QQ-S-766 - Steel Plates, Sheets, and Strip-Corrosion-Resisting.
WW-P-351 - Pipe; Red Brass, (Copper Alloy No. 230), Seamless Standard Pipe Size, Regular and Extra-Strong.
WW-T-791 - Tubing; Brass, Seamless.

Federal Standard:

Fed. Std. No. 123 - Marking for Domestic Shipment (Civilian Agencies).

(Activities outside the Federal Government may obtain copies of Federal Specifications, Standards, and Handbooks as outlined under General Information in the Index of Federal Specifications and Standards and at the prices indicated in the Index. The Index, which includes cumulative monthly supplements as issued, is for sale on a subscription basis by the Superintendent of Documents, U.S. Government Printing Office, Washington, D.C., 20402.

(Single copies of this specification and other product specifications required by activities outside the Federal Government for bidding purposes are available without charge at the General Services Administration Regional Offices in Boston, New York, Washington, D.C., Atlanta, Chicago, Kansas City, Mo., Ft. Worth, Denver, San Francisco, Los Angeles, and Seattle, Wash.

FSC 5110, 3455

Source: https://assist.dla.mil -- Downloaded: 20261O-26T12:39Z
Check the source to verify that this is the current version before use.

(Federal Government activities may obtain copies of Federal Specifications, Standards, and Handbooks and the *Index of Federal Specifications and Standards* from established distribution points in their agencies.)

Military Specification:

MIL-H-15424 - Hand Tools; Packaging of.

Military Standards:

MIL-STD-105 - Sampling Procedures and Tables for Inspection by Attributes.
MIL-STD-129 - Marking for Shipment and Storage.

(Copies of Military Specifications and Standards required by contractors in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer).

3. REQUIREMENTS

3.1 Qualification, grade A. The hacksaw blades furnished as grade A under this specification shall be products which are qualified for listing on the applicable qualified products list (QPL) at the time set for opening of bids (see 4.2 and 6.4).

3.2 Material.

3.2.1 Grade A. The material used in the manufacture of grade A blades shall be high-speed steel which (in the hardened and tempered condition) can be reheated to 1100°F. for 5 hours, followed by cooling to room temperature, and retain a hardness of Rockwell "C" 60 or greater.

3.2.2 Grade B. The material used in the manufacture of grade B blades shall be as specified in 3.7.2.

3.3 Finish. All blades covered in this specification shall be free from corrosion and loose scale and shall have a protective coating to prevent corrosion. Grade A, high-speed steel blades, hand and power, shall be painted over the entire surface with paint or lacquer which will not interfere with the cutting teeth.

3.4 Marking. Each hacksaw blade shall be marked in a plain and durable manner with the name of manufacturer or with a brand name or trademark of such known character that the source of manufacture may be readily determined. In addition, as applicable, blades shall be marked "high-speed" or "HSS", except that type II, class 2 blades shall be marked "high-speed edge" or "HSS edge", to clearly indicate the use of high-speed steel.

3.5 Deformity of blades. Blades shall be free from crimps, buckles, or warpage. When a straight edge is placed against the side of the blade at the toothed edge and at the back edge, any concave or convex deviation in the contacting edge from the straight edge shall not exceed the maximum deviation shown in table I.

TABLE I. Straightness tolerance

Blade length (nominal)	Maximum deviation
Inches	Inch
10	3/64
12 thru 18	1/16
21 thru 24	5/64
30	3/32

3.6 Blade ends. The blade ends shall be heat-treated in such a manner as to preclude the pin holes pulling out or the ends breaking when blades are tensioned in accordance with tests in section 4.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:39Z
Check the source to verify that this is the current version before use.

3.7 Type 1, hand. Type 1 hand blades shall conform to table II (see 6.2). Tolerances shall be in accordance with table III.

TABLE II. Type 1, hand

Nominal 1/ length	Number of teeth per inch	Width	Thickness		Length overall	Center to center of pinholes	Pinhole diameter
			High-speed steel	Standard steel			
Inches		Inch	Inch	Inch	Inches	Inches	Inch
S10 2/	18, 24, 32	1/2	0.025	0.025	10-3/8	9-7/8	.158
S12 2/	14, 18, 24, 32	1/2	.025	.025	12-3/8	11-7/8	.158
D12 3/	18 on one side; 24 on other side	1/2	---	.025	12-3/8	11-7/8	.158

1/ Symbols - S-indicates single-edge, i.e., blades with teeth on 1 edge only.
D-indicates double edge blades, i.e., blades with teeth on both edges.

2/ S10 and S12 blades are furnished in both standard and high-speed steel.

3/ D12 blades are furnished in standard steel only.

TABLE III. Dimensional tolerances for hand hacksaw blades

Blade dimension	Tolerances (in inches)
Width	± 1/64
Thickness, high-speed steel	± 0.003
Thickness, standard steel	plus 0.001 minus 0.003
Overall length	± 1/16
Pinholes, center to center	± 1/16
Pinhole diameter	± 0.010

3.7.1 Grade A, high-speed steel. Grade A blades shall be of high-speed steel, set and heat-treated to make at least the minimum number of cuts as specified in section 4 for grade A blades.

3.7.1.1 Class 1, all-hard. Class 1 all-hard blades shall be uniformly hardened throughout except at the ends.

3.7.1.2 Class 2, flexible-back. Class 2 flexible-back blades shall have soft backs and shall be hardened on the tooth edge only. Class 2, flexible baldes shall withstand the bending test, as specified in section 4.

3.7.2 Grade B, high-carbon or low-tungsten steel. Grade B blades shall be of high-carbon or low-tungsten steel, set and heat-treated to make at least the minimum number of cuts, as specified in section 4 for Grade B blades.

3.7.2.1 Class 2, flexible-back. Class 2 flexible-back blades shall have soft backs hardened on the tooth edge only or the back of the blade beyond the cutting edge shall have a soft core. Class 2 flexible blades shall withstand the bending test specified in section 4.

3.8 Type II, power. Type II, power blades shall conform to table IV (see 6.2).

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:39Z
Check the source to verify that this is the current version before use.

TABLE IV. Type II, power

Nominal length	Number of teeth per inch	Width		Thickness ± 0.003	Length overall ± 1/16	Center to center of pinholes ± 1/16	Pinhole diameter ± 0.010
		Class 1 ± 1/64	Class 2				
Inches		Inches	Inches	Inch	Inches	Inches	Inch
12	14, 18	5/8	5/8 (+1/16, -1/64)	0.032	12-1/2	11-7/8	3/16
12	10, 14	1	1 (+3/32, -1/64)	.050	12-3/4	11-7/8	9/32
14	10, 14	1	1 (+3/32, -1/64	.050	14-3/8	13-1/2	9/32
14	4, 6, 10	1-1/4	1-1/4 (+1/8, -1/64)	.062	14-1/2	13-1/2	9/32
14	4, 6	1-1/2	1-1/2 (+1/8, -1/64)	.075	14-1/2	13-1/2	9/32
17	10, 14	1	1 (+3/32, -1/64)	.050	17-3/8	16-1/2	9/32
17	4, 6, 10	1-1/4	1-1/4 (+1/8, -1/64)	.062	17-1/2	16-1/2	9/32
18	6, 10	1-1/4	1-1/4 (+1/8, -1/64)	.062	18-1/2	17-1/2	9/32
18	4, 6	1-1/2	1-1/2 (+1/8, -1/64)	.075	18-1/2	17-1/2	9/32
18	4, 6	1-3/4	1-3/4 (+1/8, -1/64)	.088	18-3/4	17-1/2	9/32
21	4, 6	1-3/4	1-3/4 (+1/8, -1/64)	.088	22-1/4	21	9/32
24	4, 6	1-3/4	1-3/4 (+1/8, -1/64)	.088	25-1/4	24	9/32
24	4	2	2 (+1/8, -1/64)	.100	25-1/4	24	25/64
30	4	2-1/2	2-1/2 (+1/8, -1/64)	.100	32	30	25/64
36	2-1/2	4-1/2	4-1/2 (+1/8, -1/16)	.125	38	36	1/2

3.8.1 Grade A, high-speed steel. Grade A blades shall be of high-speed steel, set and heat-treated to make at least the minimum number of cuts as specified in section 4 for grade A power blades.

3.8.1.1 Class 1, one piece, all-hard. Class 1 blades, except at the ends, shall be either uniformly hardened throughout or gradient hardened.

3.8.1.2 Class 2, welded composite, high-speed edge. Class 2 blades shall have a high-speed, steel cutting edge welded to a soft back, and shall be hardened on the tooth edge.

3.9 Workmanship. Workmanship of the hacksaw blades shall be free from all imperfections which may affect the general appearance, function, or serviceability.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the supplier is responsible for the performance of all inspection requirements, as specified herein. Except as otherwise specified, the supplier may use his own facilities or any commercial laboratory acceptable to the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure that supplies and services conform to prescribed requirements.

4.2 Qualification tests for grade A blades. Qualification tests shall be conducted at a laboratory satisfactory to the Naval Ship Engineering Center (see 6.4 and 6.5). Qualification tests shall consist of the examinations in 4.4.1 and the tests specified in 4.5 and 4.7.1.

4.2.1 Samples for qualification. Qualification tests are conducted by groups of grade A blades which a manufacturer may produce. Each group of grade A blades consists of all sizes and tooth counts of blades which conform to a specific type and class of this specification. A manufacturer may request a test for any of the groups for which he desires approval. Representative samples, required for testing for qualification approval for each individual group, shall be as specified in table VI. Should the representative samples satisfactorily pass the qualification test, approval will be granted for the entire group of grade A blades represented by the samples.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:39Z
Check the source to verify that this is the current version before use.

TABLE V. Representative samples for qualification tests

Group, grade A only	Size, inches	Tooth count/inch	Number of samples required
A (Type I, class 1)	12 x 1/2 x 0.025	18, 24, 32	72 (24 of each tooth count)
B (Type I, class 2)	12 x 1/2 x 0.025	18, 24, 32	72 (24 of each tooth count)
C (Type II, class 1)	17 x 1-1/4 x 0.062	4, 6, 10	72 (24 of each tooth count)
D (Type II, class 2)	17 x 1-1/4 x 0.062	4, 6, 10	72 (24 of each tooth count)

4.3 Sampling for quality conformance inspection.

4.3.1 Lot. All hacksaw blades of the same type, class, size and number of teeth per inch offered for delivery at one time shall be considered a lot for purposes of quality conformance inspection.

4.3.2 Sample. A random sample of hacksaw blades shall be selected from each lot in accordance with MIL-STD-105 at Inspection Level II. The acceptable quality level (AQL) shall be 2.5 percent defective.

4.4 Quality conformance inspection. Quality conformance inspection shall be performed on each sample blade selected in accordance with 4.3.2. Quality conformance inspection shall consist of the following:

(a) Examination (see 4.4.1).
(b) Tests (see 4.6 and 4.7.2.3).
(c) Inspection of preservation and packaging (see 4.8).

4.4.1 Examination. Each blade selected in accordance with 4.3.2 shall be examined for compliance with the requirements of this specification. Examination shall be conducted as specified in table VI. Each sample blade shall be examined for straightness by placing a straightedge against either side of the blade at the toothed edge and measuring the maximum clearance between blade surface and straightedge. The straightedge examination shall be repeated at the back edge of the blade. The maximum measured clearance between blade surface and straightedge at any point shall not exceed the maximum permissible deviation specified in table I. Nonconforming blades shall not be offered for delivery and if the number of defective blades exceeds the acceptable number for the samples tested, the lot represented by the sample shall be rejected.

TABLE VI. Classification of defects

Categories	Defects
Critical:	
1	None defined.
Major:	
101	Type, grade, class, and size not as specified.
102	Material not as specified; blade broken or not free from cracks, crimps, buckles, warpage or scale.
103	Teeth chipped, broken or deformed.
104	Toothed edge and back edge concave or convex deviation (straightness) exceeds the allowable maximum.
105	Number of teeth per inch not as specified.
106	Thickness, width, overall length and center to center distance between pineholes not within required tolerances.
107	Diameter of pineholes not within specified limits.
108	High-speed steel cutting edge not securely welded to soft back as required (type II, grade A, class 2 only).
109	Blade not coated to prevent corrosion as specified; evidence of rust or corrosion.
110	Material designation of blade or cutting edge (as applicable) not marked as required (types I and II, grade A only).
Minor:	
201	Marking, manufacturer's name, brand or trademark missing, incorrect, illegible, or not durably marked on each blade.

Source: https://assist.dla.mil -- Downloaded: 202610-26T12:39Z
Check the source to verify that this is the current version before use.

4.4.2 Production check tests.

4.4.2.1 Grade A. The production check test for grade A blades shall be conducted when specified by the ordering activity (see 6.2) or the responsible technical agency or at the discretion of the qualifying activity when production check tests are specified or ordered. Six blades from each lot covered by the contract shall be selected for the check test. Type I, grade A blades shall be tested as specified in 4.7.2.1 and shall complete a minimum of 90 cuts. Faliure of blades to complete a minimum of 90 cuts in the production check test shall be cause for rejection of lot and removal of all type I, grade A blades from the Qualified Products List. Type II, grade A blades shall be tested as specified in 4.7.2.2 and shall complete a minimum of 60 cuts. Failure of the blades to complete a minimum of 60 cuts in the production check test shall be cause for rejection of the lot and removal of all type II, grade A blades from the Qualified Products List.

4.5 Qualification tests for grade A blades.

4.5.1 Type I, grade A. A set of 18 blades consisting of 6 each of 18-, 24-, and 32-tooth count blades shall complete a minimum of 300 cuts when tested as specified in 4.7.2.1. In no event shall one blade be used to make more than 30 cuts.

4.5.2 Type II, grade A. A set consisting of 6 each of 4-, 6-, and 10-tooth count blades shall complete a minimum of 225 cuts when tested as specified in 4.7.2.2. In no event shall one blade be used to make more than 20 cuts.

4.6 Quality conformance tests.

4.6.1 Bending test. Six type I, class 2, grades A and B blades of each tooth count, from each lot (see 4.3.2) covered by the contract or purchase order, shall be selected and subjected to the bending test as specified in 4.7.1 to determine its flexibility.

4.6.2 Cutting test.

4.6.2.1 Type I, grade B. Six blades selected from each lot shall be subjected to a practical test as specified in 4.7.2.3 by cutting off the number of pieces of the test material specified in table VII. Failure of a blade shall be considered to have occurred if the blade does not cut off the number of pieces specified in table VII or if either the body or teeth of the blade break, or the blade teeth become so dull as to stop cutting. If more than one blade representative of a given lot of the same class, length, and number of teeth per inch fails, the lot represented shall be rejected.

TABLE VII. Cutting tests for grade B blades

Teeth per inch, grade-B blades	Number of pieces cut, minimum	Test material (see 4.7.2.3)
14	5	Cast-iron bar, 1.2 inch machined diameter.
18	6	Cold finished steel bar, 1-inch diameter.
24	6	Brass pipe, 3/4-inch iron pipe size.
32	6	Brass tubing, 2.375 inch outside diameter, 0.065 inch thickness.

4.7 Test procedures.

4.7.1 Bending test. Type I, class 2, grades A and B blades shall be bent to determine their flexibility. The bend shall be made by grasping the flat surface of the blade between the thumb and forefinger of each hand at the pinholes and drawing the blade end together until the centers of the pinholes are not less than 2 inches and not more than 3 inches apart. The bend shall be made in not less than 2 seconds nor more than 5 seconds. Blades shall have been held at a temperature of 68° to 75°F. for at least 30 minutes prior to bending. If any sample blade breaks, the lot represented by the sample shall be rejected.

4.7.2 Cutting tests.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:39Z
Check the source to verify that this is the current version before use.

4.7.2.1 Type I, grade A. Type I, grade A high-speed steel, hand hacksaw blades shall be evaluated for cutting performance on a 6- by 6-inch gravity feed, power-hacksaw machine under the following conditions:

Blade tension, pounds	400
Gravity feed pressure, pounds	35
Maximum lift on return strokes, inch	0.25
Cutting fluid	None
Speed, strokes per minute	60

Test logs shall be stacks of corrosion-resistant steel strips made from sheets which conform to the requirements for class 304, condition A, annealed, finish number 4 of QQ-S-766. The test logs for the various tooth counts shall be composed as follows:

Blade tooth count	Test log
14, 18	10 strips, 1-1/2 inches wide by 0.106-0.109 inch thick by 18 inches long.
24	8 strips, 1-1/2 inches wide by 0.106-0.109 inch thick by 18 inches long.
32	12 strips, 1-1/2 inches wide by 0.059-0.062 inch thick by 18 inches long separated by 1/32 inch steel spacers not in way of cut.

The test log shall be secured in the vise of the hacksaw with the plane of the strips vertical and successive cuts taken. The number of strokes required per cut shall be recorded until the blade fails or completes 30 cuts. Failure shall be considered to have occurred when the blade breaks, becomes dull, or cuts at an angle. The blade shall be considered dull when the number of strokes per cut reaches:

1200 for 14 T, 18 T, and 24 T all-hard blades
1500 for 14 T, 18 T, and 24 T flexible blades
800 for 32 T all-hard blades
1000 for 32 T flexible blades

The blades shall be considered to have cut at an angle when the cut deviates from the straight vertical path by more than 1/16 inch three times in succession.

4.7.2.2 Type II, grade A. Type II, grade A high-speed steel, power-hacksaw blades shall be evaluated for cutting performance on a 6- by 6-inch or 9- by 9-inch gravity feed, power-hacksaw machine or positive-feed machine, as applicable, in cutting steel test logs under the following conditions:

Blade thickness, inch	0.032	0.050	0.062	0.062
Blade tooth count	14, 18	10, 14	10	4, 6
Blade tension, pounds	600	1000	1500	1500
Feed pressure, pounds	50	75	100	125
Test-log diameter, inches	1-3/4	1-3/4	2	2-3/4
Lift on return stroke, inch	0.25	0.25	0.25	0.25
Speed, strokes per minute	60	60	60	60
Cutting fluid	None	None	None	None

Blades thicker than 0.062 inch shall be tested in a positive feed machine with a feed of 0.003 inch per stroke. Blade tension shall correspond to a tensile stress of 20,000 pounds per square inch (p.s.i.) on the nominal cross section of the blade or the frame capacity of the machine, if lower. The test logs shall be 2-3/4 inches in diameter for 4- and 6-tooth blades and 2 inches in diameter for 10-tooth blades. Test logs shall consist of solid round bars of corrosion-resisting steel conforming to class 304, condition A annealed of table I, hot finished and pickled of QQ-S-763.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:39Z
Check the source to verify that this is the current version before use.

The bars shall not be cold worked but finished hot during rolling. The test logs shall subsequently be heat-treated by holding at 1750°F. for two hours and quenching in water. The test logs shall be secured in the vise of the hacksaw and cuts taken with the test blade on successive test logs under the specified conditions. The number of strokes required per cut shall be recorded until the blade fails or completes 20 cuts. Failure shall be considered to have occurred when the blade breaks, becomes dull, or cuts at an angle. The blade shall be considered dull when the number of strokes per cut rises to:

2000 for 0.032	18 T blades
1500 for 0.032	14 T blades
1500 for 0.050	10 T and 14 T blades
1200 for 0.062	10 T blades
2000 for 0.062	6 T blades
1500 for 0.062	4 T blades

Blades thicker than 0.062 inch shall be considered dull when the wear of the teeth is 0.020 inch in the height of the teeth. The blades shall be considered to have cut at an angle when the cut deviates from the straight vertical path by more than 1/16 inch three times in succession.

4.7.2.3 Type I, grade B. The sample blade under test selected in accordance with 4.6.2.1 and shall be fixed in a hacksaw frame and tightened by hand as taut as possible without using any tool. The hand hacksaw frame shall be a heavy duty frame. The blade shall be fitted so that the teeth cut on the forward stroke. The test material shall include the following in accordance with table VII.

(a) Cast-iron bars. Cast-iron bars shall be 1.2 inch diameter; classes 20, 25, or 30 conforming to QQ-I-652.

(b) Cold-finished steel bars. Cold-finished steel bars shall be 1-inch diameter, free cutting, No. B1112 conforming to QQ-S-633.

(c) Brass pipe. Brass pipe shall be 3/4 inch iron-pipe size; grades A, B, or C; standard weight conforming to WW-P-351.

(d) Brass tubing. Brass tubing shall be 2.375 inches outside diameter; 0.065 inch wall thickness; type B; grades 1, 2, or 3 conforming to WW-T-791.

The test material to be cut shall be securely held in a vise or other suitable support so that there is no looseness, slippage, or excessive overhang. For solid members other than pipe and tubing, the cut shall be started on a spot previously scribed or scratched. The cutting stroke shall be as full (long) as possible. All cuts shall be made at not more than 40 cutting strokes per minute. Sufficient pressure shall be maintained during each cutting stroke to keep the teeth cutting and to prevent any slipping. On each return stroke the blade shall be sufficiently raised to prevent contact of the teeth with the bottom of the cut. No cutting fluid shall be applied in the course of the cutting test.

4.8 Inspection of preparation for delivery requirements. An inspection shall be made to determine that the preservation, packaging, packing, and marking comply with the requirements in section 5 of this specification. Defects shall be scored in accordance with table VIII. For examination of interior packaging, the sample unit shall be one shipping container fully prepared for delivery selected at random just prior to the closing operations. Defects of closure listed shall be examined on shipping containers fully prepared for delivery. The lot size shall be the number of shipping containers in the end item inspection lot.

TABLE VIII. Classification of defects

Examine	Defects
Markings (exterior and interior)	Omitted; incorrect; illegible; improper size, location, sequence, or method of application.
Materials	Any component missing or damaged.
Workmanship	Inadequate application of components such as incomplete closure of container flaps, loose strapping, inadequate stapling. Distortion of container.

5. PREPARATION FOR DELIVERY

5.1 Preservation, packaging, and packing. Unless otherwise specified (see 6.2), the blades shall be preserved, packaged, and packed in accordance with MIL-H-15424. The level of preservation and packaging shall be A or C and the levels of packing A, B, or C as specified (see 6.2). If level B packaging is required, (see 6.3).

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:39Z
Check the source to verify that this is the current version before use.

5.1.1 As part of the requirements of section 5 of this specification, table II is considered as part of and used in lieu of that portion of table I of MIL-H-15424 covering blades.

TABLE II. Blades

Column 1	Column 2	Column 3	Column 4	Column 5	Column 6	Column 7
Blade:						
Hacksaw:						
Hand	P-2	I	100	—	30	3,000
Power	P-2, P-7, P-10	I	10	---	12	120

5.2 Marking.

5.2.1 Civil agencies. In addition to markings required by the contract or order, the interior packages and shipping containers shall be marked in accordance with Fed. Std. No. 123.

5.2.2 Military agencies. In addition to markings required by the contract or order, the interior packages and shipping containers shall be marked in accordance with MIL-STD-129.

6. NOTES

6.1 Intended use. The hacksaw blades described herein are intended to be used for cutting metal, pipe, tubing, and other similar materials.

6.2 Ordering data. Purchasers should select the preferred options permitted herein and include the following information in procurement documents:

(a) Title, number, and date of this specification.
(b) Type, grade, and class required (see 1.2).
(c) Size and number of teeth per inch required (see tables II and IV).
(d) Production check test, if required, for grade A blades (see 4.4.2.1).
(e) Level of preservation, packaging, and packing required (see 5.1).

6.3 Civil agency procurement. When level B packaging is required for civil agency procurement, the requirements in 5.1, level A packaging shall apply.

6.4 With respect to products requiring qualification, awards will be made only for products which are at the time set for opening of bids, qualified for inclusion in applicable Qualified Products List (QPL) GGG-B-451, whether or not such products have actually been so listed by that date. The attention of the suppliers is called to this requirement, and manufacturers are urged to arrange to have the products that they propose to offer to the Federal Government tested for qualification, in order they they may be eligible to be awarded contracts or orders for the products covered by this specification. The activity responsible for the qualified products list is the Naval Ship Engineering Center, Department of the Navy, Washington, D.C. 20360, and information pertaining to qualification of products may be obtained from that activity. Application for Qualification tests shall be made in accordance with "Provisions Governing Qualification" (see 6.5).

6.5 Copies of "Provisions Governing Qualification" may be obtained upon application to Commanding Officer, Naval Supply Depot, 5801 Tabor Avenue, Philadelphia, Pennsylvania 19120.

6.6 This specification conforms to Simplified Practice Recommendation R90-62 insofar as is practicable.

6.7 Supersession data. Type I, grade B, class 1 blade is obsolete and has been replaced by type I, grade B, class 2, flexible back.

MILITARY CUSTODIANS:

Army - GL
Navy - SH
Air Force - 69

Review activities:

Army - GL
Navy - SH
Air Force - 69

User activities:

Navy - MC, YD

Preparing activity:

Navy - SH

CIVIL AGENCY INTEREST:

GSA - FSS

Orders for this publication are to be placed with General Services Administration, acting as an agent for the Superintendent of Documents. See section 2 of this specification to obtain extra copies of documents referenced herein. Price of this specification 10 cents each.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:39Z
Check the source to verify that this is the current version before use.