INCH-POUND

MIL-C-70462C (AR)
AMENDMENT 3
28 MARCH 1990

SUPERSEDING
AMENDMENT 2
28 April 1989

MILITARY SPECIFICATION

CHARGE, PROPELLING, 155MM, M203A1
LOADING, ASSEMBLING AND PACKING

This Amendment forms a part of Military Specification MIL-C-70462C (AR) dated 4 April 1986, and is approved for use within the US Army Armament Munitions and Chemical Command and is available for use by all Departments and Agencies of Department of Defense.

PAGE 3

3.5 Delete in its entirety and substitute new paragraph 3.5:

"3.5 Moisture content of black powder. The moisture content of the black powder at the igniter loading station at the time of loading shall not exceed 0.7%. The moisture content of the black powder in the basepad of the propelling charge shall be determined in accordance with 4.5.5."

3.6 Delete entire paragraph.

3.8 Delete heading "Avg Press Max (PSI)" and all entries under the same heading.

PAGE 7

4.4.1d Delete in its entirety and substitute the following new paragraphs:

"4.4.1d Case bodies from not more than one interfix number from one manufacturer.

4.4.1e Igniter containers and rear caps from not more than one interfix number from one manufacturer."

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T03:29Z
Check the source to verify that this is the current version before use.

PAGE 15

* 4.4.2.7 Major 102: Delete "completely" and substitute "securely".

PAGE 16

* 4.4.2.7 Delete Major Defect 105.

PAGE 23

4.5.6 Delete entire paragraph.

* 4.5.8 Delete in its entirety and substitute the following new paragraphs:

"4.5.8 Cloth, spun viscose rayon resin impregnated.

4.5.8.1 Cloth for base end igniter. Each roll, as a minimum, shall be tested for compliance with the physical characteristics listed in Table I in 3.5 of MIL-C-43157. Testing will be in accordance with 4.3.1 of MIL-C-43157. Any sample which fails to comply with the applicable requirement shall be cause for rejection of the cloth bolt represented by the sample. The method of inspection to be used during production is to be established by the contractor and approved by the Government. The method, as minimum, shall contain positive assurance that the material being utilized has been verified for compliance with the specification requirements as stated above (see 6.16).

4.5.8.2 Cloth for lead laminated rayon cloth, liner backing and strap. At the time cloth is introduced to the sewing or cutting operation, an identification will be made for each roll to verify that proper material is used. Any cloth failing to be identified as proper material in accordance with applicable drawing and specifications shall be removed from the sewing and cutting operation."

4.5.9 Delete in its entirety and substitute new paragraph 4.5.9:

"4.5.9 Proving ground assessments. These tests shall be conducted at a Government proving ground in accordance with the applicable acceptance test procedure using M549, RA or PXR-6325 projectiles inert loaded within 0.1 pound of an as

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T03:29Z
Check the source to verify that this is the current version before use.

fired weight of 96.0 pounds using primer, M82 and fired from M198 Howitzer with cannon M199 with 75 percent (minimum) remaining life. Firing shall be conducted with a spindle to charge base standoff of 1 inch (plus or minus 1/4 inch). Prior to firing, all charges shall be temperature conditioned in a large conditioning box with adequate air circulation at the required temperature for a minimum of 24 hours and assurance will be made that when fired, the charges are at the conditioning temperature. The following tolerance shall apply to all 145 degrees F and 70 degrees F conditioning: 145 degrees F from 140 degrees F to 145 degrees F; 70 degrees F from 68 degrees F to 72 degrees F. Copper crusher gages (2) shall be used to measure the maximum chamber pressure of each charge. One rear piezo gage shall be used to measure the maximum chamber pressure of each charge for information and ignition delay of each charge. Velocity coils will be used to measure the muzzle velocity of each charge. Temperature indicator (thermometer) strips shall be placed on the side of all charges or on the side of the metal containers, as applicable. If any indicator strip shows the charge has been exposed to a temperature greater than 145 degrees F, that charge will not be fired."

PAGE 24

4.5.9.3.2 Delete entire paragraph.

PAGE 26

6.8 Delete heading "Avg Press Max" and all entries under the same heading.

NOTE: The margins of this amendment are marked with an asterisk or vertical line to indicated where changes (additions, modifications, corrects, deletions) from the previous amendment were made. This was done as a convenience only and the Government assume no liability whatsoever for any inaccurancies in these notations. Bidders and contractors are cautioned to evaluate the requirements of this document based on the entire content irrespective of the marginal notations and relationship to the last previous amendment.

Custodian:
Army-AR

Preparing activity:
Army-AR

(Project 1320-AB90)

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T03:29Z
Check the source to verify that this is the current version before use.