MIL-P-48322B (AR)
AMENDMENT 3
14 April 1982
SUPERSEDING
AMENDMENT 2
2 February 1982

MILITARY SPECIFICATION

PROJECTILE, 8 INCH, HE, RA, M650
AFT WARHEAD SECTION AND STRIPPABLE COATING ASSEMBLY

This amendment forms a part of Military Specification MIL-P-48322B (AR), dated 22 May 1981 and is approved for use by the U.S. Army Armament Research and Development Command, and is available for use by all Departments and Agencies of the Department of Defense.

PAGE 1

Preamble: Change the word "Department" to "Departments"

PAGE 2

* 2.2: Delete "E18 - Test for Rockwell Hardness of Metallic Materials" and substitute the following:

"E10 - Test for the Brinnell Hardness of Metallic Materials".

Add "E103 - Rapid Indentation Hardness Testing of Metallic Materials".

PAGE 7

Table I, delete: "Interior Surface Finish" and substitute the following:

"Surface Finish 25 3.9 4.4.2.4".

FSC 1320

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T19:22Z
Check the source to verify that this is the current version before use.

PAGE 10

* 4.4.2.2, delete: Major Defect 103.

Add the following Category and Test:

"Info Only

301 Slow bend precrack charpy test c 3.4 4.5.3".

Delete: Critical Defect 3 and Note (a).

PAGE 11

* 4.4.2.3, delete Major Defect 101 and substitute:

"101 Pitch diameter of base thread, min., 0.40% 3.2 Gage".

Add Minor Defects 203 and 204 as follows:

"203 Pitch diameter of base thread, max., 0.65% 3.2 Gage
204 Major diameter of base thread, max., 0.65% 3.2 Gage".

PAGE 13

4.4.2.4: Add the following Major defects:

"117 Width of knurl, min. .40% 3.2 Gage
118 Distance from base end to knurl after knurling shall be checked near the first peak and the last peak and shall be no greater than .003 max 100% 3.2 Gage".

Delete Minor defect 212 in its entirety.

Add the following Minor defects:

"213 Finish of base insulator cavity .65% 3.2 Visual
214 Surface finish .65% 3.9 Visual
215 Evidence of poor workmanship 1.0% 3.14 Visual".

PAGE 14

4.4.2.5, Critical defect 2: Change "Visual/4.5.9" to "Visual/Lighting".

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T19:22Z
Check the source to verify that this is the current version before use.

PAGE 16

4.4.2.7: Delete Major defect 102 and substitute the following:

"102 Insulation or adhesive above max .40% 3.2 Gage".

PAGE 19

4.4.2.10: Change Dwg. No. from "9288037" to "9280132".

PAGE 20

4.4.3.1.1: In the third sentence change the word "selected" to "selecting".

PAGE 21

* 4.4.3.3: Delete: "ingate" and substitute "ingot"

* 4.4.3.5: Delete in its entirety.

* 4.4.3.7: Delete: "3.5.11" and substitute "3.11".

PAGE 22

* 4.4.3.9: Delete the first sentence and substitute the following:

"After qualification in accordance with TTC-490, two salt spray samples shall be taken each week, one during the first 30 minutes of production and a second at any other time."

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T19:22Z
Check the source to verify that this is the current version before use.

4.5.1: Delete in its entirety and substitute the following:

"The hardness test shall be conducted in accordance with ASTM Method E 103 and the following:

a. The surface of the body in the area to be hardness tested shall be prepared by machining or grinding a flat of sufficient depth, 0.15 inches minimum, to remove scale and get below the decarburization zone. (Note: Flats and impressions shall be completely removed by final machining.)

b. Hardness tester periodic verification shall be performd using Brinnell test standards manufactured in accordance with ASTM Method E-10 in lieu of production samples.

c. All hardness test measurements shall be automatically recorded.

d. The hardness tester shall use a standard 10mm Brinnel/Ball. The hardness tester shall determine hardness in accordance with the following test sequence. First, the tester shall clamp the body to be tested with a 10,000 - 500 lb. clamping load. Second, apply a minor load of approximately 10% of the 3000Kg of total test load. Third, apply the total test load. The clamping load will not be exceeded when the test load is applied. Fourth, relax the total test load back to the minor load. Fifth, automatically measure this penetrator travel from initial minor load position to new minor load position following application of the total load. Sixth, display hardness and release the body.

e. One reading shall be taken at location X and one at location Y as indicated on Dwg. 9287943."

PAGE 23

* 4.5.2, line 22: Delete "in accordance with Data Item Description DI-T-1906".

* 4.5.3, line 4: Delete "in accordance with Data Item Description DI-T-1906".

* 4.5.6: Delete in its entirety.

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T19:22Z
Check the source to verify that this is the current version before use.

4.5.7: Delete the first two sentences and substitute the following:

"The unpainted warhead, after nose threading but prior to base threading and knurling, shall be mounted in a suitable test fixture in accordance with Dwg. 9287968. The warhead will then be subjected to the pressure requirements on the applicable drawing. Any warhead which fails to comply with the applicable requirements shall be classed defective and removed from the lot."

PAGE 24

4.5.8: Delete the first two sentences and substitute the following:

"The warheads shall be ultrasonically inspected after threading the nose but prior to threading and knurling the base using equipment and procedures in accordance with 4.5.8.1. With the exception of the forward threaded area, the warhead shall be inspected with ultrasonics throughout all of the material."

PAGE 26

5.1: Change "Level C" to "Level B".

PAGE 27

6.5: Change "measured to gaged" to "measured or gaged".

PAGE 28

6.14: Delete in its entirety.

The margins of this amendment are marked with an asterisk to indicate where changes (additions, modifications, corrections, deletions) from the previous amendment were made. This was done as a convenience only and the Government assumes no liability whatsoever for any inaccuracies in these notations. Bidders and contractors are cautioned to evaluate the requirements of this document based on the entire content irrespective of the marginal notations and relationship to the last previous amendment.

Custodian:
Army - AR

Preparing activity:
Army - AR

(Project 1320-A646)

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T19:22Z
Check the source to verify that this is the current version before use.