MILITARY SPECIFICATION

STEEL : BARS AND FORGINGS, CHROMIUM-NICKEL-MOLYBDENUM-VANADIUM (FOR TORPEDO MK 46 MOD 0)

This specification is approved for use by the Naval Sea Systems Command, Department of the Navy, and is available for use by all departments and agencies of the Department of Defense.

1. SCOPE

1.1 Scope. This specification covers chromium-nickel-molybdenum-vanadium steel bars and forgings,

1.2 Classification.

1.2.1 Type. Bars and forgings are of the followings types in accordance with the methods of manufacturing (see 3.3,1.1):

Type I - Air-melted steel
Type II - Vacuum-melted steel

1.2.2 Grades. Forgings are classified in three grades in accordance with the methods of testing (see 3.3.1.2).

1.2.3 Composition. Bars and forgings are classified in two compositions in accordance with the percentage of sulphur and phosphorus (see 3,3.183).

1.2.4 Condition, Bars and forgings are classified in two conditions in accordance with the methods of annealing (see 3,3,1,4).

Source: https://assist.dla.mil -- Downloaded: 202610-23T04:57Z
Check the source to verify that this is the current version before use.

2, APPLICABLE DOCUMENTS

* 2.1 Issues of documents, The following documents of the issues in effect on the date of invitation for bids or request for proposals form a part of this specification to the extent specified herein, In the event of conflict between this specification-and other documents referenced herein, the requirements of this specification shall apply,

SPECIFICATIONS

Military

MIL-I-6868	Inspection Process, Magnetic Particle
MIL-C-16173	Corrosion Preventive Compound, Solvent Cutback, Cold-Application
MIL-U-81055	Ultrasonic Inspection, Immersion, of Wrought Metals, General Specifications for

STANDARDS

Federal

FED-STD-151	Metals : Test Methods

Military

MIL-STD-129	Marking for Shipment and Storage

(Copies of specifications, standards, drawings, and publications required by contractors in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

* 2.2 Other publications. The following documents form a part of this specification to the extent specified herein. Unless otherwise indicated, the issue in effect on the date of invitation for bids or request for proposals shall apply. In the event of conflict between this specification and other documents referenced herein, the requirements of this specification shall apply.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T04:57Z
Check the source to verify that this is the current version before use.

SPECIFICATIONS

Aerospace Material Specification (AMS)

AMS 2251	Tolerances - Alloy Steel Bars
AMS 2300	Premium Aircraft Quality Steel Cleanliness
AMS 2301	Aircraft Quality Steel Cleanliness
AMS 2808	Identification, Forgings

* (Copies of Aeorspace Material Specifications may be obtained from the Society of Automotive Engineers, Inc., 400 Commonwealth Drive, Warrendale, Pa. 15096,)

American Society for Testing and Materials (ASTM)

* ASTM E 9	Compression Testing of Metallic Materials at Room Temperature
ASTM E 45	Determining the' Inclusion Content of Steel
* ASTM E 112	Estimating the Average Grain Size of Metals
* ASTM A 255	End-Quench Test for Hardenability of Steel
* ASTM E 381	Macroetched Steel, Rating

(Application for copies of the ASTM standards by serial designation and title should be made to the American Society for Testing and Materials, 1916 Race Street, Philadelphia, Pa, 19103.)

3, REQUIREMENTS

3.1 Preproduction sample, When specified in the contract or order, a preproduction sample shall be manufactured using the procedure proposed for the production lot, The sample shall consist of sufficient material from each heat to perform the tests of 4.4 and shall be tested, as specified herein, for the purpose of determining, prior to starting production, that the suppliers production methods are capable of yielding bars and forgings that comply with the technical requirements of the contract, Any production of steel prior to approval of the preproduction sample shall be at the contractor's risk,

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T04:57Z
Check the source to verify that this is the current version before use.

3.2 Basic requirements.

3.2.1 Materials and treatments of materials. Unless otherwise specified in the contract or order, bars and forgings shall be manufactured and treated in accordance with the requirements specified herein,

3.2.2 Gages. The supplier shall provide whatever gages are necessary and adequate to assure that the bars and forgings will meet the requirements specified herein and the dimensions of the applicable drawings,

3.3 Physical characteristics.

3.3.1 Material. The bars and forgings shall be fine-grain, electric-furnace-grade steel and shall conform to the applicable requirements of this specification,

3.3.1.1 Type.

3.3.1.1.1 Type I, air-melted steel. Type I steel shall be manufactured in accordance with industry standards for electric-furnace-grade steel.

3.3.1.1.2 Type II, vacuum-melted steel. Type II steel shall be produced by consumable-electrode, vacuum remelting or by vacuum-induction melting, Type II steel shall conform to composition A.

3.3.1.2 Grade. Forgings shall be provided in three grades and shall be classified as grade A, B, or C in accordance with the tests to which they have been subjected. The tests for bars and each grade of forgings shall be as specified in table I.

3.3.1.3 Chemical composition. The chemical composition of the steel, as determined by a check analysis of the deliverable product, shall conform to the requirements of table 11, Steel is classified as composition A or B, in accordance with the percentage of sulphur and phosphorus it contains,

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T04:57Z
Check the source to verify that this is the current version before use.

TABLE I. Required tests for each grade of steel,

Tests	Forgings			Bars
	Grade A	Grade B	Grade C	
Chemical	X	X	X	X
Ultrasonic	X			
Magnetic particle	X	X	X	X
Grain flow	X	X		
Impact	X			
Grain size	X	X	X	X
Decarburization	X			X
Inclusion rating	X	X		X
Hardenability	X	X	X	X
Tensile	X	X	X	X
Macroetch test	X			X

TABLE II. Chemical composition of steel.

Element	Percent by weight	Product analysis	
		Under min.	Over max.
Carbon	0.33 - 0,38	0,02	0.02
Manganese	0,60 - 0,85	0,03	0.03
Silicon	0.40 - 0060	0,05	0.05
Chromium	0,65 - 0.90	0,03	0.03
Nickel	1,65 - 2,00	0,05	0.05
Molybdenum	0,30 - 0,40	0,02	0,02
Vanadium	0,17 - 0,23	0,02	0,02
Sulphur	0.010 Max. (comp A)[1] 0.025 Max. (comp B)		0.005
Phosphorous	0.025 Max. (comp A)[1] 0,025 Max. (comp B)		06005 0,005

‘Sulphur plus phosphorus shall be 0.025 percent maximum.

3.3.1,4 Condition.

* 3.3.1.4,1 Condition A. Condition A steel shall be annealed to a maximum hardness of Rockwell 241 HB (100 HRB), in accordance with ASTM E 9.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T04:57Z
Check the source to verify that this is the current version before use.

3.3.1.4.2 Condition B. Condition B steel shall be normalized and tempered to a maximum hardness of 30 HRC (100 HRB).

3.3.1.5 Hardenability. The steel shall be hardenable to a Rockwell "C" hardness of 56 maximum at 1 inch and 47 maximum at 1-1/2 inches from surface when tested in accordance with method ASTM A 225, using a normalizing temperature of 1700° ± 10° F.

3.3.1.6 Grain size, The austenitic grain size shall be predominantly No, 5 or finer with a single grain as large as No. 3 permissible per ASTM E 112.

3.3.1.7 Decarburization.

3.3.1.7.1 Bars. Ground, turned, or polished bars shall be free from decarburization ground, turned, or polished surfaces. Hot-rolled bars shall have decarburization no greater than that specified in table 111.

TABLE 111. Decarburization limits for bar stock,

Nominal distance between opposite faces (inch)	Maximum depth of decarburization (inch)[1]
up to 0.375	0.010
0.375 to 0.500	0.012
0.500 to 0.625	0.014
0.625 to 1.000	0.017
1.00 to 1.50	0.020
1.50 to 2.00	0.025
2.00 to 2.50	0.030
2.50 to 3.00	0.035
over 3.00 to 4.0 inclusive	0.045

[1]The value specified as the maximum depth of decarburization is the sum of the complete plus the partial decarburization.

3.3.1.7.2 Forgings. Forgings, all grades, shall have a decarburization of 0.035 inch depth, maximum, This limit shall include partial and complete decarburization.

Source: https://assist.dla.mil -- Downloaded: 202610-23T04:57Z
Check the source to verify that this is the current version before use.

3.3.1.8 Mechanical properties. After quenching in oil maintained at 125° ± 5° F from 1575° ± 25° F and tempering for 2 hours, minimum, at a temperature of 700° F, minimum, the material shall have the following mechanical properties:

a. Yield strength (0,2 percent offset) Longitudinal or transverse 190,000 psi, min.

b. Ultimate strength, longitudinal or transverse 215,000 psi, min.

c. Elongation in four diameters

(1) For stock 6 inches or less in greatest thickness, longitudinal orientation 10 percent, min.

(2) For stock over 6 inches in greatest thickness, transverse orientation 10 percent, min.

d. Impact strength (V-notch) 10 foot-pounds, min.

3.3.1.8.1 Bars shall be capable of meeting: longitudinal tensile strength--215,000 psi, min.; longitudinal yield strength (0,2% offset)--190,000 psi, min.; and longitudinal elongation in 2 inches--lO%, based or a forged or rolled 4-inch round heattreated in accordance with 3.3.1.8.

3.3.1.9 Internal defects. When inspected in accordance with table I, internal defects of bars, forgings, and forging stock shall be in accordance with the following requirements.

3.3.1.9.1 Inclusion rating. This rating is based on specimens representing the worst area of inclusions in the deliverable product. The procedure for determining the inclusion ratings shall be performed in accordance with method A, of ASTM E 45, The inclusion rating shall not exceed the average values listed in table IV.

3.3.1.9.2 Ultrasonic indications, Internal defects shall not exceed the criteria established for quality level I indications specified in MIL-S-81055.

Source: https://assist.dla.mil -- Downloaded: 202610-23T04:57Z
Check the source to verify that this is the current version before use.

TABLE IV. Inclusion rating.

Inclusion type[1]	Material type I		Material type II	
	Thin series	Heavy series	Thin series	Heavy series
A	2.0	2.0	1.5	1.0
B	3.0	2.0	1.5	1.0
C	3.0	2.0	1.0	1.0
D	2.0	3.0	2.0	1.5

[1]ASTM E 45.

3.3.1.9.3 Macroetch testing of bars, type I, composition B. Visual examination of deep-acid-etched reforging stock in sizes up to and including 36 square inches shall be equal to or better than $S_2R_1C_2$; sizes over 36 to and including 100 square inches shall be equal to or better than $S_2R_2C_3$ of ASTM E 381. Macroscopic examination of finished bars is required only if the manufacturers inspection of the microstructure at an earlier stage of processing such as forged bars, blooms, or billets has not been accomplished, Two or more billet slices at least 1/4 inch thick shall be selected to represent each heat of steel from which material is submitted for acceptance.

3.3.1.10 Surface defects. The steel shall have no imperfections of a nature or degree that will be detrimental to the stamping, forming, machining, or fabrication of finished parts.

3.3.1.11 Tolerances. Unless otherwise specified, tolerances for bar stock shall conform to AMS 2251. Tolerances for forgings shall be as specified by the applicable engineering documents,

3.3.2 Forgings.

3.3.2.1 Process. Unless a specific process is designated, forgings shall be formed by any of the following processes:

a. Smith (flat die)
b. Hammer die
c. press die
d. Hot upset
e. Ring roll

Source: https://assist.dla.mil -- Downloaded: 202610-23T04:57Z
Check the source to verify that this is the current version before use.

3.3.2.2 Grain flow. Forging stock shall be of such size and dimensions that the work accomplished in forming to finished shape shall result in approximately uniform grain size throughout. The forging techniques employed shall produce an internal grain flow pattern such that the direction of flow in highly stressed areas shall be essentially parallel to the principal stresses, as specified in applicable engineering documents. The grain flow pattern shall be essentially free from re-entrant and from sharply folded flow lines.

3.3.2.3 Welding, Forgings shall not be welded, except as indicated on applicable drawings approved by the procuring activity.

3.3.2.4 Flash. Forging flash shall be removed substantially flush with the adjacent surfaces, Gouging or penetration below the forging surface shall not be permitted.

3.3.2.5 Cleaning, All forgings shall be thoroughly cleaned by tumbling machining, shot or sand blasting, pickling, or other process approved by the procuring activity.

3.3.2.5.1 Cleanliness. Unless otherwise specified, the steel shall conform to the requirements of the following specifications:

a. Type I AMS 2301 on a heat qualification basis
b. Type II AMS 2300

* 3.3.3 Identification marking. Each bar or forging shall be identified with the following information as applicable:

a. Number and revision letter of this specification
b. Supplier identification
c. Supplier heat number
d. Type, composition, and condition
e. Grade of forgings
f. Drawing number of machined forging
g. Serial number (forgings only).

3.3.3.1 Bars. The identification characters shall not be less than three-eighths inch in height, shall be applied using a suitable marking fluid, and shall be capable of being removed in hot alkaline cleaning solution without rubbing. The characters shall be sufficiently durable to withstand ordinary handling.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T04:57Z
Check the source to verify that this is the current version before use.

3.3.3.1.1 Marking location. Each bar shall be marked in lengthwise rows of characters recurring at intervals of not greater than 2 feet, with the rows not greater than 3 inches apart and alternately staggered.

3.3.3.1.1.1 Alternate location. When the procuring activity so authorizes, each bar may be marked near one end.

3.3.3.2 Forgings. The method of marking forgings shall be in accordance with the requirements of AMS 2808.

3.3.4 Workmanship. Bars and forgings furnished under this specification shall be uniform in quality and shall be free from tears, internal ruptures, imbedded scale, segregations, or other imperfections considered detrimental to the suitability of the product for the intended use.

4. QUALITY ASSURANCE PROVISIONS

* 4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the contractor is responsible for the performance of all inspection requirements as specified herein, Except as otherwise specified in the contract or order, the contractor may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government, The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

4.2 Classification of inspections. Inspection of the steel bars and forgings shall be classified as preproduction inspection and acceptance inspection. The inspection samples shall be subjected to the tests specified in table I, as applicable, using the test methods specified herein,

4.3 Sampling. After samples have been separated from the parent material, no further forging or heat reduction shall be performed on the material for test samples, The test samples, if made separately from the forging, shall be heattreated with the forgings they represent.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T04:57Z
Check the source to verify that this is the current version before use.

4.3.1 Preproduction samples. The preproduction samples of steel bars and forgings (specified in the contract or purchase order) shall be manufactured in accordance with 3,1 and 3,3, and shall be subjected to the tests detailed in 4.4 at an activity designated by the procuring activity Acceptance of the preproduction sample shall be based on no defects in the sample.

4.3.1.1 Chemical analysis. A minimum of one sample for chemical analysis shall be taken from each heat of steel represented in the forgings or bars, Samples shall be taken from any point midway between the surface and center of solid forgings or bars or forging stock where the sections exceed 1-1/2 inches, or at any point midway between the inner and outer surfaces of the wall of hollow forgings, For forgings or bars or forging stock where sections are 1-1/2 inches or less, samples shall be taken by drilling entirely through the material, the surface drillings being discarded, Upon approval of the procuring activity, samples may be taken from broken tensile specimens, Each sample shall consist of not less than 2 ounces of material. Samples for chemical analysis may be waived, at the discretion of the procuring activity, provided that all the material under inspection can be identified as being made from a heat or heats previously analyzed and found to be in accordance with requirements of the respective material specification.

4.3.1.2 Ultrasonic inspection. Unless otherwise authorized by the procuring activity, each grade A forging shall be ultrasonically inspected in accordance with MIL-U-81055.

4.3.1.3 Grain flow, After the forging technique has been established, one forging (grades A and B only) shall be selected to represent grain flow. If the forging practice is altered, one additional forging shall be submitted for each change in forging practice.

4.3.1.4 Impact. For grade A forgings, three or more samples representing each heat of steel submitted for acceptance shall be selected for impact testing.

4.3.1.5 Grain size. One or more samples shall be selected from each heat of steel represented in a shipment.

4.3.1.6 Decarburization. One or more samples shall be selected from each processing condition for decarburization testing.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T04:57Z
Check the source to verify that this is the current version before use.

4.3.1.7 Inclusion rating. Sampling for inclusion rating shall be in accordance with ASTM E 45, method A.

4.3.1.8 Hardenability. One or more samples for the end-quench hardenability tests shall be selected and tested from each heat of steel represented in a shipment.

4.3.1.9 Tensile specimens. Three or more tensile test specimens, from the same heat, physical condition, and size as the material that is submitted for acceptances shall be selected from each processing condition of forgings. When forgings are made in multiple from a single forging, that is, forged in one piece and cut apart during machining, tests on samples from the larger forging shall apply to the individual units.

4.3.1.9.1 Selection of tensile specimens. Whenever practicable, the samples for tensile test specimens shall be taken from the material in a section where the least reduction takes place, When this is not practicable because of the size or shape of the forging or because of the excessive cost of destroying a component part, test specimens shall be taken from full-size prolongation of the material in the direction of the maximum reduction. When neither of the above methods is possible, a separate test coupon may be prepared from the same billet or bloom as the forging or bar it represents. The percentage reduction given this coupon shall be l ot greater than the minimum amount of reduction given the forging.

4.3.2 Acceptance inspection samples. The quantity and type of samples for acceptance inspection shall be the same as the preproduction samples (4.3.1).

4.4 Test methods. The test methods specified in table V shall be used to determine that the material meets the requirements of this specification.

4.4.1 Chemical composition. Chemical analysis shall be accomplished in accordance with FED-STD-151 by wet chemical, spectrochemical, or other approved analytic methods, In the event of dispute, analysis shall be by wet chemical methods except for carbon which shall be by the combustion method, The chemical composition shall conform to the requirements of 3.3.1.3.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T04:57Z
Check the source to verify that this is the current version before use.

TABLE V. Test methods.

	Test	Method	Result to conform to-
	Chemical composition	(See 4.4.1)	3.3.1.3
	Hardness (Brinell)	FED-STD-151, ASTM E 10	3.3.1.4.1 or 3.3.1.4.2 (as applicable)
*	Hardenability (end-quench)	ASTM A 255	3.3.1.5
	Grain size (austenite)	FED-STD-151, method 311	3.3.1.6
	Decarburization	(See 4.4.2)	3.3.1.7.1 or 3.3.1.7.2 (as applicable)
*	Mechanical properties (tension)	FED-STD-151, method 211	3.3.1.8 (a), (b), and (c)
	Mechanical properties (impact)	FED-STD-151, method 221	3.3.1.8(d)
	Inclusion rating	ASTM E 45, method A	3.3.1.9.1
	Ultrasonic indications	(See 4.4.3)	3.3.1.9.2
	Surface defects	MIL-I-6868, wet process	3.3.1.10
	Tolerance (bars)	AMS 2251	3.3.1.11
	Tolerance (forgings)	Applicable drawings	Applicable drawings
	Cleanliness (type I steel)	AMS 2301	3.3.2.5.1
	Cleanliness (type II steel)	AMS 2300	3.3.2.5.1
	Grain flow (macroetch)	FED-STD-151, method 321[1]	3.3.2.2

[1]This test method shall be used to check grain flow structure and may be waived at the discretion of the procuring activity when the size of the forging is so large as to make sectioning impracticable.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T04:57Z
Check the source to verify that this is the current version before use.

4.4.2 Decarburization testing. Unless otherwise agreed upon by the procuring activity and supplier, decarburization shall be measured by a hardness traverse-of the cross-section of a representative hardened bar or forging, Hardness readings shall be accomplished by Vickers, Knoop, or other hardness methods approved by the procuring activity, The depth of decarburization shall be measured from the original surface to the point at which no further increase in hardness occurs. Forgings that shall be machined on all surfaces to remove 0.050 inch minimum of material may be exempted from the test, Decarburization shall conform to the requirements of 3.3.1.7.1 or 3.3.1.7.2 as applicable, Depth of the zone of decarburization below a surface shall be determined by examination of a metallographic specimen or specimens representing the entire cross section of bars 1 inch or less in diameter or width, With bars over 1 inch in diameter or width, the section shall exhibit not less than 1 linear inch of the original surface of the bar, This specimen shall be polished, etched with 5 percent nital, and examined at 100 diameters magnification,

4.4.3 Ultrasonic testing. Unless otherwise specified by the procuring activity, each grade A forging shall be completely inspected in accordance with MIL-U-81055, quality level I.

4.4. Examination, Forgings and bars shall be examined to ensure compliance with the requirements of this specification with respect to workmanship, tolerances, identification, preservation, packing, and marking,

4.5 Rejection. Forgings or bars that fail to meet all applicable requirements of this specification shall be rejected.

5. PACKAGING

5.1 Preservation-packaging, Unless otherwise specified, all materials shall be prepared for storage by coating with corrosion preventive compound conforming to MIL-C-16173, grade 2.

5.2 Packing. All material shall be packed in such a manner as to prevent damage during ordinary handling and transportation.

5.3 Marking. Interior packages and exterior shipping containers shall be marked in accordance with MIL-STD-129. Marking shall include the following:

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T04:57Z
Check the source to verify that this is the current version before use.

a. Supplier's name
b. Product designation or drawing number (Forgings only)
c. Lot number or heat number
d. Date of manufacture
e. Number of pieces
f. Specification number, revision letter, type, and composition.

6. NOTES

6.1 Intended use. Material procured in accordance with this specification is intended primarily for fabrication of parts which require fusion, resistance, or flash welding and shall be capable of attaining a minimum pressure of 190,000 psi, 0.2 percent offset yield strength after heat treatment by oil quenching or Marquenching and tempering.

6.2 Ordering data. Procurement documents should specify the following:

a. Title, number, and date of this specification
b. Material form (bars or forgings)
c. Type and grade (of forging), or type of bar (1.2.1 and 1.2.2)
d. Composition and condition (1.2.3 and 1.2.4)
e. Preproduction inspection (see 3.1)
f. Lot size
g. Place of delivery,
h. Alternate marking, if permitted
i. Forging process,if applicable
j. Serial number (forgings only).

* 6.3 The margins of this specification are marked with asterisks to indicate where changes (additions, modifications, corrections, deletions) from the previous issue were made. This was done as a convenience only and the Government assumes no liability whatsoever for any inaccuracies of these notations, Bidders and contractors are cautioned to evaluate the requirements of this document based on the entire content irrespective of the marginal notations and relationship to the last previous issue.

Custodian:
Navy - OS

Preparing activity:
Navy - OS
(Project No. 1355-N385)

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T04:57Z
Check the source to verify that this is the current version before use.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T04:57Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

OMB Approval
No. 22-R255

INSTRUCTIONS: The purpose of this form is to solicit beneficial comments which will help achieve procurement of suitable products at reasonable cost and minimum delay, or will otherwise enhance use of the document. DoD contractors, government activities, or manufacturers/vendors who are prospective suppliers of the product are invited to submit comments to the government. Fold on lines on reverse side, staple in corner, and send to preparing activity. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or to amend contractual requirements. Attach any pertinent data which may be of use in improving this document. If there are additional papers, attach to form and place both in an envelope addressed to preparing activity.

DOCUMENT IDENTIFIER AND TITLE MIL-S-81054A(OS) Steel: Bars and Forgings, Chromium-Nickel-Molybdenum-Vanadium (For Torpedo Mk 46 Mod 0)

NAME OF ORGANIZATION AND ADDRESS

CONTRACT NUMBER

MATERIAL PROCURED UNDER A

☐ DIRECT GOVERNMENT CONTRACT ☐ SUBCONTRACT

1. HAS ANY PART OF THE DOCUMENT CREATED PROBLEMS OR REQUIRED INTERPRETATION IN PROCUREMENT USE?
   A. GIVE PARAGRAPH NUMBER AND WORDING.

   B. RECOMMENDATIONS FOR CORRECTING THE DEFICIENCIES

2. COMMENTS ON ANY DOCUMENT REQUIREMENT CONSIDERED TOO RIGID

3. IS THE DOCUMENT RESTRICTIVE?

   ☐ YES ☐ NO *(If "Yes", in what way?)*

4. REMARKS

SUBMITTED BY *(Printed or typed name and address - Optional)*

TELEPHONE NO.

DATE

DD FORM 1 JAN 72 1426

REPLACES EDITION OF 1 JAN 66 WHICH MAY BE USED

S/N 0102-014-1802

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T04:57Z
Check the source to verify that this is the current version before use.

FOLD

POSTAGE AND FEES PAID

U.S. MAIL

OFFICIAL BUSINESS
PENALTY FOR PRIVATE USE $300

Commanding Officer
Naval Ordnance Station
Attn: 611
Indian Head, Maryland 20640

FOLD

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T04:57Z
Check the source to verify that this is the current version before use.