MIL-W-585E(ME)
4 February 1976
SUPERSEDING
MIL-W-585D
30 October 1967

MILITARY SPECIFICATION

WIRE FABRIC: STEEL, WELDED

This specification is approved for use by the U.S. Army Mobility Equipment Research and Development Center, Department of the Army, and is available for use by all Departments and Agencies of the Department of Defense.

1. SCOPE

1.1 Scope. This specification covers welded steel-wire fabric, to include bare or coated wire.

1.2 Classification. The wire fabric shall be of the following types and mesh sizes, as specified (see 6.2):

Type II - 2- by 2-inch, 2- by 2-1/2-inch, or 2- by 2-5/8-inch mesh (19 Gage).

Type III - 2- by 6-inch mesh (16 Gage).

2. APPLICABLE DOCUMENTS

2.1 Issues of documents. The following documents of the issue in effect on date of invitation for bids or request for proposal form a part of this specification to the extent specified herein.

SPECIFICATIONS

FEDERAL

QQ-S-781 - Strapping, Steel, and Seals.

FSC 5335

Source: https://assist.dla.mil -- Downloaded: 202610-16T07:50Z
Check the source to verify that this is the current version before use.

STANDARDS

FEDERAL

FED. STD. No. 356	- Commercial Packaging of Supplies and Equipment.

MILITARY

MIL-STD-105	- Sampling Procedures and Tables for Inspection by Attributes.
MIL-STD-129	- Marking for Shipment and Storage.
MIL-STD-130	- Identification Marking of US Military Property.

(Copies of specifications and standards required by suppliers in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

2.2 Other publications. The following documents form a part of this specification to the extent specified herein. Unless otherwise indicated, the issue in effect on date of invitation for bids or request for proposal shall apply.

AMERICAN SOCIETY FOR TESTING AND MATERIALS (ASTM)

A 390-71 - Zinc-Coated (Galvanized) Steel Poultry Netting (Hexagonal and Straight Line) and Woven Steel Poultry Fencing.

(Application for copies should be addressed to the American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.)

(Technical society and technical association specifications and standards are generally available for reference from libraries. They are also distributed among technical groups and using Federal agencies.)

3. REQUIREMENTS

3.1 Description. The welded wire fabric shall consist of a series of longitudinal and transverse steel wire arranged at right angles to each other and welded together at all points of intersection.

Source: https://assist.dla.mil -- Downloaded: 202640-16T07:50Z
Check the source to verify that this is the currentversion before use.

3.2 Material. Material shall be as specified herein. Materials not specified shall be selected by the supplier and shall be subject to all provisions of this specification.

3.3 Construction. The welded wire fabric shall be constructed of wire accurately spaced and alined in the finished product. The longitudinal and transverse wires shall be spaced center to center in accordance with the mesh size as specified herein. The wire shall be securely connected at each area of intersection by either the percussive or the flash welding (resistance) process to provide coalescence over the entire fabric.

3.3.1 Dimensions. The tolerance in the spacing of the mesh shall be plus or minus 1/8 inch. Tolerance in the full length of the fabric shall be within plus or minus 2 percent, and for the full width shall be within plus or minus 1/2 inch. The wire fabric shall be furnished in rolls 150 feet long and 72 inches wide.

3.4 Zinc coating. The wire fabric shall be zinc coated after welding in accordance with ASTM A 390.

3.5 Type II. Type II wire fabric shall be constructed of steel wire conforming to ASTM A 390 having a nominal diameter of 0.041 inch (19 gage).

3.6 Type III. Type III wire fabric shall be constructed of steel wire conforming to ASTM A 390 having a nominal diameter of 0.062 inch (16 gage).

3.7 Identification marking. Each roll of welded wire fabric shall be identified in accordance with MIL-STD-130. In addition, special marking shall include a metal tag bearing the wire diameter, mesh size, and the length and width of the fabric roll.

3.8 Workmanship. The welded wire fabric shall be uniform and free from kinks, broken wires, and rust pits. All protruding ends of the wire shall be cut flush with the sides and ends of the finished wire fabric.

Source: https://assist.dla.mil -- Downloaded: 202610-16T07:50Z
Check the source to verify that this is the current version before use.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract, the contractor is responsible for the performance of all inspection requirements specified herein. Except as otherwise specified in the contract, the contractor may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

4.1.1 Material inspection. The supplier is responsible for insuring that materials used are manufactured, examined, and tested in accordance with referenced specifications and standards, as applicable.

4.2 Classification of inspections. The inspection requirements specified herein are classified as follows:

(a) Quality conformance inspection (see 4.3).
(b) Inspection of preparation for delivery (see 4.5).

4.3 Quality conformance inspection.

4.3.1 Sampling. Sampling for examination shall be in accordance with MIL-STD-105, Level S-2.

4.3.1.1 Lot. A lot shall consist of all fabricated wire fabric of the same type offered at the same time.

4.3.2 Examination. Samples selected in accordance with 4.3.1 shall be examined as specified in 4.4.1. AQL shall be 2.5 percent defective for major defects and 6.5 percent defective for minor defects.

4.4 Inspection procedure.

4.4.1 Examination. The welded wire fabric shall be examined as specified herein for the following defects:

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T07:50Z
Check the source to verify that this is the current version before use.

Major

101. Welding not as specified.
102. Mesh size not as specified.
103. Wire size not as specified.
104. Zinc coating not as specified.
105. Workmanship not as specified.

Minor

201. Width and length of roll not as specified.
202. Marking not as specified.

4.5 Inspection of preparation for delivery.

4.5.1 Quality conformance inspection of pack.

4.5.1.1 Unit of product. For the purpose of inspection, a completed pack prepared for shipment shall be considered a unit of product.

4.5.1.2 Sampling. Sampling for examination shall be in accordance with MIL-STD-105.

4.5.1.3 Examination. Samples selected in accordance with 4.5.1.2 shall be examined for the following major defects. AQL shall be 2.5 percent defective.

106. Materials and methods not as specified for Level A.
107. Ends of wire not bent as specified for Level A.
108. Strapping not as specified for Level A.
109. Strapping not positioned as specified for Level A.
110. Marking missing, illegible, incorrect, or incomplete.

5. PACKAGING

5.1 Packing. Packing shall be Level A or Commercial, as specified (see 6.2).

5.1.1 Level A. The ends of the wire on the outside of the rolls shall be bent into the rolls to prevent snagging. Each roll shall be secured with strapping conforming to QQ-S-781, Class 1, Type I or IV,

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T07:50Z
Check the source to verify that this is the current version before use.

size as applicable or Class 2, Type IV, size as applicable. Unless otherwise specified (see 6.2), strapping shall be Finish B. When specified (see 6.2), strapping shall be Finish A. The strapping shall be positioned 6 inches from each end of the roll and intermediate straps spaced not more than 20 inches apart.

5.1.2 Commercial. The wire shall be packed in accordance with FED. STD. No. 356.

5.2 Marking.

5.2.1 Level A. Level A marking shall be in accordance with MIL-STD-129.

5.2.2 Commercial. Commercial marking shall be in accordance with FED. STD. No. 356.

6. NOTES

6.1 Intended use. Types II and III welded wire fabrics are intended for use as a base in the manufacture of camouflage garnish netting.

6.2 Ordering data. Procurement documents should specify the following:

(a) Title, number, and date of this specification.
(b) Type and mesh size of wire fabric required (see 1.2).
(c) Degree of packing required (see 5.1).
(d) When strapping shall be other than as specified (see 5.1.1).

6.3 Classification changes. Type I, Classes 1, 2, and 3 have been deleted. Deleted material is covered in RR-W-375. Two- by 2-inch mesh has been added to Type II.

Custodian:

Army - ME

Preparing activity:

Army - ME

Review activities:

Army - MU, MI
DSA - IS

Project No. 5335-0130

Source: https://assist.dla.mil -- Downloaded: 202610-16T07:50Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

OMB Approval
No. 22-R255

INSTRUCTIONS. The purpose of this form is to solicit beneficial comments which will help achieve procurement of suitable products at reasonable cost and minimum delay, or will otherwise enhance use of the document. DoD contractors, government activities, or manufacturers' vendors who are prospective suppliers of the product are invited to submit comments to the government. Fold on lines on reverse side, staple in corner, and send to preparing activity. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or to amend contractual requirements. Attach any pertinent data which may be of use in improving this document. If there are additional papers, attach to form and place both in an envelope addressed to preparing activity.

DOCUMENT IDENTIFIER AND TITLE
MIL-W-585E(ME) Wire Fabric: Steel, Welded

NAME OF ORGANIZATION AND ADDRESS

CONTRACT NUMBER

MATERIAL PROCURED UNDER A
☐ DIRECT GOVERNMENT CONTRACT ☐ SUBCONTRACT

1 HAS ANY PART OF THE DOCUMENT CREATED PROBLEMS OR REQUIRED INTERPRETATION IN PROCUREMENT USE?
a GIVE PARAGRAPH NUMBER AND WORDING

b RECOMMENDATIONS FOR CORRECTING THE DEFICIENCIES

2 COMMENTS ON ANY DOCUMENT REQUIREMENT CONSIDERED TOO RIGID

3 IS THE DOCUMENT RESTRICTIVE?
YES NO If "Yes", in what way?

4 REMARKS

SUBMITTED BY (Printed or typed name and address - Optional)

TELEPHONE NO

DATE

DD FORM 1 JAN 72 1426

PREVIOUS EDITION OF 1 JAN 68 MAY BE USED

Source: https://assist.dla.mil -- Downloaded: 202610-16T07:50Z
Check the source to verify that this is the current version before use.

FOLD

POSTAGE AND FEES PAID
DEPARTMENT OF THE ARMY
DOD – 314

OFFICIAL BUSINESS
PENALTY FOR PRIVATE USE $300

Commander
US Army Mobility Equipment Research and
Development Command
ATTN: DRXFB-DS
Fort Belvoir, VA 22060

FOLD

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T07:50Z
Check the source to verify that this is the current version before use.