INCH-POUND
MIL-DTL-24643/54E
22 August 2002
SUPERSEDING
MIL-C-24643/54D
22 November 1994

DETAIL SPECIFICATION SHEET

CABLE, ELECTRICAL, TYPE LS8NW6

This specification is approved for use by all Departments and Agencies of the Department of Defense.

The requirements for acquiring the product described herein shall consist of this specification sheet and the issue of MIL-DTL-24643 listed in that issue of the Department of Defense Index of Specifications and Standards (DoDISS) specified in the solicitation.

REQUIREMENTS:

Qualification required.

Construction (non-watertight)

First -	Copper conductor, uncoated, AWG size 12, class B stranding, ASTM B8.
Second -	Separator (opaque white) may be used at manufacturer's option where required to provide free-stripping insulation.
Third -	Cross-linked polyethylene or ethylene propylene rubber insulation. Minimum average thickness 0.030 inch. Standard identification code shall be applied by method 1 or method 3. When identification method 1 is used insulation color shall be black.
Fourth -	Eight conductors cabled together with a lay not greater than 24 times the pitch diameter. Fillers shall be used as necessary to form a firm, well-rounded assembly.
Fifth -	Binder tape applied helically with overlap.
Sixth -	Cross-linked polyolefin jacket. Minimum average thickness 0.040 inch. Maximum overall diameter 0.670 inch.

Notes 1.LS8NW6 military part number - M24643/54-01UN.

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.
Source: https://assist.dla.mil -- Downloaded: 2026-10-20T00:17Z
Check the source to verify that this is the current version before use.

EXAMINATION AND TESTS:

Basic electrical:	Requirements
Conductor Resistance - ohms/1000 feet at 25°C, maximum	1.72
Voltage withstand - volts, root mean square, minimum	4000
Insulation resistance - Conductor to conductor,	
Megohms -1000 feet, minimum	4200
Conductor continuity	No failure

Group A:	
Visual and dimensional	No failure

Group B:	
Cross-linked proof test (percent, maximum)	
Insulation	50
Jacket (When tested at 200°C)	50
Cold bending, cable - 5 inch mandrel diameter maximum	No damage
Tear - pounds per inch thickness, minimum (ASTM D 470)	35
Physicals (unaged)	
Insulation	
Ethylene propylene rubber	
Tensile strength - lb/in^2, minimum	700
Elongation - percent, minimum	250
Cross-linked polyethylene	
Tensile strength - lb/in^2, minimum	1800
Elongation - percent, minimum	250
Jacket (cable)	
Tensile strength - lb/in^2, minimum	1300
Elongation - percent, minimum	160

Group C:	
Physicals - (aged)	
Insulation	
Ethylene propylene	
Air oven	
Tensile strength - percent of unaged, minimum	75
Elongation - percent of unaged minimum	75
Cross-linked polyethylene	
Air oven	
Tensile strength - percent of unaged, minimum	80
Elongation - percent of unaged minimum	80

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T00:17Z
Check the source to verify that this is the current version before use.

Jacket (cable)
Air oven
Tensile strength - percent of unaged, minimum 60
Elongation - percent of unaged minimum 60
Hot oil immersion
Tensile strength - percent of unaged, minimum 50
Elongation - percent of unaged, minimum 50
Shrinkage ..... No failure
Heat distortion - percent of unaged, maximum 30
Permanence of printing (conductor) (method 1 only)
cycles, minimum 25
Permanence of printing (jacket) - cycles,
minimum (method 1 only) 125

Group D:
Flame propagation (cable) ..... No failure

QUALIFICATION INSPECTION:

Qualification inspection shall include basic electrical, all of groups A, B, C and D, plus the following:

	Requirements
Cold working (minus 20 ± 2°C)	No damage
Aging and compatibility (cable) (125 ± 5°C)	No failure
Abrasion resistance (jacket) - scrapes, minimum	75
Acid gas equivalent - percent, maximum	
Jacket	2
Fillers	2
Insulation	18
Halogen content - percent, maximum	
Jacket	0.2
Fillers	0.2
Immersion (jacket)	
Tensile strength - percent of unaged, minimum	50
Elongation - percent of unaged, minimum	50
Smoke index, maximum	
Jacket	25
Fillers	45
Insulation	45
Toxicity index, maximum	
Jacket	5
Fillers	5
Insulation	1.5
Durometer (jacket) - (type A) hardness, minimum	80
Weathering (jacket)	No failure

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T00:17Z
Check the source to verify that this is the current version before use.

UNIT ORDERING LENGTHS: 2000 feet nominal

Custodians:
Army - MI
Navy - SH

Preparing Activity:
Navy - SH
(Project 6145-2308-052)

Review Activities:
Army - AV, CR
Navy - CG, EC
DLA – CC

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T00:17Z
Check the source to verify that this is the current version before use.