INCH-POUND
MIL-DTL-24643/55F
1 October 2009
SUPERSEDING
MIL-DTL-24643/55E
22 August 2002

DETAIL SPECIFICATION SHEET

CABLE, ELECTRICAL, -20 °C TO +90 °C, TYPE LS4NW

This specification is approved for use by all Departments and Agencies of the Department of Defense.

The requirements for acquiring the product described herein shall consist of this specification sheet and MIL-DTL-24643.

Construction, Non-Watertight

First	-	Copper conductor, coated or uncoated 8 AWG, Class B stranding, ASTM B8.
Second	-	Separator may be used at manufacturer's option where required to provide free-stripping insulation.
Third	-	Thermoset insulation with 0.045-inch minimum average thickness. Standard identification code shall be applied by Method 1 or Method 3. If Method 1 is used, the insulation color shall be black.
Fourth	-	Four conductors cabled together with a lay in accordance with 3.4.4 of MIL-DTL-24643. Fillers may be used as necessary to form a firm well-rounded assembly.
Fifth	-	An optional binder.
Sixth	-	Cross-linked polyolefin jacket. Minimum average wall thickness of 0.050 inch. Maximum overall cable diameter 0.740 inch.

NOTE: LS4NW-8 military part number M24643/55-01UN.

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T00:17Z
Check the source to verify that this is the current version before use.

REQUIREMENTS:

Qualification required.

INSPECTION:

Basic Electricals:	
Conductor resistance (ohms/1000 feet at 25 °C, max.)	0.679
Voltage withstand (volts, root mean square, min.)	
Conductor to conductor	4500
Insulation resistance (megohms/1000 feet, min.)	
Conductor to conductor	4200
Conductor continuity	No failure
Group A:	
Visual and dimensional	No failure
Group B:	
Cold bending cable	No failure
Thermoset proof test (percent, max.)	
Insulation	50
Jacket (when tested at 200 °C)	50
Physicals (unaged)	
Insulation (extruded)	
Tensile strength (lb/in^2, min.)	700
Elongation (percent, min.)	150
Jacket (cable)	
Tensile strength (lb/in^2, min.)	1300
Elongation (percent, min.)	160
Tear (lb/in thickness, min.)	35
Group C:	
Physicals (aged) air oven	
Insulation (extruded)	
Tensile strength (percent of unaged, min.)	75
Elongation (percent of unaged, min.)	75
Jacket (cable)	
Tensile strength (percent of unaged, min.)	60
Elongation (percent of unaged, min.)	60

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T00:17Z
Check the source to verify that this is the current version before use.

Permanence of printing (conductor), Method 1 only (cycles, min.)	25
Permanence of printing (jacket) (cycles, min.)	125
Heat distortion (percent of unaged, max.)	30
Shrinkage	No failure
Group D:	
Flame propagation (cable)	No failure
Qualification Inspection:	
Qualification inspection shall include basic electricals; groups A, B, C, and D; plus the following:	
Cold Working (minus 20±2 °C)	No damage
Aging and compatibility (cable) (125±5 °C)	No failure
Abrasion resistance (jacket) (scrapes, min.)	75
Acid gas equivalent (percent, max.)	
Jacket	2
Fillers	2
Insulation	18
Halogen content (percent, max.)	
Jacket	0.2
Fillers	0.2
Insulation	0.2
Immersion (jacket)	
Tensile strength (percent of unaged, min.)	50
Elongation (percent of unaged, min.)	50
Smoke index (max.)	
Jacket	25
Fillers	45
Insulation	45
Toxicity index (max.)	
Jacket	5
Fillers	5
Insulation	1.5
Durometer (jacket) - Type A (hardness, min.)	80
Weathering (jacket)	No failure
Electrical moisture absorption	No FAILURE

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T00:17Z
Check the source to verify that this is the current version before use.

UNIT ORDERING LENGTHS:

Type and size	Feet (nominal)
LS4NW-8	1500

CHANGES FROM PREVIOUS ISSUE: Marginal notations are not used in this revision to identify changes with respect to the previous issue due to the extent of the changes.

Custodians:
Army – MI
Navy – SH

Preparing Activity:
Navy – SH
(Project 6145-2008-059)

Review Activities:
Army – AR, AV, CR
Navy – CG, EC
DLA – CC

NOTE: The activities listed above were interested in this document as of the date of this document. Since organizations and responsibilities can change, you should verify the currency of the information above using the ASSIST Online database at http://assist.daps.dla.mil.

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T00:17Z
Check the source to verify that this is the current version before use.