INCH-POUND
MIL-DTL-24643/56F
1 October 2009
SUPERSEDING
MIL-DTL-24643/56E
22 August 2002

DETAIL SPECIFICATION SHEET

CABLE, ELECTRICAL, -20 °C TO +90 °C, TYPE LS2SWL

This specification is approved for use by all Departments and Agencies of the Department of Defense.

The requirements for acquiring the product described herein shall consist of this specification sheet and MIL-DTL-24643.

Construction, Watertight

First	-	Copper conductor, coated or uncoated 16 AWG, Class B stranding, ASTM B8.
Second	-	Separator may be used at manufacturer's option where required to provide free-stripping insulation.
Third	-	Thermoset insulation with nominal wall thickness 0.019 inch; wall thickness may vary from nominal as necessary, in order for completed cable to meet the specified electrical requirements. Colored insulation with one black and one white conductor for each pair.
Fourth	-	Two conductors (one black and one white) cabled together with a nominal lay of 3 inches to form a pair.
Fifth	-	An optional binder.
Sixth	-	Braided shield of 34 or 36 AWG tin-coated copper. Braid angle of 30 to 35 degrees; minimum coverage of 85 percent.
Seventh	-	Shield insulation of two polyester tapes, outer tape sealed. An alternate shield insulation may consist of one polyester tape plus an extruded jacket of a suitable transparent material, minimum average thickness of the transparent material 0.003 inch. The standard identification code shall be applied by Method 2.
Eighth	-	Seven shielded pairs cabled together with a lay in accordance with 3.4.4 of MIL-DTL-24643. Cabling sequence shall be consecutive, starting with pair no. 1, from the center outward. Fillers may be used as necessary to make a firm, well-rounded assembly.
Ninth	-	An optional binder.
Tenth	-	Cross-linked polyolefin jacket. Minimum average wall thickness of 0.075 inch. Overall cable diameter shall be 0.860 inch minimum, 0.910 inch maximum.

NOTE: LS2SWL-7 military part number M24643/56-01UN.

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T00:17Z
Check the source to verify that this is the current version before use.

REQUIREMENTS:

Qualification required.

INSPECTION:

Basic Electricals:	
Conductor resistance (ohms/1000 feet at 25 °C, max.)	4.66
Voltage withstand (volts, root mean square, min.)	
Conductor to conductor	2000
Conductor to shield	1000
Component shield to component shield	500
Insulation resistance (megohms/1000 feet, min.)	
Conductor to conductor	1000
Conductor to shield	500
Component shield to component shield	100
Conductor continuity	No failure
Shield continuity	No failure
Group A:	
Visual and dimensional	No failure
Capacitance	
Mutual capacitance, 1 kilohertz (KHz) (pF/ft, max.)	35
Capacitance unbalanced (percent max.)	10
Watertightness (see MIL-DTL-24643 for limits of water leakage)	No failure
Group B:	
Thermoset proof test (percent, max.)	
Insulation	50
Jacket (when tested at 200 °C)	50
Drip (95±1 °C)	Zero
Physicals (unaged)	
Insulation (extruded)	
Tensile strength (lb/in^2, min.)	700
Elongation (percent, min.)	150
Jacket (cable)	
Tensile strength (lb/in^2, min.)	1300
Elongation (percent, min.)	160

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T00:17Z
Check the source to verify that this is the current version before use.

Tear (lb/in thickness, min.)	35
Group C:	
Physicals (aged) air oven	
Insulation (extruded)	
Tensile strength (percent of unaged, min.)	75
Elongation (percent of unaged, min.)	75
Jacket (cable)	
Tensile strength (percent of unaged, min.)	60
Elongation (percent of unaged, min.)	60
Permanence of printing (jacket) (cycles, min.)	125
Heat distortion (percent of unaged, max.)	30
Shrinkage	No failure
Cable fill (sealant) removability	No failure
Shield (conformance to material, construction and coverage)	No failure
Group D:	
Flame propagation (cable)	No failure
Qualification Inspection:	
Qualification inspection shall include basic electricals; groups A, B, C, and D; plus the following:	
Cold Working (minus 20±2 °C)	No damage
Aging and compatibility (cable) (125±5 °C)	No failure
Abrasion resistance (jacket) (scrapes, min.)	75
Acid gas equivalent (percent, max.)	
Jacket	2
Fillers	2
Insulation	18
Shield insulation	2
Halogen content (percent, max.)	
Jacket	0.2
Fillers	0.2
Insulation	0.2
Immersion (jacket)	
Tensile strength (percent of unaged, min.)	50
Elongation (percent of unaged, min.)	50

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T00:17Z
Check the source to verify that this is the current version before use.

Smoke index (max.)	
Jacket	25
Fillers	45
Insulation	45
Toxicity index (max.)	
Jacket	5
Fillers	5
Insulation	1.5
Durometer (jacket) - Type A (hardness, min.)	80
Weathering (jacket)	No failure
Electrical moisture absorption	No failure

UNIT ORDERING LENGTHS:

Type and size	Feet (nominal)
LS2SWL-7	1500

CHANGES FROM PREVIOUS ISSUE: Marginal notations are not used in this revision to identify changes with respect to the previous issue due to the extent of the changes.

Custodians:
Army – MI
Navy – SH

Preparing Activity:
Navy – SH
(Project 6145-2008-060)

Review Activities:
Army – AR, AV, CR
Navy – CG, EC
DLA – CC

NOTE: The activities listed above were interested in this document as of the date of this document. Since organizations and responsibilities can change, you should verify the currency of the information above using the ASSIST Online database at http://assist.daps.dla.mil.

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T00:17Z
Check the source to verify that this is the current version before use.