INCH-POUND
MIL-DTL-24643/58F
1 October 2009
SUPERSEDING
MIL-DTL-24643/58E
22 August 2002

DETAIL SPECIFICATION SHEET

CABLE, ELECTRICAL, -20 °C TO +90 °C, TYPE LS2CS

This specification is approved for use by all Departments and Agencies of the Department of Defense.

The requirements for acquiring the product described herein shall consist of this specification sheet and MIL-DTL-24643.

Construction, Non-Watertight

First	-	Copper conductor, tin-coated, 26 AWG, 7 strands, ASTM B286.
Second	-	Separator may be used at manufacturer's option where required to provide free-stripping insulation.
Third	-	Thermoset insulation nominal wall thickness 0.015 inch; wall thickness may vary from nominal as necessary, in order for completed cable to meet the specified electrical requirements. Standard identification code shall be applied by Method 6.
Fourth	-	Two conductors (one black and one white) cabled together to form a pair in accordance with table I. All pairs to be left-hand lay.
Fifth	-	The specified number of pairs (see table II) cabled together with a lay in accordance with table III. Cabling sequence shall be consecutive, starting with no. 1 from the center outward. Fillers may be used as necessary to form a firm, well-rounded assembly.
Sixth	-	An optional binder.
Seventh	-	Braided shield of tin-coated copper.
Eighth	-	Spirally-wrapped polyethylene terephthalate (polyester film) separator tape.
Ninth	-	Braided shield of tin-coated copper.
Tenth	-	An optional binder.
Eleventh	-	Cross-linked polyolefin jacket (see table II for thickness).

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T00:19Z
Check the source to verify that this is the current version before use.

TABLE I. Pair lay.

LS2CS-77				65	66	67	62, 68, 71, 74, 77	63, 69, 72, 75	61, 64, 70, 73, 76
	LS2CS-60			53	54	55	45, 48, 51, 56, 59	43, 46, 49, 52, 56, 60	44, 47, 50, 58
		LS2CS-42		27, 39	28, 40	29, 41	19, 22, 25, 30, 33, 36, 42,	20, 23, 26, 31, 34, 37	21, 24, 32, 35, 38
			LS2CS-18	13	14	15	7, 10, 16	8, 11, 17	9, 12, 18
				1	2	3	4	5	6
Cable type and size				1.6	3.5	2.5	4.5	2.1	2.9
				Length of lay (inches)					

Pair number

TABLE II. Details.

Military part no. M24643/58	Type and size	Number of pairs	Cable jacket thickness min. avg. (inch)	Overall diameter	
				min. (inch)	max. (inch)
-01UD	LS2CS-6	6	0.063	0.400	0.430
-02UD	LS2CS-18	18	0.063	0.550	0.590
-03UD	LS2CS-42	42	0.063	0.750	0.800
-04UD	LS2CS-60	60	0.082	0.880	0.930
-05UD	LS2CS-77	77	0.085	1.000	1.070

TABLE III. Cable lay.

	LS2CS-6		LS2CS-18		LS2CS-42		LS2CS-60		LS2CS-77	
	No. of pairs	Lay (inches)	No. of pairs	Lay (inches)	No. of pairs	Lay (inches)	No. of pairs	Lay (inches)	No. of pairs	Lay (inches)
Core	6	3.5	6	3.5	1	1.6	6	3.5	3	2.75
Layer 1			12	6.0	7	4.0	12	6.5	9	5.0
Layer 2					14	6.5	18	8.0	15	7.5
Layer 3					20	8.5	24	10.0	22	10.0
Layer 4									28	12.0

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T00:19Z
Check the source to verify that this is the current version before use.

REQUIREMENTS:

Qualification required.

INSPECTION:

Basic Electricals:	
Conductor resistance (ohms/1000 feet at 25 °C, max.)	42.17
Voltage withstand (volts, root mean square, min.)	
Conductor to conductor	2000
Conductor to overall shield	1000
Insulation resistance (megohms/1000 feet, min.)	
Conductor to conductor	500
Conductor to overall shield	500
Overall shield to overall shield	100
Conductor continuity	No failure
Shield continuity	No failure
Jacket flaws	No failure
Group A:	
Visual and dimensional	No failure
Characteristic impedance, at 1 megahertz (MHz) (ohms)	135±15
Group B:	
Cold bending cable	No failure
Bending endurance	
At 25 °C (cycles, min.)	25
Thermoset proof test (percent, max.)	
Insulation	50
Jacket (when tested at 200 °C)	50
Physicals (unaged)	
Insulation (extruded)	
Tensile strength (lb/in^2, min.)	700
Elongation (percent, min.)	150
Jacket (cable)	
Tensile strength (lb/in^2, min.)	1300
Elongation (percent, min.)	160
Tear (lb/in thickness, min.)	35

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T00:19Z
Check the source to verify that this is the current version before use.

Group C:	
Physicals (aged) air oven	
Insulation (extruded)	
Tensile strength (percent of unaged, min.)	75
Elongation (percent of unaged, min.)	75
Jacket (cable)	
Tensile strength (percent of unaged, min.)	60
Elongation (percent of unaged, min.)	60
Permanence of printing (jacket) (cycles, min.)	125
Heat distortion (percent of unaged, max.)	30
Shrinkage	No failure
Shield (conformance to material, construction and coverage)	No failure
Surface transfer impedance (Type LS only)	
Milliohms per meter (max.)	700
EMP response (dB, min.)	60
Group D:	
Flame propagation (cable)	No failure
Qualification Inspection:	
Qualification inspection shall include basic electricals; groups A, B, C, and D; plus the following:	
Aging and compatibility (cable) (125±5 °C)	No failure
Abrasion resistance (jacket) (scrapes, min.)	75
Acid gas equivalent (percent, max.)	
Jacket	2
Fillers	2
Insulation	18
Shield insulation	2
Halogen content (percent, max.)	
Jacket	0.2
Fillers	0.2
Insulation	0.2
Immersion (jacket)	
Tensile strength (percent of unaged, min.)	50
Elongation (percent of unaged, min.)	50

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T00:19Z
Check the source to verify that this is the current version before use.

Smoke index (max.)	
Jacket	25
Fillers	45
Insulation	45
Toxicity index (max.)	
Jacket	5
Fillers	5
Insulation	1.5
Durometer (jacket) - Type A (hardness, min.)	80
Weathering (jacket)	No failure
Electrical moisture absorption	No failure

UNIT ORDERING LENGTHS:

Type and size	Feet (nominal)
LS2CS all sizes	1000

CHANGES FROM PREVIOUS ISSUE: Marginal notations are not used in this revision to identify changes with respect to the previous issue due to the extent of the changes.

Custodians:
Army – MI
Navy – SH

Preparing Activity:
Navy – SH
(Project 6145-2008-064)

Review Activities:
Army – AR, AV, CR
Navy – CG, EC
DLA – CC

NOTE: The activities listed above were interested in this document as of the date of this document. Since organizations and responsibilities can change, you should verify the currency of the information above using the ASSIST Online database at http://assist.daps.dla.mil.

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T00:19Z
Check the source to verify that this is the current version before use.