INCH-POUND
MIL-DTL-24643/66A(SH)
w/INT. AMENDMENT 1
11 July 2011

USED IN LIEU OF
MIL-DTL-24643/66A
28 January 2010

DETAIL SPECIFICATION SHEET

CABLE, ELECTRICAL, 1000 VOLTS, TYPE LS2OW

This specification is approved for interim use by the Naval Sea Systems Command. Other activities in the Department of Defense may use this interim amendment or may continue using MIL-DTL-24643/66A.

The requirements for acquiring the product described herein shall consist of this specification sheet and MIL-DTL-24643.

Construction (Watertight with Circuit Integrity)

First	-	Copper conductor, coated or uncoated (see table I for size).
Second	-	Thermoset insulation, extruded or taped (see table I for minimum average wall).
Third	-	Optional glass braid.
Fourth	-	Optional covering, unless required (see 3.3.5 of MIL-DTL-24643).
Fifth	-	Two conductors shall be cabled together to form a firm, well-rounded assembly with a lay not less than 8 or greater than 16 times the cabled diameter. Standard identification code applied by Method 1, 3, or 5. Fillers may be used as necessary to form a firm well-rounded assembly.
Sixth	-	Aluminum foil/polyester tape/aluminum foil. 0.002-inch thick with 45 percent overlap.
Seventh	-	Braided shield of tin-coated copper. AWG and coverage as necessary to comply with shield performance requirements.
Eighth	-	An optional binder.
Ninth	-	Cross-linked polyolefin jacket (see table I for wall thickness).

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T00:21Z
Check the source to verify that this is the current version before use.

TABLE I. Details.

Military part no. M24643/66 (type)	Conductors size (AWG)	Insulation resistance (megohms)	Insulation wall thickness min. avg. (inches)	Jacket wall thickness min. avg. (inches)	Overall diameter (inches)		Conductor resistance per 1000 feet at 25 °C (ohms)
					Min.	Max.	
-01UO (LS2OW-3)	16 (Class B)	500	0.018	0.027	0.412	0.442	4.3
-02UO (LS2OW-4)	14 (Class B)	500	0.018	0.028	0.429	0.460	2.68
-03UO (LS2OW-9)	10 (Class B)	500	0.018	0.036	0.513	0.551	1.08
-04UO (LS2OW-14)	9 (Class B)	500	0.025	0.040	0.639	0.686	0.859
-05UO (LS2OW-23)	7 (Class B)	500	0.025	0.050	0.743	0.797	0.543
-06UO (LS2OW-50)	3 (Class C)	200	0.035	0.050	0.894	0.959	0.21
-07UO (LS2OW-75)	1 (Class C)	175	0.035	0.050	1.033	1.108	0.134
-08UO (LS2OW-100)	0 (Class D)	160	0.035	0.060	1.149	1.232	0.106
-09UO (LS2OW-200)	0000 (Class D)	125	0.050	0.060	1.519	1.630	0.053

REQUIREMENTS:

Qualification Required.

INSPECTION:

Basic Electricals:

Conductor resistance (ohms/1000 feet at 25 °C, max.)	See table I
Voltage withstand (volts, root mean square, min.)	
Conductor to conductor (sizes 3 – 9)	3000
Conductor to conductor (sizes 14 – 200)	5000
Conductor to shield (sizes 3 – 9)	1500
Conductor to shield (sizes 14 – 200)	2500
Insulation resistance (megohms/1000 feet, min.)	
Sizes 3 – 200	See table I
Conductor and shield continuity	No failure
Jacket flaws	No failure

Group A:

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T00:21Z
Check the source to verify that this is the current version before use.

Visual and dimensional	No failure
Watertightness (see MIL-DTL-24643 for limits of water leakage)	No failure
Crack resistance (applicable to constructions using glass braids with coverings)	No damage
Group B:	
Thermoset proof test (percent, max.)	
Insulation (extruded insulations only)	50
Jacket (when tested at 200 °C)	50
Drip (95±1 °C)	Zero
Cold bending (cable)	No damage
Gas flame (1 hour)	No failure
Physicals (unaged)	
Insulation (extruded insulations only)	
Tensile strength (lb/in^2, min.)	700
Elongation (percent, min.)	150
Jacket (cable)	
Tensile strength (lb/in^2, min.)	1300
Elongation (percent, min.)	160
Tear (lb/in thickness, min.)	35
Group C:	
Physicals (aged) (air oven)	
Jacket (cable)	
Tensile strength (percent of unaged, min.)	60
Elongation (percent of unaged, min.)	60
Shrinkage	No failure
Heat distortion (percent of unaged, max.)	30
Permanence of printing (conductor – Method 1 only) (cycles, min.)	25
Permanence of printing (jacket) (cycles, min.)	125
Cable sealant removability	No failure
Surface transfer impedance	
Milliohms per meter, max.	700
EMP, response (db, min.)	60
Group D:	

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T00:21Z
Check the source to verify that this is the current version before use.

Flame propagation (cable)	No failure

Qualification Inspection:

Qualification inspection shall include basic electricals; groups A, B, C, and D; plus the following:

Gas flame (3 hours)	No failure
Aging and compatibility (cable) (125±5 °C)	No failure
Abrasion resistance	
Jacket (75 scraps, min.)	No damage
Insulation (extruded insulation only, 250 scraps, min.)	No damage
Acid gas equivalent (percent, max.)	
Jacket	2
Fillers	2
Insulation	18
Halogen content (percent, max.)	
Jacket	0.2
Fillers	0.2
Insulation	0.2
Immersion (jacket)	
Tensile strength (percent of unaged, min.)	50
Elongation (percent of unaged, min.)	50
Smoke index, max.	
Jacket	25
Fillers	45
Insulation	35
Toxicity index, max.	
Jacket	5
Fillers	5
Insulation	1.5
Durometer (jacket) – Type A (hardness, min.)	80
Weathering (jacket)	No failure

UNIT ORDERING LENGTHS:

Type and size	Feet (nominal)
LS2OW	500

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T00:21Z
Check the source to verify that this is the current version before use.

AMENDMENT NOTATIONS: The margins of this specification are marked with vertical lines to indicate modifications generated by this amendment. This was done as a convenience only and the Government assumes no liability whatsoever for any inaccuracies in these notations. Bidders and contractors are cautioned to evaluate the requirements of this document based on the entire content irrespective of the marginal notations.

Preparing Activity:
Navy – SH
(Project 6145-2011-028)

NOTE: The activities listed above were interested in this document as of the date of this document. Since organizations and responsibilities can change, you should verify the currency of the information above using the ASSIST Online database at https://assist.daps.dla.mil.

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T00:21Z
Check the source to verify that this is the current version before use.