



CLEAR AUTOMOTIVE NITROCELLULOSE LACQUER

REF: LN-450

1. PRODUCT DESCRIPTION:

Formulated with top quality raw materials such as nitrocellulose resin, active ingredients, solvents and selected additives to obtain a finish with good gloss, adhesion, hardness, flexibility and weather resistance.

2. USES:

It is especially used for refinishing cars, trucks, motorcycles, bicycles, and the metal-mechanic industry in general.

3. TECHNICAL DATA:

CHARACTERISTIC	STANDARD VALUE
Color	Clear
Weight/Gal (Kg/ Gl)	3.48 – 3.58
STORMER viscosity at 25°C.	120 – 125 KU
DRYING (25°C, 50% RH)	
Touch	15 minutes
Driving	60 minutes
Repainted	45 minutes

NOTE: Practical coverage may vary depending on the type of substrate to which it is applied, manner of application and film thickness.

4. SURFACE PREPARATION:

- ✓ Before applying TONNER® NITROCELLULOSIC LACQUER, it is necessary to check the surface to be worked on, in such a way that it is clean and dry, free of rust, grease, dust, dirt or any impurity that affects the final finish. Remove rust, paint and loose particles using sandpaper or putty knife.



DATA SHEET AUTOMOTIVE LINE

LN-450 CLEAR AUTOMOTIVE NITROCELLULOSE
LACQUER

FO GP 49

JULY 2023

VERSION 4

Page 2 of 3

- ✓ All defects that may affect the final surface finish must be repaired. If it is necessary to correct imperfections or patch up, apply *TONNER® PUTTY* following the application instructions (See Technical Data Sheet of the Putty). Subsequently apply *TONNER® NITROCELLULOSIC FINISH* following the application instructions (See Technical Data Sheet of the nitrocellulose primer). Once it is dry, sand and finish.

5. PRODUCT PREPARATION:

- ✓ Shake the paint very well with a spatula, scraping the wall and the bottom of the container, until a completely uniform material is obtained.
- ✓ Dilute 1 part of *TONNER® NITROCELLULOSIC LACQUER* with a maximum of 2 parts of **EXTRA FINE THINNER TONNER® TH-100**.
- ✓ It is recommended to maintain the suggested ratio so as not to alter the final properties of the product.
- ✓ Paint with a compressed air gun between 40 and 60 pounds. Gun opening 2.5 mm. The application distance should be 20 to 25 cm from the surface.
- ✓ Apply up to 3 coats with 45 minute intervals between coats.

6. PRESENTATIONS:

- ✓ 5 gallon pail
- ✓ Gallon
- ✓ Quart

7. STORAGE AND SAFETY RECOMMENDATIONS:

- ✓ Keep out of reach of children.
- ✓ The product must be kept stored in a well-ventilated and cool place.
- ✓ Keep away from heat, hot surfaces, sparks, open flames and other sources of ignition.
Do not smoke near or while handling the product.
- ✓ Contains flammable products.



**DATA SHEET
AUTOMOTIVE LINE**

LN-450 CLEAR AUTOMOTIVE NITROCELLULOSE
LACQUER

FO GP 49

JULY 2023

VERSION 4

Page 3 of 3

- ✓ Maintain natural or local ventilation when applying the product, since it gives off vapors that can combust in the presence of sparks, flames or any other source of ignition.
- ✓ Keep containers tightly sealed. Once the container is opened, the product should be used in the shortest possible time, following the storage and safety recommendations.
- ✓ Do not eat or drink while handling the product.
- ✓ Avoid prolonged inhalation of its vapors, using adequate protection elements such as a respirator with filters for gases and vapors organic and inorganic.
- ✓ Wear rubber gloves and protective clothing/eye/face protection equipment.
- ✓ Practice all proper personal hygiene after using the product.
- ✓ Dispose of the content/container in accordance with current regulations. The waste for no reason should be thrown into the pipe or any natural or artificial water source.

For more information on handling, storage, safety, among others, request the product's Safety Data Sheet.

The technical data and usage specifications given in this data sheet are for user guidance based on the experience of the Company and its Technical Department. The foregoing does not constitute a guarantee since we do not know the conditions of use, storage or handling of the product. Therefore, it is the user's responsibility to carry out their own tests before using our products. Pinturas Tonner® reserves the right to modify this technical information without prior notice, without this meaning a reduction in the quality of the products. Our Technical Department is available to resolve any concerns.

***Pinturas Tonner. Calle 53 No. 3 –41. Entrada-3-Cazucá-Soacha-Bogotá-Colombia.
PBX (601) 780 32 99***

www.pinturastonner.com