

## Report of Steel Tension Testing

Ordered by : OUSEN  
Project Name : For Sale  
Telephone : 0887188806  
Reference : ITC.414(O2025-2025-ousen)  
Testing Date : OCTOBER 27, 2025

**a** Thickness                      b-Width                       $L_i$  Initial Elongation in mm                       $\sigma_{e(0.2)}$  Limite Elongation of 0.2%  
**S** Section in  $\text{mm}^2$                       **F** Forces in kN                      **Rm** Tensile Strength in Mpa  
 $\epsilon_r$  Deformation at rupture                       $F_e$  Forces in kN at the elastic limit                      **E** Young modulus in Gpa  
 $\sigma$  Stress in Mpa                       $F_r$  Forces in kN at rupture                       $L_r$  Elongation in mm at rupture  
 $\sigma_e$  Yield strength in Mpa                      **L** Elongation in mm                      **RB** Round Bar, DB : Deformed Bar

| N° | Testing            |             | $\phi$ |         | S     | F     |       | L     |       | $\sigma$   |       | $\epsilon_r$ |
|----|--------------------|-------------|--------|---------|-------|-------|-------|-------|-------|------------|-------|--------------|
|    | Type               |             | Reals  | Testing |       | $F_e$ | $F_r$ | $L_i$ | $L_r$ | $\sigma_e$ | Rm    |              |
| 1  | Steel Wire Mesh A6 | (WM-6)-5392 | 6      | 6       | 28.27 | 16.80 | 18.57 | 30.00 | 33.00 | 594.2      | 656.7 | 10.00%       |
| 2  |                    | (WM-6)-5393 | 6      | 6       | 28.27 | 16.90 | 18.84 | 30.00 | 33.00 | 597.7      | 666.3 | 10.00%       |
| 3  |                    | (WM-6)-5394 | 6      | 6       | 28.27 | 16.70 | 18.93 | 30.00 | 33.00 | 590.6      | 669.6 | 10.00%       |


Executive Engineer

  
Mr. KHEM Ratha


Head of Laboratory

  
Dr. KY SAMBATH

For Dean of Faculty

  
Dr. HAN Virak

Deputy Director General of ITC

  
Dr. CHUNHIENG Thavarith