Technical Data Sheet
OPUDA'S MATT Emulsion

Product code OPD-MT - Emulsion range - Revision 2026-09

This sheet states the figures used by the product page and the paint calculator on opudapaint.com. Coverage is quoted for one coat on a sound, sealed surface; porous substrates absorb more.

SPECIFICATION

Finish	Matt (flat), sheen < 5%
Coverage	11 m2 per litre, single coat, sealed surface
Recommended coats	2
Touch dry	1 hour at 25 degC / 60% RH
Recoat	3 hours
Full cure	7 days
Thinning	First coat: up to 10% clean water on porous plaster. Finish coat: undiluted.
VOC / base	Water-based, low VOC
Surfaces	Interior walls and ceilings
Pack sizes	1 L - 4 L - 10 L - 20 L
Guarantee	5 years

PRODUCT CLAIMS (AS PRINTED ON THE PAIL)

- High quality, for walls and ceilings
- Smooth finish with better flow
- Extra coverage per litre
- Anti-fungi additive for humid rooms
- Eco-friendly, low odour
- 5-year guarantee

APPLICATION

1. Prepare: scrape, fill and sand. New plaster must cure 28 days, then seal with one coat of alkali-resisting primer.
2. Prime: one coat OPUDA'S Alkali-Resisting Primer. Allow 4 hours.
3. Cut in: ceilings and corners with a 3-inch brush before rolling.
4. Coat 1: roll from a wet edge in 1 m2 sections. Thin up to 10% on porous plaster.
5. Coat 2: after 3 hours, undiluted, at right angles to the first coat.
6. Cure: do not wash or scrub for 7 days. Ventilate well.

LIMITATIONS

Do not apply when the substrate or ambient temperature is below 10 degC, or when relative humidity is above 85%. Do not apply over active damp, mould or efflorescence: correct the cause first. Do not wash the film for 7 days. Colour on a screen cannot guarantee a physical match; approve a painted sample on the actual wall before full application.

GUARANTEE

The guarantee applies to the supplied product when applied in accordance with this sheet, on a sound and correctly prepared

Digital values are approximations; physical chips are the authority.

substrate, in the specified system. It does not cover failure caused by structural movement, water ingress, inadequate preparation or application outside these instructions.

Digital values are approximations; physical chips are the authority.