Technical Data Sheet
OPUDA'S Alkali-Resisting Primer

Product code OPD-PRM - Emulsion range - Revision 2026-09

This sheet states the figures used by the product page and the paint calculator on opudapaint.com. Coverage is quoted for one coat on a sound, sealed surface; porous substrates absorb more.

SPECIFICATION

Finish	Primer (sealing coat)
Coverage	10 m2 per litre, single coat
Recommended coats	1
Touch dry	2 hours
Recoat	4 hours
Full cure	3 days
Thinning	Up to 20% clean water on very porous render.
VOC / base	Water-based, low VOC
Surfaces	New plaster, interior and exterior walls
Pack sizes	4 L - 20 L
Guarantee	-

PRODUCT CLAIMS (AS PRINTED ON THE PAIL)

- Blocks alkali burn on new render
- Seals uneven porosity
- Improves topcoat coverage
- Quick recoat

APPLICATION

1. Allow new render to cure at least 14 days, ideally 28.
2. Brush down salt bloom; treat with a stabilising wash and dry fully.
3. One full coat by brush and roller. Do not thin unless very porous.
4. Recoat with Matt or Silk after 4 hours.

LIMITATIONS

Do not apply when the substrate or ambient temperature is below 10 degC, or when relative humidity is above 85%. Do not apply over active damp, mould or efflorescence: correct the cause first. Do not wash the film for 7 days. Colour on a screen cannot guarantee a physical match; approve a painted sample on the actual wall before full application.

GUARANTEE

The guarantee applies to the supplied product when applied in accordance with this sheet, on a sound and correctly prepared substrate, in the specified system. It does not cover failure caused by structural movement, water ingress, inadequate preparation or application outside these instructions.

Digital values are approximations; physical chips are the authority.