Technical Data Sheet
OPUDA'S Screeding Compound

Product code OPD-SCR - Emulsion range - Revision 2026-09

This sheet states the figures used by the product page and the paint calculator on opudapaint.com. Coverage is quoted for one coat on a sound, sealed surface; porous substrates absorb more.

SPECIFICATION

Finish	Filler / base coat
Coverage	1.6 m2 per kg at 1 mm thickness
Recommended coats	2
Touch dry	3 hours
Recoat	4 hours
Full cure	3 days
Thinning	Mix 1 kg to approximately 0.4 L clean water; rest 10 minutes.
VOC / base	Cementitious, low VOC
Surfaces	Interior walls, ceilings, new blockwork
Pack sizes	10 kg - 25 kg
Guarantee	-

PRODUCT CLAIMS (AS PRINTED ON THE PAIL)

- Levels uneven blockwork
- Sands to a fine finish
- Strong bond, minimal shrinkage

APPLICATION

1. Damp down the wall so it does not pull water from the mix.
2. Pass 1: 1-2 mm with a steel trowel, tight. Allow to set.
3. Pass 2: second thin pass to close the surface. Allow 4 hours.
4. Sand with 120 grit, dust off, prime before painting.

LIMITATIONS

Do not apply when the substrate or ambient temperature is below 10 degC, or when relative humidity is above 85%. Do not apply over active damp, mould or efflorescence: correct the cause first. Do not wash the film for 7 days. Colour on a screen cannot guarantee a physical match; approve a painted sample on the actual wall before full application.

GUARANTEE

The guarantee applies to the supplied product when applied in accordance with this sheet, on a sound and correctly prepared substrate, in the specified system. It does not cover failure caused by structural movement, water ingress, inadequate preparation or application outside these instructions.

Digital values are approximations; physical chips are the authority.