Technical Data Sheet
OPUDA'S Synthetic Gloss

Product code OPD-GLS - Emulsion range - Revision 2026-09

This sheet states the figures used by the product page and the paint calculator on opudapaint.com. Coverage is quoted for one coat on a sound, sealed surface; porous substrates absorb more.

SPECIFICATION

Finish	Gloss, sheen 80%+
Coverage	13 m2 per litre, single coat
Recommended coats	2
Touch dry	4 hours
Recoat	16 hours
Full cure	7 days
Thinning	Recommended solvent only, maximum 5%. Not water-thinnable.
VOC / base	Solvent-based. Ventilate and use appropriate PPE.
Surfaces	Timber and metal: doors, gates, frames, railings
Pack sizes	1 L - 4 L - 20 L
Guarantee	3 years

PRODUCT CLAIMS (AS PRINTED ON THE PAIL)

- Hard, impact-resistant film
- Interior and exterior joinery
- Good flow and levelling
- Weather resistant

APPLICATION

1. Strip loose coating, sand to a sound edge, degrease steel with a solvent wipe.
2. Prime: zinc-rich or red-oxide primer on metal; wood primer on timber, knots sealed.
3. Coat 1: brush with the grain or length of the steel. Avoid over-brushing.
4. Coat 2: after 16 hours. Thin coats always beat thick ones.

LIMITATIONS

Do not apply when the substrate or ambient temperature is below 10 degC, or when relative humidity is above 85%. Do not apply over active damp, mould or efflorescence: correct the cause first. Do not wash the film for 7 days. Colour on a screen cannot guarantee a physical match; approve a painted sample on the actual wall before full application.

GUARANTEE

The guarantee applies to the supplied product when applied in accordance with this sheet, on a sound and correctly prepared substrate, in the specified system. It does not cover failure caused by structural movement, water ingress, inadequate preparation or application outside these instructions.

Digital values are approximations; physical chips are the authority.