

Interlayer-distance control of spectral reconstruction in twisted graphene

Vladislav Efremkin,¹ Thomas D. Kühne,^{1,*} and Emil Prodan²

¹*Center for Advanced Systems Understanding (CASUS),*

Helmholtz-Zentrum Dresden-Rossendorf (HZDR), 02826 Görlitz, Germany

²*Department of Physics, Yeshiva University, New York, New York 10016, USA*

(Dated: September 16, 2026 — Author-review draft)

Quasiperiodic bilayers offer a route to spectral structures associated with higher-dimensional topology, but identifying their electronic counterparts requires going beyond idealized lattice models. We investigate the joint dependence of graphene electronic spectra on twist angle and imposed interlayer distance using density-functional calculations and a real-space tight-binding model. Layer-projected density-of-states maps evolve from weakly angle-dependent ridges at large separation to a more strongly reorganized pattern of branching spectral weight as the layers approach. Calculations with two Gaussian basis sets show qualitatively related structures in the compressed regime. An independently reproduced two-layer model isolates the competition between interlayer and intralayer hopping and provides a dimensionless comparison with this evolution. The results identify a candidate regime for Hofstadter-like spectral reconstruction without an applied magnetic field. They establish a spectral observation in constrained finite geometries, rather than a determination of bulk gap labels or Chern numbers.

The Hofstadter butterfly connects spectral structure, incommensurability, and topology in a particularly direct way [1]. In electronic moiré systems, magnetic flux and a long-wavelength superlattice can generate a fractal quantum Hall spectrum [2]. A complementary route replaces magnetic flux by geometric incommensurability. Reconfigurable acoustic crystals demonstrated how density-of-states measurements reveal butterfly spectra and how a controllable phason exposes their boundary states [3]. More generally, quasiperiodic systems can realize topological responses associated with synthetic dimensions [4, 5]. These connections motivate a concrete materials question: can changing the coupling between two atomically resolved, twisted layers expose an electronic spectral pattern analogous to the one found in simpler quasiperiodic models?

Twisted graphene is a natural setting for this question, but several physically distinct mechanisms must be separated. Low-energy magic-angle bands arise from the competition between interlayer tunneling and the momentum mismatch of the Dirac cones [6]. Pressure modifies that competition [7]. Related calculations address compressed 30° quasicrystals [8] and the relation between magic angles and interlayer distances [9]. Meanwhile, twisting and sliding can organize spectra through higher-dimensional topology [10–12]. Here the control variable is the imposed layer separation, and the observable is the electronic density of states over a broad twist-angle interval. We do not apply a magnetic field or infer a Hall response from the spectral resemblance.

We combine two deliberately distinct descriptions. The first is an atomistic density-functional-theory (DFT) survey of a periodic graphene sheet covered by a rotated, hydrogen-terminated graphene patch. The second is an all-pairs, distance-dependent tight-binding model on two coincident disks. The DFT calculation retains the chem-




FIG. 1. Distinct geometries used in the comparison. (a) Actual 45°, $d = 2.15 \text{ \AA}$ DFT input, viewed along the layer normal. Gray and blue denote lower- and upper-layer carbon, and orange denotes terminating hydrogen. The outline is the periodic cell. (b) Schematic of the coincident-disk construction used in the model. The schematic radius is reduced for clarity. Calculations use $R = 25a$. The two geometries are not treated as equivalent finite-size realizations.

ical and self-consistent electronic structure of the finite geometry, while the model isolates a geometric coupling mechanism. Their comparison is qualitative: neither the model hopping scale nor its distance parameter is fitted to the DFT spectra.

The DFT survey covers ten interlayer separations ranging from 2.00 to 3.30 $\text{\AA}$. The detailed input series available at $d = 2.15 \text{ \AA}$ contains 51 angles from 30° to 60° in steps of 0.6°. Its lower layer contains 1250 carbon atoms in a 25×25 graphene supercell with nearest-neighbor distance 1.42 $\text{\AA}$. The upper patch has 955–1013 carbon atoms and 84–100 hydrogen atoms, depending on angle. Both layers are planar in the inputs. These are fixed-geometry energy calculations, not a pressure-

relaxed structural series. Geometry, termination, and numerical settings are documented in the Supplemental Material (SM) [13].

The calculations use CP2K [14, 15], the PBE functional [16], GTH pseudopotentials, and principally the SZV-MOLOPT-GTH basis [17]. The input requests spin-polarized self-consistency, a 300-Ry density-grid cutoff, and Fermi–Dirac occupations at 300 K. Selected maps use a DZVP basis. The D3 dispersion correction [18] accounts for the long-range attraction important for interlayer binding in graphene [19]. It contributes to the energy and forces but does not itself modify the Kohn–Sham spectrum at a fixed geometry. The electronic temperature must also be distinguished from the broadening used to display a DOS.

In a nonorthogonal Gaussian basis, the Kohn–Sham matrix problem is

$$\mathbf{H}_\sigma \mathbf{c}_{n\sigma} = \varepsilon_{n\sigma} \mathbf{S} \mathbf{c}_{n\sigma}, \quad \mathbf{c}_{n\sigma}^\dagger \mathbf{S} \mathbf{c}_{m\sigma} = \delta_{nm}. \quad (1)$$

Here $\mathbf{S}$ is the overlap matrix, not an additional interaction. For the Löwdin-type projection employed by CP2K, the weight on the lower-layer atomic orbitals is [20]

$$w_{n\sigma}^{(L)} = \sum_{\mu \in L} \left| (\mathbf{S}^{1/2} \mathbf{c}_{n\sigma})_\mu \right|^2. \quad (2)$$

A broadened layer-projected DOS therefore has the form

$$\rho_{L,\eta}(E) = \frac{1}{N_L} \sum_{n\sigma} w_{n\sigma}^{(L)} g_\eta(E - \varepsilon_{n\sigma} + E_F), \quad (3)$$

where E is measured from E_F , N_L specifies the normalization, and g_η is a normalized display kernel. Equation (3) defines the observable. The supplied image maps are retained on their original energy and intensity scales, without reconstructing quantitative spectral weights from colors. Their postprocessing kernel and normalization require confirmation from the state-resolved output. Occupation smearing alone does not supply this information.

Figure 2 illustrates the principal observation. At $d = 3.30$ Å, the prominent spectral ridges depend only weakly on angle over most of the displayed interval. Decreasing the separation bends and redistributes these ridges. By $d = 2.55$ Å, the occupied-state region contains additional angular structure. At $d = 2.15$ Å, pronounced curved branches and intervening low-weight regions replace much of the nearly horizontal organization. The full survey shows this change across a range of separations rather than at a single isolated configuration. At the smallest supplied separation, the maps are more congested. The data do not support assigning a sharply defined critical distance.

The SZV and DZVP maps at $d = 2.25$, 2.20, and 2.15 Å retain related large-scale spectral features, although their sharpness and detailed shapes differ (SM). This is a useful

qualitative basis check, not a demonstration of converged gap widths. A layer projection also need not coincide with the total DOS: states concentrated on the upper patch or its edge can have small lower-layer weight. A dark interval in a projected, broadened DOS is consequently a candidate depletion region, not by itself a bulk spectral gap.

To isolate the coupling mechanism, we use the supplied honeycomb model with primitive vectors $\mathbf{a}_1 = (\sqrt{3}a, 0)$ and $\mathbf{a}_2 = (\sqrt{3}a/2, 3a/2)$ and basis positions $(0, 0)$ and $(0, a)$. Thus a denotes the nearest-neighbor distance. Retaining sites inside a disk of radius R gives a set P_R . The bilayer consists of $(\mathbf{r}, 0)$ and $(\mathbf{R}_\theta \mathbf{r}, d)$ for every $\mathbf{r} \in P_R$, where $\mathbf{R}_\theta$ is the in-plane rotation matrix. On orthonormal site states, the Hamiltonian is

$$\hat{H}_{\text{TB}} = \sum_{i \neq j} t_0 \exp[-r_{ij}/\xi] |i\rangle \langle j|, \quad r_{ij} = |\mathbf{x}_i - \mathbf{x}_j|. \quad (4)$$

The sum includes both layers and all pairs, with zero on-site energies and no distance cutoff. This real, isotropic hopping model is not an orbital-resolved parametrization of carbon: in particular, it does not resolve the angular dependence of π and σ bonding.

Normalizing energies by the nearest-neighbor intralayer hopping, $t_{\text{nn}} = t_0 e^{-a/\xi}$, exposes the relevant competition. The largest possible hopping between vertically aligned sites satisfies

$$\frac{t_{\perp}^{\text{max}}}{t_{\text{nn}}} = \exp[(a - d)/\xi]. \quad (5)$$

This is an upper-envelope coupling, not an assertion that every site has a vertically aligned partner. For $\xi/a = 0.03$, changing d/a from 0.99 to 0.98 to 0.97 changes this ratio from 1.40 to 1.95 to 2.72. Small geometric changes can therefore reorganize the spectrum even when the intralayer Hamiltonian is fixed. The numerical values of d/a cannot be converted into DFT separations without a separately established mapping.

Figure 3 is obtained by independently diagonalizing this model using the parameters of the supplied notebook. The two disks contain 3020 sites in total, and the DOS includes all eigenvalues. The calculations resolve a redistribution of angular spectral weight as the interlayer coupling grows, with curved branches and low-weight regions reminiscent of the DFT maps. This comparison supports a geometric hybridization interpretation of the spectral evolution. It does not establish a one-to-one correspondence between individual branches or gaps. Changing the hopping range ξ also changes further-neighbor intralayer hopping and therefore constitutes a distinct model change (SM).

The connection to topology is a hypothesis that the present spectra make concrete, not an invariant extracted from their appearance. In quasiperiodic bilayers, relative translations supply phason coordinates. Gap labeling




FIG. 2. Evolution of the supplied lower-layer projected DOS maps with imposed separation, using the SZV basis. The source images are reproduced without intensity manipulation. Their angular axis Θ is in degrees. The displayed data cover approximately 30° – 60° , while the source axes extend beyond that interval. The ordinate retains the supplied $E - E_F$ scale. Dark-to-bright colors encode increasing spectral weight. No common quantitative intensity calibration is assumed. White columns within the sampled interval are missing or unconverged calculations, not spectral gaps. All ten distances and the DZVP comparisons are shown in the SM.




FIG. 3. Independent reproduction of the supplied tight-binding model, Eq. (4), with $R/a = 25$, $\xi/a = 0.03$, and 1510 sites per layer. Energies are normalized by t_{nn} . The Gaussian DOS is normalized to one state, summed over the full bilayer, and evaluated on a refined 2001-point energy grid. Its width is the full spectral span divided by 1000 for each panel. The common color scale is clipped above $t_{nn}\rho = 0.5$. The negative-angle half follows from the exact layer-exchange symmetry of this disk model. These model data are not DFT calculations or a fit to Fig. 2.

constrains the integrated DOS of a gapped bulk spectral projector [10, 21]. Schematically, the relevant quantity is

$$\mathcal{N}(E; \theta) = \tau \left[\mathbf{1}_{(-\infty, E]}(\hat{H}_\theta) \right], \quad (6)$$

with a specified trace-per-volume normalization τ . It counts states below E , rather than the fraction of a state on a selected layer. For a topological assignment, a candidate gap must survive bulk and numerical convergence tests, and its spectral projector must support the corresponding gap-label or phason-response analysis. Neither

a butterfly-like outline nor a near-zero projected DOS supplies that test. In particular, a twist-angle scan is not itself an adiabatic sliding cycle, and no quantized pumping or second-Chern response is inferred here.

The finite geometries impose an additional limitation. The hydrogen-terminated patch covers only part of the lower sheet, and its termination changes with angle. The disk model removes the nonoverlapping sample-shape regions emphasized in the original model construction, but it does not remove boundary states. Accordingly, the six-fold angular organization expected for a bulk honeycomb

system cannot be imposed as an exact identity on the finite DFT patches or on registry-sensitive commensurate configurations. A bulk-interior projection and a size series are needed to separate quasiperiodic reconstruction from edge and coverage effects.

In summary, the available first-principles survey identifies interlayer distance as a control parameter for substantial angular spectral reconstruction in constrained twisted graphene geometries. An independently reproduced real-space model explains why the ratio of interlayer to intralayer hopping is an effective organizing variable. The most promising extension is now well defined: connect the observed depletion regions to converged bulk gaps and evaluate their phason-dependent topology. This would turn a materials-level spectral candidate into a test of the higher-dimensional physics suggested by quasiperiodic acoustic and mechanical systems, without conflating that prospect with a result already established.

Data availability. The manuscript archive is publicly available in the GitHub repository <https://github.com/DCM-Uni-Paderborn/Hofstadter-Butterfly>. It contains the supplied $d = 2.15 \text{ \AA}$ input structures, original DFT panel images, and the code and eigenvalues for the model reproduction. State-resolved DFT output and the original DOS postprocessing scripts were not available for this analysis. Quantitative DFT gap extraction and complete reproduction of the displayed DFT maps therefore remain open.

Use of AI-assisted tools. AI-assisted tools were used to organize source material and develop analysis scripts.

* tkuehne@cp2k.org

- [1] D. R. Hofstadter, Energy levels and wave functions of Bloch electrons in rational and irrational magnetic fields, *Physical Review B* **14**, 2239 (1976).
- [2] C. R. Dean, L. Wang, P. Maher, C. Forsythe, F. Gharahi, Y. Gao, J. Katoh, M. Ishigami, *et al.*, Hofstadter's butterfly and the fractal quantum Hall effect in moiré superlattices, *Nature* **497**, 598 (2013).
- [3] X. Ni, K. Chen, M. Weiner, D. J. Apigo, C. Prodan, A. Alù, E. Prodan, and A. B. Khanikaev, Observation of Hofstadter butterfly and topological edge states in reconfigurable quasi-periodic acoustic crystals, *Communications Physics* **2**, 55 (2019).
- [4] Y. E. Kraus, Y. Lahini, Z. Ringel, M. Verbin, and O. Zeitler, Topological States and Adiabatic Pumping in Quasicrystals, *Physical Review Letters* **109**, 106402 (2012).
- [5] E. Prodan, Virtual topological insulators with real quantized physics, *Physical Review B* **91**, 245104 (2015).
- [6] R. Bistritzer and A. H. MacDonald, Moiré bands in twisted double-layer graphene, *Proceedings of the National Academy of Sciences* **108**, 12233 (2011).
- [7] M. Yankowitz, S. Chen, H. Polshyn, Y. Zhang, K. Watanabe, T. Taniguchi, D. Graf, A. F. Young, *et al.*, Tuning superconductivity in twisted bilayer graphene, *Science* **363**, 1059 (2019).
- [8] G. Yu, M. I. Katsnelson, and S. Yuan, Pressure and electric field dependence of quasicrystalline electronic states in 30° twisted bilayer graphene, *Physical Review B* **102**, 045113 (2020).
- [9] A. Palamara, M. Pisarra, and A. Sindona, Magic distances in twisted bilayer graphene, *npj 2D Materials and Applications* **9**, 100 (2025).
- [10] M. I. N. Rosa, M. Ruzzene, and E. Prodan, Topological gaps by twisting, *Communications Physics* **4**, 130 (2021).
- [11] Y. Su and S.-Z. Lin, Topological sliding moiré heterostructure, *Physical Review B* **101**, 041113 (2020).
- [12] M. Fujimoto, H. Koschke, and M. Koshino, Topological charge pumping by a sliding moiré pattern, *Physical Review B* **101**, 041112 (2020).
- [13] (2026), see Supplemental Material for the input-geometry audit, numerical settings, full DFT image survey, exact model energy and DOS rescaling, model reproduction, and the distinction between projected spectral depletion and a topologically labeled bulk gap.
- [14] T. D. Kühne, M. Iannuzzi, M. Del Ben, V. V. Rybkin, P. Seewald, F. Stein, T. Laino, R. Z. Khaliullin, *et al.*, CP2K: An electronic structure and molecular dynamics software package - Quickstep: Efficient and accurate electronic structure calculations, *The Journal of Chemical Physics* **152**, 194103 (2020).
- [15] M. Iannuzzi, J. Wilhelm, F. Stein, A. Bussy, H. Elgabarty, D. Golze, A.-S. Hehn, M. Graml, S. Marek, B. Sertcan Gökmen, C. Schran, H. Forbert, R. Z. Khaliullin, A. Kozhevnikov, M. TAILLEFUMIER, R. Meli, V. V. Rybkin, M. Brehm, R. Schade, O. Schütt, J. V. Pototschnig, H. Mirhosseini, A. Knüpfer, D. Marx, M. Krack, J. Hutter, and T. D. Kühne, The CP2K Program Package Made Simple, *The Journal of Physical Chemistry B* **130**, 1237 (2026).
- [16] J. P. Perdew, K. Burke, and M. Ernzerhof, Generalized Gradient Approximation Made Simple, *Physical Review Letters* **77**, 3865 (1996).
- [17] H. Mirhosseini, T. M. A. Müller, M. Krack, T. D. Kühne, and J. Hutter, *The UZH protocol: Separating errors and constructing improved CP2K basis sets and pseudopotentials* (2026), [arXiv:2606.11064 \[physics.chem-ph\]](https://arxiv.org/abs/2606.11064).
- [18] S. Grimme, J. Antony, S. Ehrlich, and H. Krieg, A consistent and accurate ab initio parametrization of density functional dispersion correction (DFT-D) for the 94 elements H-Pu, *The Journal of Chemical Physics* **132**, 154104 (2010).
- [19] I. V. Lebedeva, A. V. Lebedev, A. M. Popov, and A. A. Knizhnik, Comparison of performance of van der Waals-corrected exchange-correlation functionals for interlayer interaction in graphene and hexagonal boron nitride, *Computational Materials Science* **128**, 45 (2017).
- [20] P.-O. Löwdin, On the Non-Orthogonality Problem Connected with the Use of Atomic Wave Functions in the Theory of Molecules and Crystals, *The Journal of Chemical Physics* **18**, 365 (1950).
- [21] M. Yoshii, S. Kitamura, and T. Morimoto, Gap labeling theorem for multilayer thin film heterostructures, *Physical Review B* **107**, 064201 (2023).