




QUALITY ASSURANCE

-Textile Laboratories-



INDEX

INTRODUCTION	2
PROCEDURE WOVEN AND CUT&SEWN	3
PROCESS MAP WOVEN AND CUT&SEWN	4
LABORATORY TESTS AND TABLE TOLERANCES WOVEN	5
LABORATORY TESTS AND TABLE TOLERANCES LEATHER	6
LABORATORY TESTS AND TABLE TOLERANCES CUT&SEWN	7
PROCEDURE KNITTED	8
LABORATORY TEST AND TABLE TOLERANCES KNITTED	9
CYCLE FOR PILLING BOX (KNITTED FABRIC)	10
LIST OF APPROVED LABORATORIES	11
QUERIES AND CLARIFICATIONS	18
DOCUMENT TO SIGN AND STAMP.....	19

INTRODUCTION

Dear Managing Directors and Production & Quality Control Directors,

As you are aware, the quality of our product is a key factor for maintaining MANGO's reputable brand image around the world. This is the reason why we are carrying out the control of lab test (physical and composition tests) and the control of harmful substances (chemical test). Furthermore, we are conducting tests in our own textile laboratory as well as independent test on random garments at the AITEX laboratories.

In this manual you will also find enclosed the textile laboratories that we have approved, the procedure that we are going to follow with the lab test, a process map, our tests and tolerances system, as well as the prices of the nominated laboratories.

We kindly request you to inform us the lab's name you have chosen, (please select only one), as well as their location as soon as possible.

This is apart of our control of harmful substances as we communicated you in MEMO EF-REC-0G001/0.

PROCEDURE FOR WOVEN AND CUT&SEWN FABRICS**SAMPLE YARDAGE:**

When MANGO confirms a collection, you should send the sample yardage if you have available in correct quality (alternative colour) to the approved laboratory to prepare the tests that our fabric technicians request you.

MANGO will ask for this test to the supplier and to the laboratory.

The lab will send the results to you and to MANGO at the same time. If the result is not correct, MANGO will contact to you. You have to apply the comments accordingly.


BULK FABRICS:

You will send the bulk fabrics to the laboratory (of each bought colour). The fabric technicians will have the possibility of requesting any other test if it is considered necessary.


The lab will send the results to you and to MANGO at the same time. If the result is not correct, MANGO will contact to you. You have to apply the comments accordingly.

PROCESS MAP WOVEN AND CUT&SEWN FABRIC

SAMPLE YARDAGE



BULK FABRIC



LABORATORY TESTS- WOVEN FABRIC

With the purpose of having a better quality control of our products, we have established the below trials.

1-Pack: Test requested to be done in all woven fabrics.

2-Optional test if it is considered necessary depending on the fabric type.

WOVEN FABRIC PACKAGE TESTS	
1- PACK	TESTING METHOD
Fiber composition	ISO 1833:2006
Determination of mass per unit length and mass per unit area	ISO 3801:1977
Determination of pH of aqueous extract.	ISO 3071:2005
Colour fastness to rubbing	ISO 105-X12:2001
Colour fastness to washing	ISO 105-C06:1994
Colour fastness to Perspiration	ISO 105-E04:2008
Colour fastness to water	ISO 105-E01:2002
Determination of the slippage resistance of yarns at a seam in woven fabrics -- Part 1	ISO 13936-1:2004
2- Optionals	TESTING METHOD
Dimensional Change After Washing	ISO 6330:2000/ISO 5077:2007
Dimensional Change After Dry Clean	ISO 3175:1999/ISO 5077:2007
Colour fastness to Dry Clean	ISO 105-D01:1993
Determination of the elasticity of fabrics:Strip test	UNE EN 14704-1:2005
Determination of water repellency of fabrics by the bundesmann rain-shower test	ISO 9865:1991
Determination of resistance to water penetration: hydorstatic pressure test	ISO 811:1981
Colour fastness to Light	ISO 105-B02:1994
Snagging	ASTM D-3939-08
Pilling test (Martindale method)	ISO 12945-2:2000
Determination of dimensional change of textil fabrics; Ironing with moist ironing cloth on ironing presses	DIN 53894-1:1980
Determination of the abrasion resistance of fabrics by the Martindale method	ISO 12947-1:1998/ ISO 12947-2:1998

Woven fabric- tolerances;

REQUIREMENTS TABLE		
WOVEN FABRIC PACKAGE TESTS		
1- PACK	TESTING METHOD	GREEN (OK)
Fiber composition	ISO 1833:2006	
Determination of pH of aqueous extract.	ISO 3071:2005	4-7,5
Colour fastness to rubbing DRY	ISO 105-X12:2001	≥ 3
Colour fastness to rubbing WET		≥ 3
Colour fastness to washing	ISO 105-C06:1994	≥ 3
Colour fastness to Perspiration	ISO 105-E04:2008	≥ 3
Colour fastness to water	ISO 105-E01:2002	≥ 3
Determination of the slippage resistance of yarns at a seam in woven fabrics -- Part 1	ISO 13936-1:2004	≥ 150
Dimensional Change After Washing	ISO 6330:2000/ISO 5077:2007	± 3% *
Dimensional Change After Dry Clean	ISO 3175:1999/ISO 5077:2007	± 3%
Colour fastness to Dry Clean	ISO 105-D01:1993	≥ 3
Determination of the elasticity of fabrics:Strip test	UNE- EN 14704-1:2005	≤ 6%
Colour fastness to Light	ISO 105-B02:1994	>5
Snagging	ASTM D-3939-08	≥ 3
Pilling test (Martindale method)	ISO 12945-2:2000	≥ 3
Determination of dimensional change of textil fabrics; Ironing with moist ironing cloth on ironing presses	DIN 53894-1:1980	± 3%
Determination of the abrasion resistance of fabrics by the Martindale method	ISO 12947-1:1998/ ISO 12947-2:1998	>15.000
Determination of resistance to water penetration: Hydrostatic Preassure Test	ISO 811:1981	≥ 90 cm.
Determination of water repellency of fabrics by the Bundesmann rain-shower test	ISO 9865:1991: Penetration	≥ 15%
	ISO 9865:1991: Absorption	≥ 3
Methods for determination of bow, skew and lengthway distortion in woven and knitted fabrics	BS 2819:1990	≤ 4%

* The dimensional stability results should be regular in all lots (positive or negative)

LABORATORY TESTS- LEATHER

With the purpose of having a better quality control of our products, we have established the below trials.

1-Pack: Test requested to be done in all leather.

TESTS	TESTING METHOD
Fiber composition	Infra-red method
PH	ISO 4046:2008
Colour fastness to cycles of to-and-fro rubbing DRY	ISO 11640:1993
Colour fastness to cycles of to-and-fro rubbing WET	ISO 11640:1993
Colour fastness to Perspiration	ISO 11641:1993
Colour fastness to water	ISO 11642:1993
Colour fastness to Light	ISO 105-B02:1994
Colour fastness to dry cleaning	ISO 11643:1993
Colour fastness to water spotting	ISO 15700:1998
Tear Strength	ISO 3377-2:2002

Leather- tolerances;

REQUIREMENTS TABLE		
SPECIFICATION FOR LEATHER		
TESTS	TESTING METHOD	OK
Fiber composition	Infra-red method	
PH	ISO 4046:2008	4-7,5
Colour fastness to cycles of to-and-fro rubbing DRY	ISO 11640:1993	≥ 3
Colour fastness to cycles of to-and-fro rubbing WET	ISO 11640:1993	≥ 3
Colour fastness to Perspiration	ISO 11641:1993	≥ 3
Colour fastness to water	ISO 11642:1993	≥ 3
Colour fastness to Light	ISO 105-B02:1994	≥ 3
Colour fastness to dry cleaning	ISO 11643:1993	≥ 3
Colour fastness to water spotting	ISO 15700:1998	≥ 3
Tear Strength	ISO 3377-2:2002	≥100 N.

LABORATORY TESTS- Cut & Sewn FABRIC

With the purpose of having a better quality control of our products, we have established the below trials.

1-Pack: Test requested to be done in all cut & sewn fabrics.

2-Optional test if it is considered necessary depending on the fabric type.

CUT & SEWN PACKAGE TESTS	
1- PACK	TESTING METHOD
Fiber composition	ISO 1833:2006
Determination of pH of aqueous extract.	ISO 3071:2005
Dimensional Change After Washing	ISO 6330:2000/ISO 5077:2007
Colour fastness to rubbing	ISO 105-X12:2001
Colour fastness to washing	ISO 105-C06:1994
Colour fastness to Perspiration	ISO 105-E04:2008
Colour fastness to water	ISO 105-E01:2002
Pilling test (Martindale method)	ISO 12945-2:2000
2- Optionals	TESTING METHOD
Dimensional Change After Dry Clean	ISO 3175:1999/ISO 5077:2007
Colour fastness to Dry Clean	ISO 105-D01:1993
Determination of dimensional change of textil fabrics on ironing presses (Hoffman)	DIN 53894-1:1980
Determination of spirality after laundering -- Part 3: Woven and knitted fabrics	ISO 16322-2:2005
Determination of linear density of yarn removed from fabric	ISO 7211-5:1984
Determination of mass per unit length and mass per unit area	ISO 3801:1977

Cut & sewn fabric- tolerances;

REQUIREMENT TABLE			GREEN
Lab test	Testing Method	Exemples	
Fiber composition	ISO 1833:2006	Percentage (Co 65% Pes 30% Ea 5%)	
Determination of Ph of aqueous extract	ISO 3071:2005	pH (5.5)	4-7,5
Determination of dimensional change in washing and drying/Domestic washing and drying procedures for textile testing	ISO 5077:2007 ISO 6330:2000	Rows (±%) Columns(±%)	± 5%
Colour fastness to rubbing	ISO 105-X12:2001	DRY WET	≥ 3 ≥ 3
Colour fastness to domestic and commercial laudering	ISO 105-C06:1994	Degradation Staining	≥ 3
Colour fastness to perspiration	ISO 105-E04:2008	Degradation Staining	≥ 3
Colour fastness to Water	ISO 105-E01:2002	Staining	≥ 3
Determination of fabric propensity to surface fuzzing and to pilling Part 2: Modified Martindale Method	ISO 12945-2:2000	Pilling result	≥ 3
Optionals if it is felt necessary			
Professional care, drycleaning and wetcleaning of fabrics and garments	ISO 3175:1999 ISO 5077:2007	Rows (±%) Columns(±%)	± 5%
Colour fastness in dry cleaning	ISO 105-D01:1993	Degradation (fabric) Staining (solvent)	≥ 3
Determination of spirality after laundering - Part 2. Woven and knitted fabrics	ISO 16322-2:2005	Rows (±%) Columns(±%)	± 5%
Determination of mass per unit of length and mass per unit area.	ISO 3801:1977	Weight gr/m2 -Float: (gr/m2)	± 5%
Determination of dimensional change of textil fabrics; Ironing with moist ironing cloth on ironing presses	DIN 53894-1:1980	Rows (±%) Columns(±%)	± 3%
Efficiency (Meters of finished fabric / kilograms of greige fabric)		m/Kg	± 0,2
Width		(%)	5%

Punto Fa, S.L. C.I.F. B-59088948


Mercaders 9-11. Polígono Industrial Riera de Caldes. Apartado de Correos 280
08184 Palau-solità i Plegamans (Barcelona) -SPAIN- Tel.: (+34) 938 602 222

PROCEDURE FOR KNITTED FABRICS

BULK FABRICS

You will send the bulk fabrics to the laboratory (of each bought colour). The fabric technicians will have the possibility of requesting any other test, not included in the pack if it is considered necessary.

PROCESS MAP KNITTED



LABORATORY TESTS- KNITTED FABRIC

With the purpose of having a better quality control of our products, we have established the below trials.

1-Pack: Test requested to be done in all knitted fabrics.

2-Optional test if it is considered necessary depending on the fabric type.

KNITWEAR PACKAGE TESTS	
1- PACK	TESTING METHOD
Fiber composition	ISO 1833:2006
Determination of pH of aqueous extract.	ISO 3071:2005
Dimensional Change After Washing	ISO 6330:2000/ISO 5077:2007
Colour fastness to rubbing	ISO 105-X12:2001
Colour fastness to washing	ISO 105-C06:1994
Colour fastness to Perspiration	ISO 105-E04:2008
Colour fastness to water	ISO 105-E01:2002
Pilling (Pilling Box Method)	ISO 12945-1:2000
2- Optionals	TESTING METHOD
Dimensional Change After Dry Clean	ISO 3175:1999/ISO 5077:2007
Colour fastness to Dry Clean	ISO 105-D01:1993

Knitted fabric- tolerances;

REQUERIMENT TABLE - KNITWEAR			GREEN
Lab test	Testing Method	Exemples	
Fiber composition	ISO 1833:2006	Percentage (Co 65% Pes 30% Ea 5%)	
Determination of Ph of aqueous extract	ISO 3071:2005	pH (5.5)	4-7,5
Dimensional change after washing	ISO 5077:2007 ISO 6330:2000	Warp - Percentage (+4%) Weft - Percentage (-2%)	± 6%
Colour fastness to rubbing	ISO 105-X12:2001	Dry Staining (2 or 2-3) Wet Staining (2 or 2-3)	≥ 3
Colour fastness to washing	ISO 105-C06:1994	*Degradation *Staining	≥ 3
Colour fastness to perspiration	ISO 105-E04:2008	*Degradation *Staining	≥ 3
Colour fastness to Water	ISO 105-E01:2002	*Staining	≥ 3
Determination of fabric propensity to surface fuzzing and to pilling -- Part 1: Pilling box method	ISO 12945-1:2000	Pilling result (3/4 or 3)	≥ 3
Optionals if it is considered necessary			
Dimensional change after dry clean	ISO 3175:1999 ISO 5077:2007	Warp - Percentage (+4%) Weft - Percentage (-2%)	± 6%
Colour fastness to dry clean.	ISO 105-D01:1993	*Degradation (fabric) *Staining (solvent)	≥ 3

CYCLES FOR PILLING BOX;

To proceed the pilling with the pillin box method following the standard ISO 12945-1:2000 we are using the below quantity of cycles depending on the composition of the fabric.

If the majority fibers is:

- Wool product (natural fibers with animal origin) 7.200 cycles.
- Synthetic fibers(Polyester, Acrylic, Polyamide...) 10.800 cycles.
- Man made fibers (Viscose, Modal...) 10.800 cycles.
- Cotton, Ramie... 14.400 cycles.

LIST OF APPROVED LABORATORIES

AITEX

- Plaza Emilio Sala, 1

E-03801 ALCOY

ALICANTE - SPAIN

Tel. +34 96 5542200

Fax. +34 96 5543494

- Room 620, Kerry Center, No 2008

Renminnan Road

Luoho District

Shenzhen

China

Tel. 0755-25181462

Website: www.aitex.es

Contact Person: Alice Cheng

E-mail: acheng@aitex.es

INTERTEK

- Intertek Testing Services Hong Kong Ltd.

4 C/F., Garment Centre

576 Castle Peak Road, Kowloon, Hong Kong

Tel. (852) 2173 8367

Fax. (852) 3403 2541

Website: www.intertek.com/consumergoods

Contact Person: Tammy Cheung

Tel. (852) 2173 8367

Fax. (852) 3403 2541

E-mail: tammy.cheung@intertek.com

- Intertek Testing Services Ltd. Shanghai

3rd Floor , Building N° 2 Shanghai Comalong

Industrial Park 889 Yi Shan Road, Shanghai, China

Tel. 86 21 6120 6060x2224

Fax. 86 21 6485 0559

Website: www.intertek-labtest.com.cn

Contact Person: Tina Wu

Tel. 86 21 6495 4782

Fax. 86 21 6485 0559

E-mail: tina.wu@intertek.com

- Intertek Testing Services (I) Pvt.Ltd.

290, Udyog Vihar, Phase-II

Gurgaon, Haryana-122 016

INDIA

Tel. +91-0124-4503400

Fax. +91-0124-4303592

Website: www.intertek.com

Contact Person: Avnish Chhabra

Tel. +91-0124-4303591

E-mail: avnish.chhabra@intertek.com

- Intertek Test Hizmetleri A.S.

Fatih Caddesi Dereboyu Sokak

No. 4/2 Halkali 34303

Istanbul - Türkiye

Tel. +90 212 471 00 65

Fax. +90 212 471 11 72

Website: www.intertek-labtest-tur.com

Contact Person: S. Ozan Boz

Tel. +90 212 473 13 59

E-mail: ozan.boz@intertek.com

SGS

- SGS Hong Kong Ltd.

5/F-8/F & 28/F. Metropole Square

2 On Yiu Street, Siu Lek Yuen

Shatin, N.T., Hong Kong

Tel. (852) 2334 4481

Website: www.hk.sgs.com

Contact Person: Cybil Law

Tel. (852) 2765 3616

E-mail: cybil.law@sgs.com

- SGS-CSTC Standard Technical Services Co.,Ltd.

Shanghai Branch

1/F,4/F,6/F,7/F,8/F,9/F,10/F, 3rd Building

No. 889, yishan Road

Xuhui District, Shanghai, China

Tel. +86 (0) 21 6140 2666

Website: www.cn.sgs.com

Contact Person: Jennifer Sun

Tel. +86 (0) 21 61 15 2151

E-mail: Jennifer.sun@sgs.com

- Consumer testing services

SGS India Pvt.Ltd.

250, Udyog Vihar

Phase-IV

Gurgaon- 122 015,

Haryana India

Tel. +91-124-2399990 to 98

Fax. +91-124-2399764

Website: www.sgs.com

Contact Person: Vinod Kumar

Tel. +91-9871794625

E-mail: vinod.kumar@sgs.com

- Consumer Testing Services

SGS Supervise Gözetme Etüd

Kontrol Servisleri A.S.

Abide-i Hürriyet Cad.

Geçit Sk. No.10

Floor : 1-2-3-4 34381 Sisli

Istanbul - Turkey

Tel. +90 (212) 368 40 00

Fax. +90 (212) 296 47 82-83

Website: www.tr.sgs.com

Contact Person: Banu Senel

Tel. +90 (212) 225 00 34 / 214

E-mail: banu.senel@sgs.com

- TEXANLAB

Mumbai H.O. (Thane)

3rd. Floor, Narmada,

Laxmi Industrial Complex,

Vartak Nagar, Pokhran Road No. 1,

Thane 400 606. INDIA

Tel. 022-2585 6169/70/71

Fax.022-2585 6172

Website :www.texanlab.com

E-mail : texanlab@vsnl.com

Contact person : Rahul Bhajekar

- EKOTEKS

Esenyurt Firuzköy Bulvari

No.29 34325

Avcılar-Istanbul, Türkiye

Tel. 00 90 212 676 78 66

Fax.00 90 212 695 20 31

Website :www.ekoteks.com

Contact person : Ece Pehlivan

E-mail : ece_pehlivan@ekoteks.com

QUERIES AND CLARIFICATIONS

On a periodic basis we will inform you of any future modifications that affect the present document.

Compliance with this regulation is an essential condition in order to work with the MANGO group as a supplier. For this reason, we ask you to sign and stamp your acceptance in the last page of the present document (page 19). Once signed and stamped, please scan and return just the last page to the e-mail address you receive it from.

For any queries or clarification, please do not hesitate to contact us:

Susana Guerra /Tel. 0034 938602222 Ext. 11466/ susana.guerra@mango.com

We take this opportunity to thank you very much for your collaboration and cooperation.

Yours faithfully,

A handwritten signature in black ink, appearing to read 'Susana Guerra', with a stylized flourish at the end.

Susana Guerra
Quality Control

[Name of supplier]

assures to comply with these regulations for any orders agreed with **PUNTO FA S.L.** and shall be responsible for any damages it may cause the latter, in the event of non-compliance with any of the regulations contained in this document:
QUALITY ASSURANCE –Textile Laboratories- reference number EF-LAB-0P-004/1

Name of the laboratory chosen

SUPPLIER: NAME AND SIGNATURE OF
GENERAL MANAGEMENT AND STAMP

PUNTO FA, S.L.



Carles Solà Vila
Quality Department Director

Manager