

Standard & Requirements

	Standard	Tolerance	Comments
Fiber Composition	ISO 1833	3%	
Determination of PH of aqueous extract	ISO 3071	4-7,5	
Colour Fastness to Rubbing DRY	ISO 105-X12	≥ 3-4	
Colour Fastness to Rubbing WET	ISO 105-X12	≥ 3	
Colour Fastness to Washing	ISO 105-C06	≥ 3-4	
Colour Fastness to Perspiration	ISO 105-E04	≥ 3-4	
Colour Fastness to Water	ISO 105-E01	≥ 3-4	
Determination of the slippage resistance of yarns at a seam in woven fabrics-- Part 1	ISO 13935-2**	≥ 80N	
Seam Slippage Resistance - Woven - Fixed Opening	ISO 13936-1	≥150N	
Dimensional Change after Washing	ISO 6330/ISO 5077	± 3%*	
Dimensional Change after Dry Clean	ISO 3175/ISO 5077	± 3%	
Colour Fastness to Dry Clean	ISO 105-D01	≥ 3-4	
Determination of the elasticity of fabrics: Strip test	UNE-EN 14704-1	≤ 6%	
Colour Fastness to Light	ISO 105-BO2	>5	Scale measure from 1 to 8
Snagging	ASTM D-3939-08	≥ 3-4	
Pilling test (Martindale method) / Pilling Box	ISO 12945-2 / ISO 12945-1	≥ 3-4	3-4 Knitwear 3 Outerwear
Determination of dimensional change of textil fabrics;ironing with moist ironing cloth on ironing presses	DIN 53894-1	± 3%	
Determination of the abrasion resistance of fabrics by the Marindale method	ISO 12947-1/ISO 12947-2	> 15000	
Determination of resistance to water penetration: Hydrostatic Pressure Test	ISO 811	≥ 90 cm	
Determination of water repellency of fabrics by the Bundesmann rain-shower test	ISO 9865: Penetration	≥ 15%	
Determination of water repellency of fabrics by the Bundesmann rain-shower test	ISO 9865: Absorption	≥ 3	
Methods for determination of bow, skew and lenghway distortion in woven and knitted fabrics	BS 2819	≤ 4%	Not applicable in Denim Garments
Determination of Spirality after laundering - Part2 Woven and Knitted Fabrics	ISO-16322-2	± 5%	Only for Circular Knit Garments

* The dimensional stability results should be regular in all lots (positive or negative)

** New Standard or Updated rate

*** Depending on the fabric characteristic some of the standard acceptance will vary.