

Strato Esterno (Giubbotti e Pantaloni tecnici ecc.) - Outer Layer (Technical Jackets & Trousers, etc.) A-Act				
Requirement Description	Conformity Reference / Test Method	Technical details	Requirements	Notes
Fiber Composition	Reg. EU 1007/2011 - GB/T 2910 - BS 4407 AATCC 20 - ISO 1833 - ASTM D 276 - FZ/T 01057-1/7		± 3%	A 1
Mass per unit area	ISO 3801	Method 5	± 5%	
Colour Fastness to Washing	ISO 105 C06	A2S at 40°C	CC ≥ 4 ST ≥ 3-4	A/A 2
Colour Fastness to Dry Cleaning	ISO 105 D01		CC ≥ 4 ST ≥ 4	A/A 3
Colour Fastness to Acid Perspiration	ISO 105 E04		CC ≥ 4 ST ≥ 3-4	A/A 2
Colour Fastness to Alkaline Perspiration	ISO 105 E04		CC ≥ 4 ST ≥ 3-4	A/A 2
Colour Fastness to Rubbing	ISO 105 X12	Dry / Wet	Dry ≥ 4 Wet ≥ 3-4	A 4
Colour Fastness to Light	ISO 105 B02		CC ≥ 4	A
Colour Fastness to Water	ISO 105 E01		CC ≥ 4 ST ≥ 3-4	A/A 2
Colour Migration on PVC	ISO 105-X10		CC ≥ 4 ST ≥ 4	
Colour Fastness to Water Spotting	ISO 105 E07	Evaluation Wet/Dry	CC ≥ 4	A/A 5
Dimensional Stability to Washing	ISO 6330 - 5077 - 3759	1 cycle - 4N at 40°C	Woven ± 2% Knitted -4% +2%	
Dimensional Stability to Dry Cleaning	Commercial cycle		Woven ± 2% Knitted -4% +2%	
Dimensional Stability to Steaming	BS 4323 or DIN 53894		Woven ± 2% Knitted -4% +2%	
Appearance after Laundering/Drycleaning	3 washing cycle + Standard Tumble drying		No noticeable changes aft 1 & 3 cycles	A 7
Movement after washing	AATCC 179	Option 1	≤ 3%	
Pilling resistance - (ICI box method)	ISO 12945-1	Evaluation at 7.200 and 10.800 revs	≥ 4	A 8/A 9
Pilling resistance - (Martindale)	ISO 12945-2	Tex-tex Evaluation at 500, 1.000 and 2000 revs	≥ 4	A 10/A 9
Seam Strength	ISO 13935-2		≥ 150N	
Seam Slippage	ISO 13936-1	6,0 mm	≥ 100 N	A 10
Bursting Strength	ISO 13938		Fabric: ≥ 280 kPa Seam: ≥ 250 kPa	A 8
Tensile Strength (Grab Method)	ISO 13934-2		Fabric up to 200 g/m²: ≥ 120 N Fabric over 200 g/m²: ≥ 170 N	A 10
Tear Strength (Dinamometric Method)	ISO 13937-2	Trouser Method	Fabric up to 200 g/m²: ≥ 10 N Fabric over 200 g/m²: ≥ 15 N	A 10
Tear Strength (Elmendorf Method)	ISO 13937-1		Fabric up to 200 g/m²: ≥ 10 N Fabric over 200 g/m²: ≥ 15 N	A 10
Abrasion resistance	ISO 12947-1 and -2	9 kPa 2 broken yarns	20.000 revs CC ≥ 3-4 at 3.000 revs	A/A 10
Water permeability (Hydrostatic head)	ISO 811	After 5 washing cycles	≥ 3000 mm	A 11
Water vapour permeability (Brethability)	ISO 11092		RET ≤ 6	
	ASTM E96	Method BW	≥ 4000 gr/m2/day	
		Method B	≥ 600 gr/m2/day	
	JIS L1099	Method B-1	≥ 15000 gr/m2/day	
Air permeability	ISO 9237	Method A-1	≥ 4000 gr/m2/day	
Electrostatic Properties	EN 1149 -1 & 3	After 5 washing cycles	≤ 10 mm/s	A 15
Spray test	EN ISO 4920	After 5 washing cycle	≤ 2,5 x 10 ⁹ Ω t50 <4 or S>0,2	A 14
pH of the aqueous extract	ISO 3071	KCl 0.1M	≥ ISO 4	A 9
Colour shade	ISO 105 J03 - ISO 105 A02	ΔE - D65 and TL84	4.0÷7.5	
Accelerated Ageing (storage) test	IHTM	7 days @70°C - 90-95%RH	≤ 1,0 / ≥ 4	A 13
Oxygen Index Number	EN 1162		Slight changes	
Down and feather sterilization	EN 1884		< 20	A 12
Oil and fat content	EN 1163		PASS	A 12
Turbidity	EN 1164		0.5÷2.0%	A 12
pH	EN 1413		≥ 300 mm	A 12
Down proof properties - Rubbing test	EN 12132-1		6.6÷8.0	A 12
			≤ 10 elements	A 12

Notes	
A	CC = Colour change - ST = Staining
A 1	No tolerance for single fiber
A 2	If there are trims and/or different colours within the garment: ST ≥ 4-5
A 3	Staining in the solvent
A 4	Pigment print: Dry ≥ 3-4 - Wet ≥ 3
A 5	To be carried out before Spray test
A 6	nil
A 7	Tumble dry: normal temperature - exhaust temperature max 80°C
A 8	For knitted fabrics only
A 9	After 5 washing cycles at After 5 washing cycles 4N@40°C.
A 10	For woven fabrics only
A 11	For water proof garments only - On fabric and seams
A 12	For feather and down filling garments only
A 13	PP sample vs Bulk or Shipment sample. ISO 105 J03 for Instrumental evaluation. ISO 105 A02 for visual evaluation .
A 14	Textiles main material shall comply with one of the two requirements at least
A 15	Requirements for fabrics with Membrane or Coating (Windproof) . For wind resistance of fabrics ≤ 30mm /s

Strato Intermedio (Maglieria,T-Shirts, Pile, Felpe, Pantaloni) -Intermediate layer (Knitwear, T-Shirts, Pile, Sweaters, Trousers) G-act				
Requirement	Description	Conformity Reference / Test Method	Technical details	Requirements
Fiber Composition		Reg. EU 1007/2011 - GB/T 2910 - BS 4407 AATCC 20 - ISO 1833 - ASTM D 276 - FZ/T 01057-1/7		± 3%
Mass per unit area		ISO 3801	Method 5	± 5%
Colour Fastness to Washing		ISO 105 C06	A2S at 40°C	CC ≥ 4 ST ≥ 3-4
Colour Fastness to Dry Cleaning		ISO 105 D01		CC ≥ 4 ST ≥ 4
Colour Fastness to Acid Perspiration		ISO 105 E04		CC ≥ 4 ST ≥ 3-4
Colour Fastness to Alkaline Perspiration		ISO 105 E04		CC ≥ 4 ST ≥ 3-4
Colour Fastness to Rubbing		ISO 105 X12	Dry / Wet	Dry ≥ 4 Wet ≥ 3-4
Colour Fastness to Light		ISO 105 B02		CC ≥ 4
Colour Migration on PVC		ISO 105-X10		CC ≥ 4 ST ≥ 4
Colour Fastness to Chlorine Bleach		ISO 105 N01	Sodium hypochloride	CC ≥ 4
Dimensional Stability to Washing		ISO 6330 - 5077 - 3759	1 cycle - 4N at 40°C	-4% +2%
Dimensional Stability to Dry Cleaning		Commercial cycle		-4% +2%
Dimensional Stability to Steaming		BS 4323 or DIN 53894		-4% +2%
Appearance after Laundering/Drycleaning		3 washing cycle + Tumble dry		No noticeable changes aft1 & 3 cycles
Movement after washing		AATCC 179	Option 1	≤ 3%
Colour shade		ISO 105 J03 - ISO 105 A02	ΔE - D65 and TL84	≤1,0 / ≥4
Accelerated Ageing (storage) test		IHTM	7 days @70°C - 90-95%RH	Slight changes
Pilling resistance - (ICI box method)		ISO 12945-1	Evaluation at 7.200 and 10.800 revs	≥ 4
Seam Strength		ISO 13935-2		≥ 150N
Bursting Strength		ISO 13938		Fabric: ≥280 kPa Seam: ≥ 250 kPa
Stretch & Recovery		EN ISO 20932-1		Stretch: ≥ 15%/Residual Extension: ≤ 5%
Electrostatic Properties		EN 1149 -1 & 3		≤2,5 x 10 ⁹ Ω t50 <4 or S>0,2
Antibacterial activities		AATCC 100	After 5 washing Cycle	≥70%
Water vapour permeability (Breathability)		ASTM E96 (B) / ISO 11092	nil	≥600 gr/m2/day / RET ≤ 6
Thermal resistance		ASTM D1518		Clo ≥0,05
UV Protection properties		EN 13758-1&2	UPF	≥ 25
Determination of deodorant property		ISO 17299	Isovaleric acid & 2-Nonenal	Odor reduction rate ≥ 80
Vertical wicking		AATCC 197-2011e2(2018)e	Option B - 3 cycle washing 3N @30°Line Dry	2mins:70mm 10mins:100mm
Drying time		AATCC 199	nil	≥50% after 30 mins
pH of the aqueous extract		ISO 3071	KCl 0.1M	4.0÷7.5

Notes	
G	CC = Colour change - ST = Staining
G 1	No tolerance for single fiber
G 2	If there are trims and/or different colours within the garment: ST ≥ 4-5
G 3	Staining in the solvent
G 4	Pigment print: Dry ≥ 3-4 - Wet ≥ 3
G 5	nil
G 6	Tumble dry: normal temperature - exhaust temperature max 80°C
G 7	After 1 washing cycles at 40°C. After 1 dry cleaning cycle when it's the only maintenance permitted in care label
G 8	For fabrics containing elastane only
G 9	After 1 hand wash cycle for wool, wool blend, kashmir, kashmir blend or precious fibres
G 10	Textiles main material shall comply with one of the two requirements at least
G 11	UV protective clothing for which compliance is claimed shall permanently be marked with pittogram provided by the standard EN 13758-2
G 13	PP sample vs Bulk or Shipment sample. ISO 105 J03 for Instrumental evaluation. ISO 105 A02 for visual evaluation

Intimo "tecnico" - "Technical" Underwear					L-Act
Requirement	Description	Conformity Reference / Test Method	Technical details	Requirements	Notes
Fiber Composition		Reg. EU 1007/2011 - GB/T 2910 - BS 4407 AATCC 20 - ISO 1833 - ASTM D 276 - FZ/T 01057-1/7		± 3%	L 1
Mass per unit area		ISO 3801	Method 5	± 5%	
Colour Fastness to Washing		ISO 105 C06	A2S at 40°C	CC ≥ 4 ST ≥ 3-4	L/L 2
Colour Fastness to Dry Cleaning		ISO 105 D01		CC ≥ 4 ST ≥ 4	L/L 3
Colour Fastness to Acid Perspiration		ISO 105 E04		CC ≥ 4 ST ≥ 3-4	L/L 2
Colour Fastness to Alkaline Perspiration		ISO 105 E04		CC ≥ 4 ST ≥ 3-4	L/L 2
Colour Fastness to Rubbing		ISO 105 X12	Dry / Wet	Dry ≥ 4 Wet ≥ 3-4	L 4
Colour Fastness to Light		ISO 105 B02		CC ≥ 3	L
Colour Migration on PVC		ISO 105-X10		CC ≥ 4 ST ≥ 4	
Colour Fastness to Water		ISO 105 E01		CC ≥ 4 ST ≥ 3-4	L/L 2
Colour Fastness to Chlorine Bleach		ISO 105 N01	Sodium hypochloride	CC ≥ 4	L
Dimensional Stability to Washing		ISO 6330 - 5077 - 3759	1 cycle - 4N at 40°C	Woven ± 2% Knitted -4% +2%	L 5
Dimensional Stability to Dry Cleaning		Commercial cycle		Woven ± 2% Knitted -4% +2%	
Dimensional Stability to Steaming		BS 4323 or DIN 53894		Woven ± 2% Knitted -4% +2%	
Appearance after Laundering/Drycleaning		3 washing cycle + Standard Tumble drying		No noticeable changes aft 183 cycles	L 5
Movement after washing		AATCC 179	Option 1	≤ 3%	
Colour shade		ISO 105 J03 - ISO 105 A02	ΔE - D65 and TL84	≤1,0 / ≥4	L 13
Pilling resistance - (ICI box method)		ISO 12945-1	Evaluation at 7.200 and 10.800 revs	≥ 4	L 7/L 8
Pilling resistance - (Martindale)		ISO 12945-2	Tex-tex Evaluation at 500, 1.000 and 2000 revs	≥ 4	L 9/L 8
Seam Strength		ISO 13935-2		≥ 120N	
Seam Slippage		ISO 13936-1	3,0 mm	≥ 80 N	L 9
Bursting Strength		ISO 13938		Fabric: ≥280 kPa Seam: ≥ 250 kPa	L 7
Tensile Strength (Grab Method)		ISO 13934-2		Fabric up to 200 g/m ² : ≥ 120 N Fabric over 200 g/m ² : ≥ 170 N	L 9
Tear Strength (Dinamometric Method)		ISO 13937-2	Trouser Method	Fabric up to 200 g/m ² : ≥ 10 N Fabric over 200 g/m ² : ≥ 15 N	L 9
Tear Strength (Elmendorf Method)		ISO 13937-1		Fabric up to 200 g/m ² : ≥ 10 N Fabric over 200 g/m ² : ≥ 15 N	L 9
Stretch & Recovery		EN ISO 20932-1		Stretch: ≥ 15%/Residual Extension: ≤ 5%	L 10
Abrasion resistance		ISO 12947-1 and -2	9 kPa 2 broken yarns	10.000 revs CC ≥ 3-4 at 3.000 revs	L/L 9
Electrostatic Properties		EN 1149 -1 & 3		≤2,5 x 10 ⁹ Ω t50 <4 or S>0,2	L 11 / L 12
Antibacterial activities		AATCC 100	After 5 washing Cycle	≥90%	
Water vapour permeability (Breathability)		ASTM E96 (B) / ISO 11092	nil	≥600 gr/m2/day / RET ≤ 6	
Drying time		AATCC 199	nil	≥50% after 30 mins	
Accelerated Ageing (storage) test		IHTM	7 days @70°C - 90-95%RH	Slight changes	
Thermal resistance		ASTM D1518		T -shirt: Clo ≥0,05 Boxer or Slip : Clo ≥0,10	
pH of the aqueous extract		ISO 3071	KCl 0.1M	4.0÷7.5	

Notes	
L	CC = Colour change - ST = Staining
L 1	No tolerance for single fiber
L 2	If there are trims and/or different colours within the garment: ST ≥ 4-5
L 3	Staining in the solvent
L 4	Pigment print: Dry ≥ 3-4 - Wet ≥ 3
L 5	Tumble dry: normal temperature - exhaust temperature max 80°C
L 6	After 3 washing cycles at 40°C. After 1 dry cleaning cycle when it's the only maintenance permitted in care label
L 7	For knitted fabrics only. After 1hand wash cycle for silk only
L 8	After 1 washing cycles at 40°C. After 1 dry cleaning cycle when it's the only maintenance permitted in care label
L 9	For woven fabrics only. After 1hand wash cycle for silk only
L 10	For fabrics containing elastane only
L 11	Textiles main material shall comply with one of the two requirements at least
L 12	Requirements for both New and after 3 washing cycles
L 13	PP sample vs Bulk or Shipment sample. ISO 105 J03 for Instrumental evaluation. ISO 105 A02 for visual evaluation

Calze Tecniche - Technical Socks J-Act				
Requirement Description	Conformity Reference / Test Method	Technical details	Requirements	Notes
Fiber Composition	Reg. EU 1007/2011 - GB/T 2910 - BS 4407	Method 5	± 3%	J 1
Fiber Composition	AATCC 20 - ISO 1833 - ASTM D 276 - FZ/T 01057-1/7			
Mass per unit area	ISO 3801		± 5%	
Colour Fastness to Washing	ISO 105 C06	A2S at 40°C	CC ≥ 4 ST ≥ 3-4	J/J 2
Colour Fastness to Dry Cleaning	ISO 105 D01		CC ≥ 4 ST ≥ 4	J/J 3
Colour Fastness to Acid Perspiration	ISO 105 E04		CC ≥ 4 ST ≥ 3-4	J/J 2
Colour Fastness to Alkaline Perspiration	ISO 105 E04		CC ≥ 4 ST ≥ 3-4	J/J 2
Colour Fastness to Rubbing	ISO 105 X12	Dry / Wet	Dry ≥ 4 Wet ≥ 3-4	J 4
Colour Fastness to Light	ISO 105 B02		CC ≥ 4	
Colour Migration on PVC	ISO 105-X10		CC ≥ 4 ST ≥ 4	
Colour Fastness to Water	ISO 105 E01		CC ≥ 4 ST ≥ 3-4	J/J 2
Colour Fastness to Chlorine Bleach	ISO 105 N01	Sodium hypochloride	CC ≥ 4	
Dimensional Stability to Washing	ISO 6330	1 cycle - 4N at 40°C	-4% +2%	J 5
Dimensional Stability to Dry Cleaning	Commercial cycle		-4% +2%	
Dimensional Stability to Steaming	BS 4323 or DIN 53894		-4% +2%	
Appearance after Laundering/Drycleaning	IHTM		No noticeable changes aft 1&3 cycles	J 5 / J 6
Movement after washing	AATCC 179	Option 1	>5%	
Pilling resistance - (ICI box method)	ISO 12945-1	Evaluation at 7.200 and 10.800 revs	≥ 3-4	J 7/J 9
Abrasion resistance	EN 13770	9 kPa 2 broken yarns	15.000/CT a 3.000 max 3/4	
Bursting Strength	ISO 13938		490 kPa	
Stretch & Recovery	EN ISO 20932-1		Stretch: ≥ 15%/Residual Extension: ≤ 5%	J 8
Antibacterial activities	AATCC 100	After 5 washing Cycle	≥90%	
Water vapour permeability (Breathability)	ASTM E96 (B) / ISO 11092	nil	≥600 gr/m2/day / RET ≤ 6	
Drying time	AATCC 199	nil	≥50% after 30 mins	
Thermal resistance	ASTM D1518		Clo ≥0,05	
Accelerated Ageing (storage) test	IHTM	7 days @70°C - 90-95%RH	Slight changes	
Electrostatic Properties	EN 1149 -1 & 3		≤2,5 x 10 ⁹ Ω t50 <4 or S>0,2	J 10
pH of the aqueous extract	ISO 3071	KCl 0.1M	4.0÷7.5	

Notes	
J	CC = Colour change - ST = Staining
J 1	No tolerance for single fiber
J 2	If there are trims and/or different colours within the sock: ST ≥ 4-5
J 3	Staining in the solvent
J 4	Pigment print: Dry ≥ 3-4 - Wet ≥ 3
J 5	Tumble dry: normal temperature - exhaust temperature max 80°C
J 6	After 3 washing cycles at 40°C. After 1 dry cleaning cycle when it's the only maintenance permitted in care label
J 7	After 1 washing cycles at 40°C. After 1 dry cleaning cycle when it's the only maintenance permitted in care label
J 8	For fabrics containing elastane only
J 9	After 1 hand wash cycle for wool, wool blend, kashmir, kashmir blend or precious fibres
J 10	Textiles main material shall comply with one of the two requirements at least

Impermeabili, Giacche Casual, Giubbotti Imb. Piuma - Raincoats, Casual Jackets, Padded Down Jackets					A
Requirement	Description	Conformity Reference / Test Method	Technical details	Requirements	Notes
Fiber Composition		Reg. EU 1007/2011 - GB/T 2910 - BS 4407 AATCC 20 - ISO 1833 - ASTM D 276 - FZ/T 01057-1/7		± 3%	A 1
Mass per unit area		ISO 3801	Method 5	± 5%	
Colour Fastness to Washing		ISO 105 C06	A2S at 40°C	CC ≥ 4 ST ≥ 3-4	A/A 2
Colour Fastness to Dry Cleaning		ISO 105 D01		CC ≥ 4 ST ≥ 4	A/A 3
Colour Fastness to Acid Perspiration		ISO 105 E04		CC ≥ 4 ST ≥ 3-4	A/A 2
Colour Fastness to Alkaline Perspiration		ISO 105 E04		CC ≥ 4 ST ≥ 3-4	A/A 2
Colour Fastness to Rubbing		ISO 105 X12	Dry / Wet	Dry ≥ 4 Wet ≥ 3-4	A 4
Colour Fastness to Light		ISO 105 B02		CC ≥ 4	A
Colour Migration on PVC		ISO 105-X10		CC ≥ 4 ST ≥ 4	
Colour Fastness to Water		ISO 105 E01		CC ≥ 4 ST ≥ 3-4	A/A 2
Colour Fastness to Water Spotting		ISO 105 E07	Evaluation Wet/Dry	CC ≥ 4	A/A 5
Dimensional Stability to Washing		ISO 6330 - 5077 - 3759	4N at 40°C - Tumble dry	Woven ± 2% Knitted -4% +2%	
Dimensional Stability to Dry Cleaning		Commercial cycle		Woven ± 2% Knitted -4% +2%	
Dimensional Stability to Steaming		BS 4323 or DIN 53894		Woven ± 2% Knitted -4% +2%	
Appearance after Laundering/Drycleaning		IHTM		No noticeable changes aft 1 & 3 cycles	A 7
Movement after washing		AATCC 179	Option 1	≤ 3%	
Pilling resistance - (ICI box method)		ISO 12945-1	Evaluation at 7.200 and 10.800 revs	≥ 4	A 8/A 9
Pilling resistance - (Martindale)		ISO 12945-2	Evaluation at 500, 1.000 and	≥ 4	A 10/A 9
Seam Strength		ISO 13935-2		≥ 150N	
Seam Slippage		ISO 13936-1	6,0 mm	≥ 100 N	A 10
Bursting Strength		ISO 13938		Fabric: ≥ 280 kPa Seam: ≥ 250 kPa	A 8
Tensile Strength (Grab Method)		ISO 13934-2		Fabric up to 200 g/m ² : ≥ 120 N Fabric over 200 g/m ² : ≥ 170 N	A 10
Tear Strength (Dinamometric Method)		ISO 13937-2	Trouser Method	Fabric up to 200 g/m ² : ≥ 10 N Fabric over 200 g/m ² : ≥ 15 N	A 10
Tear Strength (Elmendorf Method)		ISO 13937-1		Fabric up to 200 g/m ² : ≥ 10 N Fabric over 200 g/m ² : ≥ 15 N	A 10
Abrasion resistance		ISO 12947-1 and -2	9 kPa 2 broken yarns	20.000 revs CC ≥ 3-4 at 3.000 revs	A/A 10
Water permeability (Hydrostatic head)		ISO 811	Water Column	≥ 1800 mm	A 11
Electrostatic Properties		EN 1149 -1 & 3		≤ 2,5 x 10 ⁹ Ω t50 <4 or S>0,2	A 14
Spray test		EN ISO 4920	After 1 washing cycle	≥ ISO 4	A 9
pH of the aqueous extract		ISO 3071	KCl 0.1M	4.0÷7.5	
Colour shade		ISO 105 J03 - ISO 105 A02	ΔE - D65 and TL84	≤ 1,0 / ≥ 4	A 13
Accelerated Ageing (storage) test		IHTM	7 days @70°C - 90-95%RH	Slight changes	
Oxygen Index Number		EN 1162		< 20	A 12
Down and feather sterilization		EN 1884		PASS	A 12
Oil and fat content		EN 1163		0.5÷2.0%	A 12
Turbidity		EN 1164		≥ 300 mm	A 12
pH		EN 1413		6.6÷8.0	A 12
Down proof properties - Rubbing test		EN 12132-1		≤ 10 elements	A 12

Notes	
A	CC = Colour change - ST = Staining
A 1	No tolerance for single fiber
A 2	If there are trims and/or different colours within the garment: ST ≥ 4-5
A 3	Staining in the solvent
A 4	Pigment print: Dry ≥ 3-4 - Wet ≥ 3
A 5	To be carried out before Spray test
A 6	nil
A 7	Tumble dry: normal temperature - exhaust temperature max 80°C
A 8	For knitted fabrics only
A 9	After 1 washing cycles at 40°C. After 1 dry cleaning cycle when it's the only maintenance permitted in care label
A 10	For woven fabrics only
A 11	For water proof garments only - On fabric and seams
A 12	For feather and down filling garments only
A 13	PP sample vs Bulk or Shipment sample. ISO 105 J03 for Instrumental evaluation. ISO 105 A02 for visual evaluation .
A 14	Textiles main material shall comply with one of the two requirements at least

Abbigliamento Uomo e Donna "Formale" e Cappotti - "Formal" Wear and Coats for Men and Women					A1
Requirement	Description	Conformity Reference / Test Method	Technical details	Requirements	Notes
Fiber Composition		Reg. EU 1007/2011 - GB/T 2910 - BS 4407		± 3%	A 1
Mass per unit area		AATCC 20 - ISO 1833 - ASTM D 276 - FZ/T 01057-1/7		± 5%	
		ISO 3801	Method 5		
Colour Fastness to Washing		ISO 105 C06	A2S at 40°C	CC ≥ 4 ST ≥ 3-4	A/A 2
Colour Fastness to Acid Perspiration		ISO 105 E04		CC ≥ 4 ST ≥ 3-4	A/A 2
Colour Fastness to Alkaline Perspiration		ISO 105 E04		CC ≥ 4 ST ≥ 3-4	A/A 2
Colour Fastness to Rubbing		ISO 105 X12	Dry / Wet	Dry ≥ 4 Wet ≥ 3-4	A 4
Colour Fastness to Light		ISO 105 B02		CC ≥ 4	A
Colour Migration on PVC		ISO 105-X10		CC ≥ 4 ST ≥ 4	
Colour Fastness to Water		ISO 105 E01		CC ≥ 4 ST ≥ 3-4	A/A 2
Colour Fastness to Water Spotting		ISO 105 E07	Evaluation Wet/Dry	CC ≥ 4	A/A 5
Dimensional Stability to Dry Cleaning		Commercial cycle		Woven ± 2% Knitted -4% +2%	
Dimensional Stability to Steaming		BS 4323 or DIN 53894		Woven ± 2% Knitted -4% +2%	
Appearance after Drycleaning		IHTM		No noticeable changes	A 7
Movement after washing		AATCC 179	Option 1	≤ 3%	
Pilling resistance - (ICI box method)		ISO 12945-1	Evaluation at 7.200 and 10.800 revs	≥ 4	A 8/A 9
Pilling resistance - (Martindale)		ISO 12945-2	Tex-tex Evaluation at 500, 1.000 and 2000 revs	≥ 4	A 10/A 9
Seam Strength		ISO 13935-2		≥ 150N	
Seam Slippage		ISO 13936-1	6,0 mm	≥ 100 N	A 10
Bursting Strength		ISO 13938		Fabric: ≥ 280 kPa Seam: ≥ 250 kPa	A 8
Tensile Strength (Grab Method)		ISO 13934-2		Fabric up to 200 g/m²: ≥ 120 N Fabric over 200 g/m²: ≥ 170 N	A 10
Tear Strength (Dinamometric Method)		ISO 13937-2	Trouser Method	Fabric up to 200 g/m²: ≥ 10 N Fabric over 200 g/m²: ≥ 15 N	A 10
Tear Strength (Elmendorf Method)		ISO 13937-1		Fabric up to 200 g/m²: ≥ 10 N Fabric over 200 g/m²: ≥ 15 N	A 10
Abrasion resistance		ISO 12947-1 and -2	9 kPa 2 broken yarns	20.000 revs CC ≥ 3-4 at 3.000 revs	A/A 10
Accelerated Ageing (storage) test		IHTM	7 days @70°C - 90-95%RH	Slight changes	
Electrostatic Properties		EN 1149 -1 & 3		≤ 2,5 x 10 ⁹ Ω	A 14
Spray test		EN ISO 4920	After 1 washing cycle	≥ ISO 4	A 9
pH of the aqueous extract		ISO 3071	KCl 0.1M	4.0÷7.5	
Colour shade		ISO 105 J03 - ISO 105 A02	ΔE - D65 and TL84	≤ 1,0 / ≥ 4	A 13

Notes	
A	CC = Colour change - ST = Staining
A 1	No tolerance for single fiber
A 2	If there are trims and/or different colours within the garment: ST ≥ 4-5
A 3	Staining in the solvent
A 4	Pigment print: Dry ≥ 3-4 - Wet ≥ 3
A 5	To be carried out before Spray test
A 6	Flat dry
A 7	After 3 washing cycles at 40°C. After 1 dry cleaning cycle when it's the only maintenance permitted in care label
A 8	For knitted fabrics only
A 9	After 1 washing cycles at 40°C. After 1 dry cleaning cycle when it's the only maintenance permitted in care label
A 10	For woven fabrics only
A 11	For water proof garments only - On fabric and seams
A 12	For feather and down filling garments only
A 13	PP sample vs Bulk or Shipment sample. ISO 105 J03 for Instrumental evaluation. ISO 105 A02 for visual evaluation .
A 14	Textiles main material shall comply with one of the two requirements at least

Pantaloni, Gonne, Calzoncini, Vestiti - <i>Pants, Skirts, Shorts, Dresses</i>					B
Requirement	Description	Conformity Reference / Test Method	Technical details	Requirements	Notes
Fiber Composition		Reg. EU 1007/2011 - GB/T 2910 - BS 4407 AATCC 20 - ISO 1833 - ASTM D 276 - FZ/T 01057-1/7		± 3%	B 1
Mass per unit area		ISO 3801	Method 5	± 5%	
Colour Fastness to Washing		ISO 105 C06	A2S at 40°C	CC ≥ 4 ST ≥ 3-4	B/B 2
Colour Fastness to Dry Cleaning		ISO 105 D01		CC ≥ 4 ST ≥ 4	B/B 3
Colour Fastness to Acid Perspiration		ISO 105 E04		CC ≥ 4 ST ≥ 3-4	B/B 2
Colour Fastness to Alkaline Perspiration		ISO 105 E04		CC ≥ 4 ST ≥ 3-4	B/B 2
Colour Fastness to Rubbing		ISO 105 X12	Dry / Wet	Dry ≥ 4 Wet ≥ 3-4	B 4
Colour Migration on PVC		ISO 105-X10		CC ≥ 4 ST ≥ 4	B
Colour Fastness to Light		ISO 105 B02		CC ≥ 4	
Colour Fastness to Water		ISO 105 E01		CC ≥ 4 ST ≥ 3-4	B/B 2
Dimensional Stability to Washing		ISO 6330 - 5077 - 3759	4N at 40°C - Tumble dry	Woven ± 2% Knitted -4% +2%	B 5
Dimensional Stability to Dry Cleaning		Commercial cycle		Woven ± 2% Knitted -4% +2%	
Dimensional Stability to Steaming		BS 4323 or DIN 53894		Woven ± 2% Knitted -4% +2%	
Appearance after Laundering/Drycleaning		IHTM		No noticeable changes aft 1&3 cycles	B5 / B 6
Movement after washing		AATCC 179	Option 1	≤ 3%	B 13
Colour shade		ISO 105 J03 - ISO 105 A02	ΔE - D65 and TL84	≤1,0 / ≥4	
Pilling resistance - (ICI box method)		ISO 12945-1	Evaluation at 7.200 and 10.800 revs	≥ 4	B7 / B8
Pilling resistance - (Martindale)		ISO 12945-2	Tex-tex Evaluation at 500, 1.000 and 2000 revs	≥ 4	B 9/B 8
Seam Strength		ISO 13935-2		≥ 150N	
Seam Slippage		ISO 13936-1	6,0 mm	≥ 100 N	B 9
Bursting Strength		ISO 13938		Fabric: ≥280 kPa Seam: ≥ 250 kPa	B 7
Tensile Strength (Grab Method)		ISO 13934-2		Fabric up to 200 g/m ² : ≥ 120 N Fabric over 200 g/m ² : ≥ 170 N	B 9
Tear Strength (Dinamometric Method)		ISO 13937-2	Trouser Method	Fabric up to 200 g/m ² : ≥ 10 N Fabric over 200 g/m ² : ≥ 15 N	B 9
Tear Strength (Elmendorf Method)		ISO 13937-1		Fabric up to 200 g/m ² : ≥ 10 N Fabric over 200 g/m ² : ≥ 15 N	B 9
Stretch & Recovery		EN ISO 20932-1		Stretch: ≥ 15%/Residual Extension: ≤ 5%	B 10
Abrasion resistance		ISO 12947-1 and -2	9 kPa-2 broken yarns	20.000 revs CC ≥ 3-4 at 3.000 revs	B/B 9
Accelerated Ageing (storage) test		IHTM	7 days @70°C - 90-95%RH	Slight changes	
Electrostatic Properties		UNI EN 1149 -1 & 3		≤2,5 x 10 ⁹ Ω	B 11
pH of the acqueous extract		ISO 3071	KCl 0.1M	4.0±7.5	

Notes	
B	CC = Colour change - ST = Staining
B 1	No tolerance for single fiber
B 2	If there are trims and/or different colours within the garment: ST ≥ 4-5
B 3	Staining in the solvent
B 4	Pigment print: Dry ≥ 3-4 - Wet ≥ 3
B 5	Tumble dry: normal temperature - exhaust temperature max 80°C
B 6	After 3 washing cycles at 40°C. After 1 dry cleaning cycle when it's the only maintenance permitted in care label
B 7	For knitted fabrics only
B 8	After 1 washing cycles at 40°C. After 1 dry cleaning cycle when it's the only maintenance permitted in care label
B 9	For woven fabrics only
B 10	For fabrics containing elastane only
B 11	Textiles main material shall comply with one of the two requirements at least
B 13	PP sample vs Bulk or Shipment sample. ISO 105 J03 for Instrumental evaluation. ISO 105 A02 for visual evaluation

Jeans - Denim					C
Requirement	Description	Conformity Reference / Test Method	Technical details	Requirements	Notes
Fiber Composition		Reg. EU 1007/2011 - GB/T 2910 - BS 4407		± 3%	C 1
Mass per unit area		AATCC 20 - ISO 1833 - ASTM D 276 - FZ/T 01057-1/7		± 5%	
Colour Fastness to Washing		ISO 105 C06	Method 5	CC ≥ 4 ST ≥3-4	C/C 2
Colour Fastness to Dry Cleaning		ISO 105 D01	A2S at 40°C	CC ≥ 4 ST ≥4	C
Colour Fastness to Acid Perspiration		ISO 105 E04		CC ≥ 4 ST ≥3-4	C/C 2
Colour Fastness to Alkaline Perspiration		ISO 105 E04		CC ≥ 4 ST ≥3-4	C/C 2
Colour Fastness to Rubbing		ISO 105 X12	Dry / Wet	Dry ≥ 3-4 Wet ≥3	C 3
Colour Migration on PVC		ISO 105-X10		CC ≥ 4 ST ≥4	C
Colour Fastness to Light		ISO 105 B02		CC ≥ 4	
Colour Fastness to Water		ISO 105 E01		CC ≥ 4 ST ≥3-4	C/C2
Dimensional Stability to Washing		ISO 6330 - 5077 - 3759	4N at 40°C - Tumble dry	± 2%	C 4
Dimensional Stability to Dry Cleaning		Commercial cycle		± 2%	
Dimensional Stability to Steaming		BS 4323 or DIN 53894		± 2%	
Appearance after Laundering/Drycleaning		IHTM		No noticeable changes aft 1&3 cycles	C4 / C5
Movement after washing		AATCC 179	Option 1	≤ 5%	
Colour shade		ISO 105 J03 - ISO 105 A02	ΔE - D65 and TL84	≤1,0 / ≥4	C 13
Accelerated Ageing (storage) test		IHTM	7 days @70°C - 90-95%RH	Slight changes	
Pilling resistance - (Martindale)		ISO 12945-2	Tex-tex Evaluation at 500, 1.000 and 2000 revs	≥ 4	C 6
Seam Strength		ISO 13935-2		≥ 170N	
Seam Slippage		ISO 13936-1	6,0 mm	≥ 120 N	
Tensile Strength (Grab Method)		ISO 13934-2		≥ 230 N	
Tensile Strength (Strip Method)		ISO 13934-1		≥ 230 N	
Tear Strength (Dinamometric Method)		ISO 13937-2	Trouser Method	≥ 10 N	
Stretch & Recovery		EN ISO 20932-1		Stretch: ≥ 15%/Residual Extension: ≤ 5%	C 7
Abrasion resistance		ISO 12947-1 and -2	9 kPa 2 broken yarns	30.000 revs CC ≥ 3-4 at 3.000 revs	C
pH of the aqueous extract		ISO 3071	KCl 0.1M	4.0÷7.5	

Notes	
C	CC = Colour change - ST = Staining
C 1	No tolerance for single fiber
C 2	If there are trims and/or different colours within the garment: ST ≥ 4-5
C 3	Staining in the solvent
C 4	Tumble dry: normal temperature - exhaust temperature max 80°C
C 5	After 3 washing cycles at 40°C. After 1 dry cleaning cycle when it's the only maintenance permitted in care label
C 6	After 1 washing cycles at 40°C. After 1 dry cleaning cycle when it's the only maintenance permitted in care label
C 7	For fabrics containing elastane only
C 13	PP sample vs Bulk or Shipment sample. ISO 105 J03 for Instrumental evaluation. ISO 105 A02 for visual evaluation

Camiceria - Shirts				D
Requirement Description	Conformity Reference / Test Method	Technical details	Requirements	Notes
Fiber Composition	Reg. EU 1007/2011 - GB/T 2910 - BS 4407 AATCC 20 - ISO 1833 - ASTM D 276 - FZ/T 01057-1/7		± 3%	D 1
Mass per unit area	ISO 3801	Method 5	± 5%	
Colour Fastness to Washing	ISO 105 C06	A2S at 40°C	CC ≥ 4 ST ≥ 3-4	D/D 2
Colour Fastness to Dry Cleaning	ISO 105 D01		CC ≥ 4 ST ≥ 4	D/D 3
Colour Fastness to Acid Perspiration	ISO 105 E04		CC ≥ 4 ST ≥ 3-4	D/D 2
Colour Fastness to Alkaline Perspiration	ISO 105 E04		CC ≥ 4 ST ≥ 3-4	D/D 2
Colour Fastness to Rubbing	ISO 105 X12	Dry / Wet	Dry ≥ 4 Wet ≥ 3-4	D 4
Colour Migration on PVC	ISO 105-X10		CC ≥ 4 ST ≥ 4	
Colour Fastness to Light	ISO 105 B02		CC ≥ 4	D
Colour Fastness to Water	ISO 105 E01		CC ≥ 4 ST ≥ 3-4	D/D 2
Dimensional Stability to Washing	ISO 6330 - 5077 - 3759	4N at 40°C - Tumble dry	Woven ± 2% Knitted -4% +2%	D 5
Dimensional Stability to Dry Cleaning	Commercial cycle		Woven ± 2% Knitted -4% +2%	
Dimensional Stability to Steaming	BS 4323 or DIN 53894		Woven ± 2% Knitted -4% +2%	
Appearance after Laundering/Drycleaning	IHTM		No noticeable changes aft 183 Cycles	D5 / D6
Movement after washing	AATCC 179	Option 1	≤ 3%	
Colour shade	ISO 105 J03 - ISO 105 A02	ΔE - D65 and TL84	≤1,0 / ≥4	D 13
Pilling resistance - (ICI box method)	ISO 12945-1	Evaluation at 7.200 and 10.800 revs	≥ 4	D 7/D 8
Pilling resistance - (Martindale)	ISO 12945-2	Tex-tex Evaluation at 500, 1.000 and 2000 revs	≥ 4	D 9/D 8
Seam Strength	ISO 13935-2		Fabric up to 120 g/m ² : ≥ 100 N Fabric over 120 g/m ² : ≥ 150 N	
Seam Slippage	ISO 13936-1	3,0 mm	Fabric up to 120 g/m ² : ≥ 80 N Fabric over 120 g/m ² : ≥ 100 N	D 9
Bursting Strength	ISO 13938		Fabric: ≥280 kPa Seam: ≥ 250 kPa	D 7
Tensile Strength (Grab Method)	ISO 13934-2		Fabric up to 120 g/m ² : ≥ 120 N Fabric over 120 g/m ² : ≥ 170 N	D 9
Tear Strength (Dinamometric Method)	ISO 13937-2	Trouser Method	Fabric up to 120 g/m ² : ≥ 10 N Fabric over 120 g/m ² : ≥ 15 N	D 9
Tear Strength (Elmendorf Method)	ISO 13937-1		Fabric up to 120 g/m ² : ≥ 10 N Fabric over 120 g/m ² : ≥ 15 N	D 9
Stretch & Recovery	EN ISO 20932-1		Stretch: ≥ 15%/Residual Extension: ≤ 5%	D 10
Abrasion resistance	ISO 12947-1 and -2	9 kPa broken yarns	10.000 revs CC ≥ 3-4 at 3.000 revs	D/D 9
Water vapour permeability (Breathability)	ASTM E96 (B) / ISO 11092	nil	≥600 gr/m2/day / RET ≤ 6	
Accelerated Ageing (storage) test	IHTM	7 days @70°C - 90-95%RH	Slight changes	
Electrostatic Properties	EN 1149 -1 & 3		≤2,5 x 10 ⁹ Ω	D 11
pH of the aqueous extract	ISO 3071	KCl 0.1M	4.0÷7.5	

Notes	
D	CC = Colour change - ST = Staining
D 1	No tolerance for single fiber
D 2	If there are trims and/or different colours within the garment: ST ≥ 4-5
D 3	Staining in the solvent
D 4	Pigment print: Dry ≥ 3-4 - Wet ≥ 3
D 5	Tumble dry: normal temperature - exhaust temperature max 80°C
D 6	After 3 washing cycles at 40°C. After 1 dry cleaning cycle when it's the only maintenance permitted in care label
D 7	For knitted fabrics only. After 1hand wash cycle for silk only
D 8	After 1 washing cycles at 40°C. After 1 dry cleaning cycle when it's the only maintenance permitted in care label
D 9	For woven fabrics only. After 1hand wash cycle for silk only
D 10	For fabrics containing elastane only
D 11	Textiles main material shall comply with one of the two requirements at least
D 13	PP sample vs Bulk or Shipment sample. ISO 105 J03 for Instrumental evaluation. ISO 105 A02 for visual evaluation

Pelle - Leather E				
Requirement Description	Conformity Reference / Test Method	Technical details	Requirements	Notes
Colour Fastness to Dry Cleaning	ISO 105 D01	Perchloroethylene	CC ≥ 4 ST ≥ 4	E/E 2
Colour Fastness to Acid Perspiration	EN ISO 11641		CC ≥ 4 ST ≥ 4	
Colour Fastness to Alkaline Perspiration	EN ISO 11641		CC ≥ 4 ST ≥ 4	E/E 1
Colour Fastness to Rubbing	EN ISO 11640	See note for testing condition	Dry ≥ 4 Wet ≥ 4	E5
Colour Fastness to Light	ISO 105 B02		CC ≥ 4	E
Colour Migration on PVC	ISO 105-X10		CC ≥ 4 ST ≥ 4	
Colour Fastness to Water Spotting	ISO 105 E07	Evaluation Wet/Dry	CC ≥ 4	E/E 3
Dimensional Stability to Dry Cleaning	Commercial cycle		± 2%	
Dimensional Stability to Steaming	BS 4323 or DIN 53894		± 2%	
Appearance after Laundering/Drycleaning	IHTM		No noticeable changes	E 4
Seam Strength	ISO 13935-2		≥ 120N	
Tensile Strength (Grab Method)	ISO 13934-2		≥ 150 N	
Tensile Strength (Strip Method)	ISO 13934-1		≥ 170 N	
Tear Strength (Dinamometric Method)	ISO 13937-2	Trouser Method	≥ 10 N	
Tear Strength (Elmendorf Method)	ISO 13937-1		≥ 10 N	
Abrasion resistance	ISO 12947-1 and -4	3 kPa	CC ≥ 3-4 at 10.000 revs No noticeable changes at 20.000 revs	E
Spray test	EN ISO 4920	After 1 dry cleaning cycle	≥ ISO 4	
Accelerated Ageing (storage) test	IHTM	7 days @70°C - 90%RH	Slight changes	
pH of the aqueous extract	ISO 3071	KCl 0.1M	3.5÷7.5	

Notes	
E	CC = Colour change - ST = Staining
E 1	If there are trims and/or different colours within the garment: ST ≥ 4-5
E 2	Staining in the solvent
E 3	To be carried out before Spray test
E 4	After 1 dry cleaning cycle
E 5	Dry -100cycles; Wet-20 cycles; Sweat - 50cycles

Costumi da bagno - Swimwear					F
Requirement	Description	Conformity Reference / Test Method	Technical details	Requirements	Notes
Fiber Composition		Reg. EU 1007/2011 - GB/T 2910 - BS 4407 AATCC 20 - ISO 1833 - ASTM D 276 - FZ/T 01057-1/7		± 3%	F 1
Mass per unit area		ISO 3801	Method 5	± 5%	
Colour Fastness to Washing		ISO 105 C06	A2S at 40°C	CC ≥ 4 ST ≥ 3-4	F/F 2
Colour Fastness to Dry Cleaning		ISO 105 D01		CC ≥ 4 ST ≥ 4	F/F 3
Colour Fastness to Acid Perspiration		ISO 105 E04		CC ≥ 4 ST ≥ 3-4	F/F 2
Colour Fastness to Alkaline Perspiration		ISO 105 E04		CC ≥ 4 ST ≥ 3-4	F/F 2
Colour Fastness to Rubbing		ISO 105 X12	Dry / Wet	Dry ≥ 4 Wet ≥ 3-4	F 4
Colour Fastness to Light		ISO 105 B02		CC ≥ 5	F/F11
Colour Fastness to Water		ISO 105 E01		CC ≥ 4 ST ≥ 3-4	F/F 2
Colour Fastness to Sea Water		ISO 105 E02		CC ≥ 4 ST ≥ 3-4	
Colour Migration on PVC		ISO 105-X10		CC ≥ 4 ST ≥ 4	F/F11
Colour Fastness to Chlorinated Water		ISO 105 E03	50 ppm	CC ≥ 4	F 5
Dimensional Stability to Washing		ISO 6330 - 5077 - 3759	4N at 40°C - Tumble dry	Woven ± 2% Knitted -4% +2%	
Dimensional Stability to Dry Cleaning		Commercial cycle		Woven ± 2% Knitted -4% +2%	F5 / F 6
Appearance after Laundering/Drycleaning		IHTM		No noticeable changes aft 183 Cycles	
Movement after washing		AATCC 179	Option 1	≤ 5%	F 13
Colour shade		ISO 105 J03 - ISO 105 A02	ΔE - D65 and TL84	≤1,0 / ≥4	
Accelerated Ageing (storage) test		IHTM	7 days @70°C - 90-95%RH	Slight changes	F 7/F 8
Pilling resistance - (ICI box method)		ISO 12945-1	Evaluation at 7.200 and 10.800 revs	≥ 4	F 9/F 8
Pilling resistance - (Martindale)		ISO 12945-2	Tex-tex Evaluation at 500, 1.000 and 2000 revs	≥ 4	
Seam Strength		ISO 13935-2		≥ 120N	F 10
Stretch & Recovery		EN ISO 20932-1		Stretch: ≥ 15%/Residual Extension: ≤ 5%	F/F 9
Abrasion resistance		ISO 12947-1 and -2	9 kPa 2 broken yarns	20.000 revs CC ≥ 3-4 at 3.000 revs	F 12
UV Protection properties		EN 13758-1&2	UPF	≥ 25	
pH of the aqueous extract		ISO 3071	KCI 0.1M	4.0±7.5	

Notes	
F	CC = Colour change - ST = Staining
F 1	No tolerance for single fiber
F 2	If there are trims and/or different colours within the garment: ST ≥ 4-5
F 3	Staining in the solvent
F 4	Pigment print: Dry ≥ 3-4 - Wet ≥ 3
F 5	Tumble dry: normal temperature - exhaust temperature max 80°C
F 6	After 3 washing cycles at 40°C
F 7	For knitted fabrics only
F 8	After 1 washing cycles at 40°C
F 9	For woven fabrics only
F 10	For fabrics containing elastane only
F 11	For Fluo, Brillant and Turquase Colour: CC ≥ 3
F 12	UV protective clothing for which compliance is claimed shall permanently be marked with pittogram provided by the standard EN 13758-2
F 13	PP sample vs Bulk or Shipment sample. ISO 105 J03 for Instrumental evaluation. ISO 105 A02 for visual evaluation

Maglieria, T-Shirts, Pullovers, Felpe - Knitwear, T-Shirts, Sweaters, Sweatshirts					G
Requirement	Description	Conformity Reference / Test Method	Technical details	Requirements	Notes
Fiber Composition		Reg. EU 1007/2011 - GB/T 2910 - BS 4407 AATCC 20 - ISO 1833 - ASTM D 276 - FZ/T 01057-1/7		± 3%	G 1
Mass per unit area		ISO 3801	Method 5	± 5%	
Colour Fastness to Washing		ISO 105 C06	A2S at 40°C	CC ≥ 4 ST ≥ 3-4	G/G 2
Colour Fastness to Dry Cleaning		ISO 105 D01		CC ≥ 4 ST ≥ 4	G/G 3
Colour Fastness to Acid Perspiration		ISO 105 E04		CC ≥ 4 ST ≥ 3-4	G/G 2
Colour Fastness to Alkaline Perspiration		ISO 105 E04		CC ≥ 4 ST ≥ 3-4	G/G 2
Colour Fastness to Rubbing		ISO 105 X12	Dry / Wet	Dry ≥ 4 Wet ≥ 3-4	G 4
Colour Fastness to Light		ISO 105 B02		CC ≥ 4	G
Colour Migration on PVC		ISO 105-X10		CC ≥ 4 ST ≥ 4	
Colour Fastness to Water		ISO 105 E01		CC ≥ 4 ST ≥ 3-4	G/G 2
Colour Fastness to Chlorine Bleach		ISO 105 N01	Sodium hypochloride	CC ≥ 4	
Dimensional Stability to Washing		ISO 6330 - 5077 - 3759	4N at 40°C - Tumble dry	-4% +2%	G5
Dimensional Stability to Dry Cleaning		Commercial cycle		-4% +2%	
Dimensional Stability to Steaming		BS 4323 or DIN 53894		-4% +2%	
Appearance after Laundering/Drycleaning		IHTM		No noticeable changes 1&3 Cycles	G5 / G6
Movement after washing		AATCC 179	Option 1	≤ 3%	
Colour shade		ISO 105 J03 - ISO 105 A02	ΔE - D65 and TL84	≤1,0 / ≥4	G 13
Accelerated Ageing (storage) test		IHTM	7 days @70°C - 90-95%RH	Slight changes	
Pilling resistance - (ICI box method)		ISO 12945-1	Evaluation at 7.200 and 10.800 revs	≥ 4	G 7/G 9
Seam Strength		ISO 13935-2		≥ 150N	
Bursting Strength		ISO 13938		Fabric: ≥280 kPa Seam: ≥ 250 kPa	
Stretch & Recovery		EN ISO 20932-1		Stretch: ≥ 15%/Residual Extension: ≤ 5%	G 8
Electrostatic Properties		EN 1149 -1 & 3		≤2,5 x 10 ⁸ Ω t50 <4 or S>0,2	G 10
UV Protection properties		EN 13758-1&2	UPF	≥ 25 ≥ 40 (UPF 40+)	G 11
pH of the aqueous extract		ISO 3071	KCl 0.1M	4.0÷7.5	

Notes	
G	CC = Colour change - ST = Staining
G 1	No tolerance for single fiber
G 2	If there are trims and/or different colours within the garment: ST ≥ 4-5
G 3	Staining in the solvent
G 4	Pigment print: Dry ≥ 3-4 - Wet ≥ 3
G 5	Tumble dry: normal temperature - exhaust temperature max 80°C
G 6	After 3 washing cycles at 40°C. After 1 dry cleaning cycle when it's the only maintenance permitted in care label
G 7	After 1 washing cycles at 40°C. After 1 dry cleaning cycle when it's the only maintenance permitted in care label
G 8	For fabrics containing elastane only
G 9	After 1 hand wash / flat dry cycle for wool, wool blend, kashmir, kashmir blend or precious fibres
G 10	Textiles main material shall comply with one of the two requirements at least
G 11	UV protective clothing for which compliance is claimed shall permanently be marked with pittogram provided by the standard EN 13758-2
G 13	PP sample vs Bulk or Shipment sample. ISO 105 J03 for Instrumental evaluation. ISO 105 A02 for visual evaluation

Fodere - Linings					H
Requirement	Description	Conformity Reference / Test Method	Technical details	Requirements	Notes
Fiber Composition		Reg. EU 1007/2011 - GB/T 2910 - BS 4407 AATCC 20 - ISO 1833 - ASTM D 276 - FZ/T 01057-1/7		± 3%	H 1
Mass per unit area		ISO 3801	Method 5	± 5%	
Colour Fastness to Washing		ISO 105 C06	A2S at 40°C	CC ≥ 4 ST ≥3-4	H/H 2
Colour Fastness to Dry Cleaning		ISO 105 D01		CC ≥ 4 ST ≥4	H/H 3
Colour Fastness to Acid Perspiration		ISO 105 E04		CC ≥ 4 ST ≥3-4	H/H 2
Colour Fastness to Alkaline Perspiration		ISO 105 E04		CC ≥ 4 ST ≥3-4	H/H 2
Colour Fastness to Rubbing		ISO 105 X12	Dry / Wet	Dry ≥ 4 Wet ≥3-4	H 4
Colour Migration on PVC		ISO 105-X10		CC ≥ 4 ST ≥4	
Colour Fastness to Light		ISO 105 B02		CC ≥ 3	H
Colour Fastness to Water		ISO 105 E01		CC ≥ 4 ST ≥3-4	H/H 2
Dimensional Stability to Washing		ISO 6330 - 5077 - 3759	4N at 40°C - Tumble dry	Woven ± 2% Knitted -4% +2%	H 5
Dimensional Stability to Dry Cleaning		Commercial cycle		Woven ± 2% Knitted -4% +2%	
Dimensional Stability to Steaming		BS 4323 or DIN 53894		Woven ± 2% Knitted -4% +2%	
Appearance after Laundering/Drycleaning		IHTM		No noticeable changes aft 1&3 cycles	H 6
Movement after washing		AATCC 179	Option 1	≤ 3%	
Pilling resistance - (ICI box method)		ISO 12945-1	Evaluation at 7.200 and 10.800 revs	≥ 4	H 7/H 8
Pilling resistance - (Martindale)		ISO 12945-2	Tex-tex Evaluation at 500, 1.000 and 2000 revs	≥ 4	H 9/H 8
Seam Strength		ISO 13935-2		≥ 120N	
Seam Slippage		ISO 13936-1	3,0 mm	≥ 100 N	H 9
Bursting Strength		ISO 13938		Fabric: ≥280 kPa Seam: ≥ 250 kPa	H 7
Tensile Strength (Grab Method)		ISO 13934-2		≥ 150 N	H 9
Tear Strength (Dinamometric Method)		ISO 13937-2	Trouser Method	≥ 10 N	H 9
Tear Strength (Elmendorf Method)		ISO 13937-1		≥ 10 N	H 9
Stretch & Recovery		EN ISO 20932-1		Stretch: ≥ 15%/Residual Extension: ≤ 5%	H 10
Abrasion resistance		ISO 12947-1 and -2	9 kPa 2 broken yarns	10.000 revs CC ≥ 3-4 at 3.000 revs	H/H 9
Electrostatic Properties		EN 1149 -1 & 3		≤2,5 x 10 ⁹ Ω t50 <4 or S>0,2	H 10
Accelerated Ageing (storage) test		IHTM	7 days @70°C - 90-95%RH	Slight changes	
pH of the aqueous extract		ISO 3071	KCl 0.1M	4.0÷7.5	

Notes	
H	CC = Colour change - ST = Staining
H 1	No tolerance for single fiber
H 2	If there are trims and/or different colours within the garment: ST ≥ 4-5
H 3	Staining in the solvent
H 4	Pigment print: Dry ≥ 3-4 - Wet ≥ 3
H 5	Tumble dry: normal temperature - exhaust temperature max 80°C
H 6	After 3 washing cycles at 40°C. After 1 dry cleaning cycle when it's the only maintenance permitted in care label
H 7	For knitted fabrics only
H 8	After 1 washing cycles at 40°C. After 1 dry cleaning cycle when it's the only maintenance permitted in care label
H 9	For woven fabrics only
H 10	For fabrics containing elastane only
H 11	Textiles main material shall comply with one of the two requirements at least

Guanti, Sciarpe, Cappelli, Scialli - Gloves, Scarves, Hats, Shawles					I
Requirement	Description	Conformity Reference / Test Method	Technical details	Requirements	Notes
Fiber Composition		Reg. EU 1007/2011 - GB/T 2910 - BS 4407 AATCC 20 - ISO 1833 - ASTM D 276 - FZ/T 01057-1/7		± 3%	I 1
Mass per unit area		ISO 3801	Method 5	± 5%	
Colour Fastness to Washing		ISO 105 C06	A2S at 40°C	CC ≥ 4 ST ≥ 3-4	I/I 2
Colour Fastness to Dry Cleaning		ISO 105 D01		CC ≥ 4 ST ≥ 4	I/I 3
Colour Fastness to Acid Perspiration		ISO 105 E04		CC ≥ 4 ST ≥ 3-4	I/I 2
Colour Fastness to Alkaline Perspiration		ISO 105 E04		CC ≥ 4 ST ≥ 3-4	I/I 2
Colour Fastness to Rubbing		ISO 105 X12	Dry / Wet	Dry ≥ 4 Wet ≥ 3-4	I 4
Colour Fastness to Light		ISO 105 B02		CC ≥ 4	I
Colour Migration on PVC		ISO 105-X10		CC ≥ 4 ST ≥ 4	
Colour Fastness to Water		ISO 105 E01		CC ≥ 4 ST ≥ 3-4	I/I 2
Colour Fastness to Chlorine Bleach		ISO 105 N01	Sodium hypochloride	CC ≥ 4	I
Dimensional Stability to Washing		ISO 6330 - 5077 - 3759	4N at 40°C - Tumble dry	Woven ± 2% Knitted -4% +2%	I 5
Dimensional Stability to Dry Cleaning		Commercial cycle		Woven ± 2% Knitted -4% +2%	
Dimensional Stability to Steaming		BS 4323 or DIN 53894		Woven ± 2% Knitted -4% +2%	
Appearance after Laundering/Drycleaning		IHTM		No noticeable changes aft 1&3 cycles	I 6
Pilling resistance - (ICI box method)		ISO 12945-1	Evaluation at 7.200 and 10.800 revs	≥ 4	I 7/I 11
Pilling resistance - (Martindale)		ISO 12945-2	Tex-tex Evaluation at 500, 1.000 and 2000 revs	≥ 4	I 10/I 9
Seam Strength		ISO 13935-2		≥ 150N	
Bursting Strength		ISO 13938		Fabric: ≥ 280 kPa Seam: ≥ 250 kPa	
Stretch & Recovery		EN ISO 20932-1		Stretch: ≥ 15%/Residual Extension: ≤ 5%	I 8
Accelerated Ageing (storage) test		IHTM	7 days @70°C - 90-95%RH	Slight changes	
pH of the aqueous extract		ISO 3071	KCl 0.1M	4.0÷7.5	

Notes	
I	CC = Colour change - ST = Staining
I 1	No tolerance for single fiber
I 2	If there are trims and/or different colours Iithin the garment: ST ≥ 4-5
I 3	Staining in the solvent
I 4	Pigment print: Dry ≥ 3-4 - Wet ≥ 3
I 5	Tumble dry: normal temperature - exhaust temperature max 80°C
I 6	After 3 washing cycles at 40°C. After 1 dry cleaning cycle when it's the only maintenance permitted in care label
I 7	After 1 washing cycles at 40°C. After 1 dry cleaning cycle when it's the only maintenance permitted in care label
I 8	For fabrics containing elastane only
I 9	After 1 washing cycles at 40°C. After 1 dry cleaning cycle when it's the only maintenance permitted in care label
I 10	For woven fabrics only
I 11	After 1 hand wash cycle for wool, wool blend, kashmir, kashmir blend or precious fibres

Pigiamera, Intimo, Lingerie - Pyjamas, Underwear, Lingerie					L
Requirement	Description	Conformity Reference / Test Method	Technical details	Requirements	Notes
Fiber Composition		Reg. EU 1007/2011 - GB/T 2910 - BS 4407 AATCC 20 - ISO 1833 - ASTM D 276 - FZ/T 01057-1/7		± 3%	L 1
Mass per unit area		ISO 3801	Method 5	± 5%	
Colour Fastness to Washing		ISO 105 C06	A2S at 40°C	CC ≥ 4 ST ≥ 3-4	L/L 2
Colour Fastness to Dry Cleaning		ISO 105 D01		CC ≥ 4 ST ≥ 4	L/L 3
Colour Fastness to Acid Perspiration		ISO 105 E04		CC ≥ 4 ST ≥ 3-4	L/L 2
Colour Fastness to Alkaline Perspiration		ISO 105 E04		CC ≥ 4 ST ≥ 3-4	L/L 2
Colour Fastness to Rubbing		ISO 105 X12	Dry / Wet	Dry ≥ 4 Wet ≥ 3-4	L 4
Colour Fastness to Light		ISO 105 B02		CC ≥ 3	L
Colour Migration on PVC		ISO 105-X10		CC ≥ 4 ST ≥ 4	
Colour Fastness to Water		ISO 105 E01		CC ≥ 4 ST ≥ 3-4	L/L 2
Colour Fastness to Chlorine Bleach		ISO 105 N01	Sodium hypochloride	CC ≥ 4	L
Dimensional Stability to Washing		ISO 6330 - 5077 - 3759	4N at 40°C - Tumble dry	Woven ± 2% Knitted -4% +2%	L 5
Dimensional Stability to Dry Cleaning		Commercial cycle		Woven ± 2% Knitted -4% +2%	
Dimensional Stability to Steaming		BS 4323 or DIN 53894		Woven ± 2% Knitted -4% +2%	
Appearance after Laundering/Drycleaning		IHTM		No noticeable changes aft 1&3 cycles	L 6
Movement after washing		AATCC 179	Option 1	≤ 3%	
Accelerated Ageing (storage) test		IHTM	7 days @70°C - 90-5%RH	Slight changes	
Colour shade		ISO 105 J03 - ISO 105 A02	ΔE - D65 and TL84	≤1,0 / ≥4	L 13
Pilling resistance - (ICI box method)		ISO 12945-1	Evaluation at 7.200 and 10.800 revs	≥ 4	L 7/L 8
Pilling resistance - (Martindale)		ISO 12945-2	Tex-tex Evaluation at 500, 1.000 and 2000 revs	≥ 4	L 9/L 8
Seam Strength		ISO 13935-2		≥ 120N	
Seam Slippage		ISO 13936-1	3,0 mm	≥ 80 N	L 9
Bursting Strength		ISO 13938		Fabric: ≥280 kPa Seam: ≥ 250 kPa	L 7
Tensile Strength (Grab Method)		ISO 13934-2		Fabric up to 200 g/m ² : ≥ 120 N Fabric over 200 g/m ² : ≥ 170 N	L 9
Tear Strength (Dinamometric Method)		ISO 13937-2	Trouser Method	Fabric up to 200 g/m ² : ≥ 10 N Fabric over 200 g/m ² : ≥ 15 N	L 9
Tear Strength (Elmendorf Method)		ISO 13937-1		Fabric up to 200 g/m ² : ≥ 10 N Fabric over 200 g/m ² : ≥ 15 N	L 9
Stretch & Recovery		EN ISO 20932-1		Stretch: ≥ 15%/Residual Extension: ≤ 5%	L 10
Abrasion resistance		ISO 12947-1 and -2	9 kPa 2 broken yarns	10.000 revs CC ≥ 3-4 at 3.000 revs	L/L 9
Electrostatic Properties		EN 1149 -1 & 3		≤2,5 x 10 ⁹ Ω t50 <4 or S>0,2	L 11
pH of the aqueous extract		ISO 3071	KCl 0.1M	4.0÷7.5	

Notes	
L	CC = Colour change - ST = Staining
L 1	No tolerance for single fiber
L 2	If there are trims and/or different colours within the garment: ST ≥ 4-5
L 3	Staining in the solvent
L 4	Pigment print: Dry ≥ 3-4 - Wet ≥ 3
L 5	Tumble dry: normal temperature - exhaust temperature max 80°C
L 6	After 3 washing cycles at 40°C. After 1 dry cleaning cycle when it's the only maintenance permitted in care label
L 7	For knitted fabrics only. After 1hand wash cycle for silk only
L 8	After 1 washing cycles at 40°C. After 1 dry cleaning cycle when it's the only maintenance permitted in care label
L 9	For woven fabrics only. After 1hand wash cycle for silk only
L 10	For fabrics containing elastane only
L 11	Textiles main material shall comply with one of the two requirements at least
L 13	PP sample vs Bulk or Shipment sample. ISO 105 J03 for Instrumental evaluation. ISO 105 A02 for visual evaluation

Neonato & Bambino fino a 36 Mesi - Babies & Childrens up to 36 Months					M
Requirement Description	Conformity Reference / Test Method	Technical details	Requirements		Notes
Fiber Composition	Reg. EU 1007/2011 - GB/T 2910 - BS 4407 AATCC 20 - ISO 1833 - ASTM D 276 - FZ/T 01057-1/7		± 3%		M 1
Mass per unit area	ISO 3801	Method 5	± 5%		
Colour Fastness to Washing	ISO 105 C06	A2S at 40°C	CC ≥ 4	ST ≥ 3-4	M/M 2
Colour Fastness to Dry Cleaning	ISO 105 D01		CC ≥ 4	ST ≥ 4	M/M 3
Colour Fastness to Acid Perspiration	ISO 105 E04		CC ≥ 4	ST ≥ 3-4	M/M 2
Colour Fastness to Alkaline Perspiration	ISO 105 E04		CC ≥ 4	ST ≥ 3-4	M/M 2
Colour Fastness to Rubbing	ISO 105 X12	Dry / Wet	Dry ≥ 4	Wet ≥ 3-4	M 4
Colour Fastness to Light	ISO 105 B02		CC ≥ 4		M
Colour Fastness to Water	ISO 105 E01		CC ≥ 4	ST ≥ 3-4	M/M 2
Colour Fastness to Sea Water	ISO 105 E02		CC ≥ 4	ST ≥ 3-4	M/M 2
Colour Fastness to Chlorine Bleach	ISO 105 N01	Sodium hypochloride	CC ≥ 4		M
Colour Fastness to Chlorinated Water	ISO 105 E03	See note M14 for details	CC ≥ 4		M / M14
Colour Migration on PVC	ISO 105-X10		CC ≥ 4	ST ≥ 4	
Colour fastness to Saliva	IHTM		CC ≥ 4	ST ≥ 4	M
Colour fastness to Urina	IHTM		CC ≥ 4	ST ≥ 3-4	M/M 2
Dimensional Stability to Washing	ISO 6330 - 5077 - 3759	4N at 40°C - Tumble dry	Woven ± 2%	Knitted -4% +2%	M 5
Dimensional Stability to Dry Cleaning	Commercial cycle		Woven ± 2%	Knitted -4% +2%	
Dimensional Stability to Steaming	BS 4323 or DIN 53894		Woven ± 2%	Knitted -4% +2%	
Appearance after Laundering/Drycleaning	IHTM		No noticeable changes aft 1&3 cycles		M 6
Movement after washing	AATCC 179	Option 1	≤ 3%		
Colour shade	ISO 105 J03 - ISO 105 A02	ΔE - D65 and TL84	≤1,0 / ≥4		M 13
Accelerated Ageing (storage) test	IHTM	7 days @70°C - 90-95%RH	Slight changes		
Pilling resistance - (ICI box method)	ISO 12945-1	Evaluation at 7.200 and 10.800 revs	≥ 4		M 7/M 8
Pilling resistance - (Martindale)	ISO 12945-2	Tex-tex Evaluation at 500, 1.000 and 2000 revs	≥ 4		M 9/M 8
Seam Strength	ISO 13935-2		Fabric up to 120 g/m ² : ≥ 100 N Fabric over 120 g/m ² : ≥ 150 N		
Seam Slippage	ISO 13936-1	3,0 mm	Fabric up to 120 g/m ² : ≥ 80 N Fabric over 120 g/m ² : ≥ 100 N		M 9
Bursting Strength	ISO 13938		Fabric: ≥280 kPa Seam: ≥ 250 kPa		M 7
Tensile Strength (Grab Method)	ISO 13934-2		Fabric up to 120 g/m ² : ≥ 120 N Fabric over 120 g/m ² : ≥ 170 N		M 9
Tear Strength (Dinamometric Method)	ISO 13937-2	Trouser Method	Fabric up to 120 g/m ² : ≥ 10 N Fabric over 120 g/m ² : ≥ 15 N		M 9
Tear Strength (Elmendorf Method)	ISO 13937-1		Fabric up to 120 g/m ² : ≥ 10 N Fabric over 120 g/m ² : ≥ 15 N		M 9
Stretch & Recovery	EN ISO 20932-1		Stretch: ≥ 15%/Residual Extension: ≤ 5%		M 10
Abrasion resistance	ISO 12947-1 and -2	9 kPa 2 broken yarns	10.000 revs CC ≥ 3-4 at 3.000 revs		M/M 9
Electrostatic Properties	EN 1149 -1 & 3		≤2,5 x 10 ⁹ Ω		M 11
pH of the acqueous extract	ISO 3071	KCl 0.1M	4.0÷7.5		

Notes	
M	CC = Colour change - ST = Staining
M 1	No tolerance for single fiber
M 2	If there are trims and/or different colours within the garment: ST ≥ 4-5
M 3	Staining in the solvent
M 4	Pigment print: Dry ≥ 3-4 - Wet ≥ 3
M 5	Tumble dry: normal temperature - exhaust temperature max 80°C
M 6	After 3 washing cycles at 40°C. After 1 dry cleaning cycle when it's the only maintenance permitted in care label
M 7	For knitted fabrics only
M 8	After 1 washing cycles at 40°C. After 1 dry cleaning cycle when it's the only maintenance permitted in care label
M 9	For woven fabrics only
M 10	For fabrics containing elastane only
M 11	Textiles main material shall comply with one of the two requirements at least
M 13	PP sample vs Bulk or Shipment sample. ISO 105 J03 for Instrumental evaluation. ISO 105 A02 for visual evaluation
M 14	Swimwear: 50 ppm. Accessories and Beachwear: 20 ppm

Calze, Collant - Socks, Tights J				
Requirement Description	Conformity Reference / Test Method	Technical details	Requirements	Notes
Fiber Composition	Reg. EU 1007/2011 - GB/T 2910 - BS 4407	Method 5	± 3%	J 1
Fiber Composition	AATCC 20 - ISO 1833 - ASTM D 276 - FZ/T 01057-1/7			
Mass per unit area	ISO 3801		± 5%	
Colour Fastness to Washing	ISO 105 C06	A2S at 40°C	CC ≥ 4 ST ≥ 3-4	J/J 2
Colour Fastness to Dry Cleaning	ISO 105 D01		CC ≥ 4 ST ≥ 4	J/J 3
Colour Fastness to Acid Perspiration	ISO 105 E04		CC ≥ 4 ST ≥ 3-4	J/J 2
Colour Fastness to Alkaline Perspiration	ISO 105 E04		CC ≥ 4 ST ≥ 3-4	J/J 2
Colour Fastness to Rubbing	ISO 105 X12	Dry / Wet	Dry ≥ 4 Wet ≥ 3-4	J 4
Colour Fastness to Light	ISO 105 B02		CC ≥ 4	
Colour Migration on PVC	ISO 105-X10		CC ≥ 4 ST ≥ 4	
Colour Fastness to Water	ISO 105 E01		CC ≥ 4 ST ≥ 3-4	J/J 2
Colour Fastness to Chlorine Bleach	ISO 105 N01	Sodium hypochloride	CC ≥ 4	
Dimensional Stability to Washing	ISO 6330	4N at 40°C - Tumble dry	-4% +2%	J 5
Dimensional Stability to Dry Cleaning	Commercial cycle		-4% +2%	
Dimensional Stability to Steaming	BS 4323 or DIN 53894		-4% +2%	
Appearance after Laundering/Drycleaning	IHTM		No noticeable changes aft 1&3 cycles	J 6
Movement after washing	AATCC 179	Option 1	>5%	
Pilling resistance - (ICI box method)	ISO 12945-1	Evaluation at 7.200 and 10.800 revs	≥ 3-4	J 7/J 9
Abrasion resistance	ISO 12947	9 kPa 2 broken yarns	15.000/CT a 3.000 max 3/4	
Bursting Strength	ISO 13938		490 kPa	
Stretch & Recovery	EN ISO 20932-1		Stretch: ≥ 15%/Residual Extension: ≤ 5%	J 8
Electrostatic Properties	EN 1149 -1 & 3		≤2,5 x 10 ⁹ Ω	J 10
Accelerated Ageing (storage) test	IHTM	7 days @70°C - 90-95%RH	Slight changes	
pH of the aqueous extract	ISO 3071	KCl 0.1M	4.0÷7.5	

Notes	
J	CC = Colour change - ST = Staining
J 1	No tolerance for single fiber
J 2	If there are trims and/or different colours within the sock: ST ≥ 4-5
J 3	Staining in the solvent
J 4	Pigment print: Dry ≥ 3-4 - Wet ≥ 3
J 5	Tumble dry: normal temperature - exhaust temperature max 80°C
J 6	After 3 washing cycles at 40°C. After 1 dry cleaning cycle when it's the only maintenance permitted in care label
J 7	After 1 washing cycles at 40°C. After 1 dry cleaning cycle when it's the only maintenance permitted in care label
J 8	For fabrics containing elastane only
J 9	After 1 hand wash cycle for wool, wool blend, kashmir, kashmir blend or precious fibres
J 10	Textiles main material shall comply with one of the two requirements at least

Accessori di Abbigliamento in Pelle: Cinture, Portafogli, Borse, Zainetti - Leather Apparel Accessories: Belts, Wallets, Bags, Back Pack					KL
Requirement Description	Conformity Reference / Test Method	Technical details	Requirements		Notes
Colour Fastness to Acid Perspiration	ISO 105 E04	pH 5,5	CC ≥4	ST ≥3-4	KL/KL 2
Colour Fastness to Alkaline Perspiration	ISO 105 E04	pH 8,0	CC ≥4	ST ≥3-4	KL/KL 2
Colour Fastness to Rubbing	EN ISO 11640	Wet / Dry @50 cycle	Dry ST ≥4	Wet ST ≥3-4	KL 2
Colour Fastness to Light	ISO 105 B02	Blue scale	≥4		K
Colour Fastness to Water	ISO 105 E01	Water G3	CC ≥4	ST ≥4	KL/KL 2
Colour Migration on PVC	ISO 105-X10		CC ≥ 4	ST ≥4	
Colour Fastness to Water Spotting	ISO 105 E06		CC ≥4		
Colour Migration	ISO X105-X10		CC ≥4	ST ≥4	
Handle attachment strenght	BS 5131		≥250 N		KL 3/KL 6
Tear Strength	EN ISO 3377-1	Single tear	≥25 N		
Abrasion resistance	EN ISO 11640	Wet / Dry @50cycle	Dry CC≥4	Wet CC≥3	
Flexing resistance	EN ISO 5402	Bally method	≥100.000 flex		
Finishing adesion resistance	EN ISO 11664	Method A	≥2N/mm		
Pull test	EN 71-1		≥90 N		KL 5
Corroton resistance	EN 22775	method 2	Slight		KL 4
Accelerated Ageing (storage) test	IHTM	7 days @70°C - 90-95%RH	Slight changes		
Color shade	ISO 105 J03 - ISO 105 A02	ΔE - D65 and TL84	≤1,0 / ≥4		
Odour Test	IHTM		negliable		
pH of the acqueous extract	ISO 4045	G3 Water	4,0 - 7,5		

Notes	
KL	CC = Colour change - ST = Staining
KL 1	If there are trims and/or different colours within the garment: ST ≥ 4-5
KL 2	Pigment print: Dry ≥ 3-4 - Wet ≥ 3
KL 3	Evening & Fashion style bags : ≥150N
KL 4	Applicable to metallic components only
KL 5	For decorative attachments: ≥70 N
KL 6	Not Applicable to Wallets

Accessori di Abbigliamento in Plastica e PU: Cinture, Portafogli, Borse, Zainetti - Plastic & PU Apparel Accessories: Belts, Wallets, Bags, Back Pack					KP
Requirement	Description	Conformity Reference / Test Method	Technical details	Requirements	Notes
Colour Fastness to Acid Perspiration		ISO 105 E04	pH 5,5	CC ≥4 ST ≥3-4	KP/KP 2
Colour Fastness to Alkaline Perspiration		ISO 105 E04	pH 8,0	CC ≥4 ST ≥3-4	KP/KP 2
Colour Fastness to Rubbing		EN ISO 11640	Wet / Dry @50 cycle	Dry ST ≥4 Wet ST ≥3-4	KP 2
Colour Fastness to Light		ISO 105 B02	Blue scale	≥4	KP
Colour Migration on PVC		ISO 105-X10		CC ≥ 4 ST ≥4	
Colour Fastness to Water		ISO 105 E01	Water G3	CC ≥4 ST ≥4	KP/KP 2
Handle attachment strenght		BS 5131		≥250 N	KP 3 / KP 6
Pull test		EN 71-1		≥90 N	KP 5
Corroton resistance		EN 22775	Method 2	Slight	KP 4
Accelerated Ageing (storage) test		IHTM	7 days @70°C - 90-95%RH	Slight changes	
Color shade		ISO 105 J03 - ISO 105 A02	ΔE - D65 and TL84	≤1,0 / ≥4	
Odour Test		IHTM		negliable	
pH of the acqueous extract		ISO 4045	G3 Water	4,0 - 7,5	

Notes	
KP	CC = Colour change - ST = Staining
KP 1	If there are trims and/or different colours within the garment: ST ≥ 4-5
KP 2	Pigment print: Dry ≥ 3-4 - Wet ≥ 3
KP 3	Evening & Fashion style bags : ≥150N
KP 4	Applicable to metallic components only
KP 5	For decorative attachments: ≥70 N
KP 6	Not applicable to Wallets

Accessori di Abbigliamento in Tessuto : Cinture, Portafogli, Borse, Zainetti - Textiles Apparel Accessories: Belts, Wallets, Bags, Back Pack					KT
Requirement Description	Conformity Reference / Test Method	Technical details	Requirements		Notes
Colour Fastness to Acid Perspiration	ISO 105 E04	pH 5,5	CC ≥ 4	ST ≥ 3-4	KT/KT 2
Colour Fastness to Alkaline Perspiration	ISO 105 E04	pH 8,0	CC ≥ 4	ST ≥ 3-4	KT/KT 2
Colour Fastness to Rubbing	ISO 105 X12	Wet / Dry	Dry ST ≥ 4	Wet ST ≥ 3-4	KT 2
Colour Fastness to Light	ISO 105 B02	Blue scale	≥ 4		KT
Colour Fastness to Water	ISO 105 E01	Water G3	CC ≥ 4	ST ≥ 4	KT/KT 2
Colour Fastness to Water Spotting	ISO 105 E06		CC ≥ 4		
Colour Migration on PVC	ISO 105 X-10		CC ≥ 4	ST ≥ 4	
Handle attachment strenght	BS 5131		≥ 250 N		KT 3/KT 6
Pilling resistance - (ICI box method)	ISO 12945-1	Evaluation at 7.200 and 10.800 revs	≥ 4		
Pilling resistance - (Martindale)	ISO 12945-2	Tex-tex Evaluation at 500, 1.000 and 2000 revs	≥ 4		
Abrasion resistance	ISO 12947-1 and -2	9 kPa 2 broken yarns	10.000 revs CC ≥ 3-4 at 3.000 revs		KT
Pull test	EN 71-1		≥ 90 N		KT 5
Corroton resistance	EN 22775	Method 2	Slight		KL 4
Accelerated Ageing (storage) test	IHTM	7 days @ 70°C - 90-95%RH	Slight changes		
Color shade	ISO 105 J03 - ISO 105 A02	ΔE - D65 and TL84	≤ 1,0 / ≥ 4		
Odour Test	IHTM		negliable		
pH of the aqueous extract	ISO 4045	G3 Water	4,0 - 7,5		

Notes	
KT	CC = Colour change - ST = Staining
KT 1	If there are trims and/or different colours within the garment: ST ≥ 4-5
KT 2	Pigment print: Dry ≥ 3-4 - Wet ≥ 3
KT 3	Evening & Fashion style bags : ≥ 150N
KT 4	Applicable to metallic components only
KT 5	For decorative attachments: ≥ 70 N
KT 6	Not Applicable to Wallets

Lenzuola & Federe - Bed Sheet & Pillow Cases					N
Requirement	Description	Conformity Reference / Test Method	Technical details	Requirements	Notes
Fiber Composition		Reg. EU 1007/2011 - GB/T 2910 - BS 4407 AATCC 20 - ISO 1833 - ASTM D 276 - FZ/T 01057-1/7		± 3%	N 1
Mass per unit area		ISO 3801	Method 5	± 5%	
Colour Fastness to Washing		ISO 105 C06	C2S at 60°C	CC ≥ 4 ST ≥ 3-4	N/N 2
Colour Fastness to Dry Cleaning		ISO 105 D01		CC ≥ 4 ST ≥ 4	N/N 3
Colour Fastness to Acid Perspiration		ISO 105 E04		CC ≥ 4 ST ≥ 3-4	N/N 2
Colour Fastness to Alkaline Perspiration		ISO 105 E04		CC ≥ 4 ST ≥ 3-4	N/N 2
Colour Fastness to Rubbing		ISO 105 X12	Dry / Wet	Dry ≥ 4 Wet ≥ 3-4	N 4
Colour Fastness to Light		ISO 105 B02		CC ≥ 5	N
Colour Migration on PVC		ISO 105-X10		CC ≥ 4 ST ≥ 4	
Colour Fastness to Water		ISO 105 E01		CC ≥ 4 ST ≥ 3-4	N/N 2
Colour Fastness to Chlorine Bleach		ISO 105 N01	Sodium hypochloride	CC ≥ 4	N
Dimensional Stability to Washing		ISO 6330 - 5077 - 3759	4N at 40°C - Tumble dry	Woven: ± 3% Knitted: -4% +2%	N 5
Dimensional Stability to Dry Cleaning		Commercial cycle		Woven: ± 3% Knitted: -4% +2%	
Dimensional Stability to Steaming		BS 4323 or DIN 53894		Woven: ± 3% Knitted: -4% +2%	
Appearance after Laundering/Drycleaning		IHTM		No noticeable changes aft 183 cycles	N 6
Movement after washing		AATCC 179	Option 1	≤ 3%	
Colour shade		ISO 105 J03 - ISO 105 A02	ΔE - D65 and TL84	≤1,0 / ≥4	N 13
Accelerated Ageing (storage) test		IHTM	7 days @70°C - 90-95%RH	Slight changes	
Pilling resistance - (ICI box method)		ISO 12945-1	Evaluation at 7.200 and 10.800 revs	≥ 4	N 7/N 8
Pilling resistance - (Martindale)		ISO 12945-2	Tex-tex Evaluation at 500, 1.000 and 2000 revs	≥ 4	N 9/N 8
Seam Strength		ISO 13935-2		≥ 120N	
Seam Slippage		ISO 13936-1	6,0 mm	≥ 80 N	N 9
Bursting Strength		ISO 13938		Fabric: ≥280 kPa Seam: ≥ 250 kPa	N 7
Tensile Strength (Grab Method)		ISO 13934-2		Fabric up to 200 g/m ² : ≥ 120 N Fabric over 200 g/m ² : ≥ 170 N	N 9
Tear Strength (Dinamometric Method)		ISO 13937-2	Trouser Method	Fabric up to 200 g/m ² : ≥ 10 N Fabric over 200 g/m ² : ≥ 15 N	N 9
Tear Strength (Elmendorf Method)		ISO 13937-1		Fabric up to 200 g/m ² : ≥ 10 N Fabric over 200 g/m ² : ≥ 15 N	N 9
Abrasion resistance		ISO 12947-1 and -2	9 kPa 2 broken yarns	10.000 revs CC ≥ 3-4 at 3.000 revs	N/N 9
Electrostatic Properties		EN 1149 -1 & 3		≤2,5 x 10 ⁹ Ω	N 10
pH of the aqueous extract		ISO 3071	KCl 0.1M	4.0÷7.5	

Notes	
N	CC = Colour change - ST = Staining
N 1	No tolerance for single fiber
N 2	If there are trims and/or different colours within the garment: ST ≥ 4-5
N 3	Staining in the solvent
N 4	Pigment print: Dry ≥ 3-4 - Wet ≥ 3
N 5	Tumble dry: normal temperature - exhaust temperature max 80°C
N 6	After 3 washing cycles at 60°C. After 1 dry cleaning cycle when it's the only maintenance permitted in care label
N 7	For knitted fabrics only
N 8	After 1 washing cycles at 60°C. After 1 dry cleaning cycle when it's the only maintenance permitted in care label
N 9	For woven fabrics only
N 10	Textiles main material shall comply with one requirements at least
N 13	PP sample vs Bulk or Shipment sample. ISO 105 J03 for Instrumental evaluation. ISO 105 A02 for visual evaluation

Strofinacci da cucina - Dish Towels					O
Requirement	Description	Conformity Reference / Test Method	Technical details	Requirements	Notes
Fiber Composition		Reg. EU 1007/2011 - GB/T 2910 - BS 4407 AATCC 20 - ISO 1833 - ASTM D 276 - FZ/T 01057-1/7		± 3%	O 1
Mass per unit area		ISO 3801	Method 5	± 5%	
Colour Fastness to Washing		ISO 105 C06	C2S at 60°C	CC ≥ 4 ST ≥ 3-4	O/O 2
Colour Fastness to Dry Cleaning		ISO 105 D01		CC ≥ 4 ST ≥ 4	O/O 3
Colour Fastness to Acid Perspiration		ISO 105 E04		CC ≥ 4 ST ≥ 3-4	O/O 2
Colour Fastness to Alkaline Perspiration		ISO 105 E04		CC ≥ 4 ST ≥ 3-4	O/O 2
Colour Fastness to Rubbing		ISO 105 X12	Dry / Wet	Dry ≥ 4 Wet ≥ 3-4	O 4
Colour Fastness to Light		ISO 105 B02		CC ≥ 5	O
Colour Migration on PVC		ISO 105-X10		CC ≥ 4 ST ≥ 4	
Colour Fastness to Water		ISO 105 E01		CC ≥ 4 ST ≥ 3-4	O/O 2
Colour Fastness to Chlorine Bleach		ISO 105 N01	Sodium hypochloride	CC ≥ 4	O
Dimensional Stability to Washing		ISO 6330 - 5077 - 3759	6N @60±3°C-Tumble dry	± 7%	O 5/O 6
Dimensional Stability to Steaming		BS 4323 or DIN 53894		± 5%	
Appearance after Laundering/Drycleaning		IHTM		No noticeable changes aft 1&3 cycles	O 7
Movement after washing		AATCC 179	Option 1	≤ 5%	
Pilling resistance - (Martindale)		ISO 12945-2	Tex-tex Evaluation at 500, 1.000 and 2000 revs	≥ 4	O 8
Tensile Strength (Grab Method)		ISO 13934-2		Fabric up to 200 g/m²: ≥ 120 N Fabric over 200 g/m²: ≥ 170 N	
Tear Strength (Dinamometric Method)		ISO 13937-2	Trouser Method	Fabric up to 200 g/m²: ≥ 10 N Fabric over 200 g/m²: ≥ 15 N	
Tear Strength (Elmendorf Method)		ISO 13937-1		Fabric up to 200 g/m²: ≥ 10 N Fabric over 200 g/m²: ≥ 15 N	
Abrasion resistance		ISO 12947-1 and -2	9 kPa 2 broken yarns	10.000 revs CC ≥ 3-4 at 3.000 revs	O
Accelerated Ageing (storage) test		IHTM	7 days @70°C - 90-95%RH	Slight changes	
Absorbency		ASTM D 4772	After 1 washing cycle	≥40%	O8
pH of the aqueous extract		ISO 3071	KCl 0.1M	4.0÷7.5	

Notes	
O	CC = Colour change - ST = Staining
O 1	No tolerance for single fiber
O 2	If there are trims and/or different colours within the garment: ST ≥ 4-5
O 3	Staining in the solvent
O 4	Pigment print: Dry ≥ 3-4 - Wet ≥ 3
O 5	Tumble dry: normal temperature - exhaust temperature max 80°C
O 6	Waffel fabrics: ± 9%
O 7	After 3 washing cycles at 60°C.
O 8	After 1 washing cycles at 60°C.

Tovaglie - Tablecloths				P
Requirement Description	Conformity Reference / Test Method	Technical details	Requirements	Notes
Fiber Composition	Reg. EU 1007/2011 - GB/T 2910 - BS 4407		± 3%	P 1
Mass per unit area	AATCC 20 - ISO 1833 - ASTM D 276 - FZ/T 01057-1/7	Method 5	± 5%	
	ISO 3801			
Colour Fastness to Washing	ISO 105 C06	C2S at 60°C	CC ≥ 4 ST ≥ 3-4	P/P 2
Colour Fastness to Dry Cleaning	ISO 105 D01		CC ≥ 4 ST ≥ 4	P/P 3
Colour Fastness to Acid Perspiration	ISO 105 E04		CC ≥ 4 ST ≥ 3-4	P/P 2
Colour Fastness to Alkaline Perspiration	ISO 105 E04		CC ≥ 4 ST ≥ 3-4	P/P 2
Colour Fastness to Rubbing	ISO 105 X12	Dry / Wet	Dry ≥ 4 Wet ≥ 3-4	P 4
Colour Fastness to Light	ISO 105 B02		CC ≥ 5	P
Colour Migration on PVC	ISO 105-X10		CC ≥ 4 ST ≥ 4	
Colour Fastness to Water	ISO 105 E01		CC ≥ 4 ST ≥ 3-4	P/P 2
Colour Fastness to Chlorine Bleach	ISO 105 N01	Sodium hypochloride	CC ≥ 4	P
Dimensional Stability to Washing	ISO 6330 - 5077 - 3759	6N @60±3°C-Tumble dry	Woven: ± 4% Knitted: -5% +1%	P 5
Dimensional Stability to Dry Cleaning	Commercial cycle		Woven: ± 4% Knitted: -5% +1%	
Dimensional Stability to Steaming	BS 4323 or DIN 53894		Woven: ± 4% Knitted: -5% +1%	
Appearance after Laundering/Drycleaning	IHTM		No noticeable changes aft 183 cycles	P 6
Movement after washing	AATCC 179	Option 1	≤ 3%	
Colour shade	ISO 105 J03 - ISO 105 A02	ΔE - D65 and TL84	≤1,0 / ≥4	P 10
Accelerated Ageing (storage) test	IHTM	7 days @70°C - 90-95%RH	Slight changes	
Pilling resistance - (ICI box method)	ISO 12945-1	Evaluation at 7.200 and 10.800 revs	≥ 4	P 7/P 8
Pilling resistance - (Martindale)	ISO 12945-2	Tex-tex Evaluation at 500, 1.000 and 2000 revs	≥ 4	P 9/P 8
Seam Strength	ISO 13935-2		≥ 120N	
Seam Slippage	ISO 13936-1	6,0 mm	≥ 80 N	P 9
Bursting Strength	ISO 13938		Fabric: ≥280 kPa Seam: ≥ 250 kPa	P 7
Tensile Strength (Grab Method)	ISO 13934-2		Fabric up to 200 g/m ² : ≥ 120 N Fabric over 200 g/m ² : ≥ 170 N	P 9
Tear Strength (Dinametric Method)	ISO 13937-2	Trouser Method	Fabric up to 200 g/m ² : ≥ 10 N Fabric over 200 g/m ² : ≥ 15 N	P 9
Tear Strength (Elmendorf Method)	ISO 13937-1		Fabric up to 200 g/m ² : ≥ 10 N Fabric over 200 g/m ² : ≥ 15 N	P 9
Abrasion resistance	ISO 12947-1 and -2	9 kPa 2 broken yarns	20.000 revs CC ≥ 3-4 at 3.000 revs	P/P 9
pH of the acqueous extract	ISO 3071	KCl 0.1M	4.0÷7.5	

Notes	
P	CC = Colour change - ST = Staining
P 1	No tolerance for single fiber
P 2	If there are trims and/or different colours within the garment: ST ≥ 4-5
P 3	Staining in the solvent
P 4	Pigment print: Dry ≥ 3-4 - Wet ≥ 3
P 5	For woven fabrics only
P 6	After 3 washing cycles at 60°C. After 1 dry cleaning cycle when it's the only maintenance permitted in care label
P 7	For knitted fabrics only
P 8	After 1 washing cycles at 60°C. After 1 dry cleaning cycle when it's the only maintenance permitted in care label
P 9	For woven fabrics only
P 10	PP sample vs Bulk or Shipment sample. ISO 105 J03 for Instrumental evaluation. ISO 105 A02 for visual evaluation

Accappatoi, Asciugamani, Teli mare - Bath Robes, Towels, Sea Towels					T
Requirement	Description	Conformity Reference / Test Method	Technical details	Requirements	Notes
Fiber Composition		Reg. EU 1007/2011 - GB/T 2910 - BS 4407		± 3%	T 1
Mass per unit area		AATCC 20 - ISO 1833 - ASTM D 276 - FZ/T 01057-1/7			
		ISO 3801	Method 5	± 5%	
Colour Fastness to Washing		ISO 105 C06	C2S at 60°C	CC ≥ 4-5 ST ≥ 4	T/T 2
Colour Fastness to Acid Perspiration		ISO 105 E04		CC ≥ 4-5 ST ≥ 4	T/T 2
Colour Fastness to Alkaline Perspiration		ISO 105 E04		CC ≥ 4-5 ST ≥ 4	T/T 2
Colour Fastness to Rubbing		ISO 105 X12	Dry / Wet	Dry ≥ 4-5 Wet ≥ 4	T 4
Colour Fastness to Light		ISO 105 B02		CC ≥ 5	T
Colour Migration on PVC		ISO 105-X10		CC ≥ 4 ST ≥ 4	
Colour Fastness to Water		ISO 105 E01		CC ≥ 4-5 ST ≥ 4	T/T 2
Colour Fastness to Sea Water		ISO 105 E02		CC ≥ 4 ST ≥ 3-4	T/T 2
Colour Fastness to Chlorine Bleach		ISO 105 N01	Sodium hypochloride	CC ≥ 4-5	T
Colour Fastness to Chlorinated Water		ISO 105 E03	20 ppm	CC ≥ 4	T
Dimensional Stability to Washing		ISO 6330 - 5077 - 3759	1 cycle - 6N at 60°C	± 8%	T 5/T 6
Dimensional Stability to Steaming		BS 4323 or DIN 53894		± 8%	T 6
Appearance after Laundering/Drycleaning		IHTM		No noticeable changes aft 1&3 cycles	T 7
Movement after washing		AATCC 179	Option 1	≤ 3%	
Colour shade		ISO 105 J03 - ISO 105 A02	ΔE - D65 and TL84	≤1,0 / ≥4	T 10
Pilling resistance - (ICI box method)		ISO 12945-1	Evaluation at 7.200 and 10.800 revs	≥ 4	T 8/T 9
Pilling resistance - (Martindale)		ISO 12945-2	Tex-tex Evaluation at 500, 1.000 and 2000 revs	≥ 4	T 10/T 9
Seam Strength		ISO 13935-2	6,0 mm	≥ 120N	
Seam Slippage		ISO 13936-1		≥ 80 N	T 10
Bursting Strength		ISO 13938		Fabric: ≥280 kPa Seam: ≥ 250 kPa	T 8
Tensile Strength (Grab Method)		ISO 13934-2		Fabric up to 200 g/m ² : ≥ 120 N Fabric over 200 g/m ² : ≥ 170 N	T 10
Tear Strength (Dinamometric Method)		ISO 13937-2	Trouser Method	Fabric up to 200 g/m ² : ≥ 10 N Fabric over 200 g/m ² : ≥ 15 N	T 10
Tear Strength (Elmendorf Method)		ISO 13937-1		Fabric up to 200 g/m ² : ≥ 10 N Fabric over 200 g/m ² : ≥ 15 N	T 10
Abrasion resistance		ISO 12947-1 and -2	9 kPa 2 broken yarns	20.000 revs CC ≥ 3-4 at 3.000 revs	T/T 10
Accelerated Ageing (storage) test		IHTM	7 days @70°C - 90-95%RH	Slight changes	
Absorbency		ASTM D 4772	After 1 washing cycle	≥40%	T9
pH of the aqueous extract		ISO 3071	KCl 0.1M	4.0±7.5	

Notes	
T	CC = Colour change - ST = Staining
T 1	No tolerance for single fiber
T 2	If there are trims and/or different colours within the garment: ST ≥ 4-5
T 3	Staining in the solvent
T 4	Pigment print: Dry ≥ 3-4 - Wet ≥ 3
T 5	Tumble dry: normal temperature - exhaust temperature max 80°C
T 6	Requirement only for Terry fabrics, Waffel fabrics: ± 9%, Woven ± 4%, Non-Woven ± 2%
T 7	After 3 washing cycles at 60°C.
T 8	For knitted fabrics only
T 9	After 1 washing cycles at 60°C.
T 10	For woven fabrics only

Coperte, Trapunte, Sacchi copri piumino - Blankets, Bed Quilts, Duvet cover					U
Requirement Description	Conformity Reference / Test Method	Technical details	Requirements		Notes
Fiber Composition	Reg. EU 1007/2011 - GB/T 2910 - BS 4407 AATCC 20 - ISO 1833 - ASTM D 276 - FZ/T 01057-1/7		± 3%		U 1
Mass per unit area	ISO 3801	Method 5	± 5%		
Colour Fastness to Washing	ISO 105 C06	A2S at 40°C	CC ≥ 4	ST ≥ 3-4	U/U 2
Colour Fastness to Dry Cleaning	ISO 105 D01		CC ≥ 4	ST ≥ 4	U/U 3
Colour Fastness to Acid Perspiration	ISO 105 E04		CC ≥ 4	ST ≥ 3-4	U/U 2
Colour Fastness to Alkaline Perspiration	ISO 105 E04		CC ≥ 4	ST ≥ 3-4	U/U 2
Colour Fastness to Rubbing	ISO 105 X12	Dry / Wet	Dry ≥ 4	Wet ≥ 3-4	U 4
Colour Fastness to Light	ISO 105 B02		CC ≥ 5		U
Colour Migration on PVC	ISO 105-X10		CC ≥ 4	ST ≥ 4	
Colour Fastness to Water	ISO 105 E01		CC ≥ 4	ST ≥ 3-4	U/U 2
Colour Fastness to Chlorine Bleach	ISO 105 N01	Sodium hypochloride	CC ≥ 4		U
Dimensional Stability to Washing	ISO 6330 - 5077 - 3759	1 cycle - 4N at 40°C	Woven: ± 4%	Knitted: -5% +3%	U 5
Dimensional Stability to Dry Cleaning	Commercial cycle		Woven: ± 4%	Knitted: -5% +3%	
Dimensional Stability to Steaming	BS 4323 or DIN 53894		Woven: ± 4%	Knitted: -5% +3%	
Appearance after Laundering/Drycleaning	IHTM		No noticeable changes aft 1&3 cycles		U 6
Movement after washing	AATCC 179	Option 1	≤ 3%		
Colour shade	ISO 105 J03 - ISO 105 A02	ΔE - D65 and TL84	≤1,0 / ≥4		U 10
Pilling resistance - (Martindale)	ISO 12945-2	Tex-tex Evaluation at 500, 1.000 and 2000 revs	≥ 4		U 9/U 8
Seam Strength	ISO 13935-2		≥ 120N		
Seam Slippage	ISO 13936-1	6,0 mm	≥ 80 N		U 9
Bursting Strength	ISO 13938		Fabric: ≥280 kPa Seam: ≥ 250 kPa		U 7
Tensile Strength (Grab Method)	ISO 13934-2		Fabric up to 200 g/m ² : ≥ 120 N Fabric over 200 g/m ² : ≥ 170 N		U 9
Tear Strength (Dinamometric Method)	ISO 13937-2	Trouser Method	Fabric up to 200 g/m ² : ≥ 10 N Fabric over 200 g/m ² : ≥ 15 N		U 9
Tear Strength (Elmendorf Method)	ISO 13937-1		Fabric up to 200 g/m ² : ≥ 10 N Fabric over 200 g/m ² : ≥ 15 N		U 9
Abrasion resistance	ISO 12947-1 and -2	9 kPa 2 broken yarns	20.000 revs CC ≥ 3-4 at 3.000 revs		U/U 9
Accelerated Ageing (storage) test	IHTM	7 days @70°C - 90-95%RH	Slight changes		
Electrostatic Properties	EN 1149 -1 & 3		≤2,5 x 10 ⁹ Ω		U 10
pH of the aqueous extract	ISO 3071	KCl 0.1M	4.0÷7.5		

Notes	
U	CC = Colour change - ST = Staining
U 1	No tolerance for single fiber
U 2	If there are trims and/or different colours within the garment: ST ≥ 4-5
U 3	Staining in the solvent
U 4	Pigment print: Dry ≥ 3-4 - Wet ≥ 3
U 5	Tumble dry: normal temperature - exhaust temperature max 80°C
U 6	After 3 washing cycles at 40°C. After 1 dry cleaning cycle when it's the only maintenance permitted in care label
U 7	For knitted fabrics only
U 8	After 1 washing cycles at 40°C. After 1 dry cleaning cycle when it's the only maintenance permitted in care label
U 9	For woven fabrics only
U 10	Textiles main material shall comply with one of the two requirements at least

Cuscini e Tessuti d'arredamento, Tende - <i>Decoration Pillow, Tablewear, Curtains</i> V				
Requirement	Description	Conformity Reference / Test Method	Technical details	Requirements
Fiber Composition		Reg. EU 1007/2011 - GB/T 2910 - BS 4407 AATCC 20 - ISO 1833 - ASTM D 276 - FZ/T 01057-1/7		± 3%
Mass per unit area		ISO 3801	Method 5	± 5%
Colour Fastness to Washing		ISO 105 C06	A2S at 40°C	CC ≥ 4 ST ≥ 3-4
Colour Fastness to Dry Cleaning		ISO 105 D01		CC ≥ 4 ST ≥ 4
Colour Fastness to Acid Perspiration		ISO 105 E04		CC ≥ 4 ST ≥ 3-4
Colour Fastness to Alkaline Perspiration		ISO 105 E04		CC ≥ 4 ST ≥ 3-4
Colour Fastness to Rubbing		ISO 105 X12	Dry / Wet	Dry ≥ 4 Wet ≥ 3-4
Colour Fastness to Light		ISO 105 B02		CC ≥ 5
Colour Migration on PVC		ISO 105-X10		CC ≥ 4 ST ≥ 4
Colour Fastness to Water		ISO 105 E01		CC ≥ 4 ST ≥ 3-4
Colour Fastness to Chlorine Bleach		ISO 105 N01	Sodium hypochloride	CC ≥ 4
Dimensional Stability to Washing		ISO 6330 - 5077 - 3759	1 cycle - 4N at 40°C	Woven: ± 3% Knitted: -4% +2%
Dimensional Stability to Dry Cleaning		Commercial cycle		Woven: ± 3% Knitted: -4% +2%
Dimensional Stability to Steaming		BS 4323 or DIN 53894		Woven: ± 3% Knitted: -4% +2%
Appearance after Laundering/Drycleaning		IHTM		No noticeable changes aft 183 cycles
Movement after washing		AATCC 179	Option 1	≤ 3%
Colour shade		ISO 105 J03 - ISO 105 A02	ΔE - D65 and TL84	≤ 1,0 / ≥ 4
Pilling resistance - (ICI box method)		ISO 12945-1	Evaluation at 7.200 and 10.800 revs	≥ 4
Pilling resistance - (Martindale)		ISO 12945-2	Tex-tex Evaluation at 500, 1.000 and 2000 revs	≥ 4
Seam Strength		ISO 13935-2	6,0 mm	≥ 120N
Seam Slippage		ISO 13936-1		≥ 80 N
Bursting Strength		ISO 13938		Fabric: ≥ 280 kPa Seam: ≥ 250 kPa
Tensile Strength (Grab Method)		ISO 13934-2		Fabric up to 200 g/m ² : ≥ 120 N Fabric over 200 g/m ² : ≥ 170 N
Tear Strength (Dinamometric Method)		ISO 13937-2	Trouser Method	Fabric up to 200 g/m ² : ≥ 10 N Fabric over 200 g/m ² : ≥ 15 N
Tear Strength (Elmendorf Method)		ISO 13937-1		Fabric up to 200 g/m ² : ≥ 10 N Fabric over 200 g/m ² : ≥ 15 N
Abrasion resistance		ISO 12947-1 and -2	9 kPa 2 broken yarns	10.000 revs CC ≥ 3-4 at 3.000 revs
Accelerated Ageing (storage) test		IHTM	7 days @70°C - 90-95%RH	Slight changes
pH of the aqueous extract		ISO 3071	KCl 0.1M	4.0÷7.5

Notes	
V	CC = Colour change - ST = Staining
V 1	No tolerance for single fiber
V 2	If there are trims and/or different colours within the garment: ST ≥ 4-5
V 3	Staining in the solvent
V 4	Pigment print: Dry ≥ 3-4 - Wet ≥ 3
V 5	Tumble dry: normal temperature - exhaust temperature max 80°C
V 6	After 3 washing cycles at 40°C. After 1 dry cleaning cycle when it's the only maintenance permitted in care label
V 7	For knitted fabrics only
V 8	After 1 washing cycles at 40°C. After 1 dry cleaning cycle when it's the only maintenance permitted in care label
V 9	For woven fabrics only
V 13	PP sample vs Bulk or Shipment sample. ISO 105 J03 for Instrumental evaluation. ISO 105 A02 for visual evaluation

Tappeti bagno - Bath Mats					Z
Requirement	Description	Conformity Reference / Test Method	Technical details	Requirements	Notes
Fiber Composition		Reg. EU 1007/2011 - GB/T 2910 - BS 4407		± 3%	Z 1
Mass per unit area		AATCC 20 - ISO 1833 - ASTM D 276 - FZ/T 01057-1/7			
		ISO 3801	Method 5	± 5%	
Colour Fastness to Washing		ISO 105 C06	A2S at 40°C	CC ≥ 4 ST ≥ 3-4	Z/Z 2
Colour Fastness to Acid Perspiration		ISO 105 E04		CC ≥ 4 ST ≥ 3-4	Z/Z 2
Colour Fastness to Alkaline Perspiration		ISO 105 E04		CC ≥ 4 ST ≥ 3-4	Z/Z 2
Colour Fastness to Rubbing		ISO 105 X12	Dry / Wet	Dry ≥ 4 Wet ≥ 3-4	Z 4
Colour Fastness to Light		ISO 105 B02		CC ≥ 5	Z
Colour Migration on PVC		ISO 105-X10		CC ≥ 4 ST ≥ 4	
Colour Fastness to Water		ISO 105 E01		CC ≥ 4 ST ≥ 3-4	Z/Z 2
Colour Fastness to Chlorine Bleach		ISO 105 N01	Sodium hypochloride	CC ≥ 4	Z
Dimensional Stability to Washing		ISO 6330 - 5077 - 3759	1 cycle - 4N at 40°C	Woven: ± 4% Knitted: -5% +2%	Z 5
Dimensional Stability to Steaming		BS 4323 or DIN 53894		Woven: ± 4% Knitted: -5% +2%	
Appearance after Laundering/Drycleaning		IHTM		No noticeable changes aft 1&3 cycles	Z 6
Movement after washing		AATCC 179	Option 1	≤ 3%	
Pilling resistance - (ICI box method)		ISO 12945-1	Evaluation at 7.200 and 10.800 revs	≥ 4	Z 7/2 8
Pilling resistance - (Martindale)		ISO 12945-2	Tex-tex Evaluation at 500, 1.000 and 2000 revs	≥ 4	Z 9/2 8
Bursting Strength		ISO 13938		Fabric: ≥ 280 kPa Seam: ≥ 250 kPa	Z 7
Tensile Strength (Grab Method)		ISO 13934-2		Fabric up to 200 g/m ² : ≥ 120 N Fabric over 200 g/m ² : ≥ 170 N	Z 9
Tear Strength (Dinamometric Method)		ISO 13937-2	Trouser Method	Fabric up to 200 g/m ² : ≥ 10 N Fabric over 200 g/m ² : ≥ 15 N	Z 9
Tear Strength (Elmendorf Method)		ISO 13937-1		Fabric up to 200 g/m ² : ≥ 10 N Fabric over 200 g/m ² : ≥ 15 N	Z 9
Abrasion resistance		ISO 12947-1 and -2	9 kPa 2 broken yarns	10.000 revs CC ≥ 3-4 at 3.000 revs	Z/Z 9
Accelerated Ageing (storage) test		IHTM	7 days @70°C - 90-95%RH	Slight changes	
pH of the aqueous extract		ISO 3071	KCl 0.1M	4.0÷7.5	

Notes	
Z	CC = Colour change - ST = Staining
Z 1	No tolerance for single fiber
Z 2	If there are trims and/or different colours within the garment: ST ≥ 4-5
Z 3	Staining in the solvent
Z 4	Pigment print: Dry ≥ 3-4 - Wet ≥ 3
Z 5	Tumble dry: normal temperature - exhaust temperature max 80°C
Z 6	After 3 washing cycles at 40°C.
Z 7	For knitted fabrics only
Z 8	After 1 washing cycles at 40°C.
Z 9	For woven fabrics only

Strato Esterno (Giubbotti e Pantaloni tecnici ecc.) - Outer Layer (Tecnical Jackets & Trousers, etc.)					A-SKI
Requirement	Description	Conformity Reference / Test Method	Technical details	Requirements	Notes
Fiber Composition		Reg. EU 1007/2011 - GB/T 2910 - BS 4407 AATCC 20 - ISO 1833 - ASTM D 276 - FZ/T 01057-1/7		± 3%	A 1
Mass per unit area		ISO 3801	Method 5	± 5%	
Colour Fastness to Washing		ISO 105 C06	A2S at 40°C	CC ≥ 4 ST ≥3-4	A/A 2
Colour Fastness to Dry Cleaning		ISO 105 D01		CC ≥ 4 ST ≥4	A/A 3
Colour Fastness to Acid Perspiration		ISO 105 E04		CC ≥ 4 ST ≥3-4	A/A 2
Colour Fastness to Alkaline Perspiration		ISO 105 E04		CC ≥ 4 ST ≥3-4	A/A 2
Colour Fastness to Rubbing		ISO 105 X12	Dry / Wet	Dry ≥ 4 Wet ≥3-4	A 4
Colour Fastness to Light		ISO 105 B02		CC ≥ 4	A
Colour Migration on PVC		ISO 105-X10		CC ≥ 4 ST ≥4	
Colour Fastness to Water		ISO 105 E01		CC ≥ 4 ST ≥3-4	A/A 2
Colour Fastness to Water Spotting		ISO 105 E07	Evaluation Wet/Dry	CC ≥ 4	A/A 5
Dimensional Stability to Washing		ISO 6330 - 5077 - 3759	1 cycle - 4N at 40°C	Woven ± 2% Knitted -4% +2%	
Dimensional Stability to Dry Cleaning		Commercial cycle		Woven ± 2% Knitted -4% +2%	
Dimensional Stability to Steaming		BS 4323 or DIN 53894		Woven ± 2% Knitted -4% +2%	
Appearance after Laundering/Drycleaning		3 washing cycle + Standard Tumble drying		No noticeable changes aft 1 & 3 cycles	A 7
Movement after washing		AATCC 179	Option 1	≤ 3%	
Pilling resistance - (ICI box method)		ISO 12945-1	Evaluation at 7.200 and 10.800 revs	≥ 4	A 8/A 9
Pilling resistance - (Martindale)		ISO 12945-2	Tex-tex Evaluation at 500, 1.000 and 2000 revs	≥ 4	A 10/A 9
Seam Strength		ISO 13935-2		≥ 150N	
Seam Slippage		ISO 13936-1	6,0 mm	≥ 100 N	A 10
Bursting Strength		ISO 13938		Fabric: ≥280 kPa Seam: ≥ 250 kPa	A 8
Tensile Strength (Grab Method)		ISO 13934-2		Fabric up to 200 g/m²: ≥ 120 N Fabric over 200 g/m²: ≥ 170 N	A 10
Tear Strength (Dinamometric Method)		ISO 13937-2	Trouser Method	Fabric up to 200 g/m²: ≥ 15 N Fabric over 200 g/m²: ≥ 20 N	A 10
Tear Strength (Elmendorf Method)		ISO 13937-1		Fabric up to 200 g/m²: ≥ 15 N Fabric over 200 g/m²: ≥ 20 N	A 10
Abrasion resistance		ISO 12947-1 and -2	9 kPa-Wool abradent 2 broken yarns	30.000 revs CC ≥ 3-4 at 3.000 revs	A/A 10
Hydrostatic head (Water permeability)		ISO 811 or JIS L1092 method B	After 5 washing cycles	≥ 5000 mm With membrane ≥ 20000 mm	A9 / A11
Air permeability (Wind Proof)		ISO 9237	After 5 washing cycles	≤10 mm/s	A9/ A15
Thermal resistance		ASTM D 1518		Clo ≥1,1	
Water vapour permeability (Brethability)		ISO 11092		RET ≤ 6	
		ASTM E96	Method BW	≥ 4000 gr/m2/day	
			Method B	≥ 600 gr/m2/day	
		JIS L1099	Method B-1	≥ 15000 gr/m2/day	
		Method A-1	≥ 4000 gr/m2/day		
Delamination resistance		ISO 4637	New&After ageing	2,8kg	A16
Cut resistance		EN ISO 13997		Fabric: ≥10N Reinforcement: ≥15N	
Electrostatic Properties		EN 1149 -1 & 3		≤2,5 x 10 ⁹ Ω t50 <4 or S>0,2	A 14
Spray test		EN ISO 4920	After 5 washing cycle	≥ ISO 4	A 9
pH of the acqueous extract		ISO 3071	KCl 0.1M	4.0÷7.5	
Colour shade		ISO 105 J03 - ISO 105 A02	ΔE - D65 and TL84	≤1,0 / ≥4	A 13
Accelerated Ageing (storage) test		IHTM	7 days @70°C - 90-95%RH	Slight changes	
Oxygen Index Number		EN 1162		< 20	A 12
Down and feather sterilization		EN 1884		PASS	A 12
Oil and fat content		EN 1163		0.5÷2.0%	A 12
Turbidity		EN 1164		≥ 300 mm	A 12
pH		EN 1413		6.6÷8.0	A 12
Down proof properties - Rubbing test		EN 12132-1		≤ 10 elements	A 12

Notes	
A	CC = Colour change - ST = Staining
A 1	No tolerance for single fiber
A 2	If there are trims and/or different colours within the garment: ST ≥ 4-5
A 3	Staining in the solvent
A 4	Pigment print: Dry ≥ 3-4 - Wet ≥ 3
A 5	To be carried out before Spray test
A 6	Method A-1 with Calcium Chloride
A 7	Tumble dry: normal temperature - exhaust temperature max 80°C
A 8	For knitted fabrics only
A 9	After 5 washing cycles 4N@40°C.
A 10	For woven fabrics only
A 11	For water proof garments only - On fabric and seams with both results reported.
A 12	For feather and down filling garments only
A 13	PP sample vs Bulk or Shipment sample. ISO 105 J03 for Instrumental evaluation. ISO 105 A02 for visual evaluation .
A 14	Textiles main material shall comply with one of the two requirements at least
A 15	Requirements for fabrics with Menbrane or Coating (Windproof) . For wind resistance of fabrics ≤ 30mm /s
A 16	Ageing : ISO 10195 A2

Strato Intermedio (Maglieria,T-Shirts, Pile, Felpe, Pantaloni) -Intermediate layer (Knitwear, T-Shirts, Pile, Sweaters, Trousers)					G-SKI
Requirement	Description	Conformity Reference / Test Method	Technical details	Requirements	Notes
Fiber Composition		Reg. EU 1007/2011 - GB/T 2910 - BS 4407		± 3%	G 1
Mass per unit area		AATCC 20 - ISO 1833 - ASTM D 276 - FZ/T 01057-1/7		± 5%	
Colour Fastness to Washing		ISO 3801	Method 5		
Colour Fastness to Dry Cleaning		ISO 105 C06	A2S at 40°C	CC ≥ 4 ST ≥3-4	G/G 2
Colour Fastness to Acid Perspiration		ISO 105 D01		CC ≥ 4 ST ≥4	G/G 3
Colour Fastness to Alkaline Perspiration		ISO 105 E04		CC ≥ 4 ST ≥3-4	G/G 2
Colour Fastness to Rubbing		ISO 105 E04		CC ≥ 4 ST ≥3-4	G/G 2
Colour Fastness to Light		ISO 105 X12	Dry / Wet	Dry ≥ 4 Wet ≥3-4	G 4
Colour Migration on PVC		ISO 105 B02		CC ≥ 4	G
Colour Fastness to Water		ISO 105-X10		CC ≥ 4 ST ≥4	
Colour Fastness to Chlorine Bleach		ISO 105 E01		CC ≥ 4 ST ≥3-4	G/G 2
		ISO 105 N01	Sodium hypochloride	CC ≥ 4	G
Dimensional Stability to Washing		ISO 6330 - 5077 - 3759	1 cycle - 4N at 40°C	-4% +2%	G 6
Dimensional Stability to Dry Cleaning		Commercial cycle		-4% +2%	
Dimensional Stability to Steaming		BS 4323 or DIN 53894		-4% +2%	
Appearance after Laundering/Drycleaning		3 washing cycle + Tumble dry		No noticeable changes aft1 & 3 cycles	G 6
Movement after washing		AATCC 179	Option 1	≤ 3%	
Colour shade		ISO 105 J03 - ISO 105 A02	ΔE - D65 and TL84	≤1,0 / ≥4	G 13
Accelerated Ageing (storage) test		IHTM	7 days @70°C - 90-95%RH	Slight changes	
Pilling resistance - (ICI box method)		ISO 12945-1	Evaluation at 7.200 and 10.800 revs	≥ 4	G 7/G 9
Seam Strength		ISO 13935-2		≥ 150N	
Bursting Strength		ISO 13938		Fabric: ≥280 kPa Seam: ≥ 250 kPa	
Stretch & Recovery		EN ISO20932-1		Stretch: ≥ 15%/Residual Extension: ≤ 5%	G 8
Electrostatic Properties		EN 1149 -1 & 3		≤2,5 x 10³ Ω t50 <4 or S>0,2	G 10
Antibacterial activities		AATCC 100	After 5 washing Cycle	≥ 70%	
Water vapour permeability (Brethability)		ASTM E96 (BW) / ISO 11092	nil	≥4000 gr/m2/day / RET ≤ 6	
Thermal resistance		ASTM D1518		Clo ≥0,05	
Determination of deodorant property		ISO 17299	Isovaleric acid & 2-Nonenal	Odor reduction rate ≥ 80	
Vertical wicking		AATCC 197-2011e2(2018)e	Option B - 3 cycle washing 3N @30°Line Dry	2mins:70mm 10mins:100mm	
Drying time		AATCC 199	nil	≥50% after 30 mins	
pH of the aqueous extract		ISO 3071	KCl 0.1M	4.0÷7.5	
Notes					
G	CC = Colour change - ST = Staining				
G 1	No tolerance for single fiber				
G 2	If there are trims and/or different colours within the garment: ST ≥ 4-5				
G 3	Staining in the solvent				
G 4	Pigment print: Dry ≥ 3-4 - Wet ≥ 3				
G 5	nil				
G 6	Tumble dry: normal temperature - exhaust temperature max 80°C				
G 7	After 1 washing cycles at 40°C. After 1 dry cleaning cycle when it's the only maintenance permitted in care label				
G 8	For fabrics containing elastane only				
G 9	After 1 hand wash cycle for wool, wool blend, kashmir, kashmir blend or precious fibres				
G 10	Textiles main material shall comply with one of the two requirements at least				
G 11	UV protective clothing for which compliance is claimed shall permanently be marked with pittogram provided by the standard EN 13758-2				
G 13	PP sample vs Bulk or Shipment sample. ISO 105 J03 for Instrumental evaluation. ISO 105 A02 for visual evaluation				

Intimo "tecnico" - "Technical" Underwear L-SKI				
Requirement Description	Conformity Reference / Test Method	Technical details	Requirements	Notes
Fiber Composition	Reg. EU 1007/2011 - GB/T 2910 - BS 4407 AATCC 20 - ISO 1833 - ASTM D 276 - FZ/T 01057-1/7		± 3%	L 1
Mass per unit area	ISO 3801	Method 5	± 5%	
Colour Fastness to Washing	ISO 105 C06	A2S at 40°C	CC ≥ 4 ST ≥ 3-4	L/L 2
Colour Fastness to Dry Cleaning	ISO 105 D01		CC ≥ 4 ST ≥ 4	L/L 3
Colour Fastness to Acid Perspiration	ISO 105 E04		CC ≥ 4 ST ≥ 3-4	L/L 2
Colour Fastness to Alkaline Perspiration	ISO 105 E04		CC ≥ 4 ST ≥ 3-4	L/L 2
Colour Fastness to Rubbing	ISO 105 X12	Dry / Wet	Dry ≥ 4 Wet ≥ 3-4	L 4
Colour Fastness to Light	ISO 105 B02		CC ≥ 3	L
Colour Migration on PVC	ISO 105-X10		CC ≥ 4 ST ≥ 4	
Colour Fastness to Water	ISO 105 E01		CC ≥ 4 ST ≥ 3-4	L/L 2
Colour Fastness to Chlorine Bleach	ISO 105 N01	Sodium hypochloride	CC ≥ 4	L
Dimensional Stability to Washing	ISO 6330 - 5077 - 3759	1 cycle - 4N at 40°C	Woven ± 2% Knitted -4% +2%	L 5
Dimensional Stability to Dry Cleaning	Commercial cycle		Woven ± 2% Knitted -4% +2%	
Dimensional Stability to Steaming	BS 4323 or DIN 53894		Woven ± 2% Knitted -4% +2%	
Appearance after Laundering/Drycleaning	3 washing cycle + Standard Tumble drying		No noticeable changes aft 1&3 cycles	L 5
Movement after washing	AATCC 179	Option 1	≤ 3%	
Colour shade	ISO 105 J03 - ISO 105 A02	ΔE - D65 and TL84	≤1,0 / ≥4	L 13
Accelerated Ageing (storage) test	IHTM	7 days @70°C - 90-95%RH	Slight changes	
Pilling resistance - (ICI box method)	ISO 12945-1	Evaluation at 7.200 and 10.800 revs	≥ 4	L 7/L 8
Pilling resistance - (Martindale)	ISO 12945-2	Tex-tex Evaluation at 500, 1.000 and 2000 revs	≥ 4	L 9/L 8
Seam Strength	ISO 13935-2		≥ 120N	
Seam Slippage	ISO 13936-1	3,0 mm	≥ 80 N	L 9
Bursting Strength	ISO 13938		Fabric: ≥ 280 kPa Seam: ≥ 250 kPa	L 7
Tensile Strength (Grab Method)	ISO 13934-2		Fabric up to 200 g/m²: ≥ 120 N Fabric over 200 g/m²: ≥ 170 N	L 9
Tear Strength (Dinamometric Method)	ISO 13937-2	Trouser Method	Fabric up to 200 g/m²: ≥ 10 N Fabric over 200 g/m²: ≥ 15 N	L 9
Tear Strength (Elmendorf Method)	ISO 13937-1		Fabric up to 200 g/m²: ≥ 10 N Fabric over 200 g/m²: ≥ 15 N	L 9
Stretch & Recovery	EN ISO 20932-1		Stretch: ≥ 15%/Residual Extension: ≤ 5%	L 10
Abrasion resistance	ISO 12947-1 and -2	9 kPa 2 broken yarns	10.000 revs CC ≥ 3-4 at 3.000 revs	L/L 9
Electrostatic Properties	EN 1149 -1 & 3		≤2,5 x 10 ⁹ Ω t50 <4 or S>0,2	L 11 / L 12
Antibacterial activities	AATCC 100	After 5 washing Cycle	≥ 90%	
Water vapour permeability (Brethability)	ASTM E96 (BW) / ISO 11092	nil	≥4000 gr/m2/day / RET ≤ 6	
Drying time	AATCC 199	nil	≥50% after 30 mins	
Thermal resistance	ASTM D1518		T -shirt: Boxer or Slip : Clo ≥0,05 Clo ≥0,10	
pH of the aqueous extract	ISO 3071	KCl 0.1M	4.0÷7.5	

Notes	
L	CC = Colour change - ST = Staining
L 1	No tolerance for single fiber
L 2	If there are trims and/or different colours within the garment: ST ≥ 4-5
L 3	Staining in the solvent
L 4	Pigment print: Dry ≥ 3-4 - Wet ≥ 3
L 5	Tumble dry: normal temperature - exhaust temperature max 80°C
L 6	After 3 washing cycles at 40°C. After 1 dry cleaning cycle when it's the only maintenance permitted in care label
L 7	For knitted fabrics only. After 1hand wash cycle for silk only
L 8	After 1 washing cycles at 40°C. After 1 dry cleaning cycle when it's the only maintenance permitted in care label
L 9	For woven fabrics only. After 1hand wash cycle for silk only
L 10	For fabrics containing elastane only
L 11	Textiles main material shall comply with one of the two requirements at least
L 12	Requirements for both New and after 3 washing cycles
L 13	PP sample vs Bulk or Shipment sample. ISO 105 J03 for Instrumental evaluation. ISO 105 A02 for visual evaluation

Calze Tecniche - Technical Socks J-SKI					
Requirement Description		Conformity Reference / Test Method	Technical details	Requirements	Notes
Fiber Composition		Reg. EU 1007/2011 - GB/T 2910 - BS 4407		± 3%	J 1
Fiber Composition		AATCC 20 - ISO 1833 - ASTM D 276 - FZ/T 01057-1/7			
Mass per unit area		ISO 3801	Method 5	± 5%	
Colour Fastness to Washing		ISO 105 C06	A2S at 40°C	CC ≥ 4 ST ≥3-4	J/J 2
Colour Fastness to Dry Cleaning		ISO 105 D01		CC ≥ 4 ST ≥4	J/J 3
Colour Fastness to Acid Perspiration		ISO 105 E04		CC ≥ 4 ST ≥3-4	J/J 2
Colour Fastness to Alkaline Perspiration		ISO 105 E04		CC ≥ 4 ST ≥3-4	J/J 2
Colour Fastness to Rubbing		ISO 105 X12	Dry / Wet	Dry ≥ 4 Wet ≥3-4	J 4
Colour Fastness to Light		ISO 105 B02		CC ≥ 4	
Colour Migration on PVC		ISO 105-X10		CC ≥ 4 ST ≥4	
Colour Fastness to Water		ISO 105 E01		CC ≥ 4 ST ≥3-4	J/J 2
Colour Fastness to Chlorine Bleach		ISO 105 N01	Sodium hypochloride	CC ≥ 4	
Dimensional Stability to Washing		ISO 6330	1 cycle - 4N at 40°C	-4% +2%	J 5
Dimensional Stability to Dry Cleaning		Commercial cycle		-4% +2%	
Dimensional Stability to Steaming		BS 4323 or DIN 53894		-4% +2%	
Appearance after Laundering/Drycleaning		IHTM		No noticeable changes aft 1&3 cycles	J 5 / J 6
Movement after washing		AATCC 179	Option 1	>5%	
Pilling resistance - (ICI box method)		ISO 12945-1	Evaluation at 7.200 and 10.800 revs	≥ 3-4	J 7/J 9
Abrasion resistance		EN 13770	9 kPa 2 broken yarns	15.000/CT a 3.000 max 3/4	
Bursting Strength		ISO 13938		490 kPa	
Stretch & Recovery		EN ISO 20932-1		Stretch: ≥ 15%/Residual Extension: ≤ 5%	J 8
Antibacterial activities		AATCC 100	After 5 washing Cycle	≥ 90%	
Water vapour permeability (Brethability)		ASTM E96 (BW) / ISO 11092	Nil	≥4000 gr/m2/day / RET ≤ 6	
Drying time		AATCC 199	nil	≥50% after 30 mins	
Thermal resistance		ASTM D1518		Clo ≥0,05	
Accelerated Ageing (storage) test		IHTM	7 days @70°C - 90-95%RH	Slight changes	
Electrostatic Properties		EN 1149 -1 & 3		≤2,5 x 10 ⁹ Ω t50 <4 or S>0,2	J 10
pH of the aqueous extract		ISO 3071	KCl 0.1M	4.0÷7.5	

Notes	
J	CC = Colour change - ST = Staining
J 1	No tolerance for single fiber
J 2	If there are trims and/or different colours within the sock: ST ≥ 4-5
J 3	Staining in the solvent
J 4	Pigment print: Dry ≥ 3-4 - Wet ≥ 3
J 5	Tumble dry: normal temperature - exhaust temperature max 80°C
J 6	After 3 washing cycles at 40°C. After 1 dry cleaning cycle when it's the only maintenance permitted in care label
J 7	After 1 washing cycles at 40°C. After 1 dry cleaning cycle when it's the only maintenance permitted in care label
J 8	For fabrics containing elastane only
J 9	After 1 hand wash cycle for wool, wool blend, kashmir, kashmir blend or precious fibres
J 10	Textiles main material shall comply with one of the two requirements at least

Guanti da Sci - Ski Gloves I-SKI				
Requirement Description	Conformity Reference / Test Method	Technical details	Requirements	Notes
Fiber Composition	Reg. EU 1007/2011 - GB/T 2910 - BS 4407 AATCC 20 - ISO 1833 - ASTM D 276 - FZ/T 01057-1/7		± 3%	I 1
Mass per unit area	ISO 3801	Method 5	± 5%	
Colour Fastness to Washing	ISO 105 C06	A2S at 40°C	CC ≥ 4 ST ≥ 3-4	I/I 2
Colour Fastness to Dry Cleaning	ISO 105 D01		CC ≥ 4 ST ≥ 4	I/I 3
Colour Fastness to Acid Perspiration	ISO 105 E04		CC ≥ 4 ST ≥ 3-4	I/I 2
Colour Fastness to Alkaline Perspiration	ISO 105 E04		CC ≥ 4 ST ≥ 3-4	I/I 2
Colour Fastness to Rubbing	ISO 105 X12	Dry / Wet	Dry ≥ 4 Wet ≥ 3-4	I 4
Colour Fastness to Light	ISO 105 B02		CC ≥ 4	I
Colour Migration on PVC	ISO 105-X10		CC ≥ 4 ST ≥ 4	
Colour Fastness to Water	ISO 105 E01		CC ≥ 4 ST ≥ 3-4	I/I 2
Colour Fastness to Chlorine Bleach	ISO 105 N01	Sodium hypochloride	CC ≥ 4	I
Dimensional Stability to Washing	ISO 6330 - 5077 - 3759	4N at 40°C - Tumble dry	Woven ± 2% Knitted -4% +2%	I 5
Dimensional Stability to Dry Cleaning	Commercial cycle		Woven ± 2% Knitted -4% +2%	
Dimensional Stability to Steaming	BS 4323 or DIN 53894		Woven ± 2% Knitted -4% +2%	
Appearance after Laundering/Drycleaning	IHTM		No noticeable changes aft 1&3 cycles	I 6
Pilling resistance - (ICI box method)	ISO 12945-1	Evaluation at 7.200 and 10.800 revs	≥ 4	I 7/I 11
Pilling resistance - (Martindale)	ISO 12945-2	Tex-tex Evaluation at 500, 1.000 and 2000 revs	≥ 4	I 10/I 9
Abrasion resistance	ISO 12947-1 and -2	9 kPa-Wool abradent 2 broken yarns	30.000 revs CC ≥ 3-4 at 3.000 revs	I 10
Seam Strength	ISO 13935-2		≥ 150N	
Bursting Strength	ISO 13938		Fabric: ≥280 kPa Seam: ≥ 250 kPa	
Stretch & Recovery	EN ISO 20932-1		Stretch: ≥ 15%/Residual Extension: ≤ 5%	
Hydrostatic head (Water permeability)	ISO 811	After 3 washing cycles	≥ 5000 mm With membrane ≥ 20000 mm	
Air permeability (Wind Proof)	ISO 9237	After 3 washing cycles	≤10 mm/s	
Water vapour permeability (Brethability)	ISO 11092		RET ≤ 6	
	ASTM E96	Method BW	≥ 4000 gr/m2/day	
		Method B	≥ 600 gr/m2/day	
	JIS L1099	Method B-1	≥ 10000 gr/m2/day	
		Method A-1	≥ 4000 gr/m2/day	
Delamination resistance	ISO 4637	New&After ageing	2,8kg	
Cut resistance	EN ISO 13997		Fabric: ≥10N	
Accelerated Ageing (storage) test	IHTM	7 days @70°C - 90-95%RH	Slight changes	
pH of the acqueous extract	ISO 3071	KCl 0.1M	4.0÷7.5	I 8

Notes	
I	CC = Colour change - ST = Staining
I 1	No tolerance for single fiber
I 2	If there are trims and/or different colours Iithin the garment: ST ≥ 4-5
I 3	Staining in the solvent
I 4	Pigment print: Dry ≥ 3-4 - Wet ≥ 3
I 5	Tumble dry: normal temperature - exhaust temperature max 80°C
I 6	After 3 washing cycles at 40°C. After 1 dry cleaning cycle when it's the only maintenance permitted in care label
I 7	After 1 washing cycles at 40°C. After 1 dry cleaning cycle when it's the only maintenance permitted in care label
I 8	For fabrics containing elastane only
I 9	After 1 washing cycles at 40°C. After 1 dry cleaning cycle when it's the only maintenance permitted in care label
I 10	For woven fabrics only
I 11	After 1 hand wash cycle for wool, wool blend, kashmir, kashmir blend or precious fibres

Period Panties				PP	
Requirement	Description	Conformity Reference / Test Method	Technical details	Requirements	Notes
Fiber Composition		Reg. EU 1007/2011 - GB/T 2910 - BS 4407 AATCC 20 - ISO 1833 - ASTM D 276 - FZ/T 01057-1/7		± 3%	PP 1
Mass per unit area		ISO 3801	Method 5	± 5%	
Colour Fastness to Washing		ISO 105 C06	A2S at 40°C	CC ≥ 4 ST ≥3-4	PP/PP 2
Colour Fastness to Dry Cleaning		ISO 105 D01		CC ≥ 4 ST ≥ 4	PP/PP 3
Colour Fastness to Acid Perspiration		ISO 105 E04		CC ≥ 4 ST ≥3-4	PP/PP 2
Colour Fastness to Alkaline Perspiration		ISO 105 E04		CC ≥ 4 ST ≥3-4	PP/PP 2
Colour Fastness to Rubbing		ISO 105 X12	Dry / Wet	Dry ≥ 4 Wet ≥3-4	PP 4
Colour Fastness to Light		ISO 105 B02		CC ≥ 3	PP
Colour Migration on PVC		ISO 105-X10		CC ≥ 4 ST ≥4	
Colour Fastness to Water		ISO 105 E01		CC ≥ 4 ST ≥3-4	PP/PP 2
Colour Fastness to Chlorine Bleach		ISO 105 N01	Sodium hypochloride	CC ≥ 4	PP
Dimensional Stability to Washing		ISO 6330 - 5077 - 3759	5A at 40°C - Tumble dry	Woven ± 2% Knitted -4% +2%	PP5
Dimensional Stability to Dry Cleaning		Commercial cycle		Woven ± 2% Knitted -4% +2%	
Dimensional Stability to Steaming		BS 4323 or DIN 53894		Woven ± 2% Knitted -4% +2%	
Appearance after Laundering/Drycleaning		IHTM		No noticeable changes aft 1&3 cycles	PP6
Movement after washing		AATCC 179	Option 1	≤ 3%	
Colour shade		ISO 105 J03 - ISO 105 A02	ΔE - D65 and TL84	≤1,0 / ≥4	PP12
Pilling resistance - (ICI box method)		ISO 12945-1	Evaluation at 7.200 and 10.800 revs	≥ 4	PP 7/PP 8
Pilling resistance - (Martindale)		ISO 12945-2	Tex-tex Evaluation at 500, 1.000 and 2000 revs	≥ 4	PP9/PP 8
Seam Strength		ISO 13935-2		≥ 120N	
Seam Slippage		ISO 13936-1	3,0 mm	≥ 80 N	PP9
Bursting Strength		ISO 13938		Fabric: ≥280 kPa Seam: ≥ 250 kPa	PP7
Tensile Strength (Grab Method)		ISO 13934-2		Fabric up to 200 g/m²: ≥ 120 N Fabric over 200 g/m²: ≥ 170 N	PP9
Tear Strength (Dinamometric Method)		ISO 13937-2	Trouser Method	Fabric up to 200 g/m²: ≥ 10 N Fabric over 200 g/m²: ≥ 15 N	PP9
Tear Strength (Elmendorf Method)		ISO 13937-1		Fabric up to 200 g/m²: ≥ 10 N Fabric over 200 g/m²: ≥ 15 N	PP9
Stretch & Recovery		EBN ISDO 20932-1		Stretch: ≥ 15%/Residual Extension: ≤ 5%	PP10
Abrasion resistance		ISO 12947-1 and -2	9 kPa 2 broken yarns	10.000 revs CC ≥ 3-4 at 3.000 revs	PP/PP9
Vertical wicking		AATCC 197-2011e2(2018)e	Option B - 3 cycle washing 3N @30°Line Dry	Light:70mm Moderate:100mm Abondent:135mm	PP13
Moisture managment Properties		AATCC 195-2011e2(2017)e2	Aft 1 washing cycle 3N @30°C Line Dry	Light:grade 2,1,1,1 Moderate:grade 3,2,2,1 Abondent:3,4,4,2	PP14
Hydrostatic head		EN 811	Aft 1 washing cycle 3N @30°C Line Dry	≥3000 mm	
Electrostatic Properties		EN 1149 -1 & 3		≤2,5 x 10 ⁹ Ω t50 <4 or S>0,2	PP11
Accelerated Ageing (storage) test		IHTM	7 days @70°C - 90-95%RH	Slight changes	
pH of the aqueous extract		ISO 3071	KCl 0.1M	4.0÷7.5	

Notes	
PP	CC = Colour change - ST = Staining
PP1	No tolerance for single fiber
PP2	If there are trims and/or different colours within the garment: ST ≥ 4-5
PP3	Staining in the solvent
PP4	Pigment print: Dry ≥ 3-4 - Wet ≥ 3
PP5	Tumble dry: normal temperature - exhaust temperature max 80°C
PP6	After 3 washing cycles at 40°C. After 1 dry cleaning cycle when it's the only maintenance permitted in care label
PP7	For knitted fabrics only. After 1hand wash cycle for silk only
PP8	After 1 washing cycles at 40°C. After 1 dry cleaning cycle when it's the only maintenance permitted in care label
PP9	For woven fabrics only. After 1hand wash cycle for silk only
PP10	For fabrics containing elastane only
PP11	Textiles main material shall comply with one of the two requirements at least
PP12	PP sample vs Bulk or Shipment sample. ISO 105 J03 for Instrumental evaluation. ISO 105 A02 for visual evaluation
PP13	After 10 minutes, on one layer at least.
PP14	Grade to be checked on "Top Surface" : Wetting time, Absorption rate, Maximum wetted, Spreading time. One direction at least.

Lenzuola & federe - bed sheet & pillow case					HTL-N
Requirement	Description	Conformity Reference / Test Method	Technical details	Requirements	Notes
Fiber Composition		Reg. EU 1007/2011 - GB/T 2910 - BS 4407 AATCC 20 - ISO 1833 - ASTM D 276 - FZ/T 01057-1/7		± 3%	HTL 1
Mass per unit area		ISO 3801	Method 5	± 5%	
Colour Fastness to Washing		ISO 105 C06	C2S @ 60°C	CC ≥ 4 ST ≥ 3-4	HTL/2/3
Colour Fastness to Acid Perspiration		ISO 105 E04		CC ≥ 4 ST ≥ 3-4	HTL/HTL2
Colour Fastness to Alkaline Perspiration		ISO 105 E04		CC ≥ 4 ST ≥ 3-4	HTL/HTL2
Colour Fastness to Rubbing		ISO 105 X12	Dry / Wet	Dry ≥ 4 Wet ≥ 3-4	HTL4
Colour Fastness to Light		ISO 105 B02		CC ≥ 5	HTL
Colour Migration on PVC		ISO 105-X10		CC ≥ 4 ST ≥ 4	
Colour Fastness to Water		ISO 105 E01		CC ≥ 4 ST ≥ 3-4	HTL/HTL2
Colour Fastness to Chlorine Bleach		ISO 105 N01	Sodium hypochloride	CC ≥ 4	HTL
Dimensional Stability to Washing		ISO 6330 - 5077 - 3759	6N @60±3°C-Tumble dry	± 3%	HTL5/6
Dimensional Stability to Steaming		BS 4323 or DIN 53894		± 3%	
Appearance after Laundering		IHTM	5 & 10 cycles	no noticeable changes	HTL7
Movement after washing		AATCC 179	Option 1	≤ 3%	HTL3
Colour shade		ISO 105 J03 - ISO 105 A02	ΔE - D65 and TL84	≤ 1,0 / ≥ 4	
Pilling resistance - (Martindale)		ISO 12945-2	Tex-tex Evaluation at 500, 1.000 and 2000 revs	≥ 4	HTL8
Tensile Strength (Grab Method)		ISO 13934-2		Fabric up to 200 g/m ² : ≥ 120 N Fabric over 200 g/m ² : ≥ 170 N	
Tear Strength (Dinamometric Method)		ISO 13937-2	Trouser Method	Fabric up to 200 g/m ² : ≥ 10 N Fabric over 200 g/m ² : ≥ 15 N	
Tear Strength (Elmendorf Method)		ISO 13937-1		Fabric up to 200 g/m ² : ≥ 10 N Fabric over 200 g/m ² : ≥ 15 N	
Abrasion resistance		ISO 12947-1 and -2	9 kPa 2 broken yarns	10.000 revs CC ≥ 3-4 at 3.000 revs	HTL
Accelerated Ageing (storage) test		IHTM	7 days @70°C - 90-95%RH	Slight changes	
pH of the acqueous extract		ISO 3071	KCl 0.1M	4.0÷7.5	

Notes	
HTL	CC = Colour change - ST = Staining
HTL1	No tolerance for single fiber
HTL2	If there are trims and/or different colours within the PRODUCT: ST ≥ 4-5
HTL3	nil
HTL4	Pigment print: Dry ≥ 3-4 - Wet ≥ 3
HTL5	Tumble dry: exhaust temperature max 80°C
HTL6	Waffel fabrics: ± 9%
HTL7	After 5 & 10 washing cycles 6N @60±3°C-Tumble
HTL8	After 1 washing cycles 6N @60±3°C-Tumble

Accappatoi, Teli & Tappetini bagno - Bathrobe, Towels & Bathmat					HTL-T
Requirement	Description	Conformity Reference / Test Method	Technical details	Requirements	Notes
Fiber Composition		Reg. EU 1007/2011 - GB/T 2910 - BS 4407		± 3%	HTL 1
Mass per unit area		AATCC 20 - ISO 1833 - ASTM D 276 - FZ/T 01057-1/7		± 5%	
		ISO 3801	Method 5		
Colour Fastness to Washing		ISO 105 C06	C2S @ 60°C	CC ≥ 4 ST ≥3-4	HTL/2/3
Colour Fastness to Acid Perspiration		ISO 105 E04		CC ≥ 4 ST ≥3-4	HTL/HTL2
Colour Fastness to Alkaline Perspiration		ISO 105 E04		CC ≥ 4 ST ≥3-4	HTL/HTL2
Colour Fastness to Rubbing		ISO 105 X12	Dry / Wet	Dry ≥ 4 Wet ≥3-4	HTL4
Colour Fastness to Light		ISO 105 B02		CC ≥ 5	HTL
Colour Migration on PVC		ISO 105-X10		CC ≥ 4 ST ≥4	
Colour Fastness to Water		ISO 105 E01		CC ≥ 4 ST ≥3-4	HTL/HTL2
Colour Fastness to Chlorine Bleach		ISO 105 N01	Sodium hypochloride	CC ≥ 4	HTL
Dimensional Stability to Washing		ISO 6330 - 5077 - 3759	6N @60±3°C-Tumble dry	± 5%	HTL3/5/6
Dimensional Stability to Steaming		BS 4323 or DIN 53894		± 5%	
Appearance after Laundering/Drycleaning		IHTM	5 & 10 cycles	no noticeable changes	HTL7
Movement after washing		AATCC 179	Option 1	≤ 3%	HTL3
Colour shade		ISO 105 J03 - ISO 105 A02	ΔE - D65 and TL84	≤1,0 / ≥4	
Pilling resistance - (Martindale)		ISO 12945-2	Tex-tex Evaluation at 500, 1.000 and 2000 revs	≥ 4	HTL8
Seam Strength		ISO 13935-2		≥ 120N	
Seam Slippage		ISO 13936-1	6,0 mm	≥ 80 N	
Bursting Strength		ISO 13938		Fabric: ≥280 kPa Seam: ≥ 250 kPa	
Tensile Strength (Grab Method)		ISO 13934-2		Fabric up to 200 g/m²: ≥ 120 N Fabric over 200 g/m²: ≥ 170 N	
Tear Strength (Dinamometric Method)		ISO 13937-2	Trouser Method	Fabric up to 200 g/m²: ≥ 10 N Fabric over 200 g/m²: ≥ 15 N	
Tear Strength (Elmendorf Method)		ISO 13937-1		Fabric up to 200 g/m²: ≥ 10 N Fabric over 200 g/m²: ≥ 15 N	
Abrasion resistance		ISO 12947-1 and -2	9 kPa 2 broken yarns	10.000 revs CC ≥ 3-4 at 3.000 revs	HTL
Absorbency		ASTM D 4772	After 1 washing cycle	≥40%	HTL8
Accelerated Ageing (storage) test		IHTM	7 days @70°C - 90-95%RH	Slight changes	
pH of the aqueous extract		ISO 3071	KCl 0.1M	4.0÷7.5	

Notes	
HTL	CC = Colour change - ST = Staining
HTL1	No tolerance for single fiber
HTL2	If there are trims and/or different colours within the PRODUCT: ST ≥ 4-5
HTL3	nil
HTL4	Pigment print: Dry ≥ 3-4 - Wet ≥ 3
HTL5	Tumble dry: exhaust temperature max 80°C
HTL6	Waffel fabrics: ± 7%
HTL7	After 5 & 10 washing cycles 6N @60±3°C-Tumble
HTL8	After 1 washing cycles 6N @60±3°C-Tumble

Tovaglie - Tableclothes					HTL-P
Requirement	Description	Conformity Reference / Test Method	Technical details	Requirements	Notes
Fiber Composition		Reg. EU 1007/2011 - GB/T 2910 - BS 4407 AATCC 20 - ISO 1833 - ASTM D 276 - FZ/T 01057-1/7		± 3%	HTL 1
Mass per unit area		ISO 3801	Method 5	± 5%	
Colour Fastness to Washing		ISO 105 C06	C2S @ 60°C	CC ≥ 4 ST ≥ 3-4	HTL/2/7
Colour Fastness to Acid Perspiration		ISO 105 E04		CC ≥ 4 ST ≥ 3-4	HTL/HTL2
Colour Fastness to Alkaline Perspiration		ISO 105 E04		CC ≥ 4 ST ≥ 3-4	HTL/HTL2
Colour Fastness to Rubbing		ISO 105 X12	Dry / Wet	Dry ≥ 4 Wet ≥ 3-4	HTL4
Colour Fastness to Light		ISO 105 B02		CC ≥ 5	HTL
Colour Migration on PVC		ISO 105-X10		CC ≥ 4 ST ≥ 4	
Colour Fastness to Water		ISO 105 E01		CC ≥ 4 ST ≥ 3-4	HTL/HTL2
Colour Fastness to Chlorine Bleach		ISO 105 N01	Sodium hypochloride	CC ≥ 4	HTL
Dimensional Stability to Washing		ISO 6330 - 5077 - 3759	6N @60±3°C-Tumble dry	± 5%	HTL5/6
Dimensional Stability to Steaming		BS 4323 or DIN 53894		± 5%	
Appearance after Laundering/Drycleaning		IHTM	5 & 10 cycles	no noticeable changes	HTL7
Movement after washing		AATCC 179	Option 1	≤ 3%	HTL3
Colour shade		ISO 105 J03 - ISO 105 A02	ΔE - D65 and TL84	≤1,0 / ≥4	
Pilling resistance - (Martindale)		ISO 12945-2	Tex-tex Evaluation at 500, 1.000 and 2000 revs	≥ 4	HTL8
Tensile Strength (Grab Method)		ISO 13934-2		Fabric up to 200 g/m ² : ≥ 120 N Fabric over 200 g/m ² : ≥ 170 N	
Tear Strength (Dinamometric Method)		ISO 13937-2	Trouser Method	Fabric up to 200 g/m ² : ≥ 10 N Fabric over 200 g/m ² : ≥ 15 N	
Tear Strength (Elmendorf Method)		ISO 13937-1		Fabric up to 200 g/m ² : ≥ 10 N Fabric over 200 g/m ² : ≥ 15 N	
Abrasion resistance		ISO 12947-1 and -2	9 kPa 2 broken yarns	10.000 revs CC ≥ 3-4 at 3.000 revs	HTL
Accelerated Ageing (storage) test		IHTM	7 days @70°C - 90-95%RH	Slight changes	
pH of the aqueous extract		ISO 3071	KCl 0.1M	4.0÷7.5	

Notes	
HTL	CC = Colour change - ST = Staining
HTL1	No tolerance for single fiber
HTL2	If there are trims and/or different colours within the PRODUCT: ST ≥ 4-5
HTL3	nil
HTL4	Pigment print: Dry ≥ 3-4 - Wet ≥ 3
HTL5	Tumble dry: exhaust temperature max 80°C
HTL6	Waffel fabrics: ± 9%
HTL7	After 5 & 10 washing cycles 6N @60±3°C-Tumble
HTL8	After 1 washing cycles 6N @60±3°C-Tumble

Teli SPA & Mare - SPA & Sea Towels HTL-S				
Requirement Description	Conformity Reference / Test Method	Technical details	Requirements	Notes
Fiber Composition	Reg. EU 1007/2011 - GB/T 2910 - BS 4407 AATCC 20 - ISO 1833 - ASTM D 276 - FZ/T 01057-1/7		± 3%	HTL 1
Mass per unit area	ISO 3801	Method 5	± 5%	
Colour Fastness to Washing	ISO 105 C06	C2S @ 60°C	CC ≥ 4-5 ST ≥ 4	HTL/2/3
Colour Fastness to Acid Perspiration	ISO 105 E04		CC ≥ 4-5 ST ≥ 4	HTL/HTL2
Colour Fastness to Alkaline Perspiration	ISO 105 E04		CC ≥ 4-5 ST ≥ 4	HTL4
Colour Fastness to Rubbing	ISO 105 X12	Dry / Wet	Dry ≥ 4-5 Wet ≥ 4	HTL
Colour Fastness to Light	ISO 105 B02		CC ≥ 5	HTL
Colour Migration on PVC	ISO 105-X10		CC ≥ 4 ST ≥ 4	
Colour Fastness to Water	ISO 105 E01		CC ≥ 4-5 ST ≥ 4	HTL/HTL 2
Colour Fastness to Sea Water	ISO 105 E02		CC ≥ 4 ST ≥ 3-4	HTL/HTL 2
Colour Fastness to Chlorine Bleach	ISO 105 N01	Sodium hypochloride	CC ≥ 4-5	HTL
Colour Fastness to Chlorinated Water	ISO 105 E03	20 ppm	CC ≥ 4	HTL
Dimensional Stability to Washing	ISO 6330 - 5077 - 3759	6N @60±3°C-Tumble dry	± 5%	HTL3/5/6
Dimensional Stability to Steaming	BS 4323 or DIN 53894		± 5%	HTL6
Appearance after Laundering/Drycleaning	IHTM		No noticeable changes aft 5 &10 cycles	HTL7
Movement after washing	AATCC 179	Option 1	≤ 3%	HTL3
Colour shade	ISO 105 J03 - ISO 105 A02	ΔE - D65 and TL84	≤1,0 / ≥4	
Pilling resistance - (Martindale)	ISO 12945-2	Tex-tex Evaluation at 500, 1.000 and 2000 revs	≥ 4	HTL8
Seam Strength	ISO 13935-2		≥ 120N	
Seam Slippage	ISO 13936-1	6,0 mm	≥ 80 N	
Bursting Strength	ISO 13938		Fabric: ≥280 kPa Seam: ≥ 250 kPa	
Tensile Strength (Grab Method)	ISO 13934-2		Fabric up to 200 g/m ² : ≥ 120 N Fabric over 200 g/m ² : ≥ 170 N	
Tear Strength (Elmendorf Method)	ISO 13937-1		Fabric up to 200 g/m ² : ≥ 10 N Fabric over 200 g/m ² : ≥ 15 N	
Abrasion resistance	ISO 12947-1 and -2	9 kPa 2 broken yarns	20.000 revs CC ≥ 3-4 at 3.000 revs	HTL/HTL10
Accelerated Ageing (storage) test	IHTM	7 days @70°C - 90-95%RH	Slight changes	
Absorbency	ASTM D 4772	After 1 washing cycle	≥40%	HTL8
pH of the aqueous extract	ISO 3071	KCl 0.1M	4.0÷7.5	

Notes	
HTL	CC = Colour change - ST = Staining
HTL1	No tolerance for single fiber
HTL2	If there are trims and/or different colours within the garment: ST ≥ 4-5
HTL3	nil
HTL4	Pigment print: Dry ≥ 3-4 - Wet ≥ 3
HTL5	Tumble dry: exhaust temperature max 80°C
HTL6	Requirement only for Terry fabrics, Waffel fabrics: ± 9%, Woven ± 4%, Non-Woven ± 2%
HTL7	After 5 & 10 washing cycles 6N @60±3°C-Tumble
HTL8	After 1 washing cycles 6N @60±3°C-Tumble

Ciabatte da Camera (monouso) - Bedroom Slipper(single use)					HTL-Y
Requirement	Description	Conformity Reference / Test Method	Technical details	Requirements	Notes
Fiber Composition		Reg. EU 1007/2011 - GB/T 2910 - BS 4407 AATCC 20 - ISO 1833 - ASTM D 276 - FZ/T 01057-1/7		± 3%	HTL 1
Mass per unit area		ISO 3801	Method 5	± 5%	
Colour Fastness to Acid Perspiration		ISO 105 E04		CC ≥ 4-5 ST ≥ 4	HTL/HTL2
Colour Fastness to Alkaline Perspiration		ISO 105 E04		CC ≥ 4-5 ST ≥ 4	HTL4
Colour Fastness to Rubbing		ISO 105 X12	Dry / Wet	Dry ≥ 4-5 Wet ≥ 4	HTL
Colour Fastness to Light		ISO 105 B02		CC ≥ 4	HTL
Colour Migration on PVC		ISO 105-X10		CC ≥ 4 ST ≥ 4	
Colour Fastness to Water		ISO 105 E01		CC ≥ 4-5 ST ≥ 4	HTL/HTL 2
Colour Fastness to Sea Water		ISO 105 E02		CC ≥ 4 ST ≥ 3-4	HTL/HTL 2
Colour Fastness to Chlorinated Water		ISO 105 E03	20 ppm	CC ≥ 4	HTL
Colour shade		ISO 105 J03 - ISO 105 A02	ΔE - D65 and TL84	≤1,0 / ≥4	
Slip resistance		EN ISO 13287	Wet & Dry	≥0,3	HTL5
Accelerated Ageing (storage) test		IHTM	7 days @70°C - 90-95%RH	Slight changes	
Absorbency		ASTM D 4772	new material	≥40%	
pH of the aqueous extract		ISO 3071	KCl 0.1M	4.0÷7.5	

Notes	
HTL	CC = Colour change - ST = Staining
HTL1	No tolerance for single fiber
HTL2	If there are trims and/or different colours within the garment: ST ≥ 4-5
HTL4	Pigment print: Dry ≥ 3-4 - Wet ≥ 3
HTL5	Not Applicable for textiles sole

Ombrelli - Umbrellas					UM
Requirement	Description	Conformity Reference / Test Method	Technical details	Requirements	Notes
Fiber Composition		Reg. EU 1007/2011 - GB/T 2910 - BS 4407 AATCC 20 - ISO 1833 - ASTM D 276 - FZ/T 01057-1/7		± 3%	UM 1
Mass per unit area		ISO 3801	Method 5	± 5%	
Colour Fastness to Light		ISO 105 B02		CC ≥ 4	UM
Colour Migration on PVC		ISO 105-X10		CC ≥ 4 ST ≥ 4	
Colour Fastness to Water		ISO 105 E01		CC ≥ 4-5 ST ≥ 4	UM/UM2
Colour shade		ISO 105 J03 - ISO 105 A02	ΔE - D65 and TL84	≤1,0 / ≥4	
Tensile strenght (Fabric)		ISO 13934-2	Wet & Dry	Wet ≥ 80 N Dry ≥ 140 N	UM3
Tensile strenght - Small parts		EN 71-1	See Standard	≥ 90 N	UM4
Accelerated Ageing (storage) test		IHTM	7 days @70°C - 90-95%RH	Slight changes	
Tear strength		EN ISO 13937	Trouser method	≥ 20 N	
Metallic accessories Corrosion resistance		EN ISO 22775	Method 1	No Change	
Rain test		AATCC 35		≥ 5g	
Spray test (water repellency)		EN 24920	New Sample	≥ ISO 4	

Notes	
UM	CC = Colour change - ST = Staining
UM1	No tolerance for single fiber
UM2	If there are trims and/or different colours within the garment: ST ≥ 4-5
UM 3	Specimens to be tested in the wet condition shall be immersed in water at room temperature until thoroughly wetted. To thoroughly wet a specimen, it may be necessary to add not more than 0.05 % of wetting agent to the water. A test of any wet specimen shall be completed within two minutes after its removal from the water.
UM4	Applicable to Children product only

Rivestimenti tessili sedute domestiche - Upholstery for domestic seating UPF-T				
Requirement Description	Conformity Reference / Test Method	Technical details	Requirements	Notes
Fiber Composition	Reg. EU 1007/2011 - GB/T 2910 - BS 4407 AATCC 20 - ISO 1833 - ASTM D 276 - FZ/T 01057-1/7		± 3%	HTL 1
Mass per unit area	ISO 3801	Method 5	± 5%	
Colour Fastness to Washing	ISO 105 C06	A2S @ 40°C	CC ≥ 4 ST ≥ 3-4	HTL/2/3
Colour Fastness to Acid Perspiration	ISO 105 E04		CC ≥ 4 ST ≥ 3-4	HTL/HTL2
Colour Fastness to Alkaline Perspiration	ISO 105 E04		CC ≥ 4 ST ≥ 3-4	HTL/HTL2
Colour Fastness to Rubbing	ISO 105 X12	Dry / Wet	Dry ≥ 4 Wet ≥ 3-4	HTL4
Colour Fastness to Light	ISO 105 B02		CC ≥ 5	HTL
Colour Migration on PVC	ISO 105-X10		CC ≥ 4 ST ≥ 4	
Colour Fastness to Water	ISO 105 E01		CC ≥ 4 ST ≥ 3-4	HTL/HTL2
Dimensional Stability to Washing	ISO 6330 - 5077 - 3759	4N @40±3°C-Tumble dry	± 3%	HTL5/6
Dimensional Stability to Steaming	BS 4323 or DIN 53894		± 3%	
Appearance after Laundering	IHTM	5 & 10 cycles	no noticeable changes	HTL7
Movement after washing	AATCC 179	Option 1	≤ 3%	HTL3
Colour shade	ISO 105 J03 - ISO 105 A02	ΔE - D65 and TL84	≤1,0 / ≥4	
Pilling resistance - (Martindale)	ISO 12945-2	After 1 washing Cycle	≥ 4	HTL8
Sear Slippage				
Tensile Strength (Grab Method)	ISO 13934-2		≥ 170 N	
Tear Strength (Dinamometric Method)	ISO 13937-2	Trouser Method	≥ 20 N	
Tear Strength (Elmendorf Method)	ISO 13937-1		≥ 20 N	
Abrasion resistance	ISO 12947-1 and -2	12 kPa 2 broken yarns	20.000 revs CC ≥ 3-4 at 3.000 revs	HTL
Accelerated Ageing (storage) test	IHTM	7 days @70°C - 90-95%RH	Slight changes	
Flammability	EN 1021-1&2	KCI 0.1M		
pH of the aqueous extract	ISO 3071		4.0÷7.5	

Notes	
HTL	CC = Colour change - ST = Staining
HTL1	No tolerance for single fiber
HTL2	If there are trims and/or different colours within the PRODUCT: ST ≥ 4-5
HTL3	nil
HTL4	Pigment print: Dry ≥ 3-4 - Wet ≥ 3
HTL5	Tumble dry: exhaust temperature max 80°C
HTL6	Waffel fabrics: ± 9%
HTL7	After 5 & 10 washing cycles 6N @60±3°C-Tumble
HTL8	After 1 washing cycles 4N @40±3°C-Tumble dry