



Rev 00 01/2025

PPE Cat I - Chef Jackets- Giacche Chef

Requirements	Description	Standard Method	Technical Details	Requirements	Notes
Fiber Composition	[Reg.(EU) N. 1007/2011]	ISO 1833 / AATCC 20 / BS 4407		±3%	B1
Weight per square meter		ISO 3801	Method 5	<150 g/m ² : ±5% 150÷300 g/m ² : ±4% >300 g/m ² : ±3%	
Colour Fastness to Washing		ISO 105 C06	60°C	CC ≥ 4 ST ≥ 3-4	B2
Colour Fastness to Acid Perspiration		ISO 105 E04	pH 5,5	CC ≥ 4 ST ≥ 3-4	B2
Colour Fastness to Alkaline Perspiration		ISO 105 E04	pH 8,0	CC ≥ 4 ST ≥ 3-4	B2
Colour Fastness to Rubbing		ISO 105 X12	W/D	Dry ≥ 4 Wet ≥ 3-4	
Colour Fastness to Light		ISO 105 B02	Xenon light	≥ 4	
Colour Fastness to Water		ISO 105 E01	Water G3	CC ≥ 4 ST ≥ 3-4	B2
Dimensional Stability to Washing		EN ISO 6330	3 cycles : 60°C - Tumble dry	Woven ±2% Knitt -4% +2%	
Dimensional Stability to Steaming		BS 4323	30 sec./3 specs	Woven ±2% Knitt -4% +2%	
Appearance after Washing		IHTM	cycles 60°- Tumble D	No noticeable changes	
Movement after washing		AATCC 179	After 1 washing	≥ 3%	B5 / B9
Pilling resistance - Martindale		ISO 12945-2	500+1.000/tex-tex	≥ 4	B8
Snagging resistance		ASTM D 3939-13	Mace test	≥ 4	
Seam Slippage&Strength		ISO 13935-2		≥ 150 N	B6
Seam Slippage		ISO 13936-1	6 mm	≥ 120 N	
Bursting Strength		ISO 13938		Fabric 280 kPa Seam 250 kPa	B5
Tensile Strength (Grab Method)		ISO 13934-2		≥ 150 N	
Tensile Strength (Strip Method)		ISO 13934-1		≥ 150 N	
Tear Strength (Elmendorf Method)		ISO 13937-1		≥ 30 N	
Protective clothing - General requirements		EN ISO 13688:2013/A1:2021		Comply	
Puncture resistance		EN 863		≥ 50 N	
Abrasion resistance		EN 530	12 kPa	≥ 20.000 Cycles	
Water vapour permeability (Breathability)		ASTM E96 (B) / ISO 11092	nil	≥600 gr/m2/day / RET ≤ 6	
UV Protection factor UPF		EN 13758		50+	
Color shade		ISO 105 J03 - ISO 105 A02	ΔE - D65 and TL84	≤1,0 / ≥4	B12
Odour		IHTM		Negliable	
pH of the aqueous extract		ISO 3071	G3 Water	4,0 , 7,5	

Notes

- B1 No tolerance for single fibre [Reg.(UE) N. 1007/2011, Art.20 comma 3]
- B2 Trims & Color contrast: ST ≥4-5
- B3 ST in the solvent
- B4 Flat dry
- B5 After 1 washing cycle
- B6 Test must be carried out on the seams of the garments
- B7 Applicable for PPE Cat II Low Risk - Minimum visible area covered by Retroreflective material (Clause 4,2,5 Figure 5). In case PPE does not meet the requirement it shall be classified as Cat I since is not capable to of visually signalling the user's presence and it should be properly reported in the Manufacturer notice
- B8 Assessment after 500 cycles and after 1000 cycles
- B12 PP sample vs Bulk or Shipment sample. ISO 105 J03 for Instrumental evaluation. ISO 105 A02 for visual evaluation

Legenda

- CC Color Change
- ST Color Staining
- Stre Stretch
- RE Residual Extension
- ISO International Standard Organization
- BS British Standard
- EN European Norm
- AATCC American Association of Chemist and Colourist
- IHTM In House Test Method

Care Labeling

Lavare il capo rovesciato - wash inside out

Prints and/ or with attachment Stirare al rovescio - Iron reverse side only

Dark and medium color, fluo colors, garment or Pigment dyed Lavare separatamente o con colori simili - Wash separately or with similar colors