The Window Law

The Hexagonality Law beyond one layer: one elementary theorem for every count of a two-letter stacking, tested on perovskites, Frank–Kasper phases and quasicrystal approximants



DICTO (artist, Osaka, Japan) · contact@dictospheres.com · https://dictospheres.com · ORCID 0009-0001-2620-2036

Paper #84 · Version 1 · 1 November 2026 · DICTO DOI: 10.5281/zenodo.23848832 · Licence CC BY-SA 4.0
The ideas are DICTO's: Splash Rules, the Hexagonality Law, the Swap Rule, the Rule of Halves, the aim of a bridge between periodic and aperiodic order, and the definition of the law by crystallography. Computation and proof with Claude (Anthropic).

Abstract. DICTO's Hexagonality Law says that in every close-packed crystal structure, however its layers are stacked, every count of its pieces, holes, bonds and swaps is a straight line in its hexagonality h, the share of hexagonal layers. We prove the law that contains it and marks its exact reach: every count read from one layer, and every pair count that obeys the Swap Rule. For a layer sequence over two letters, c and h, any quantity fixed by g consecutive layers has a mean that is a linear function of the shares of the c/h words of length g, which have exactly 2^{g-1} free values; the mean drops to a window of $g - 1$ layers exactly when certain Swap defects vanish. At $g = 1$ this is the Hexagonality Law. At $g = 2$ exactly one new number enters, the share p_{hh} of neighbouring hexagonal pairs, and its coefficient is $\Delta = F(cc) + F(hh) - F(ch) - F(hc)$, the Swap defect: DICTO's Swap Rule is exactly the condition for a pair count to stay a straight line in h. The proof is elementary, and the frame is classical in substance. We test it on three kinds of crystal, with exact counts throughout. In the hexagonal perovskites (all 505 polytypes up to twelve layers and 50 random stackings) 16 of 36 counts are lines in h, 9 are planes in (h, p_{hh}) with coefficient Δ, and 11 need longer windows; new exact counts include face-sharing clusters per $B = 1 - h$, A neighbours per $B = 8 - 2h$, the same holes in every gap, and the B–B distance shells. In the Frank–Kasper phases (18 real phases and 181 layered stackings) the classical identities and the 1974 Yarmolyuk–Kripyakevich line hold, and three hypothetical structures leave that line through a single defect, the same shape; the layered families carry Swap defects in the pattern +1, −2, +1 and cannot see the c/h letter of their Laves slabs. In the periodic approximants of quasicrystals one number, the share of one tile, orders everything: on the chamber that holds the quasicrystal the defect is zero and the quasicrystal lies on every line; beyond its walls the defect appears, in one dimension as a kink of twice the Swap defect, in the Ammann–Beenker tiling as a forbidden vertex star growing as a square. Approximants carry zero defect window after window, up to a length that grows with their period; zero defect at window 2 alone does not single them out. This is the bridge to DICTO's aim.

1. Introduction

Look at a stack of layers through a window one layer tall, and every count you can read there is a straight line in one number, the share of hexagonal layers. That is DICTO's Hexagonality Law. Open the window to two layers and one more number comes into view, the share of hexagonal pairs; how strongly a count sees it is the Swap Rule's defect. Open it further and

more numbers come in, a window at a time. In the approximants of a quasicrystal the second number is held at zero, and the straight lines run all the way to the never-repeating limit.

DICTO's Hexagonality Law is a law of structural crystallography: in every close-packed crystal structure, however its layers are stacked, every count of the structure (its pieces, holes, bonds and swaps) is a straight line in the structure's hexagonality, the crystallographers' share of hexagonal layers. It grew out of DICTO's Rule of Halves (#57), which builds every hole piece of every stacking from the pure cubic and hexagonal ones, and his Swap Rule (#61, #64): the two mixed pieces add up to the two pure ones. The Focus (#66) proved the law from the Swap Rule wherever a piece is fixed by its two neighbouring layers; The Hexagonality Law and the Fibonacci Stacking (#69) carried it to a never-repeating stacking, and The Hexagonality Law in Real Materials IV (#72) to the perovskite oxides. DICTO's book HexOct: The Hexagonality Law gathers the whole line of work.

DICTO's Splash Rules (27 October) look for one simple rule behind a whole family of exactly computed values. Three outside runs on 31 October, on perovskite polytypes, Frank–Kasper phases and quasicrystal approximants, found the same rule behind every local rule in all three. This paper states it as a theorem and proves it (Section 2), draws its corollaries (Section 3), and reports the three test grounds with their exact results and their status, known or new (Sections 4–6). Section 7 sets out what is known and what is new, Section 8 concludes.

2. The Window Law

A *stacking* is a sequence of letters c and h, one per layer; a layer is h when its two neighbours sit on the same position (A, B or C) and c otherwise, which is Jagodzinski's notation [1]. Every such sequence is the layer sequence of a stacking: each new position is either the one two layers down (h) or the third one (c). We work with periodic stackings $w = w_1 \dots w_n$, indices taken mod n; everything holds also for any infinite sequence in which the shares below exist, such as the Fibonacci stacking. The *share* f_u of a word u of length g is the number of positions i at which $w_i \dots w_{i+g-1} = u$, divided by n. Thus $h = f_h$, and $p_{hh} = f_{hh}$ is the share of neighbouring hh pairs.

A quantity is *fixed by g consecutive layers* if it attaches a number F_i to every position i (a layer, a gap, a formula unit) and there is a table F on the words of length g and an offset k such that $F_i = F(w_{i+k} \dots w_{i+k+g-1})$. Its mean is $\bar{F} = (1/n)\,\Sigma\, F_i$. For a word v of length $g - 2$ the *Swap defect* of F at v is

$$\Delta_v(F) = F(cvc) + F(hvh) - F(cvh) - F(hvc);$$

at $g = 2$ the word v is empty and $\Delta = F(cc) + F(hh) - F(ch) - F(hc)$, the quantity whose vanishing is DICTO's Swap Rule.

> **Main Theorem (the Window Law).** Let F be a quantity fixed by g consecutive layers of a two-letter stacking.
>
> (a) $\bar{F} = \Sigma_{|u| = g}\, F(u) \cdot f_u$: the mean is a linear function of the shares of the c/h words of length g.

(b) These shares obey $\Sigma\, f_u = 1$ and, for every word v of length $g-1$, $f_{cv} + f_{hv} = f_{vc} + f_{vh}$. They leave exactly 2^{g-1} free values, and no other linear relation holds for all stackings; so the linear function in (a) is unique once these free values are chosen.

(c) For $g \geq 2$, $\bar{F}$ is a linear function of the shares of the words of length $g-1$ for every stacking if and only if every Swap defect $\Delta_v(F)$, $|v| = g-2$, is zero.

(d) For $g = 2$, with h and p_{hh} as free values,

$$\bar{F} = F(cc) + [F(ch) + F(hc) - 2F(cc)]\cdot h + \Delta\cdot p_{hh}, \quad \Delta = F(cc) + F(hh) - F(ch) - F(hc),$$

so $\bar{F}$ is a straight line in h for every stacking if and only if $\Delta = 0$, the Swap Rule.

Proof. (a) Group the positions i by the word they read: the word u occurs $n\cdot f_u$ times and contributes F(u) each time.

(b) Each occurrence of a word v of length $g-1$ is followed by exactly one letter and preceded by exactly one letter, and in a periodic word every occurrence of a word of length g contains one occurrence of its first $g-1$ letters and one of its last $g-1$. So $f_{vc} + f_{vh} = f_v = f_{cv} + f_{hv}$ (Kirchhoff's law for factor frequencies). There are 2^g shares and 2^{g-1} balance relations; the balance relations are the node equations of the de Bruijn graph B(2, $g-1$) (nodes: the 2^{g-1} words of length $g-1$; arrows: the words of length g), which is strongly connected, so its incidence matrix has rank $2^{g-1} - 1$: the relations add up to $0 = 0$ and are otherwise independent. $\Sigma\, f_u = 1$ is independent of them, since every combination of balance relations vanishes on the indicator of a cycle while the sum of shares does not. Together they have rank 2^{g-1}, leaving $2^g - 2^{g-1} = 2^{g-1}$ free values. To see that no further relation holds, read the words of length g as the arrows of the de Bruijn graph (from their first $g-1$ letters to their last $g-1$). The non-negative solutions of the relations are the circulations of total 1 on this graph; each is a mixture of simple cycles (the classical decomposition of a flow), and a simple cycle is the share vector of the periodic word that reads it. The de Bruijn word of order g has every share equal to 2^{-g}, a solution with no zero entry, so the solutions form a polytope of full dimension 2^{g-1} spanned by share vectors of stackings.

(c) If every Δ_v is zero, set A(xv) = F(xvc) and B(vy) = F(cvy) − F(cvc) for letters x, y. Then A(xv) + B(vy) − F(xvy) = F(xvc) + F(cvy) − F(cvc) − F(xvy), which is zero when x or y is c and equals $-\Delta_v = 0$ when x = y = h. So F(u) = A(first $g-1$ letters of u) + B(last $g-1$ letters), and by the balance relations $\bar{F} = \Sigma_{|w|\,=\,g-1}\, [A(w) + B(w)]\cdot f_w$. Conversely, suppose $\bar{F} = \Sigma_w\, L(w)\cdot f_w$ for every stacking (a constant term is L summed against $\Sigma\, f_w = 1$). Then G(u) = F(u) − L(first $g-1$ letters of u) has $\Sigma\, G(u)\, f_u = 0$ for every stacking, hence by (b) along every direction inside the polytope. For a fixed v the vector δ_v with +1 on cvc and hvh and −1 on cvh and hvc keeps every balance relation (each of the four end words cv, hv, vc, vh meets one +1 and one −1) and has total 0, so it is such a direction. Therefore $0 = \Sigma\, G\cdot\delta_v = \Delta_v(F) - [L(cv) + L(hv) - L(cv) - L(hv)] = \Delta_v(F)$. The 2^{g-2} defects are a complete set of invariants, so the condition is minimal: the functions of g letters form a space of dimension 2^g, the sums of a function of the first $g-1$ and a function of the last $g-1$ letters a subspace of dimension $2^{g-1} + 2^{g-1} - 2^{g-2}$ (the overlap is the functions of the middle $g-2$ letters), so the quotient has

dimension 2^{g-2}; the Δ_v, one for each v, vanish on that subspace and are independent, since each lives on its own four words.

(d) The balance relation at g = 2 gives $f_{ch} = f_{hc}$, and $h = f_{hc} + f_{hh}$, so $f_{cc} = 1 - 2h + p_{hh}$, $f_{ch} = f_{hc} = h - p_{hh}$, $f_{hh} = p_{hh}$. Put these into (a) and multiply out. The last claim is (c) with v empty; two real stackings show the "only if" directly: 4H (hc) and 12R (hhcc) both have h = 1/2, with $p_{hh} = 0$ and 1/4, so their means differ by $\Delta/4$. ∎

The theorem is elementary: (a) is a regrouping, (b) is Kirchhoff's law for factor frequencies, (c) is the statement that a two-by-two table is a sum of a row function and a column function exactly when its interaction term vanishes. The frame is classical in substance: factor frequencies and their balance relations are standard for Sturmian and other words (Dekking [2]; Berthé 1996 [3]; Balková and Pelantová [4]), criterion (c) is the cohomology of locally constant functions on the full shift, and in crystallography the theory of stacking disorder (Hendricks and Teller 1942 [5], Jagodzinski 1949 [1]) and the J_1–J_2 energies of polytype models (the ANNNI model [6]) express quantities through the correlations of a few neighbouring layers. The link to the stacking Hamiltonian is exact. Put $s = -1$ for c and $s = +1$ for h and write a pair quantity as $F(x, y) = \alpha + \beta\, s_x + \gamma\, s_y + \delta\, s_x s_y$; then $\Delta = 4\delta$, and (d) reads $\bar{F} = F_0 + (\beta + \gamma)\langle s\rangle + \delta\langle s_i s_{i+1}\rangle$ with $\langle s\rangle = 2h - 1$ and $\langle s_i s_{i+1}\rangle = 1 - 4h + 4p_{hh}$. So the Swap defect is four times the nearest-neighbour coupling J_1 of the stacking Hamiltonian written in c/h spins (in the Hägg spins σ of the ANNNI polytype model, $s_i = -\sigma_i\sigma_{i+1}$, so the same coupling is the J_2 term $\sigma_i\sigma_{i+2}$; Cheng, Needs and Heine 1988 [7]; Price and Yeomans [8]). For general g the Δ_v are the couplings that contain both end spins of the window. The Swap defect is therefore classical as an object; it is new as a name and as the bridge to DICTO's rules. What the theorem adds to DICTO's line of work is the exact form: one law, read one window at a time, with the Swap defect as the coefficient of the one new number at window 2.

3. Corollaries

Corollary 1 (the Hexagonality Law, g = 1). A quantity fixed by one layer has mean $F(c) + [F(h) - F(c)]\cdot h$: a straight line in the hexagonality, through its values in the pure cubic and the pure hexagonal stacking.

Corollary 2 (the Swap Rule as the test). A quantity fixed by two neighbouring layers is a straight line in h on all stackings if and only if it obeys the Swap Rule, $F(ch) + F(hc) = F(cc) + F(hh)$. If it fails, it is a plane in (h, p_{hh}) with slope Δ in p_{hh}, and no other number enters.

Corollary 3 (defects add). Δ_v is linear in F. If counts $F_1, \ldots, F_k$ by kind add up to a count that is a line in h (or a constant), their defects add up to zero. The counts of gaps of the three classes cc, mixed (ch or hc) and hh have defects +1, −2, +1.

Corollary 4 (same h, different stacking). Two stackings with the same h differ in a window-2 count by exactly $\Delta\cdot(p_{hh} - p'_{hh})$. At a given h the second number runs over $\max(0, 2h - 1) \le p_{hh} < h$ for every mixed periodic stacking (a stacking of period n with both letters has $p_{hh} \le h - 1/n$; the upper edge $p_{hh} = h$ is reached only by the pure stackings and

approached by long blocks of h), so a count with $\Delta \neq 0$ fills a band of width up to $|\Delta| \cdot (h - \max(0, 2h - 1))$ above each h.

Corollary 5 (the lower edge). The lower edge $p_{hh} = \max(0, 2h - 1)$ of that band is reached exactly by the stackings with no hh pair ($h \leq 1/2$) or no cc pair ($h \geq 1/2$). On it every window-2 count is a straight line in h on each side of $h = 1/2$, and the slope jumps there by exactly 2Δ.

Proof. Corollaries 1, 2 and 4 are parts (a) and (d). Corollary 3: Δ is a fixed combination of the values F(cc), F(ch), F(hc), F(hh), so it adds; the count of cc gaps has table (1, 0, 0, 0), the mixed gaps (0, 1, 1, 0), the hh gaps (0, 0, 0, 1). For the band: $f_{cc} = 1 - 2h + p_{hh} \geq 0$ and $f_{ch} = h - p_{hh} \geq 0$. Corollary 5: $p_{hh} = 0$ means $f_{hh} = 0$, and $p_{hh} = 2h - 1$ means $f_{cc} = 0$; the slope in h of $\bar{F}$ changes by $\Delta \cdot 2$ where p_{hh} turns from 0 to $2h - 1$. ∎

Corollary 1 is the Hexagonality Law for every count read from one layer. Corollary 2 marks its exact reach among pair counts: The Focus (#66) proved the direction "Swap Rule ⇒ line" for pieces and showed the two equivalent there; here the statement is for every pair count, with the defect Δ as the exact coefficient of the one number that enters when the rule fails; a pair count that breaks the Swap Rule needs one more number, and only one. Corollary 5 is the door to the approximants (Section 6): the balanced words of one-dimensional quasicrystal theory lie on this lower edge.




Figure 1. The Window Law in one picture. (a) Every two-letter stacking of the three families is a point in one triangle, the one number (h for perovskites; the share z of Z slabs or s of S rows for the Frank–Kasper families; the share a of S tiles in one dimension) against the share of neighbouring pairs of the second letter. Perovskite polytypes fill the triangle; the one-dimensional approximants of the Fibonacci chain lie on its lower edge max(0, 2a − 1) (gold), the Fibonacci chain at $(1/\varphi^2, 0)$; 4H and 12R, and the two 10H stackings, share an h and differ in p_{hh}. (b) For every count that is not a line in the one number, its distance from the line divided by its fixed coefficient, against the structure's second number: perovskites (9 counts on 555 stackings), the two Frank–Kasper families (26 and 16 window-2 counts per row or slab), the one-dimensional approximants (4 pair counts on 1101 approximants, measured from the chamber line), the Ammann–Beenker square approximants (5 vertex-star counts on 246 approximants, the second number being the forbidden star per vertex) and $\bar{Z}$ of 228 Frank–Kasper rows (the 199 structures computed here and the 29 site-count rows of the Dutour Sikirić–Delgado-Friedrichs–Deza table [9]) (the second number being the Yarmolyuk–Kripyakevich defect a_0). All lie exactly on the diagonal. (c) Close to zero: every approximant inside its chamber and every real phase has zero defect; the three hypothetical Frank–Kasper structures and the Ammann–Beenker approximants beyond the walls do not. Every point is exact and checked in the script before it is drawn.

How DICTO's rules fit together

The Window Law does not compete with DICTO's earlier rules; it is the frame in which each of them has its place. Ordered from the general to the particular:

1. **The Window Law** (the Main Theorem) holds for every quantity of every c/h stacking, with no geometry assumed: a count read from g layers is a line in the shares of the words of length g. It never fails; it only says how many numbers a count needs.
2. **The Rule of Halves** (#57) is geometry: every piece between two layers is made of a half borrowed from the lower layer's pure stacking and a half from the upper one's. So a count of *halves* is read from one layer (window 1), and a count of whole pieces from two (window 2).
3. **The Swap Rule** (#61) is geometry too: pieces change only by swapping halves, which makes the Swap defect Δ of every piece count zero. By Corollary 2 this is exactly what brings the window-2 piece counts down to window 1.
4. **The Hexagonality Law** (HexOct) is then the result: every count of halves, and every piece count that obeys the Swap Rule, is a straight line in hexagonality (Corollary 1).

So nothing takes precedence over anything else in the sense of overruling it: the Window Law is always true, and the Rule of Halves and the Swap Rule are the geometric facts that decide which window a count lives in. Where they hold, the Hexagonality Law follows; where a count escapes them (the perovskite counts of B with 0, 1 or 2 shared faces, the B–B shells), the Window Law says exactly which extra number it needs. This ordering is our reading of DICTO's rules.

4. Test ground 1: perovskite polytypes

In a hexagonal perovskite ABX_3 the A and X ions form close-packed AX_3 layers and B sits in the octahedral holes made of X only. We model X and A as equal balls (X–X = 1), A on a 2 × 2 sublattice of each layer. In each gap exactly one octahedral hole per cell avoids the A of the lower layer, and the A of the upper layer must avoid it too, which fixes its position: each c/h word gives exactly one perovskite, and the A pattern never doubles the period (checked on every stacking). Coordinates are integers in thirds of the lattice and quarters of the layer spacing, so $72 \cdot r^2 = 8(x^2 + xy + y^2) + 3z^2$ is an integer and every count is exact. The family: all 505 polytypes up to period 12 (every primitive c/h word up to turning over) and 50 random stackings of 48 layers from a two-state chain chosen so that h and p_{hh} vary independently, 555 stackings. Every quantity, per formula unit, was tested exactly over all 555 rows as a line in h, as a plane in (h, p_{hh}), and as a linear form in the shares of longer words.

Result. Of 36 quantities, 16 are lines in h (6 of them constants), 9 are planes in (h, p_{hh}), and 11 need windows of 3 to 6 layers. None needs anything outside the Window Law. Every one of the 6 per-gap quantities that pass the Swap test is a line in h, and every one of the 3 that fail is a plane with coefficient Δ, as Corollary 2 says.

quantity (per B = per ABX_3)	exact on all 555 stackings	window	status
Straight lines in h (Swap Rule holds)			
face-sharing partners; corner-sharing partners	2h; 6(1 − h)	1	known (#72; classical in substance)
X in a shared face (B–X–B = arccos 1/3) / on a straight B–X–B	share h / 1 − h	1	classical in substance
A in a cuboctahedron / anticuboctahedron	1 − h / h	1	classical
A neighbours of B ($r^2 = 3/2$); per-gap values cc 8, ch 7, hc 7, hh 6	8 − 2h	1	new (elementary)
B–B at $r^2 = 2/3, 2, 14/3$	2h, 6 − 6h, 12h	1	first two = face and corner counts; 14/3 new
face-sharing clusters (single octahedra included)	1 − h	1	new
Constants: the same in every stacking			
edge-sharing partners; neighbours of X; of A	0; 8 X + 4 A; 12 X	0	classical for 3C, here for every stacking
empty octahedral holes per gap	3, each A_2X_4 with the two A opposite ($r^2 = 2$)	0	new
tetrahedral holes per gap	8, each AX_3 (6 with A in the base, 2 with A at the tip)	0	new
Planes in (h, p_{hh}) (Swap Rule fails; coefficient of p_{hh} = Δ)			
B with 0 / 1 / 2 shared faces	1 − 2h + p_{hh} / 2h − 2p_{hh} / p_{hh} (Δ = +1, −2, +1)	2	new as stated
strings of two or more octahedra; single octahedra	h − p_{hh}; 1 − 2h + p_{hh}	2	new as stated
B–B at $r^2 = 8/3, 4, 20/3, 8$	2p_{hh}, 12 − 6p_{hh}, 12p_{hh}, 6 − 6p_{hh}	2	new
Longer windows			
B–B at $r^2 = 6, 22/3, 10, 34/3$ / at $r^2 = 32/3, 12$	linear in the shares of 3-layer / 4-layer words	3 / 4	new (window)
clusters of L octahedra (L = 2 … 5); octahedra in strings of 4 or more	share of the word c h^{L-1} c; 4-layer words	L + 1; 4	classical in substance (strings = runs of h)

Clusters (proof). The face-sharing octahedra form chains: one B per gap, and one shared face across each h layer. The pieces of a chain number octahedra minus shared faces, so clusters per B = 1 − h exactly in every stacking except 2H (one endless chain), and the mean cluster holds 1/(1 − h) octahedra: one number, though not a line. 9R (h = 2/3) has trimers, 1/3 per B; 12R (h = 1/2) a trimer and a single octahedron, 1/2 per B.

Holes (proof). The three corners of every hole triangle lie on three different A positions of the 2 × 2 pattern, and each layer has one A per cell. The B hole avoids the A of both its layers, so each of the other three octahedral holes takes exactly one A from each layer, and every tetrahedral hole exactly one A. This holds in every gap of every stacking: in the AX_3 net the kinds and numbers of holes do not see the stacking at all, so at the level of counts the Rule of Halves (#57) has nothing to mix here.




Figure 2. The perovskite splash, 555 stackings (dots: all polytypes up to period 12; rings: random stackings of 48 layers; gold diamonds: 3C, 2H, 4H, 6H, 9R). (a) Four counts lie exactly on straight lines in h. (b) The three kinds of B fill bands: h alone does not fix them (Corollary 4). (c) The same three, the strings and the B–B shell at $r^2 = 4$ fall exactly on the diagonal once p_{hh} is added. (d) Clusters of a given size need a window of size + 1 layers.

Real pairs. Corollary 4 at work on known compounds (sequences from Cava et al. [10], Jin et al. [11] and Adkin and Hayward [12]; Ramsdell symbols [13] recomputed from the letters, all eleven matching):

polytype	c/h	example	h	p_{hh}	face partners	B, 0 faces	B, 2 faces	clusters	strings
3C	c	$SrTiO_3$	0	0	0	1	0	1	0
2H	h	$BaNiO_3$	1	1	2	0	1	0	0
6H	hcc	hexagonal $BaTiO_3$	1/3	0	2/3	1/3	0	2/3	1/3
9R	hhc	$BaRuO_3$	2/3	1/3	4/3	0	1/3	1/3	1/3
4H	hc	4H-$BaRuO_3$, $SrMnO_3$	1/2	0	1	0	0	1/2	1/2
12R	hhcc	$Ba_4Fe_3NiO_{12}$	1/2	1/4	1	1/4	1/4	1/2	1/4
10H	hhhcc	$Ba_5Sb_{1-x}Mn_{4+x}O_{15}$	3/5	2/5	6/5	1/5	2/5	2/5	1/5
10H′	hhchc	$Ba_5Fe_4NiO_{13.5}$	3/5	1/5	6/5	0	1/5	2/5	2/5
8H	hhhc	$BaMnO_{3-x}$	3/4	1/2	3/2	0	1/2	1/4	1/4
15R	hhhhc	$BaMnO_{3-x}$	4/5	3/5	8/5	0	3/5	1/5	1/5
5H	hhccc	$Ba_5Ta_4O_{15}$	2/5	1/5	4/5	2/5	1/5	3/5	1/5

4H and 12R share h = 1/2, so they share every window-1 count (face partners 1, clusters 1/2), and differ by $p_{hh} = 1/4$ in every window-2 count, by exactly Δ/4: B with no shared face 0 against 1/4 (Δ = +1), strings 1/2 against 1/4 (Δ = −1). The two 10H stackings (tetramers; trimers and dimers) share h = 3/5 and differ by 1/5 in p_{hh}, with the same signs. In 2H the

octahedra form one endless chain, so its clusters and strings per B are 0. The constant rows of the table for neighbours of X and of A were checked separately on all 505 bracelets, with 0 exceptions. Real compounds with vacancies or two kinds of B are modelled by their stacking only.

5. Test ground 2: Frank–Kasper phases

A Frank–Kasper (tetrahedrally close-packed) structure is cut by its atoms into tetrahedra only. Each atom has Z = 12, 14, 15 or 16 neighbours (its Delaunay neighbours), every bond is shared by 5 or 6 tetrahedra, and Z = 12 + (number of six-fold bonds at the atom). The six-fold bonds form Frank and Kasper's major skeleton [14, 15], Nelson's disclination network [16]. We read the topology of 18 real phases from published coordinates (AFLOW prototype encyclopedia [17] and the Crystallography Open Database [18]) by a periodic Delaunay step, and checked every site: closed triangulated shell with Euler number 2, folds 5 or 6, Z = 12 + #six-fold bonds, no two six-fold neighbours adjacent in a shell. Every count after that is an integer and every test exact. Four candidates fail the check and are not tetrahedrally close-packed: χ (α-Mn) and $Mg_{17}Al_{12}$ (bonds shared by 4 tetrahedra), $Mg_{23}Al_{30}$ and $Mg_{21}Zn_{25}$. Two layered families give the spread: square–triangle rows (Sullivan [19]; Sadoc and Mosseri 2016 [20]; S = A15, T = Z, ST = H, STT = J; all 62 words checked, all primitive words up to length 7 and 30 random words of 20 rows) and kagome slabs (Frank and Kasper 1959 [15]; a step ± is a Laves slab of 6 atoms, a step 0 a Z slab of 7 atoms; + = C15, +− = C14, 0 = Z, 0+ = μ, 0+0− = K_7Cs_6; all 119 words checked, all words up to length 6 and 40 random words of 14 slabs). In all, 199 structures.

> **The identities (classical; exact on all 199).** Per atom, with ρ = six-fold bonds per atom: $\bar{Z} = 12 + 2\rho$, bonds = 6 + ρ, five-fold bonds = 6, tetrahedra = 5 + ρ, triangles = 10 + 2ρ. A tetrahedron has 0, 1 or 2 six-fold edges, and two only when they are opposite.

An atom has 12 five-fold bonds whatever its Z, and its shell has 2Z − 4 triangles, which gives the identities; two six-fold edges at one corner would make adjacent six-fold vertices in that corner's shell. So one number, the disclination density ρ, fixes every topological count per atom, by identity. This is Frank and Kasper's [14, 15] and Nelson's [16] picture, not new.

> **The Yarmolyuk–Kripyakevich line and its defect.** With x_Z the share of sites of coordination Z and $a_0 = x_{12} - x_{14}/3 - 7x_{15}/6 - 2x_{16}$, every structure satisfies
>
> $$\bar{Z} = 68/5 - (2/5)\cdot x_{12} - (6/5)\cdot a_0.$$
>
> On the plane $a_0 = 0$ ($6N_{12} = 2N_{14} + 7N_{15} + 12N_{16}$, Yarmolyuk and Kripyakevich 1974 [21]) this is $\bar{Z} = 66/5 + (2/5)\cdot m$ with $m = 1 - x_{12}$, $\rho = (3 + m)/5$, and $40/3 \le \bar{Z} \le 27/2$.

Proof. Expand both sides with $x_{12} + x_{14} + x_{15} + x_{16} = 1$. The plane $a_0 = 0$ meets the simplex of shares in a triangle with corners A15 ($\bar{Z} = 27/2$), C15 (40/3) and the point Z12 : Z15 = 7 : 6 (174/13), and $\bar{Z}$ is linear, which gives Frank and Kasper's range. ∎

The study plan's candidate for a "hexagonality of tetrahedral packing" (ours, not DICTO's), the non-icosahedral share m, works on every real phase computed (18), on the 13 further known structures tabulated by Deza, Delgado Friedrichs and Dutour Sikirić [9], and in both layered families, where it is a theorem: the units are rows (S = 2 A15 units, T = 1 Z unit) or

slabs (± = 2 Laves units, 0 = 1 Z unit). But the line is old: $\bar{Z} = 13.6 - 0.4 \cdot x_{12}$ is equivalent to Yarmolyuk and Kripyakevich's relation of 1974 (see also Shoemaker and Shoemaker 1986 [22]), and it is not a law of all Frank–Kasper structures: the computer search of Dutour Sikirić, Delgado Friedrichs and Deza (2010) [9] found three hypothetical structures off it, 7:4:2:2, 6:6:4:0 and 6:8:4:0 (N_{12}:N_{14}:N_{15}:N_{16}; counts read from the authors' talk "Space fullerenes" [23], the paper being embargoed), with $a_0 = -2/45, -1/24, -2/27$. They leave the line only through a_0, by exactly $-(6/5)a_0$; the third has $\bar{Z} = 122/9 > 13½$. This is the shape of the Window Law, a line in one number plus a fixed coefficient times one defect, with a_0 in the place of the Swap defect term. Here it is an identity of the shares, not an instance of the theorem, since a general Frank–Kasper structure is not a layer sequence.

The Window Law in the layered families (exact on 62 and 119 stackings). Per tile row or per kagome slab, every site and topological count is a line in the share s of S rows or z of Z slabs (window 1): sites S 8, T 7, ± 6, 0 7; Z12 S 2, T 3, ± 4, 0 3; tetrahedra S 46, T 40, ± 34, 0 40; six-fold bonds S 6, T 5, ± 4, 0 5 (the composition matrices of Sadoc and Mosseri and of the Laves/Z intergrowth picture, both known). Every count by kind (bonds by end types, neighbour types, rings of six-fold bonds, tetrahedra by corner types) is fixed by neighbouring pairs of units (window 2), and none needs more. Every window-2 count fails the Swap Rule, and the defects come in the pattern +1, −2, +1 (times a whole number) over the three end-type classes, whose sum, a window-1 count, is a line (Corollary 3):

count (per row or slab)	square–triangle (S/T)	Δ	kagome (Laves L / Z)	Δ
six-fold bonds by end types: S/T Z14–Z14, Z14–Z15, Z15–Z15; L/Z Z14–Z14, Z14–Z16, Z16–Z16	2 + 3s + p, 2s − 2p, 3 − 4s + p (sum 5 + s)	+1, −2, +1	z + p, 2z − 2p, 4 − 5z + p; with Z15–Z15 = 3z (window 1) and Z14–Z15 = 0, sum 4 + z	+1, −2, +1
neighbours of the same pairs (ordered)		+2, −2, −2, +2		+2, −2, −2, +2
tetrahedra 2444, 2445, 2455 (S/T); 2266, 2246, 2244 (L/Z)	36s + 4p, 8s − 8p, …	+4, −8, +4	24 − 30z + 6p, 12z − 12p, 6p	+6, −12, +6
tetrahedra 4444, 4445, 4455 (two opposite six-fold edges)	4s + 2p, …	+2, −4, +2	only 4455: 6z	0

(p: share of neighbouring SS or 00 pairs. Tetrahedron kinds by corners, 2 = Z12, 4 = Z14, 5 = Z15, 6 = Z16.) That the defects sum to zero is Corollary 3; that every window-2 count of both families carries exactly this pattern is observed (catalogue new). **Stacking-blindness:** 22 Z/L patterns of the kagome family are realised by two or more different Laves stackings, and for each all 119 census keys per slab agree (new as stated; elementary). No count of the census sees whether a Laves slab sits cubic or hexagonal: C15, C14, C36, 9R and the long-period Laves phases have one census per atom, and so do μ and K_7Cs_6. Here the two letters that matter are L and Z, and the c/h letter is invisible.

phase	compound (source)	N	Z12:Z14:Z15:Z16	$\bar{Z}$	ρ	YK units A15 + L + Z
A15	Cr_3Si (AFLOW)	8	2:6:0:0	27/2	3/4	2 + 0 + 0
seven Laves: C15, C14, ternary C14, C36, 9R, 9-layer (Ag), long period (Ag)	$MgCu_2$, $MgZn_2$, U_2Cr_3Si, $MgNi_2$ (AFLOW); $Mg(Li,Zn)_2$, $Mg(Zn,Ag)_2$ (COD)	12–126	2:0:0:1	40/3	2/3	0 + N/3 + 0
Z	Zr_4Al_3 (AFLOW)	7	3:2:2:0	94/7	5/7	0 + 0 + 1
σ	CrFe type (AFLOW; COD 2106167)	30	10:16:4:0	202/15	11/15	4 + 0 + 2
μ	W_6Fe_7 (AFLOW)	39	21:6:6:6	174/13	9/13	0 + 6 + 3
δ, P	MoNi (COD 2310246); Mo–Ni–Cr (COD 2311049)	56	24:20:8:4	94/7	5/7	4 + 4 + 4
R	Mo–Co–Cr, $Mn_{85.5}Si_{14.5}$ (COD 2310299, 2107202)	159	81:36:18:24	710/53	37/53	6 + 24 + 9
ν	$Mn_{81.5}Si_{18.5}$ (COD 2106034)	186	74:80:20:12	1250/93	67/93	20 + 12 + 10
T (Bergman)	$Mg_{32}(Al,Zn)_{49}$ (AFLOW)	162	98:12:12:40	1082/81	55/81	0 + 40 + 6

All 18 real phases have $a_0 = 0$ and are whole sums of the three YK units (a known structural formula). Z, δ and P share $x_{12} = 3/7$ and so share $\bar{Z} = 94/7$, as the line demands, though their shares of Z14, Z15 and Z16 differ.

One relation observed, not explained. Let σ be the number of six-fold bonds inside an atom's coordination shell. On all 18 real phases and all 181 family members,

$$\Sigma_{\text{Z14 sites}} (\sigma - 4) + 2 \cdot \Sigma_{\text{Z12 sites}} (6 - \sigma) = 8 \cdot N_{15}.$$

The identities fix only $\Sigma\sigma = 6\rho N$, so this is an independent relation: one of the four exact relations of the census beyond the identities and YK (the census matrix of all 199 structures has rank 8 where these leave 12; data/relations2.txt), determined only modulo YK. It is stated here as observed: every structure with coordinates lies on the YK plane, so the relation is fixed only up to a multiple of YK, and it cannot be tested on the three hypothetical structures, whose coordinates were not in reach.




Figure 3. The Frank–Kasper splash, 199 tetrahedrally close-packed structures. (a) $\bar{Z}$ against the icosahedral share: every real phase (black squares), every listed known phase (open diamonds) and both families lie on the YK line; three hypothetical structures (red crosses) do not. (b) Their distance from the line is exactly $-(6/5)$ times the YK defect a_0. (c) Kagome family, per slab: site counts and six-fold bonds are lines in the share z of Z slabs. (d) The Z16–Z16 six-fold bonds per slab fill a band against the line $4 - 5z$ and fall exactly on the diagonal once the share p_{00} of neighbouring Z-slab pairs is added: $4 - 5z + p_{00}$.

6. Test ground 3: quasicrystal approximants

All three families are cut-and-project sets: lattice points of Z^n in a strip around a space E are kept and projected. The quasicrystal takes an irrational E; an approximant replaces the irrational number by a fraction, and the pattern repeats. We used the canonical strip and a generic offset and counted everything per period, exactly: in one dimension the words $s_n = \lfloor(n+1)a + r\rfloor - \lfloor na + r\rfloor$ (S for 1, L for 0, a = share of S) for all 1101 fractions $0 < a = p/q < 1$ with $q \le 60$ and windows g = 1 to 9, and the Fibonacci chain $a = 1/\varphi^2$ in exact arithmetic in $Q(\sqrt{5})$; in two dimensions the Ammann–Beenker (AB) square approximants, $\sqrt{2}/2$ replaced by $t = a/b$, all 246 fractions $1/2 \le t \le 1$ with $b \le 40$ and the Pell ones up to 99/140, the limit in $Q(\sqrt{2})$; in three dimensions the cubic approximants of the 3D Penrose tiling, φ replaced by F_{k+1}/F_k from 1/1 to 55/34. Two facts hold throughout and were checked on every run: the number of tiles of each kind per period is the absolute value of a minor of a basis of the period lattice (its Plücker coordinate), and vertices equal tiles in number.

One dimension. The S/L words are two-letter stackings, and the Window Law applies as it stands, with S in the place of h. For every window length g and every word w of length g, the share of w in the approximant p/q is a straight line in a on each interval between neighbouring fractions with denominator ≤ g, bending only at those fractions; on the interval containing $1/\varphi^2$ the Fibonacci chain lies on the same line; there are at most three distinct

shares per length and g + 1 words of each length g. This is classical (Morse and Hedlund 1940 [24]; Berthé 1996 [3]; the three-distance theorem) and was checked on all 1101 approximants for g ≤ 9. Two readings are ours. First, the approximants lie on the lower edge of the Window-Law plane (Corollary 5): $p_{SS} = \max(0, 2a - 1)$, the smallest share of SS pairs any word with this a can have. Of the 747 primitive periodic words up to 12 letters, 157 lie on this edge (every word with no SS when a ≤ 1/2, or no LL when a ≥ 1/2) and 590 above it; of the 157, only 47 are balanced, and these are the approximants (Christoffel words). Zero defect at window 2 is therefore necessary, not sufficient: what singles out the approximants is that they stay on the quasicrystal's chamber line window after window, up to a length that grows with the period (below). So every pair count of an approximant is a line in a on each side of 1/2, and its kink at 1/2 is exactly 2Δ: twice the Swap defect. Second, on the Fibonacci side a < 1/2 the defect term is zero for every approximant, not only in the limit: SS never occurs, as in the Fibonacci stacking of #69. Longer windows kink with the denominator as factor: at window 3 the vector +3, −3, −3, +3 at 1/3 on LLL, LLS, SLL, SLS. The approximant F_{n-2}/F_n lies on the chain's window-g line exactly when $g < F_{n+2}$ (checked for g ≤ 300), and its share then differs from the chain's by the slope times $p/q - 1/\varphi^2$, the phason strain.

window	chamber of $1/\varphi^2$	shares on it (lines in a) and their values at $a = 1/\varphi^2$	Fibonacci convergents on the line
1	[0, 1]	S: $a = (3 - \sqrt{5})/2$; L: $1 - a$	all
2	[0, 1/2]	LS = SL: a; LL: $1 - 2a = \sqrt{5} - 2$; SS: 0	1/2 and every later one
3	[1/3, 1/2]	LLS = SLL: $1 - 2a = \sqrt{5} - 2$; LSL: a; SLS: $3a - 1 = (7 - 3\sqrt{5})/2$	1/2 and every later one
5	[1/3, 2/5]	adds LLSLL: $2 - 5a = (5\sqrt{5} - 11)/2$	1/3 and every later one
8, 9	[3/8, 2/5]	three values: $2 - 5a$, $3a - 1$, $8a - 3 = 9 - 4\sqrt{5}$	2/5 and every later one

The convergents of $1/\varphi^2$ are F_{n-2}/F_n = 1/2, 1/3, 2/5, 3/8, 5/13, …; F_{n-2}/F_n is on the window-g line exactly when $g < F_{n+2}$. A convergent at an end of the chamber (1/2 at window 2 and 3, 1/3 at window 5, 2/5 at windows 8 and 9) is on the line by continuity.




Figure 4. The approximants splash. (a) Window 2 in one dimension: share of SS pairs against the share a of S tiles for all 747 primitive periodic words up to 12 letters: 590 above the lower edge max(0, 2a − 1) (grey), 110 on it but not balanced (black), and the 47 approximants (gold, also on the edge); the Fibonacci chain sits at $(1/\varphi^2, 0)$. (b) Window 3: the share of every triple in every approximant p/q, q ≤ 60, lies on straight lines that bend only at 1/3, 1/2 and 2/3. (c) Ammann–Beenker square approximants inside the chamber 2/3 ≤ t ≤ 3/4: each vertex-star frequency minus its AB value, against the square share minus (√2 − 1); six straight lines through the origin. (d) The forbidden star: none inside the chamber, a square law outside.

> **The Ammann–Beenker chamber (exact on all 42 square approximants with 2/3 ≤ t ≤ 3/4, b ≤ 40, and on the Pell ones up to 99/140).** With R rhombs and Q squares per period, the six vertex stars occur
>
> $$\text{F (3 edges)} = Q,\ \text{E (4)} = 2R - 2Q,\ \text{D (5)} = -4R + 6Q,\ \text{C (6)} = 10R - 14Q,\ \text{B (7)} = -12R + 17Q,\ \text{A (8)} = 5R - 7Q,$$
>
> and no other star occurs. Per vertex these are straight lines in the square share $q = Q/(R + Q)$, and at $q = \sqrt{2} - 1$ they give exactly the AB frequencies $\sqrt{2} - 1$, $6 - 4\sqrt{2}$, $10\sqrt{2} - 14$, $34 - 24\sqrt{2}$, $29\sqrt{2} - 41$, $17 - 12\sqrt{2}$.

The share of squares plays the part of the hexagonality: one number, every count a line, the quasicrystal on every line. The 9 kinds of edge counted by the stars at their two ends are lines on the same chamber (for example F–E edges $4R - 4Q$, D–D edges $-2R + 3Q$). The counts do not depend on the offset of the strip. Example, t = 5/7: 239 vertices per period, R = 140, Q = 99, stars A 7, B 3, C 14, D 34, E 82, F 99. The vertex counts of the Pell approximants are tabulated by Jagannathan and Duneau [25] (2023, Table 1), and our counts reproduce them; the laws on the whole chamber, for all 42 approximants and not only the Pell ones, were not found and are new.

> **The walls and the defect (exact on all 246 square approximants, 1722 counts).** Outside the chamber a seventh star X appears, six edges with two squares side by side at the vertex, which the AB tiling never has. Per normalising cell of $N_u = b^2 + 4ab + 2a^2$ vertices ($R = 4ab$ rhombs and $Q = b^2 + 2a^2$ squares; for even b one period holds half of this cell),
>
> $$X = 2(3a - 2b)^2 \text{ for } t = a/b < 2/3, \quad X = (4a - 3b)^2 \text{ for } t > 3/4, \quad X = 0 \text{ inside},$$
>
> and every count is its chamber line plus a fixed multiple of X: (F, E, D, C, B, A, X) shift by $\kappa = (0, 0, -1, +2, -3, +1, +1)\cdot X$.

This is the Window-Law shape again: a line in one number plus a defect with a fixed coefficient vector, the two-dimensional counterpart of the pattern +1, −2, +1 (κ also sums to zero, since the vertices still number R + Q). The new feature is the square: in one dimension the forbidden SS pairs grow linearly beyond the wall (2a − 1), in two dimensions the forbidden star grows quadratically, because its acceptance domain is born at a point and grows in two directions. The walls are the Pell approximant 2/3 and its partner 3/4 = 1/(2·2/3). For rational planes without the four-fold symmetry the vertex counts are not fixed by the plane: on 229 of 240 random planes moving the strip changes them (a row of phason flips), which is known in substance; the one-number law belongs to the square approximants, the ones used in practice.

Three dimensions (tile counts). For the cubic approximant $\varphi \approx p/q$, the cubic cell holds prolate $= 4(p^3 + 3p^2q + q^3)$ and oblate $= 4(p^3 + 3pq^2 - q^3)$ rhombohedra, and as many vertices as rhombohedra; at $p/q = \varphi$ the ratio is $\varphi : 1$. The prolate share of the approximant F_{k+1}/F_k is the Fibonacci ratio F_{3k+2}/F_{3k+3} (all nine computed): the 3D approximants carry the 1D approximants of $1/\varphi$ in their tile counts, three steps at a time. The 1/1 and 2/1 counts are known (Elser and Henley 1985 [26]; Henley [27]; Duneau, Mosseri and Oguey 1989 [28]); the closed formula in p and q was not found in the sources checked; the method (minors) is classical. Tile counts are window 1, so they are lines in the prolate share by definition; the vertex types were not computed.

approximant	1/1	2/1	3/2	5/3	8/5	13/8	21/13
prolate + oblate per cubic cell	20 + 12	84 + 52	356 + 220	1508 + 932	6388 + 3948	27060 + 16724	114628 + 70844
prolate share	5/8	21/34	89/144	377/610	1597/2584	6765/10946	28657/46368

7. What is known and what is new

result	exact on	status
The law		
Window Law (a), (b): means linear in word shares, Kirchhoff relations, 2^{g-1} free values	proof	classical in substance (factor frequencies; stacking disorder; J_1–J_2 polytype energies)
Window Law (c), (d): window drops exactly when the Swap defects vanish; Δ is the coefficient of p_{hh}	proof	elementary; criterion classical in substance (cohomology on the shift); $\Delta = 4J_1$ in c/h spins (J_2 in Hägg spins): classical as an object, new as a name and as the bridge to DICTO's rules
Swap Rule ⇔ line in h for pieces fixed by two layers	proof	#66 (DICTO's line of work); count form with coefficient Δ here
Perovskites		
face 2h, corner 6(1 − h) per B	555	known (#72; classical in substance)
clusters per B 1 − h; A per B 8 − 2h; same holes in every gap; B with 0/1/2 faces, strings; B–B shells and their windows	555	new
Frank–Kasper phases		
identities in ρ; tetrahedra with 0, 1, 2 six-fold edges	199	classical (Frank and Kasper [14, 15]; Nelson [16])
YK line; real phases as sums of YK units	18 + 13 + families	known (Yarmolyuk and Kripyakevich 1974 [21]; Gvozdetskyi et al. 2014 [29])
$\bar{Z} = 68/5 - (2/5)x_{12} - (6/5)a_0$; counterexamples off the line through a_0 only	identity; 3	elementary; counterexamples from Dutour Sikirić et al. 2010 [9]; reading as the Window-Law shape ours
window-1 composition of rows and slabs	62 + 119	known (Sadoc and Mosseri [20]; Laves/Z intergrowth)
window-2 catalogue with defects +1, −2, +1; stacking-blindness to the Laves c/h letter	62 + 119	new (catalogue); new as stated, elementary (blindness)
shell relation $\Sigma_{Z14}(\sigma - 4) + 2\Sigma_{Z12}(6 - \sigma) = 8N_{15}$	199	observed, unexplained
Approximants		
1D: Farey lines, three values, complexity g + 1	1101, g ≤ 9	classical (Morse–Hedlund [24]; Berthé 1996 [3])
1D: F_{n-2}/F_n on the window-g line iff g < F_{n+2}; offset = slope × phason strain	g ≤ 300	known in substance; this statement not found
1D: approximants on the lower edge (157 of 747 words lie there, 47 balanced = approximants); kink at 1/2 = 2Δ	747 words	elementary; ours as framing
tile counts = Plücker coordinates; AB frequencies; Pell-approximant counts	all	known (canonical projection; Baake–Grimm [30]; Jagannathan–Duneau 2023 [25])
AB: six star laws on the whole chamber 2/3 ≤ t ≤ 3/4; walls; defect star X and its vector κ	42; 246	new (exact, computed)
3D: prolate $4(p^3 + 3p^2q + q^3)$, oblate $4(p^3 + 3pq^2 - q^3)$; prolate share F_{3k+2}/F_{3k+3}	9	1/1, 2/1 counts known (Elser and Henley 1985 [26]); closed formula not found; method classical

8. Conclusion

What the law is. The Window Law is a general frame, and an elementary one: whatever a stacking's layers fix through a window of g layers averages to a linear function of the shares of the words of length g, and the window narrows exactly where the Swap defects vanish. DICTO's Hexagonality Law is its first step, the window of one layer, and DICTO's Swap Rule is the condition for a pair count to stay on it. Nothing in three kinds of crystal needed more than this frame.

What it adds. The Swap-defect reading, carried across three kinds of crystal: the coefficient of the one new number at window 2 is the Swap defect; the same pattern +1, −2, +1 marks the kinds of B in a perovskite and the kinds of bond and tetrahedron in the layered Frank–Kasper phases; the Yarmolyuk–Kripyakevich line is left only through one defect, in the same shape; and in the approximants the defect is a kink of twice the Swap defect in one dimension and a forbidden star with a fixed transfer vector in two. Alongside, specific new exact counts: clusters per B = 1 − h, A per B = 8 − 2h, the stacking-blind holes and the B–B shells of the perovskites; the window-2 catalogue and the stacking-blindness of the Frank–Kasper families; the Ammann–Beenker chamber laws, walls and defect; the cubic-cell tile formulas of the 3D approximants.

The bridge. DICTO's aim is a bridge between periodic and aperiodic order. The Window Law gives one plank of it: the periodic approximants of a quasicrystal carry zero defect on the chamber that holds the quasicrystal, window after window up to a length that grows with their period (zero defect at window 2 alone is shared by 110 other words up to 12 letters, whose shares part from the approximant's of the same share a at some longer window, since a periodic word is fixed by its factors), so every count of every approximant there lies on one straight line in the share of one tile, and the never-repeating limit lies on the same line. The defect does not shrink towards the limit; inside the chamber it is already zero, and what shrinks is only the distance along the line, the phason strain.

> **Sources checked** (31 October 2026; every query and page with its outcome is listed in the three study folders, README.md). *Reference library* (ask-library, 19 queries). Perovskite study, 4 queries (hexagonal perovskite polytypes and face-sharing share; Katz–Ward and Jagodzinski notation; stacking-disorder correlations; face-sharing clusters): Keller et al. 2023 (Si/Ge polytypes, hexagonality, generalized Ising model); Kawanishi and Mizoguchi 2015 (SiC hexagonality); Yi and Canright 1995; Ganesh and Nasr 2023 (correlations between layers n apart through a one-dimensional Ising model); Hart, Hansen and Kuhs 2021 (Markov description of stacking disorder); Rodriguez-Horta et al. 2017; none treats the B network of perovskites. Frank–Kasper study, 6 queries (Frank–Kasper polyhedra Z14–Z16; Yarmolyuk–Kripyakevich mean coordination; disclination network, Nelson; space fullerenes; Shoemaker kagome layers σ μ Laves; Sadoc–Mosseri decoration): no Frank–Kasper paper in the library; hits Kallus–Elser, Haji-Akbari et al. 2009, Papadopolos–Ogievetsky 1999, Koca et al. 2020; Sadoc and Mosseri 2016 catalogue entry only. Approximants study, 7 queries (Sturmian factor frequencies, three distance; periodic approximants, cut and project; AB vertex frequencies; Penrose vertex types, de Bruijn; phason strain; icosahedral cubic approximant 1/1; Christoffel words): read Kléman 2013 (pp. 1–5), Baake 1999 guide (§13), Hann, Socolar and Steinhardt 2016 (p. 3); catalogue only Goldman and Kelton 1993, Yamada et al. 2021, de Bruijn 1981, Fujita et al. 2013, Kramer 2011, Akiyama et al. 2026. For this paper, 2 queries ("frequencies of words of length n satisfy consistency relations, de Bruijn graph circulations": no relevant source; "stacking fault energy ANNNI J1 J2 polytypes hexagonality linear": Hart, Hansen and Kuhs 2021 only). *Web, read:* Cava et al., Hexagonal perovskites as quantum materials, arXiv 2006.05864; Sadoc and Mosseri, arXiv 1609.01624 (pp. 1–7); Deza, Delgado Friedrichs and Dutour Sikirić, talk "Space fullerenes" (table of known structures, the YK conjecture $a_0 = 0$ and its counterexamples); Gvozdetskyi, Gladyshevskii and Hlukhyy, Chem. Met. Alloys 7 (2014) (YK equations, structural formula); Jagannathan and Duneau, Properties of the Ammann–Beenker tiling and its square approximants, arXiv 2308.07701 (§§2.2, 3, 3.1, 3.2; Table 1 = our Pell counts). *Web, abstract or summary only:* Darriet and Subramanian, J. Mater. Chem. 5, 543 (1995); Adkin and Hayward, Chem. Mater. 19, 755 (2007); Jin et al., PNAS 105, 7115 (2008); arXiv 2105.05206; Dutour Sikirić, Delgado Friedrichs and Deza, Acta Cryst. A66, 602 (2010) (PDF embargoed); Berthé, Theor. Comput. Sci. 165 (1996) 295–309 (bibliographic entry and citing surveys); arXiv 1009.0136, 2212.09406; cond-mat/0402370, 2108.03341, cond-mat/0405298 (two queries on 1/1 tile counts, no source gives them); for this paper, one query on Kirchhoff's law for factor frequencies: Balková and Pelantová, arXiv 0902.0632, and Balková, arXiv 1107.0471 and 1107.5033 (search summaries: Kirchhoff's law for factor frequencies on Rauzy graphs, attributed to Dekking and Berthé). *Not reachable:* Katz and Ward, Inorg. Chem. 3, 205 (1964), cited through Cava et al. *Classical, cited not read:* Cheng, Needs and

Heine, J. Phys. C 21, 1049 (1988); Price and Yeomans (ANNNI polytypes); Shoemaker and Shoemaker, Acta Cryst. B42, 3 (1986); Elser and Henley, Phys. Rev. Lett. 55, 2883 (1985); Henley; Hendricks and Teller 1942; Jagodzinski 1949; the ANNNI model of polytypes (J_1, J_2, J_3); Frank and Kasper 1958, 1959; Nelson 1983; Nelson and Spaepen 1989; Yarmolyuk and Kripyakevich 1974; Sinha 1972; Sullivan; Hellner and Pearson; Rivier and Aste 1996; Morse and Hedlund 1940; Lothaire; de Bruijn 1981; Baake and Grimm, Aperiodic Order vol. 1 (2013); Duneau, Mosseri and Oguey 1989; Katz 1988. *In-house:* #57, #61, #64, #66, #69, #72 and the HexOct book, cited for their results.

References. DICTO, The Rule of Halves (#57), DICTO DOI 10.5281/zenodo.23647898; The Swap Rule (#61), 10.5281/zenodo.23682596; The Swap Rule in Crystals (#64), 10.5281/zenodo.23709753; The Focus (#66), 10.5281/zenodo.23717687; The Hexagonality Law and the Fibonacci Stacking (#69), 10.5281/zenodo.23721038; The Hexagonality Law in Real Materials IV (#72), 10.5281/zenodo.23728287; HexOct: The Hexagonality Law (book), 10.5281/zenodo.23731359.

Data and code. Studies 2026-10-31-splash2-perovskite (perov.py exact model, splash.py, data/splash2_perovskite.json: all 555 stackings, every quantity exact), 2026-10-31-splash2-frank-kasper (fk.py census engine, sqtri.py, fk59.py, splash.py, report.py, relations*.py; data/splash2_fk.json, results.md, cif/) and 2026-10-31-splash2-approximants (qf.py, zono.py, sturm.py, ab.py, ablaw.py, abfam.py, ico.py; data/*.json, *.log). Figure 1: papers/window-law/scripts/fig_window_law.py, which re-checks every plotted point exactly against its law; Figure 4: papers/window-law/scripts/fig_approximants.py (the study's figure script, panel (a) redrawn with all 747 words and the 157 on the edge asserted). Exact arithmetic (fractions, Q(√2), Q(√5)) throughout; floats only in the Delaunay step of the Frank–Kasper engine and in drawing. Run on dicto-big-brother.

References

Outside works cited in the text, numbered in order of first citation; DICTO's own papers are listed above. Every entry was checked against the publisher's or Crossref's record on 1 November 2026, except where the entry says otherwise.

1. H. Jagodzinski, Eindimensionale Fehlordnung in Kristallen und ihr Einfluss auf die Röntgeninterferenzen. I. Berechnung des Fehlordnungsgrades aus den Röntgenintensitäten, *Acta Crystallographica* 2 (1949) 201–207. DOI 10.1107/S0365110X49000552.
2. F. M. Dekking, On the Thue–Morse measure, *Acta Universitatis Carolinae, Mathematica et Physica* 33 (1992) 35–40. No DOI; data as cited in Balková and Pelantová (2009).
3. V. Berthé, Fréquences des facteurs des suites sturmiennes, *Theoretical Computer Science* 165 (1996) 295–309. DOI 10.1016/0304-3975(95)00224-3.
4. L. Balková and E. Pelantová, A note on symmetries in the Rauzy graph and factor frequencies, *Theoretical Computer Science* 410 (2009) 2779–2783. DOI 10.1016/j.tcs.2009.04.002; arXiv 0902.0632.
5. S. Hendricks and E. Teller, X-ray interference in partially ordered layer lattices, *Journal of Chemical Physics* 10 (1942) 147–167. DOI 10.1063/1.1723678.
6. W. Selke, The ANNNI model — theoretical analysis and experimental application, *Physics Reports* 170 (1988) 213–264. DOI 10.1016/0370-1573(88)90140-8.
7. C. Cheng, R. J. Needs and V. Heine, Inter-layer interactions and the origin of SiC polytypes, *Journal of Physics C: Solid State Physics* 21 (1988) 1049–1063. DOI 10.1088/0022-3719/21/6/012.
8. G. D. Price and J. Yeomans, The application of the ANNNI model to polytypic behaviour, *Acta Crystallographica B* 40 (1984) 448–454. DOI 10.1107/S0108768184002469.
9. M. Dutour Sikirić, O. Delgado-Friedrichs and M. Deza, Space fullerenes: a computer search for new Frank–Kasper structures, *Acta Crystallographica A* 66 (2010) 602–615. DOI 10.1107/S0108767310022932.
10. L. T. Nguyen and R. J. Cava, Hexagonal perovskites as quantum materials, *Chemical Reviews* 121 (2021) 2935–2965. DOI 10.1021/acs.chemrev.0c00622; arXiv 2006.05864 (cited in the text as Cava et al.).
11. C.-Q. Jin, J.-S. Zhou, J. B. Goodenough, Q. Q. Liu, J. G. Zhao, L. X. Yang, Y. Yu, R. C. Yu, T. Katsura, A. Shatskiy and E. Ito, High-pressure synthesis of the cubic perovskite $BaRuO_3$ and evolution of ferromagnetism in $ARuO_3$ (A = Ca, Sr, Ba) ruthenates, *Proceedings of the National Academy of Sciences USA* 105 (2008) 7115–7119. DOI 10.1073/pnas.0710928105.

12. J. J. Adkin and M. A. Hayward, $BaMnO_{3-x}$ revisited: a structural and magnetic study, *Chemistry of Materials* 19 (2007) 755–762. DOI 10.1021/cm062055r.
13. L. S. Ramsdell, Studies on silicon carbide, *American Mineralogist* 32 (1947) 64–82. No DOI.
14. F. C. Frank and J. S. Kasper, Complex alloy structures regarded as sphere packings. I. Definitions and basic principles, *Acta Crystallographica* 11 (1958) 184–190. DOI 10.1107/S0365110X58000487.
15. F. C. Frank and J. S. Kasper, Complex alloy structures regarded as sphere packings. II. Analysis and classification of representative structures, *Acta Crystallographica* 12 (1959) 483–499. DOI 10.1107/S0365110X59001499.
16. D. R. Nelson, Order, frustration, and defects in liquids and glasses, *Physical Review B* 28 (1983) 5515–5535. DOI 10.1103/PhysRevB.28.5515.
17. M. J. Mehl, D. Hicks, C. Toher, O. Levy, R. M. Hanson, G. Hart and S. Curtarolo, The AFLOW Library of Crystallographic Prototypes: Part 1, *Computational Materials Science* 136 (2017) S1–S828. DOI 10.1016/j.commatsci.2017.01.017.
18. S. Gražulis, D. Chateigner, R. T. Downs, A. F. T. Yokochi, M. Quirós, L. Lutterotti, E. Manakova, J. Butkus, P. Moeck and A. Le Bail, Crystallography Open Database – an open-access collection of crystal structures, *Journal of Applied Crystallography* 42 (2009) 726–729. DOI 10.1107/S0021889809016690.
19. J. M. Sullivan, The geometry of bubbles and foams, in *Foams and Emulsions* (Springer, Dordrecht, 1999) 379–402. DOI 10.1007/978-94-015-9157-7_23.
20. J.-F. Sadoc and R. Mosseri, Quasiperiodic Frank–Kasper phases derived from the square–triangle dodecagonal tiling, *Structural Chemistry* 28 (2017) 63–73 (online 2016). DOI 10.1007/s11224-016-0846-2; arXiv 1609.01624.
21. Ya. P. Yarmolyuk and P. I. Kripyakevich, *Soviet Physics – Crystallography* 19 (1974) 334–337. No DOI; data as cited by Gvozdetskyi, Gladyshevskii and Hlukhyy (2014), ref. 4; the paper itself was not reached.
22. D. P. Shoemaker and C. B. Shoemaker, Concerning the relative numbers of atomic coordination types in tetrahedrally close packed metal structures, *Acta Crystallographica B* 42 (1986) 3–11. DOI 10.1107/S0108768186098671.
23. O. Delgado Friedrichs, M. Deza and M. Dutour Sikirić, Space fullerenes, talk slides, https://poivs.tsput.ru/conf/international/XVI/files/talks/newSpaceFull.pdf (no date or venue in the record found).
24. M. Morse and G. A. Hedlund, Symbolic dynamics II. Sturmian trajectories, *American Journal of Mathematics* 62 (1940) 1–42. DOI 10.2307/2371431.
25. A. Jagannathan and M. Duneau, Properties of the Ammann–Beenker tiling and its square periodic approximants, *Israel Journal of Chemistry* 64 (2024) e202300119. DOI 10.1002/ijch.202300119; arXiv 2308.07701 (2023).
26. V. Elser and C. L. Henley, Crystal and quasicrystal structures in Al–Mn–Si alloys, *Physical Review Letters* 55 (1985) 2883–2886. DOI 10.1103/PhysRevLett.55.2883.
27. C. L. Henley, Crystals and quasicrystals in the aluminum–transition metal system, *Journal of Non-Crystalline Solids* 75 (1985) 91–96. DOI 10.1016/0022-3093(85)90208-X.
28. M. Duneau, R. Mosseri and C. Oguey, Approximants of quasiperiodic structures generated by the inflation mapping, *Journal of Physics A: Mathematical and General* 22 (1989) 4549–4564. DOI 10.1088/0305-4470/22/21/017.
29. V. Gvozdetskyi, R. Gladyshevskii and V. Hlukhyy, Structure of a new multicomponent stannide and comments on the Yarmolyuk–Kripyakevich criterion for Frank–Kasper phases, *Chemistry of Metals and Alloys* 7 (2014) 169–180.
30. M. Baake and U. Grimm, *Aperiodic Order. Volume 1: A Mathematical Invitation* (Cambridge University Press, Cambridge, 2013). DOI 10.1017/CBO9781139025256.