BARLOG Plastics
Mehr aus Polymer.

Technical data
KEBABLEND / EC FE211005/1 PBT

KEBABLEND / EC FE211005/1 PBT is an electrically conductive compound based on PBT with a 20% CF recyclate content.

A large application potential for this compound lies in the substitution of metal housings (metal replacement/lightweight construction) with regard to EMC-compatible component design. As a housing material, KEBABLEND / EC FE211005/1 PBT offers the advantage of electromagnetic shielding without additional surface treatments.

Polymer: PBT

ISO designation: PBT-CF20-HI

Productgroup: Electrically conductive compounds, Functionalized compounds

Brief description of the product family:
KEBABLEND is a wide range of functional compounds, often tailor-made to customer requirements. Under the trade name KEBABLEND, we market magnetizable, thermally or electrically conductive compounds, high-density injection molding materials, compounds for radiation protection applications, detectable plastics and much more.

Properties:

dimensionally stable, electrically conductive, good chemical resistance, good aging behavior, high continuous used temperature, High strength, High stiffness, semi-crystalline, PFAS-free

Typical areas of application:

Housing, Sliding elements, Bearing bushes, Structural components

Industries:

Automotive, Railroad industry, Electrical and electronics industry, Industry, Agriculture, Mechanical Engineering, Furniture industry, Sports & Recreation

Physical properties

Density in kg/m³ | ISO 1183-1	1290

Mechanical properties

Tensile modulus in MPa | ISO 527-1	14000
Stress at break in MPa | ISO 527-1	130
Strain at break in % | ISO 527-1	4
Impact strength (Charpy) at 23°C in kJ/m² | ISO 179-1eU	80
Notched impact strength (Charpy) at 23°C in kJ/m² | ISO 179-1eA	17.5

Rheological properties

Molding shrinkage in flow direction in % | ISO 294-4	0.2
Molding shrinkage transverse to the flow direction in % | ISO 294-4	0.4

Thermal properties

Melting temperature (DSC, 10°C/min) in °C | ISO 11357-1/-3	227

Processing instructions:

Pre-drying:

Dryer type: dry air dryer
Temperature: 80°C
Drying time: 4 – 8 h
Target moisture content: <0,02%

Recommended basic settings:

Melt temperature: 250 – 260°C
Mold temperature: 90 – 120°C
Injection speed: high
Back pressure (spec.): 40 – 80 bar

Machine selection:

Screw: 3-zone screw with non-return valve.
Nozzle: Open nozzle or shut-off nozzle
Wear protection: Wear protected according to machine manufacturer’s recommendation, suitable for processing fiber-reinforced plastics
Injection unit: Shot volume = 50-80% of the maximum metering volume

Legal notices:

The information in this data sheet is based on our current knowledge and experience. Due to the wide range of possible influences during processing and application of our products, they do not exempt the processor from carrying out his own tests and trials. A legally binding assurance of certain properties or suitability for a specific application cannot be derived from our information.

* FE products are development products which are still in the trial phase. Technical data may still change in the course of product and process development. No final decision has yet been made on the commercialization of FE products. We reserve the right to discontinue the manufacture of FE products without giving further reasons.

Created at: 09.11.2026

Am Weidenbach 8-10	Telefon +49 (0)2206 90851-100	E-Mail: kontakt@barlog.de
51491 Overath	Telefax +49 (0)2206 90851-199	Web: www.barlog.de