Technical data
KEBABLEND MW 39.1500 PPA

KEBABLEND MW 39.1500 PPA is a PPA-based product for the production of soft magnetic components. The achievable permeability (µr) is about 47 and the saturation (Js) is about 495mT

Polymer: PPA

ISO designation: PA9T-MED

Productgroup: Magnetic compounds, Functionalized compounds

Brief description of the product family:

KEBABLEND is a wide range of functional compounds, often tailor-made to customer requirements. Under the trade name KEBABLEND, we market magnetizable, thermally or electrically conductive compounds, high-density injection molding materials, compounds for radiation protection applications, detectable plastics and much more.

Properties:

dimensionally stable, high continuous used temperature, semi-crystalline, soft magnetic, PFAS-free

Typical areas of application:

Industries:

Physical properties

Density in kg/m³ | ISO 1183-1	3900

Mechanical properties

Tensile modulus in MPa | ISO 527-1	30000
Stress at break in MPa | ISO 527-1	80
Strain at break in % | ISO 527-1	0.25
Impact strength (Charpy) at 23°C in kJ/m² | ISO 179-1eU	13
Notched impact strength (Charpy) at 23°C in kJ/m² | ISO 179-1eA	3.5

Rheological properties

Molding shrinkage in flow direction in % | ISO 294-4	0.1
Molding shrinkage transverse to the flow direction in % | ISO 294-4	0.1

Thermal properties

Melting temperature (DSC, 10°C/min) in °C | ISO 11357-1/-3	300

Electrical properties	
Volume resistivity in Ohm*m | IEC 60093	1e+6

Processing instructions:

Pre-drying:

Dryer type: dry air dryer
Temperature: 80°C
Drying time: 4 – 8 h
Target moisture content: <0,1%

Recommended basic settings:

Melt temperature: 310 – 340°C
Mold temperature: 140 – 180°C
Injection speed: medium – high

Machine selection:

Screw: special injection units for magnetic compounds; low compression screws with non-return valve
Nozzle: Open nozzle
Wear protection: Wear and corrosion protected according to machine manufacturer’s recommendation suitable for processing magnetic compounds
Injection unit: Shot volume = 50-80% of maximum metering volume

Further important processing information:

The residence time of the melt in the screw antechamber should be kept as short as possible. If this is not observed, segregation can occur due to the large difference in density between the filler and the substrate if the downtimes are too high. The ideal here is metering time = cooling time. A medium back pressure leads to optimum homogenization. Due to the high filler content, the spraying equipment must be equipped with wear and corrosion protection.

Legal notices:

The information in this data sheet is based on our current knowledge and experience. Due to the wide range of possible influences during processing and application of our products, they do not exempt the processor from carrying out his own tests and trials. A legally binding assurance of certain properties or suitability for a specific application cannot be derived from our information.

* FE products are development products which are still in the trial phase. Technical data may still change in the course of product and process development. No final decision has yet been made on the commercialization of FE products. We reserve the right to discontinue the manufacture of FE products without giving further reasons.

Created at: 09.11.2026

Am Weidenbach 8-10
51491 Overath

Telefon +49 (0)2206 90851-100
Telefax +49 (0)2206 90851-199

E-Mail: kontakt@barlog.de
Web: www.barlog.de