BARLOG Plastics
Mehr aus Polymer.

Technical data
KEBABLEND / MW FE 200802/3 (development product*)

KEBABLEND / MW FE 200802/3 is a development product based on PPS for the production of soft magnetic components. The achievable permeability (µr) is about 4 and the saturation (Js) is about 230 mT.

Polymer: PPS

ISO designation: PPS-MED

Productgroup: Magnetic compounds, Functionalized compounds, Shielding compounds

Brief description of the product family:
KEBABLEND is a wide range of functional compounds, often tailor-made to customer requirements. Under the trade name KEBABLEND, we market magnetizable, thermally or electrically conductive compounds, high-density injection molding materials, compounds for radiation protection applications, detectable plastics and much more.

Properties:

dimensionally stable, semi-crystalline, soft magnetic, PFAS-free

Typical areas of application:

Industries:

Automotive, Electrical and electronics industry, Household appliances, Mechanical Engineering

Physical properties

Density in kg/m³ | ISO 1183-1	2670.00

Mechanical properties

Tensile modulus in MPa | ISO 527-1	10700
Stress at break in MPa | ISO 527-1	72
Strain at break in % | ISO 527-1	0.8
Impact strength (Charpy) at 23°C in kJ/m² | ISO 179-1eU	13.7
Notched impact strength (Charpy) at 23°C in kJ/m² | ISO 179-1eA	2.6

Rheological properties

Molding shrinkage in flow direction in % | ISO 294-4	0,79
Molding shrinkage transverse to the flow direction in % | ISO 294-4	0,78

Thermal properties

Melting temperature (DSC, 10°C/min) in °C | ISO 11357-1/-3	280

Processing instructions:

Pre-drying:

Dryer type: dry air dryer.
Temperature: 120 – 130 °C
Drying time: 2 – 3 h
Recommended max. residual moisture: < 0.02 %.

Recommended basic settings:

Melt temperature: 300 – 330°C
Mold temperature: 140 – 160°C
Injection speed: medium – high
Holding pressure: high
Back pressure: 40 – 80bar (spec.)

Machine selection:

Screw: special injection units for magnetic compounds; low-compression screws with non-return valve
Nozzle: Open nozzle
Wear protection: Wear and corrosion protected according to the machine manufacturer’s recommendation suitable for processing magnetic compounds
Injection unit: shot volume = 50-80% of the maximum metering volume

Legal notices:

The information in this data sheet is based on our current knowledge and experience. Due to the wide range of possible influences during processing and application of our products, they do not exempt the processor from carrying out his own tests and trials. A legally binding assurance of certain properties or suitability for a specific application cannot be derived from our information.

* FE products are development products which are still in the trial phase. Technical data may still change in the course of product and process development. No final decision has yet been made on the commercialization of FE products. We reserve the right to discontinue the manufacture of FE products without giving further reasons.

Created at: 09.11.2026

Am Weidenbach 8-10
51491 Overath

Telefon +49 (0)2206 90851-100
Telefax +49 (0)2206 90851-199

E-Mail: kontakt@barlog.de
Web: www.barlog.de