BARLOG Plastics
Mehr aus Polymer.

Technical data
KEBABLEND / TC FE 181003 PBT (Development product*)

KEBABLEND / TC FE 181003 PBT is a special compound based on PBT, which is thermally conductive and electrically insulating.

Polymer: PBT

ISO designation: PBT-GF-X

Productgroup: THERMALLY CONDUCTIVE COMPOUNDS, Functionalized compounds

Brief description of the product family:
KEBABLEND is a wide range of functional compounds, often tailor-made to customer requirements. Under the trade name KEBABLEND, we market magnetizable, thermally or electrically conductive compounds, high-density injection molding materials, compounds for radiation protection applications, detectable plastics and much more.

Properties:

thermally conductive, PFAS-free

Typical areas of application:

Pumps and motors, Pump housing, Structural components, Connecting elements

Industries:

Automotive, Household appliances, Industry, Mechanical Engineering, Furniture industry

Physical properties

Density in kg/m³ | ISO 1183-1	1680

Mechanical properties

Tensile modulus in MPa | ISO 527-1	13300
Stress at break in MPa | ISO 527-1	95
Strain at break in % | ISO 527-1	1.5
Impact strength (Charpy) at 23°C in kJ/m² | ISO 179-1eU	30

Thermal properties

Melting temperature (DSC, 10°C/min) in °C | ISO 11357-1/-3	225
Maximum service temperature long term in °C | ISO 2578	120
Burning behavior at thickness 0.4 mm | IEC 60695-11-10	HB
Thermal conductivity in plane in W/mK | DIN EN 821	1.5
Thermal conductivity through plane in W/mK | DIN EN 821	1.0

Processing instructions:

Pre-drying:

Dryer type: dry air dryer
Temperature: 80°C
Drying time: 4 – 8 h
Moisture content during processing: < 0.02%.

Recommended basic settings:

Melt temperature: 250 – 260°C
Mold temperature: 90 – 120°C
Injection speed: high
Back pressure: 40 – 80bar (spec.)

Machine selection:

Screw: 3-zone screw with non-return valve
Nozzle: Open nozzle or shut-off nozzle
Wear protection: Wear protected according to machine manufacturer’s recommendation, suitable for processing fiber reinforced plastics
Injection unit: Shot volume = 50-80% of the maximum metering volume

Legal notices:

The information in this data sheet is based on our current knowledge and experience. Due to the wide range of possible influences during processing and application of our products, they do not exempt the processor from carrying out his own tests and trials. A legally binding assurance of certain properties or suitability for a specific application cannot be derived from our information.

* FE products are development products which are still in the trial phase. Technical data may still change in the course of product and process development. No final decision has yet been made on the commercialization of FE products. We reserve the right to discontinue the manufacture of FE products without giving further reasons.

Created at: 09.11.2026

Am Weidenbach 8-10	Telefon +49 (0)2206 90851-100	E-Mail: kontakt@barlog.de
51491 Overath	Telefax +49 (0)2206 90851-199	Web: www.barlog.de