BARLOG Plastics
Mehr aus Polymer.

Technical data
KEBABLEND / TC FE 190802 PPS (Development product*)

KEBABLEND / TC FE 190802 PPS is a functionalized compound based on PPS, which is thermally conductive and electrically insulating.

Polymer: PPS

ISO designation: PPS-I-GF+MD65

Productgroup: THERMALLY CONDUCTIVE COMPOUNDS, Functionalized compounds

Brief description of the product family:
KEBABLEND is a wide range of functional compounds, often tailor-made to customer requirements. Under the trade name KEBABLEND, we market magnetizable, thermally or electrically conductive compounds, high-density injection molding materials, compounds for radiation protection applications, detectable plastics and much more.

Properties:

dimensionally stable, electrically isolating, good chemical resistance, high continuous used temperature, High stiffness, hydrolysis stable, semi-crystalline, thermally conductive, PFAS-free

Typical areas of application:

Heat sink, Pumps and motors, Pump housing, Structural components, Connecting elements

Industries:

Automotive, Household appliances, Industry, Mechanical Engineering, Furniture industry

Physical properties

Density in kg/m³ | ISO 1183-1	1840

Mechanical properties

Tensile modulus in MPa | ISO 527-1	18500
Stress at break in MPa | ISO 527-1	115
Strain at break in % | ISO 527-1	0.7
Impact strength (Charpy) at 23°C in kJ/m² | ISO 179-1eU	18
Notched impact strength (Charpy) at 23°C in kJ/m² | ISO 179-1eA	5.5

Rheological properties

Molding shrinkage in flow direction in % | ISO 294-4	0.2
Molding shrinkage transverse to the flow direction in % | ISO 294-4	0.65

Thermal properties

Melting temperature (DSC, 10°C/min) in °C | ISO 11357-1/-3	280
Maximum service temperature long term in °C | ISO 2578	200

Thermal properties

Thermal conductivity in plane in W/mK | DIN EN 821	1.0
Thermal conductivity through plane in W/mK | DIN EN 821	1.1
Burning behavior at thickness 0.8 mm | IEC 60695-11-10	V0

Electrical properties

Surface resistivity in ohm | IEC 60093	1E14
Electric strength in kV/mm | IEC 60243-1	27

Processing instructions:

Pre-drying:

Dryer type: dry air dryer (!).
Temperature: 120 – 140 °C
Drying time: 4 – 8 h
Recommended max. residual moisture: < 0.02 %.

Recommended basic settings:

Melt temperature: 320 – 340°C
Mold temperature: 140 – 180°C (As a rule of thumb, the higher the requirements, the higher the mold temperature).
Back pressure: < 10 bar (spec.)

The injection speed should be set as a slow – fast – slow profile. As a principle: as fast as possible, as slow as necessary.

Machine selection:

In the processing of PPS, wear- and corrosion-protected injection units have proven their worth. The injection unit should be selected so that the shot volume is 50 – 80% of the maximum metering volume. The dwell time should be kept as short as possible.

Legal notices:

The information in this data sheet is based on our current knowledge and experience. Due to the wide range of possible influences during processing and application of our products, they do not exempt the processor from carrying out his own tests and trials. A legally binding assurance of certain properties or suitability for a specific application cannot be derived from our information.

* FE products are development products which are still in the trial phase. Technical data may still change in the course of product and process development. No final decision has yet been made on the commercialization of FE products. We reserve the right to discontinue the manufacture of FE products without giving further reasons.

Created at: 09.11.2026

Am Weidenbach 8-10
51491 Overath

Telefon +49 (0)2206 90851-100
Telefax +49 (0)2206 90851-199

E-Mail: kontakt@barlog.de
Web: www.barlog.de