Customer support: **+39-0332 409111** Email: **marketing@it.lati.com**

LATICONTHER 52/11 CPG/700

Family: LATICONTHER Base resin: Polypropylene homopolymer (PPh)

Compare Technical request Sampling request Quotation request

General information

High thermal conductivity product based on Polypropylene homopolymer (PPh). Special filler / Glass fibres. PFAS-free product.

The products mentioned herein are not suitable for applications in contact with foodstuffs or for potable water transportation, or for toy manufacturing.

The products mentioned herein are not suitable for applications in the pharmaceutical, medical or dental sector.

Features

- Thermally conductive

Additives

- Ceramic fillers
- Glass fibres

Download documents

Technical datasheets

IT | UK | US | DE | FR | ES | PT

Certificates

Restricted substances list - English

Restricted substances list - Italian

Technical characteristics

PHYSICAL PROPERTIES	STANDARD	VALUE	MEASURE UNITS
Density	ISO 1183	2.1	g/cm³

PHYSICAL PROPERTIES	STANDARD	VALUE	MEASURE UNITS
Linear shrinkage at moulding			
Longitudinal (2.0mm/60MPa)	ISO 294-4	0.40 ÷ 0.80	%
Transversal (2.0mm/60MPa)	ISO 294-4	0.60 ÷ 1.00	%
Dimensional stability	---	64	
Moisture absorption			
Saturation, in air	ISO 62-4	0.03	%
MECHANICAL PROPERTIES	**STANDARD**	**VALUE**	**MEASURE UNITS**
CHARPY impact strength			
Unnotched, at +23°C	ISO 179-1eU	8	kJ/m²
Notched, at +23°C	ISO 179-1eA	3.5	kJ/m²
Tensile elongation			
At break (5 mm/min), 23°C	ISO 527	1	%
Tensile strength			
At break (5 mm/min), 23°C	ISO 527	35	MPa
Elastic modulus			
Tensile (1 mm/min), 23°C	ISO 527	5600	MPa
THERMAL PROPERTIES	**STANDARD**	**VALUE**	**MEASURE UNITS**
Coefficient of linear thermal expansion (CLTE)			
+30°C to +100°C (longitudinal)	ISO 11359	50	$\times 10^{-6}\ K^{-1}$
+30°C a +100°C (transversal)	ISO 11359	90	$\times 10^{-6}\ K^{-1}$
VICAT - Softening point			
50N (heating rate 120°C/h)	ISO 306	120	°C
HDT - Heat Deflection Temperature			
0.45 MPa	ISO 75	150	°C
1.81 MPa	ISO 75	125	°C
Thermal conductivity			
in plane	ASTM E 1461-92	0.8	W/mK
through plane	ASTM E 1461-92	0.6	W/mK
ELECTRICAL PROPERTIES	**STANDARD**	**VALUE**	**MEASURE UNITS**
Dielectric strength (short period)			

PHYSICAL PROPERTIES	STANDARD	VALUE	MEASURE UNITS
2 mm thickness, 23°C, dry	ASTM D 149	32	kV/mm
MELT TEMPERATURE	**STANDARD**	**VALUE**	**MEASURE UNITS**
Suggested melt temperature	---	230 ÷ 250	°C
MOULD TEMPERATURE	**STANDARD**	**VALUE**	**MEASURE UNITS**
Suggested mould temperature	---	30 ÷ 50	°C

Drying conditions (hot air dessiccator)

Predrying needed. At least 2 hours at 80 ÷ 90°C

Injection speed

Injection speed: medium to high. Setting an injection profile should improve moulding.

Hot runners

Usage of hot runner: not suggested

LATI MATERIALS BASIC DATABASE

Company
LATI Industria Termoplastici S.p.A.
Registered office: via F. Baracca, 7- I
21040 VEDANO OLONA (VA) ITALY

Contacts
E-mail: marketing@it.lati.com
PEC: lati@pec.net
Phone: +39-0332 409111
Fax: +39-0332 409235/307

Info
C.F., P. IVA e Reg. Impr. di VA n. 00214880122
Codice Destinatario SDI: K1L103O
R.E.A. di Varese n. 41557

Legal
Privacy & cookie policy
Conditions of use

Copyright © 2026 - LATI Industria Termoplastici S.p.A. | Realizzato da Weblink