Customer support: **+39-0332 409111** Email: **marketing@it.lati.com**

LATICONTHER 62 GR/50-V0

Family: LATICONTHER Base resin: Polyamide 6 (PA 6)

Compare Technical request Sampling request Quotation request

General information

High thermal conductivity product based on Polyamide 6 (PA 6). Graphite. Flame retardant, UL94 V-0 class, with brominated flame retardants, free of PBB/PBDE. High stiffness. PFAS-free product.

The products mentioned herein are not suitable for applications in contact with foodstuffs or for potable water transportation, or for toy manufacturing.

The products mentioned herein are not suitable for applications in the pharmaceutical, medical or dental sector.

Features

- Thermally conductive
- Flame retardant, with brominated flame retardants

Additives

- Graphite

Download documents

Technical datasheets

IT | UK | US | DE | FR | ES | PT

Certificates

Restricted substances list - English

Restricted substances list - Italian

Technical characteristics

PHYSICAL PROPERTIES	STANDARD	VALUE	MEASURE UNITS

PHYSICAL PROPERTIES	STANDARD	VALUE	MEASURE UNITS
Density	ISO 1183	1.68	g/cm³
Linear shrinkage at moulding			
Longitudinal (2.0mm/60MPa)	ISO 294-4	0.25 ÷ 0.50	%
Transversal (2.0mm/60MPa)	ISO 294-4	0.30 ÷ 0.75	%
Dimensional stability	---	50	
Moisture absorption			
Saturation, in air	ISO 62-4	1.2	%
MECHANICAL PROPERTIES	**STANDARD**	**VALUE**	**MEASURE UNITS**
CHARPY impact strength			
Unnotched, at +23°C	ISO 179-1eU	4.5	kJ/m²
Notched, at +23°C	ISO 179-1eA	2	kJ/m²
Tensile elongation			
At break (5 mm/min), 23°C	ISO 527	0.5	%
Tensile strength			
At break (5 mm/min), 23°C	ISO 527	40	MPa
Elastic modulus			
Tensile (1 mm/min), 23°C	ISO 527	9600	MPa
THERMAL PROPERTIES	**STANDARD**	**VALUE**	**MEASURE UNITS**
Coefficient of linear thermal expansion (CLTE)			
+30°C to +100°C (longitudinal)	ISO 11359	25	$\times 10^{-6}\ K^{-1}$
+30°C a +100°C (transversal)	ISO 11359	30	$\times 10^{-6}\ K^{-1}$
VICAT - Softening point			
50N (heating rate 120°C/h)	ISO 306	205	°C
HDT - Heat Deflection Temperature			
0.45 MPa	ISO 75	210	°C
1.81 MPa	ISO 75	180	°C
Thermal conductivity			
in plane	ASTM E 1461-92	17	W/mK
through plane	ASTM E 1461-92	2	W/mK
FLAMMABILITY	**STANDARD**	**VALUE**	**MEASURE UNITS**

PHYSICAL PROPERTIES	STANDARD	VALUE	MEASURE UNITS
Oxygen Index	ASTM D 2863	41	%
Flammability rating			
3 mm thickness	UL 94	V-0	
1.5 mm thickness	UL 94	V-0	
0.75 mm thickness	UL 94	V-0	
GWFI - Glow Wire Flammability Index			
2 mm thickness	IEC 60695-2-12	960	°C
1.5 mm thickness	IEC 60695-2-12	960	°C
1 mm thickness	IEC 60695-2-12	960	°C
GWIT - Glow Wire Ignition Test			
2 mm thickness	IEC 60695-2-13	900	°C
1 mm thickness	IEC 60695-2-13	900	°C
ELECTRICAL PROPERTIES	**STANDARD**	**VALUE**	**MEASURE UNITS**
Electrical resistivity			
Surface, dry	IEC 62631	2E3	ohm
MELT TEMPERATURE	**STANDARD**	**VALUE**	**MEASURE UNITS**
Suggested melt temperature	---	240 ÷ 260	°C
MOULD TEMPERATURE	**STANDARD**	**VALUE**	**MEASURE UNITS**
Suggested mould temperature	---	70 ÷ 100	°C

Storage

PAY ATTENTION! Material is prone to absorb moisture.

Drying conditions (hot air dessiccator)

Predrying needed. At least 2 hours at 70 ÷ 90°C

Injection speed

Injection speed: medium. Setting an injection profile should improve moulding.

Hot runners

Usage of hot runner: to be evaluated

LATI MATERIALS BASIC DATABASE

Company
LATI Industria Termoplastici S.p.A.
Registered office: via F. Baracca, 7- I
21040 VEDANO OLONA (VA) ITALY

Contacts
E-mail: marketing@it.lati.com
PEC: lati@pec.net
Phone: +39-0332 409111
Fax: +39-0332 409235/307

Info
C.F., P. IVA e Reg. Impr. di VA n. 00214880122
Codice Destinatario SDI: K1L103O
R.E.A. di Varese n. 41557

Legal
Privacy & cookie policy
Conditions of use

Copyright © 2026 - LATI Industria Termoplastici S.p.A. | Realizzato da **Weblink**