Customer support: **+39-0332 409111** Email: **marketing@it.lati.com**

LATICONTHER 62 GR/50

Family: LATICONTHER Base resin: Polyamide 6 (PA 6)

Compare Technical request Sampling request Quotation request

General information

High thermal conductivity product based on Polyamide 6 (PA 6). Graphite. PFAS-free product.

The products mentioned herein are not suitable for applications in contact with foodstuffs or for potable water transportation, or for toy manufacturing.

The products mentioned herein are not suitable for applications in the pharmaceutical, medical or dental sector.

Features

- Thermally conductive

Additives

- Graphite

Download documents

Technical datasheets

IT | UK | US | DE | FR | ES | PT

Certificates

Restricted substances list - English

Restricted substances list - Italian

Technical characteristics

PHYSICAL PROPERTIES	STANDARD	VALUE	MEASURE UNITS
Density	ISO 1183	1.51	g/cm³
Linear shrinkage at moulding			

PHYSICAL PROPERTIES	STANDARD	VALUE	MEASURE UNITS
Longitudinal (2.0mm/60MPa)	ISO 294-4	0.25 ÷ 0.50	%
Transversal (2.0mm/60MPa)	ISO 294-4	0.35 ÷ 0.85	%
Dimensional stability	---	48	
Moisture absorption			
Saturation, in air	ISO 62-4	1.4	%
MECHANICAL PROPERTIES	**STANDARD**	**VALUE**	**MEASURE UNITS**
CHARPY impact strength			
Unnotched, at +23°C	ISO 179-1eU	7	kJ/m²
Notched, at +23°C	ISO 179-1eA	3.4	kJ/m²
Tensile elongation			
At break (5 mm/min), 23°C	ISO 527	0.9	%
At break (5 mm/min), 60°C	ISO 527	2.6	%
At break (5 mm/min), 90°C	ISO 527	3.8	%
At break (5 mm/min), 120°C	ISO 527	3.9	%
At break (5 mm/min), 150°C	ISO 527	4.1	%
Tensile strength			
At break (5 mm/min), 23°C	ISO 527	50	MPa
At break (5 mm/min), 60°C	ISO 527	35	MPa
At break (5 mm/min), 90°C	ISO 527	30	MPa
At break (5 mm/min), 120°C	ISO 527	25	MPa
At break (5 mm/min), 150°C	ISO 527	20	MPa
Elastic modulus			
Tensile (1 mm/min), 23°C	ISO 527	13000	MPa
Tensile (1 mm/min), 60°C	ISO 527	4600	MPa
Tensile (1 mm/min), 90°C	ISO 527	3000	MPa
Tensile (1 mm/min), 120°C	ISO 527	2600	MPa
Tensile (1 mm/min), 150°C	ISO 527	2000	MPa
THERMAL PROPERTIES	**STANDARD**	**VALUE**	**MEASURE UNITS**
Coefficient of linear thermal expansion (CLTE)			
+30°C to +100°C (longitudinal)	ISO 11359	25	$\times 10^{-6}\ K^{-1}$

PHYSICAL PROPERTIES	STANDARD	VALUE	MEASURE UNITS
+30°C a +100°C (transversal)	ISO 11359	30	× 10^{-6} K^{-1}
VICAT - Softening point			
50N (heating rate 120°C/h)	ISO 306	200	°C
HDT - Heat Deflection Temperature			
0.45 MPa	ISO 75	210	°C
1.81 MPa	ISO 75	180	°C
Thermal conductivity			
in plane	ASTM E 1461-92	20	W/mK
through plane	ASTM E 1461-92	3	W/mK

FLAMMABILITY	STANDARD	VALUE	MEASURE UNITS
Flammability rating			
3 mm thickness	UL 94	HB	
1.5 mm thickness	UL 94	HB	

ELECTRICAL PROPERTIES	STANDARD	VALUE	MEASURE UNITS
Electrical resistivity			
Surface, dry	IEC 62631	5E3	ohm

MELT TEMPERATURE	STANDARD	VALUE	MEASURE UNITS
Suggested melt temperature	---	250 ÷ 270	°C

MOULD TEMPERATURE	STANDARD	VALUE	MEASURE UNITS
Suggested mould temperature	---	80 ÷ 100	°C

Storage

PAY ATTENTION! Material is prone to absorb moisture.

Drying conditions (hot air dessiccator)

Predrying needed. At least 2 hours at 80 ÷ 100°C

Injection speed

Injection speed: medium to high. Setting an injection profile should improve moulding.

Hot runners

Usage of hot runner: to be evaluated

Other information



Stress - strain curves at different temperatures

LATI MATERIALS BASIC DATABASE

Company
LATI Industria Termoplastici S.p.A.
Registered office: via F. Baracca, 7- I
21040 VEDANO OLONA (VA) ITALY

Contacts
E-mail: marketing@it.lati.com
PEC: lati@pec.net
Phone: +39-0332 409111
Fax: +39-0332 409235/307

Info
C.F., P. IVA e Reg. Impr. di VA n. 00214880122
Codice Destinatario SDI: K1L103O
R.E.A. di Varese n. 41557

Legal
Privacy & cookie policy
Conditions of use

Copyright © 2026 - LATI Industria Termoplastici S.p.A. | Realizzato da **Weblink**