Customer support: **+39-0332 409111** Email: **marketing@it.lati.com**

LATICONTHER 66 VH MI02 G/35

Family: LATICONTHER Base resin: Polyamide 66 (PA 66)

Compare Technical request Sampling request Quotation request

General information

High thermal conductivity product based on Polyamide 66 (PA 66). Glycol stabilised. Improved mechanical properties. Glass fibres. High stiffness. PFAS-free product.

The products mentioned herein are not suitable for applications in contact with foodstuffs or for potable water transportation, or for toy manufacturing.

The products mentioned herein are not suitable for applications in the pharmaceutical, medical or dental sector.

Features

- Thermally conductive

Additives

- Glass fibres

Download documents

Technical datasheets

IT | UK | US | DE | FR | ES | PT

Certificates

Restricted substances list - English

Restricted substances list - Italian

Technical characteristics

PHYSICAL PROPERTIES	STANDARD	VALUE	MEASURE UNITS
Density	ISO 1183	1.61	g/cm³

PHYSICAL PROPERTIES	STANDARD	VALUE	MEASURE UNITS
Linear shrinkage at moulding			
Longitudinal (2.0mm/60MPa)	ISO 294-4	0.30 ÷ 0.60	%
Transversal (2.0mm/60MPa)	ISO 294-4	0.65 ÷ 0.95	%
Dimensional stability	---	52	
Moisture absorption			
Saturation, in air	ISO 62-4	1.4	%
MECHANICAL PROPERTIES	**STANDARD**	**VALUE**	**MEASURE UNITS**
CHARPY impact strength			
Unnotched, at +23°C	ISO 179-1eU	10	kJ/m²
Notched, at +23°C	ISO 179-1eA	6	kJ/m²
Tensile elongation			
At break (5 mm/min), 23°C	ISO 527	1.1	%
Tensile strength			
At break (5 mm/min), 23°C	ISO 527	115	MPa
Elastic modulus			
Tensile (1 mm/min), 23°C	ISO 527	16000	MPa
THERMAL PROPERTIES	**STANDARD**	**VALUE**	**MEASURE UNITS**
Coefficient of linear thermal expansion (CLTE)			
+30°C to +100°C (longitudinal)	ISO 11359	20	$\times 10^{-6}\ K^{-1}$
+30°C a +100°C (transversal)	ISO 11359	30	$\times 10^{-6}\ K^{-1}$
VICAT - Softening point			
50N (heating rate 120°C/h)	ISO 306	245	°C
HDT - Heat Deflection Temperature			
0.45 MPa	ISO 75	255	°C
1.81 MPa	ISO 75	245	°C
Thermal conductivity			
in plane	ASTM E 1461-92	5	W/mK
through plane	ASTM E 1461-92	1.2	W/mK
MELT TEMPERATURE	**STANDARD**	**VALUE**	**MEASURE UNITS**
Suggested melt temperature	---	280 ÷ 300	°C

PHYSICAL PROPERTIES	STANDARD	VALUE	MEASURE UNITS

MOULD TEMPERATURE	STANDARD	VALUE	MEASURE UNITS
Suggested mould temperature	---	80 ÷ 100	°C

Storage

PAY ATTENTION! Material is prone to absorb moisture.

Drying conditions (hot air dessiccator)

Predrying needed. At least 2 hours at 80 ÷ 100°C

Injection speed

Injection speed: medium to high. Setting an injection profile should improve moulding.

Hot runners

Usage of hot runner: possible

LATI MATERIALS BASIC DATABASE

Company
LATI Industria Termoplastici S.p.A.
Registered office: via F. Baracca, 7- I
21040 VEDANO OLONA (VA) ITALY

Contacts
E-mail: marketing@it.lati.com
PEC: lati@pec.net
Phone: +39-0332 409111
Fax: +39-0332 409235/307

Info
C.F., P. IVA e Reg. Impr. di VA n. 00214880122
Codice Destinatario SDI: K1L103O
R.E.A. di Varese n. 41557

Legal
Privacy & cookie policy
Conditions of use

Copyright © 2026 - LATI Industria Termoplastici S.p.A. | Realizzato da Weblink