Customer support: **+39-0332 409111** Email: **marketing@it.lati.com**



# LATICONTHER 87/28 GR/50



Family: LATICONTHER Base resin: Polycarbonate (PC)

Compare Technical request Sampling request Quotation request

## General information

High thermal conductivity product based on Polycarbonate (PC). Graphite. PFAS-free product.

The products mentioned herein are not suitable for applications in contact with foodstuffs or for potable water transportation, or for toy manufacturing.

The products mentioned herein are not suitable for applications in the pharmaceutical, medical or dental sector.

Features

- Thermally conductive

Additives

- Graphite

## Download documents

Technical datasheets

IT | UK | US | DE | FR | ES | PT

Certificates

Restricted substances list - English

Restricted substances list - Italian

## Technical characteristics

| PHYSICAL PROPERTIES | STANDARD | VALUE | MEASURE UNITS |
|---|---|---|---|
| **Density** | ISO 1183 | 1.48 | g/cm³ |
| **Linear shrinkage at moulding** | | | |

| PHYSICAL PROPERTIES | STANDARD | VALUE | MEASURE UNITS |
|---|---|---|---|
| Longitudinal (2.0mm/60MPa) | ISO 294-4 | 0.20 ÷ 0.40 | % |
| Transversal (2.0mm/60MPa) | ISO 294-4 | 0.50 ÷ 0.80 | % |
| Dimensional stability | --- | 48 | |
| **Moisture absorption** | | | |
| Saturation, in air | ISO 62-4 | 0.12 | % |
| **MECHANICAL PROPERTIES** | **STANDARD** | **VALUE** | **MEASURE UNITS** |
| **CHARPY impact strength** | | | |
| Unnotched, at +23°C | ISO 179-1eU | 7 | kJ/m² |
| Notched, at +23°C | ISO 179-1eA | 4 | kJ/m² |
| **Tensile elongation** | | | |
| At break (5 mm/min), 23°C | ISO 527 | 0.8 | % |
| **Tensile strength** | | | |
| At break (5 mm/min), 23°C | ISO 527 | 35 | MPa |
| **Elastic modulus** | | | |
| Tensile (1 mm/min), 23°C | ISO 527 | 7000 | MPa |
| **THERMAL PROPERTIES** | **STANDARD** | **VALUE** | **MEASURE UNITS** |
| **Coefficient of linear thermal expansion (CLTE)** | | | |
| +30°C to +100°C (longitudinal) | ISO 11359 | 20 | $\times 10^{-6}\ K^{-1}$ |
| +30°C a +100°C (transversal) | ISO 11359 | 25 | $\times 10^{-6}\ K^{-1}$ |
| **VICAT - Softening point** | | | |
| 50N (heating rate 120°C/h) | ISO 306 | 145 | °C |
| **HDT - Heat Deflection Temperature** | | | |
| 0.45 MPa | ISO 75 | 140 | °C |
| 1.81 MPa | ISO 75 | 135 | °C |
| **Thermal conductivity** | | | |
| in plane | ASTM E 1461-92 | 10 | W/mK |
| through plane | ASTM E 1461-92 | 1.5 | W/mK |
| **ELECTRICAL PROPERTIES** | **STANDARD** | **VALUE** | **MEASURE UNITS** |
| **Electrical resistivity** | | | |
| Surface, dry | IEC 62631 | 8E3 | ohm |

| PHYSICAL PROPERTIES | STANDARD | VALUE | MEASURE UNITS |
|---|---|---|---|
| **MELT TEMPERATURE** | **STANDARD** | **VALUE** | **MEASURE UNITS** |
| Suggested melt temperature | --- | 290 ÷ 300 | °C |
| **MOULD TEMPERATURE** | **STANDARD** | **VALUE** | **MEASURE UNITS** |
| Suggested mould temperature | --- | 100 ÷ 120 | °C |

## Drying conditions (hot air dessiccator)

Predrying needed. At least 3 hours at 110 ÷ 120°C

## Injection speed

Injection speed: medium to high. Setting an injection profile should improve moulding.

## Hot runners

Usage of hot runner: to be evaluated

LATI MATERIALS BASIC DATABASE

**Company**
LATI Industria Termoplastici S.p.A.
Registered office: via F. Baracca, 7- I
21040 VEDANO OLONA (VA) ITALY

**Contacts**
E-mail: marketing@it.lati.com
PEC: lati@pec.net
Phone: +39-0332 409111
Fax: +39-0332 409235/307

**Info**
C.F., P. IVA e Reg. Impr. di VA n. 00214880122
Codice Destinatario SDI: K1L103O
R.E.A. di Varese n. 41557

**Legal**
Privacy & cookie policy
Conditions of use

Copyright © 2026 - LATI Industria Termoplastici S.p.A. | Realizzato da Weblink