Technical Data Sheet - Preliminary Product

Alfater XL®

ALFATER XL A80 2EC0000

(Last update: 10.02.2025)

M⚙COM

Base Polymer	Thermoplastic Vulcanisate (PP+EPDM)
Colour	black
Service Temperature	max. range (depending on load, geometry, etc.) -40-125 °C
Special Features	electrically conductive, reduced surface resistivity, good weathering resistance, good chemical resistance, good ozone reistance, good hot air resistance, good hydrolysis resistant
Market Segment	Automotive, Machinery, electrical and electronic, building and construction
Application Area	injection moulded parts, extruded parts, coextrusion
Typical Applications	functional components with electrical conductivity, seals, sealing lip, profile, 2K components
Adhesion to	Polypropylene Homopolymer, Polypropylene Copolymer, Polyethylene, Thermoplastic Vulcanisate (PP+EPDM), Thermoplastic Olefin Elastomer, Thermoplastic Elastomer general

Pre-Drying Conditions	in a dry air (dessiccant) dryer 70-80 °C for 2-4 h max. moisture content <0,10 %
Processing Injection Moulding	melt temperature 195-230 °C mould temperature 10-60 °C injection speed high back pressure (hydraulic) >5 bar holding pressure 50-70% of injection pressure
Processing Extrusion	melt temperature 200-240 °C die temperature 200-230 °C
Storage	dry, protected from light not above 30°C tightly sealed

Properties	Value	Dimension	Test Norm
Mechanical Properties			
Tensile Stress at 100% Elongation (Type 2)	4.2	MPa	ISO 37
Tensile Strength (Type 2)	8.4	MPa	ISO 37
Tear Strength (Method Ba)	40	kN/m	ISO 34-1
Elongation at Break (Type 2)	470	%	ISO 37
Shore Hardness A (15s)	80	-	ISO 868
Thermal Properties			
Compression Set (22h / 100°C / 25% / Type A)	60	%	ISO 815
Compression Set (22h / 70°C / 25% / Type A)	53	%	ISO 815
Compression Set (72h / 22°C / 25% / Type A)	30	%	ISO 815
Compression Set (72h / 125°C / 25% / Type A)	70	%	ISO 815

Alfater XL®

ALFATER XL A80 2EC0000

(Last update: 10.02.2025)

M:COM

Electrical Properties			
Surface Resistance	25	Ohm	DIN EN 62631-3-2
Physical Properties			
Density	1000	kg/m³	ISO 1183
Ageing Properties			
Ozone resistance (method A)	passed	-	ISO 1431-1A
Flammability			
Flammability (1.5 mm)	HB	class	UL 94
Glow Wire (GWFI, 650°C, 2.0mm)	passed	-	DIN EN 60695

Liability Exclusion

These are guide values and not a specification. The test values mentioned are representative values only and not binding minimum or maximum figures. These test values have been determined on standardised test specimens and can be affected by pigmentation, mould design and processing conditions.

Any information given on the chemical and physical characteristics of our products, including, without limitation, technical advice on applications, whether verbally, in writing or by testing the product, is given to the best of our knowledge and in good faith and does not exempt the buyer from carrying out their own investigations and tests in order to ascertain the product's specific suitability for the purpose intended.

The buyer is solely responsible for confirming the suitability of the product for a particular application, its utilization and processing and must observe any applicable laws and government regulations. **NO EXPRESS OR IMPLIED RECOMMENDATION OR WARRANTY IS GIVEN WITH REGARD TO THE SUITABILITY OF THE PRODUCT FOR A PARTICULAR APPLICATION, SUCH AS, BUT NOT LIMITED TO, SAFETY-CRITICAL COMPONENTS OR SYSTEMS.**

Healthcare uses: the supply of any product by ALBIS for any medical, pharmaceutical or diagnostic application is conditional to an assessment by ALBIS in terms of compliance with ALBIS' internal risk management policy – even for products which are in general designated for use in Healthcare applications.
Important: irrespective of product type or designation, ALBIS does not recommend or support the use of any products it supplies which fall into the following medical, pharmaceutical or diagnostic application categories:

- risk class III applications according to EU directive 93/42/EEC
- any bodily implant application for greater than 30 days
- any critical component in any medical device that supports or sustains human life.

At all times, our standard terms and conditions of sale apply.