Hostalen GM 9310 C BLACK

(PE-HD) LyondellBasell Industries

Rheological properties	Value	Unit	Test Standard
ISO Data			
Melt Flow Index, MFI	4.5	g/10min	ISO 1133
MFI temperature	190	°C	-
MFI load	21.6	kg	-

Mechanical Properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	1250	MPa	ISO 527
Yield stress	26	MPa	ISO 527
Yield strain	7	%	ISO 527
Tensile Creep Modulus, 1h	780	MPa	ISO 899-1
Notched Impact Strength (Charpy), +23°C	5	kJ/m²	ISO 179/1eA
Notched Impact Strength (Charpy), -30°C	3	kJ/m²	ISO 179/1eA
Ball Indentation Hardness	55	MPa	ISO 2039-1

Thermal Properties	Value	Unit	Test Standard
ISO Data			
Vicat softening temperature, 50°C/h 50N	83	°C	ISO 306

Electrical Properties	Value	Unit	Test Standard
ISO Data			
Volume Resistivity	100000	Ohm*m	IEC 62631-3-1
Surface Resistivity	10000	Ohm	IEC 62631-3-2
ASTM Data			
Surface Resistivity	10000	Ohm	ASTM D 257
Volume Resistivity	100000	Ohm*cm	ASTM D 257

Other Properties	Value	Unit	Test Standard
ISO Data			
Density	1000	kg/m³	ISO 1183

Characteristics

Processing

Sheet Extrusion, Other Extrusion, Pipe/Tube Extrusion

Special Characteristics

Electrically Conductive

Delivery form

Black

Disclaimer

Liability Exclusion
These guide values are measured and provided by the product manufacturer and have been determined on standardised test specimens and can be affected by pigmentation, mould design and processing conditions. M-Base has taken the guide values from the producer's original Technical Data Sheet. **ALBIS AND M-BASE ARE THEREFORE NOT RESPONSIBLE FOR THE ACCURACY OF THE GUIDE VALUES AND CANNOT GIVE ANY WARRANTY WITH REGARD TO THEIR CORRECTNESS.**

Any information given on the chemical and physical characteristics of our products, including, without limitation, technical advice on applications, whether verbally, in writing or by testing the product, is given to the best of our knowledge and in good faith and does not exempt the buyer from carrying out their own investigations and tests in order to ascertain the product's specific suitability for the purpose intended.

The buyer is solely responsible for confirming the suitability of the product for a particular application, its utilization and processing and must observe any applicable laws and government regulations. **NO EXPRESS OR IMPLIED RECOMMENDATION OR WARRANTY IS GIVEN WITH REGARD TO THE SUITABILITY OF THE PRODUCT FOR A PARTICULAR APPLICATION, SUCH AS, BUT NOT LIMITED TO, SAFETY-CRITICAL COMPONENTS OR SYSTEMS.**

Healthcare uses: the supply of any product by ALBIS for any medical, pharmaceutical or diagnostic application is conditional to an assessment by ALBIS in terms of compliance with ALBIS' internal risk management policy – even for products which are in general designated for use in Healthcare applications.
Important: irrespective of product type or designation, ALBIS does not recommend or support the use of any products it supplies which fall into the following medical, pharmaceutical or diagnostic application categories:

- risk class III applications according to EU directive 93/42/EEC
- any bodily implant application for greater than 30 days
- any critical component in any medical device that supports or sustains human life.

At all times, our standard terms and conditions of sale apply.