LATAMID 12 AM H2 K/30 NT:0045

Compound based on Polyamide 12 (PA 12). 3D printing version. Improved thermal stabilisation. Carbon fibres. PFAS-free product.

The products mentioned herein are not suitable for applications in contact with foodstuffs or for potable water transportation, or for toy manufacturing.

The products mentioned herein are not suitable for applications in the pharmaceutical, medical or dental sector.

PHYSICAL PROPERTIES	STANDARD	VALUE	MEASURE UNITS
Density			
injection moulding	ISO 1183	**1.17**	g/cm³
MECHANICAL PROPERTIES	**STANDARD**	**VALUE**	**MEASURE UNITS**
CHARPY impact strength			
Unnotched, at 23°C, injection moulding	ISO 179-1eU	**45.0**	kJ/m²
Notched, at 23°C, injection moulding	ISO 179-1eA	**10.0**	kJ/m²
MECHANICAL PROPERTIES	**STANDARD**	**VALUE**	**MEASURE UNITS**
Tensile elongation			
At break (5 mm/min), 23°C, injection moulding	ISO 527	**3.0**	%
Tensile strength			
At break (5 mm/min), 23°C, injection moulding	ISO 527	**140**	MPa
THERMAL PROPERTIES	**STANDARD**	**VALUE**	**MEASURE UNITS**
VICAT - Softening point			
50 N (heating rate 120°C/h), injection moulding	ISO 306	**170**	°C
HDT - Heat Deflection Temperature			
0.45 MPa, injection moulding	ISO 75	**180**	°C
1.81 MPa, injection moulding	ISO 75	**175**	°C

LATAMID 12 AM H2 K/30 NT:0045 - Processing conditions

FILAMENT EXTRUSION PARAMETERS	VALUE	MEASURE UNITS
Material drying (at least 4h @ …)	**80**	°C
Suggested temperature range of filament production	**210 - 230**	°C

3D PRINTING SUGGESTED CONDITIONS	VALUE	MEASURE UNITS
Filament drying conditions	**90**	°C
Extruder temperature	**250 - 260**	°C
Chamber conditioning	**OFF**	
Nozzle type	**Steel**	
Annealing conditions (per mm)	**1h @ 80°C**	

MOULDED SPECIMEN CONDITIONS	VALUE	MEASURE UNITS
Melt temperature	**230**	°C
Mould temperature	**80**	°C

APPROVALS

Please, check our site or contact LATI for details.

CONTACTS

LATI Industria Termoplastici S.p.A.
Via F. Baracca, 7 - I - 21040 VEDANO OLONA (VA)
Tel. +39-0332-409111 - Fax +39-0332-409260
email: techserv@it.lati.com
http://www.lati.com
http://lambda.lati.it

Values shown are based on testing of specimens obtained through a manufacturing process, conditioned according to the standard and represent data that fall within the standard range of properties for non-coloured material, if not otherwise specified. As they may be subject to variations, these values do not represent a sufficient basis for any part design and are not intended for use in establishing values for specification purposes. Properties of manufactured parts can be influenced by a wide range of factors including, but not limited to, colorants, part design, processing equipment, processing conditions, post-treatment conditions, environmental conditions and usage of regrind during the transformation process. If data are explicitly indicated as provisional, range of properties has to be considered wider. This information and technical assistance are provided as a convenience for informational purposes only and are subject to change without notice. The customer shall always ensure that the latest release of technical information is at his own disposal. Lati S.p.A. extends no warranties or guarantee, including a warranty of merchantability of whatever use is made of the product, and make no representations as to the accuracy, suitability, reliability, completeness and sufficiency of the information provided, and assume no responsibility regarding the consequences of its use or for any printing errors. It is the customer's responsibility to inspect and test our products in order to determine to his own satisfaction whether they are suitable for his intended uses and applications or used in conjunction with third-party materials. This application-specific analysis shall at least include preliminary testing to determine the suitability for the customer's particular purpose from a technical as well as health, safety, and environmental standpoint. Such testing has not necessarily been done by us as the manner in which the customer uses and the purpose to which utilises our products are beyond our control. Lati S.p.A. does not accept and hereby disclaims liability for any damages whatsoever in connection with the use of or reliance on this information. No one is authorised to make any warranties, issue any immunities or assume any liabilities on behalf of Lati S.p.A. except in a writing signed by a specifically authorised Lati S.p.A. executive. Unless otherwise agreed in writing, the exclusive remedy for all claims is replacement of the product or refund of the purchase price at Lati's option, and in no event shall Lati S.p.A. be liable for special, consequential, incidental, punitive or exemplary damages. No information herein can be considered as a suggestion to use any product in conflict with intellectual property rights. Lati S.p.A. disclaims any liability that may be claimed for infringement or alleged infringement of patents. Unless specifically stated in writing, the products mentioned herein are not suitable for applications in the pharmaceutical, medical or dental sector, and toys manufacturing, in contact with foodstuff or for potable water transportation. For any other issues Lati S.p.A. Conditions of Sales apply.

Copyright © LATI S.p.A. 2021