Handling Instruction

Soft Magnetic Compound

＜Safety Information＞

Handle in accordance with good industrial hygiene and safety practice.

Avoid breathing processing fume or vapor.

Process using adequate ventilation.

More detail about Safety information, Please refer to MSDS（SDS）.

1. Supply and Storage

- -Quality Guarantee Period is 6 month after delivered with unopened condition.
- -Avoid moisture absorption to store (keep dry and ordinary temperature, avoid direct sunlight).
- -Recommend to storage in the airtight container after opening the package.

2. Injection Molding

■Preliminary drying

Recommend the preliminary drying of compound before molding by following reasons

- Stabilize the molding condition.
- Stabilize the appearance and strength of molding product.
- Unopened compound could possibly absorb moisture according to the storage conditions.

Recommend the convection type dehumidifier hopper dryer for effective drying.

- Drying optimal condition varies according to the moisture absorbency of compound and seasons.
  Select drying conditions on the molded part quality accordingly

Recommended drying condition（The dehumidification type dryer）

Nylon 6 base TS – 1＊○○	80 ℃ / 3 Hours
Nylon 12 base TS – 2＊○○	80 ℃ / 3 Hours
Thermal resistant Nylon base TS – 3＊○○	120 ℃ / 2 Hours
PPS base TS – 6＊○○ TM – 6＊○○	120 - 130 ℃ / 1 -2 Hours

■Molding machine

Quality of molded product varies according to the size of machine, spec of die and maintenance condition.

Recommend to use abrasion proof screw and cylinder.

Recommend the Screw to be equipped with the ring to prevent back-flow.

■ Temperature of cylinder

Recommend not to produce an increase in temperature more than necessary inside the cylinder.

Recommend not to leave the compound long residence time inside the cylinder.

■ Mold

The mould must be wear-resistant.

Temperature of cylinder and mold（Reference conditions）

	Rear 〔℃〕	Front〔℃〕	Nozzle〔℃〕	Die〔℃〕
Nylon 6 base	225~235	250~265	245~260	100~135
Nylon 12 base	215~240	225~245	200~220	100~140
Thermal resistant Nylon base	300~320	305~325	310~320	120~140
PPS base TS – 6＊○○	300~320	320~345	310~340	110~145
PPS base TM – 6＊○○	280~290	290~300	280~290	135~150

Question about handling and molding our compound other than those above,
we will reply immediately.

MATE CO., LTD.
526-3, Saeki, Wake-Cho, Wakegun, Okayama, 709-0514 JAPAN
TEL:+81-869-88-0243 / FAX:+81-869-88-0204