Description

Image







Caption

1. Super light camera body in die-cast magnesium. © Canon 2. Magnesium Alloy body of a camera (Sony Alpha 900 made and owned by Sony Corporation). © SkywalkerPL at en.wikipedia - (CC BY 3.0) 3. Cast magnesium wheel alloy of a high-end sports car. © Klau

The material

Magnesium is a metal almost indistinguishable from aluminum in color, but of lower density. It is the lightest of the light-metal trio (with partners aluminum and titanium) and light it is: a computer case made from magnesium is barely two thirds as heavy as one made from aluminum. It, aluminum and magnesium are the mainstays of airframe engineering. Only beryllium is lighter, but its expense and potential toxicity limit its use to special applications only. Magnesium is flammable, but this is only a problem when it is in the form of powder or very thin sheet. It costs more than aluminum but nothing like as much as titanium. Die and investment castings account for about 75% of magnesium alloy consumption. Almost all are used for components that remain below 150 C in service, since above this temperature most Mg alloys soften.

Compositional summary

Mg+alloying elements, e.g. Al, Mn, Si, Zn, Cu, Li, rare earth elements

General properties

Density		1.75e3	-	1.87e3	kg/m^3
Price	*	2.9	-	3.49	GBP/kg
Date first used		1930			

Mechanical properties

Young's modulus		42	-	47	GPa
Shear modulus		15	-	18	GPa
Bulk modulus		35	-	41	GPa
Poisson's ratio		0.29	-	0.31	

Yield strength (elastic limit)		70	-	215	MPa
Tensile strength		119	-	283	MPa
Compressive strength		70	-	215	MPa
Elongation		1	-	10	% strain
Hardness - Vickers		35	-	90	HV
Fatigue strength at 10^7 cycles	*	60	-	125	MPa
Fracture toughness	*	12	-	18	MPa.m^0.5
Mechanical loss coefficient (tan delta)		0.001	-	0.03	

Thermal properties

Melting point		447	-	649	°C
Maximum service temperature		130	-	190	°C
Minimum service temperature		-83.2	-	-53.2	°C
Thermal conductor or insulator?		Good conductor			
Thermal conductivity		50	-	125	W/m.°C
Specific heat capacity		955	-	1.06e3	J/kg.°C
Thermal expansion coefficient		24.6	-	28	µstrain/°C

Electrical properties

Electrical conductor or insulator?		Good conductor			
Electrical resistivity		5.5	-	15	µohm.cm

Optical properties

Transparency		Opaque			

Critical Materials Risk

High critical material risk?		Yes			

Processability

Castability		4	-	5	
Formability		2	-	3	
Machinability		5			
Weldability		4			
Solder/brazability		2	-	3	

Durability: water and aqueous solutions

Water (fresh)		Excellent			
Water (salt)		Excellent			
Soils, acidic (peat)		Limited use			
Soils, alkaline (clay)		Limited use			

Wine	Acceptable

Durability: acids

Acetic acid (10%)	Limited use
Acetic acid (glacial)	Unacceptable
Citric acid (10%)	Limited use
Hydrochloric acid (10%)	Unacceptable
Hydrochloric acid (36%)	Unacceptable
Hydrofluoric acid (40%)	Acceptable
Nitric acid (10%)	Unacceptable
Nitric acid (70%)	Unacceptable
Phosphoric acid (10%)	Unacceptable
Phosphoric acid (85%)	Unacceptable
Sulfuric acid (10%)	Acceptable
Sulfuric acid (70%)	Unacceptable

Durability: alkalis

Sodium hydroxide (10%)	Acceptable
Sodium hydroxide (60%)	Acceptable

Durability: fuels, oils and solvents

Amyl acetate	Excellent
Benzene	Excellent
Carbon tetrachloride	Excellent
Chloroform	Excellent
Crude oil	Limited use
Diesel oil	Excellent
Lubricating oil	Excellent
Paraffin oil (kerosene)	Excellent
Petrol (gasoline)	Excellent
Silicone fluids	Excellent
Toluene	Excellent
Turpentine	Excellent
Vegetable oils (general)	Excellent
White spirit	Excellent

Durability: alcohols, aldehydes, ketones

Acetaldehyde	Excellent
Acetone	Excellent

Ethyl alcohol (ethanol)	Excellent
Ethylene glycol	Excellent
Formaldehyde (40%)	Excellent
Glycerol	Excellent
Methyl alcohol (methanol)	Excellent

Durability: halogens and gases

Chlorine gas (dry)	Limited use
Fluorine (gas)	Acceptable
O2 (oxygen gas)	Unacceptable
Sulfur dioxide (gas)	Excellent

Durability: built environments

Industrial atmosphere	Acceptable
Rural atmosphere	Excellent
Marine atmosphere	Limited use
UV radiation (sunlight)	Excellent

Durability: flammability

Flammability	Non-flammable

Durability: thermal environments

Tolerance to cryogenic temperatures	Unacceptable
Tolerance up to 150 C (302 F)	Acceptable
Tolerance up to 250 C (482 F)	Unacceptable
Tolerance up to 450 C (842 F)	Unacceptable
Tolerance up to 850 C (1562 F)	Unacceptable
Tolerance above 850 C (1562 F)	Unacceptable

Geo-economic data for principal component

Annual world production, principal component	1.15e6			tonne/yr
Reserves, principal component	2.4e15	-	2.54e15	tonne

Primary material production: energy, climate change and water

Climate change (CO2-eq) (virgin grade production)	* 21.3	-	23.4	kg/kg
Embodied energy (virgin grade production)	* 309	-	341	MJ/kg
Water usage	* 934	-	1.03e3	l/kg

Material processing: energy

Metal casting, embodied energy	* 46	-	55.1	MJ/kg

Metal powder forming, embodied energy	* 56.9	-	71	MJ/kg
Chemical vapor deposition (CVD), embodied energy	* 1.33e4	-	1.5e4	MJ/kg
Machining, coarse, embodied energy	* 17.8	-	20	MJ/kg
Machining, fine, embodied energy	* 24.3	-	27.8	MJ/kg
Machining, grinding, embodied energy	* 30.8	-	35.7	MJ/kg
Machining, laser, CO2, embodied energy	* 1.58	-	1.79	MJ/m

Material processing: climate change

Metal casting, climate change (CO2-eq)	* 3.29	-	4	kg/kg
Metal powder forming, climate change (CO2-eq)	* 4.63	-	5.78	kg/kg
Chemical vapor deposition (CVD), climate change (CO2-eq)	* 1.09e3	-	1.24e3	kg/kg
Machining, coarse, climate change (CO2-eq)	* 1.17	-	1.31	kg/kg
Machining, fine, climate change (CO2-eq)	* 1.59	-	1.82	kg/kg
Machining, grinding, climate change (CO2-eq)	* 2.02	-	2.34	kg/kg
Machining, laser, CO2, climate change (CO2-eq)	* 0.13	-	0.147	kg/m

Recycling and end of life

Recycle	✓			
Functional recycle	✗			
Climate change (CO2-eq), recycling	* 8.09	-	8.89	kg/kg
Embodied energy, recycling	* 12.4	-	13.6	MJ/kg
Recycle fraction in current supply	33			%
Combust for energy recovery	✗			
Landfill	✓			
Biodegrade	✗			
Toxicity rating	Non-toxic			
A renewable resource?	✗			

Environmental notes

Magnesium is the fifth most abundant metal in the Earth's crust, and the third in its oceans - and it can be extracted economically from both (the Dead Sea, thick with dissolved salts - is the best source of all). But its extraction is very energy intensive, consuming three times more per unit weight than commodity polymers and nearly twice as much as aluminum. It can be recycled, and doing this uses barely one fifth as much energy.

Supporting information


Design guidelines

The push for compact, light, electronics (laptops, mobile phones) and light-weight vehicles (wheels, in-cabin metal parts) has prompted designers to look harder at magnesium alloys than ever before, and has stimulated production and driven prices down. What does it offer^- Magnesium has a low density, good mechanical damping, much better thermal conductivity than steel, less good electrical conductivity than copper and aluminum, but still good. It survives well in the protected environment of a house or office, but it corrodes badly in salt water and acids; even sweat is enough to tarnish it, so it has to be coated. It is easy to machine, but because of its low stiffness, parts must be firmly clamped while doing so. Magnesium alloys are designed for specific forming purposes. Some (like AZ63, AZ92 and AM100) have been formulated for investment casting; the AZ91 range are used for die casting. Most magnesium alloys can be welded using TIG or MIG methods; and soldering and adhesive bonding are both feasible. Spot and seam welds are possible but only in low stress applications; riveting is better, provided aluminum rivets are used to avoid galvanic corrosion.

Technical notes

The classification system of the American Society for Testing Materials (ASTM) is the most widely used. In this system, the first two letters indicate the principal alloying elements, thus: A = aluminum, C = copper, E = rare earths, K = zirconium, L = lithium, M = manganese, S = silicon, Z = zinc. The letter corresponding to the element present in the greatest quantity is used first; if they are equal, they are listed alphabetically. The letters are followed by numbers that list the amount of the principal alloying elements in weight % rounded to the nearest whole number; thus AZ91 means the alloy 90% Mg, 9% Al and 1% Zn; LA141 means the alloy 85% Mg, 14% Li and 1% Al.

Phase diagram



Phase diagram description

Cast magnesium alloys are based on alloys of magnesium (Mg) with 2 - 9% aluminum (Al), some with additions of zirconium, manganese or copper. This is the magnesium - aluminum phase diagram.

Typical uses

Aerospace, automotive, sports goods such as bicycles, nuclear fuel cans, vibration damping and shielding of machine tools, engine case castings, crank cases, transmission housings, automotive wheels, ladders, housings for electronic equipment, particularly mobile phone and portable computer chassis, camera bodies, office equipment, marine hardware and lawnmowers.

Tradenames

Electron, Dowmetal, Revere alloy, Eclipsalloy

Links

ProcessUniverse

Producers

Reference

Values marked * are estimates.
ANSYS, Inc. provides no warranty for this data.

Values marked * are estimates.
ANSYS, Inc. provides no warranty for this data.