



Infection of orthopedic implants with emphasis on bacterial adhesion process and techniques used in studying bacterial-material interactions

Marta Ribeiro, Fernando J. Monteiro & Maria P. Ferraz

To cite this article: Marta Ribeiro, Fernando J. Monteiro & Maria P. Ferraz (2012) Infection of orthopedic implants with emphasis on bacterial adhesion process and techniques used in studying bacterial-material interactions, Biomatter, 2:4, 176-194, DOI: [10.4161/biom.22905](https://doi.org/10.4161/biom.22905)

To link to this article: <https://doi.org/10.4161/biom.22905>



Copyright © 2012 Landes Bioscience



Published online: 01 Oct 2012.



Submit your article to this journal [↗](#)



Article views: 9723



View related articles [↗](#)



Citing articles: 192 View citing articles [↗](#)

Infection of orthopedic implants with emphasis on bacterial adhesion process and techniques used in studying bacterial-material interactions

Marta Ribeiro,^{1,2,*} Fernando J. Monteiro^{1,2} and Maria P. Ferraz^{1,3}

¹Instituto de Engenharia Biomédica; Universidade do Porto; Porto, Portugal; ²Departamento de Engenharia Metalúrgica e Materiais; Universidade do Porto; Porto, Portugal;

³Centro de Estudos em Biomedicina; Universidade Fernando Pessoa; Porto, Portugal

Keywords: orthopedic implants, bone infections, bacterial adhesion, *Staphylococcus*, bacteria-material interactions

Staphylococcus comprises up to two-thirds of all pathogens in orthopedic implant infections and they are the principal causative agents of two major types of infection affecting bone: septic arthritis and osteomyelitis, which involve the inflammatory destruction of joint and bone. Bacterial adhesion is the first and most important step in implant infection. It is a complex process influenced by environmental factors, bacterial properties, material surface properties and by the presence of serum or tissue proteins. Properties of the substrate, such as chemical composition of the material, surface charge, hydrophobicity, surface roughness and the presence of specific proteins at the surface, are all thought to be important in the initial cell attachment process. The biofilm mode of growth of infecting bacteria on an implant surface protects the organisms from the host immune system and antibiotic therapy. The research for novel therapeutic strategies is incited by the emergence of antibiotic-resistant bacteria. This work will provide an overview of the mechanisms and factors involved in bacterial adhesion, the techniques that are currently being used studying bacterial-material interactions as well as provide insight into future directions in the field.

Introduction

Bone and joint degenerative and inflammatory problems affect millions of people worldwide. In fact, they account for half of all chronic diseases in people over 50 years of age in developed countries. In addition, it is predicted that the percentage of the population over 50 years affected by bone diseases will double by 2020.¹

An artificial implant must possess both structural and surface compatibility with the host tissue. With particular reference to bone implants, mechanical and physico-chemical compatibility is required. Each type of material used in orthopedic devices has its

own advantages particularly suitable for specific applications.² Orthopedic implant devices are intended to restore the function of load-bearing joints which are subjected to high levels of mechanical stresses, wear and fatigue in the course of normal activity. These devices include prostheses for hip, knee, ankle, shoulder and elbow joints. They also include the fracture fixation devices such as wires, pins, plates, screws, etc. Metals (Ti-6Al-4V, Co-Cr-Mo and stainless steel), polymers [poly(methyl methacrylate) (PMMA) and ultrahigh-molecular-weight polyethylene (UHMWPE)] and ceramics (alumina, zirconia and hydroxyapatite) are the three classes of materials that are most commonly used for fabricating orthopedic implants.³ Although Ti alloys, Co-Cr alloys, and stainless steel alloys are commonly used in orthopedic devices, Ti alloys and Co-Cr alloys are the most common metals used in total-joint arthroplasty (TJA) devices.³ For example, Co-Cr alloys and ceramics are best suited for bearing surfaces, such as femoral heads, because of their superior hardness and resistance to wear.³ Ti alloys are commonly used for nonbearing surface components (femoral necks, stems and porous coatings) instead of Co-Cr or stainless steel because of their superior resistance to corrosion and because their torsional and axial stiffness are closer to those of bone, resulting in less stress shielding of bone compared with other alloys.³ Greater ductility (3-fold better percentage of elongation at fracture) of stainless steel relative to titanium and Co-Cr makes stainless steel ideal for fixation cables used in total-knee arthroplasty procedures.³ Polymers are commonly used in orthopedics as articulating surfaces of joint replacements and as interpositional cementing material between bone and implant surfaces. The most common polymers used in TJA products are ultrahigh molecular weight polyethylene (UHMWPE) and polymethylmethacrylate (bone cement or PMMA). PMMA is used for fixation of joint replacement implants.⁴ The most important application of bioactive ceramics such as hydroxyapatite has been the coating of orthopedic metal implants, at locations where a strong interface with bone is required (i.e., femoral stems and acetabular metal-backs for the hip joints and tibial and femoral components for the knee joints).⁵ Alumina and zirconia are primarily used in the fabrication of femoral heads.⁶ On the other hand, the introduction of an implant in the body is always associated with the risk of microbial infection, particularly for the fixation of

*Correspondence to: Marta Ribeiro; Email: ribeiro_marta88@hotmail.com
Submitted: 02/13/12; Revised: 10/19/12; Accepted: 11/14/12
<http://dx.doi.org/10.4161/biom.22905>

open-fractured bones and joint-revision surgeries.⁷ Infection is a major problem in orthopedics leading to implant failure. It is a challenging task to treat orthopedic implant infections that may lead to implant replacement and, in severe cases, may result in amputation and mortality.⁸ Sources of infectious bacteria include the environment of the operating room, surgical equipment, clothing worn by medical and paramedical staff, resident bacteria on the patient's skin and bacteria already residing in the patient's body.⁵ Implant-associated infections are the result of bacteria adhesion to an implant surface and subsequent biofilm formation at the implantation site.⁹ Formation of biofilm takes place in several stages, starting with rapid surface attachment, followed by multilayered bacterial cell proliferation and intercellular adhesion in an extracellular polysaccharide matrix.¹⁰ The formation of biofilms on medical devices presents three major problems. First, bacterial communities on these surfaces represent a reservoir of bacteria that can be shed into the body, leading to a chronic infection. Second, biofilm bacteria are highly resistant to treatment with antibiotics; therefore, once these bacterial communities form, they are extremely difficult to eliminate with conventional antimicrobial therapies. Finally, because host responses and antimicrobial therapies are often unable to eliminate bacteria growing in a biofilm, a chronic inflammatory response at the site of the biofilm may be produced.¹¹

If bacterial adhesion occurs before tissue regeneration takes place, host defenses often cannot prevent surface colonization for certain bacterial species that are capable of forming a protective biofilm layer. Therefore, inhibiting bacterial adhesion is essential to prevent implant-associated infection, because biofilm are extremely resistant to both the immune system and antibiotics.^{12,13} Therefore, to succeed in orthopedic implants, implant materials must be habitable by bone-forming cells (favoring adhesion of osteoblasts), hinder formation of soft connective tissue (hindering adhesion of fibroblasts) and be anti-infective (discouraging bacterial adhesion).¹⁴

Bacterial Infections of Orthopedic Implants

Tens of millions of medical devices are used each year and, in spite of many advances in biomaterials, a significant proportion of each type of device becomes colonized by bacteria and becomes the focus of an implant-related infection.¹⁵ A very large proportion of all implant-related infections are caused by staphylococci (roughly four out of five), and two single staphylococcal species, respectively *Staphylococcus aureus* and *Staphylococcus epidermidis*, account together for two out of three infection isolates.¹⁶ They represent, in absolute, the main causative agents in orthopedics.^{16,17} While this review relates to bacteria in general, more emphasis is given to *S. aureus* and *S. epidermidis* since they are the main causative agents of implant-related infections in orthopedics.

Staphylococcus. Bacteria of the genus *Staphylococcus* are Gram-positive, nonspore forming facultative anaerobes that grow by aerobic respiration or fermentation, with diameters of 0.5–1.5 µm. They are characterized by individual cocci, which divide in more than one plane to form grape-like clusters.¹⁸

Staphylococcus comprises up to two-thirds of all pathogens in orthopedic implant infections and they are the principal causative agents of two major types of infection affecting bone, septic arthritis and osteomyelitis, which involve the inflammatory destruction of joint and bone; these infections are difficult to treat because of the ability of the organisms to form small colonies and to grow into biofilms. Many *Staphylococcus* strains, particularly *S. epidermidis* and some *S. aureus* strains, produce biofilm.^{18–20}

Staphylococcus aureus. *Staphylococcus aureus* is an important nosocomial pathogen, able to cause a variety of human disease conditions. It can often be found as a commensal and a transient or persistent part of the resident flora of the skin and anterior nares in a large proportion (20–50%) of the human population. However, when cutaneous/mucous barriers are breached, severe and at times life threatening infections can develop. Nosocomial infections by *S. aureus* are particularly frequent in immunocompromised and severely debilitated patients, and prevail in the presence of indwelling medical devices.^{18,21–23}

Treatment of *S. aureus* infections is often complex, namely due to the emergence of methicillin-resistant *S. aureus* (MRSA) strains and resistance to other classes of antibiotics. Because of its pathogenic potential and complexity of its treatment, MRSA has received more attention than its methicillin-sensitive counterpart (MSSA). MRSA are resistant to β -lactam antibiotics (oxacillin, penicillin and amoxicillin), including third generation cephalosporins, streptomycin, tetracycline and sulfonamides; and upon exposure to vancomycin and other glycopeptide antibiotics, certain MRSA strains become less susceptible to these antibiotics.^{18,21}

S. aureus possesses several cell-surface adhesion molecules that facilitate its binding to bone matrix. Binding involves a family of adhesins that interact with extracellular matrix (ECM) components and these adhesins have been termed microbial surface components recognizing adhesive matrix molecules (MSCRAMMs). Specific MSCRAMMs are needed for the colonization of specific tissues and for the adhesion to biomaterials and to the ECM proteins deposited on the biomaterial surface. Particular MSCRAMMs include fibronectin-binding proteins, fibrinogen-binding proteins, elastin-binding adhesin and collagen-binding adhesin. A number of these adhesins have already been thoroughly investigated and identified as critical virulence factors implicated in various phases of infection, including early colonization, invasion, tissue localization and cell internalization.^{18,24,25}

In recent years, the polysaccharide intercellular adhesin (PIA) has been found in many *S. aureus* strains, and is required for biofilm formation and bacterium-bacterium adhesion.¹⁷ This adhesin is responsible for the production of the extracellular polysaccharide matrix that makes up the biofilm. It is known that once a biofilm has formed, the bacteria within the biofilm are protected from phagocytosis and antibiotics.¹⁸

S. aureus produces virulence factors to facilitate disease causation, and rapidly develops antimicrobial resistance. The cell-surface virulence factors include the microbial surface components recognizing adhesive matrix molecules

(MSCRAMMs) as receptors in the human host, other surface proteins, polysaccharide intercellular adhesin and capsular polysaccharides. The cell-surface MSCRAMMs typically are produced during exponential growth phase. The role of these various virulence factors is to provide nutrients required for survival in the host, and microbial cell protection from the host immune system during lesion formation. The secreted virulence factors, typically produced during the post-exponential and stationary phases, include a large group of exoenzymes, such as proteases, glycerol ester hydrolase (lipase) and nucleases that make nutrients available to the microorganism.¹⁸

Staphylococcus epidermidis. *Staphylococcus epidermidis* is the most frequently isolated member of the group of coagulase-negative staphylococci (CoNS) from implant-associated infections and they are associated with nosocomial or hospital-acquired infections, and have been found to be more antibiotic resistant than *S. aureus*.¹⁷ This group is diagnostically distinguished from *S. aureus* by its inability to produce coagulase.^{18,26,27}

S. epidermidis very often becomes the major infective agent in compromised patients, such as drug abusers and immunocompromised patients (patients under immunosuppressive therapy, AIDS patients and premature newborns). The entry door into the human body in all of these infections is usually an intravascular catheter.²⁷ The pathogenesis of implant-associated *S. epidermidis* infections is characterized by its ability to colonize a surface and form a thick, multilayered biofilm, often referred to as slime. This biofilm is composed of an extracellular polysaccharide known as polysaccharide intercellular adhesin (PIA), which is essential for *S. epidermidis* biofilm formation. PIA production is also known to protect *S. epidermidis* from phagocytosis and other major components of the host defense system. Generally, the success of *S. epidermidis* as a pathogen has to be attributed to its ability to adhere to surfaces and to remain there, under the cover of a protecting extracellular material, in relative silence.^{18,26-29}

S. epidermidis does not produce many toxins and tissue damaging exoenzymes, as does *S. aureus*. To date, few ECM recognizing adhesins have been identified for *S. epidermidis*; however, adhesins to fibronectin, fibrinogen, vitronectin and collagen have been identified.^{18,27}

Bone tissue infections. Bone tissue infections, namely osteomyelitis, septic arthritis and prosthetic joint infections (PJI), still represent the worst complications of orthopedic surgery and traumatology. The main pathways of infection for osteomyelitis, septic arthritis and PJI are either hematogenous, resulting from bacteremia; contiguous, when the infection is transmitted from local tissue; or direct, resulting from infiltration of bone, often following injury, surgery or implantation of a foreign body, such as joint replacement.^{20,30-33}

Osteomyelitis. Osteomyelitis describes a range of infections in which bone is colonized with microorganisms, with associated inflammation and bone destruction. The occurrence, type, severity and clinical prognosis of osteomyelitis depend on the interplay of a triad of factors, including the characteristics and virulence of the infecting pathogen, the properties of the host and the source of infection.^{20,30}

The most common etiologic agents causing osteomyelitis are *Staphylococcus aureus*, *Pseudomonas aeruginosa*, *Staphylococcus epidermidis* and *Escherichia coli*. Historically, *S. aureus* has been the dominant pathogen for all classes of osteomyelitis, accounting for 45% of infections; however, the appearance of the microorganism dropped to 27% by 1988.^{30,34}

The establishment of osteomyelitis begins with the infiltration of microorganisms into the body. Early infections are usually related to trauma or contamination during surgery; however, a number of improvements in surgical procedures have been responsible for reducing the infection rate. Late infections, which may not occur until after a number of months postoperatively, can also result from bacterial contamination during trauma, surgery or via remote infections. In many of these cases, bacteria introduced during trauma or surgery became dormant for an extended period of time.^{30,34}

Haematogenous osteomyelitis most frequently affects children and the elderly.³⁵ In children, the incidence is typically between 1 in 5,000 and 1 in 10,000.³⁶ It has been argued that the incidence of hematogenous osteomyelitis is decreasing with an annual fall in childhood cases of 0.185 per 100,000 people recorded in Glasgow, Scotland between 1970 and 1997.³⁶⁻³⁸ Conversely, osteomyelitis resulting from direct infection is reported as being increased.^{38,39} This is probably due to motor-vehicle accidents and the increasing use of orthopedic fixation devices and total joint implants.³⁸

Implanted biomaterials can act as an avenue for both bacterial contamination and colonization toward the development of osteomyelitis. The mechanisms of infection are quite complex and vary with the species of bacteria. If the conditions are favorable, bacteria create an initial attachment to the surface. A permanent attachment develops as protein adhesin-receptors form along with a polysaccharide film after the distance between the cell and the surface is sufficiently reduced. Because biomaterials do not elicit an antiphagocytic reaction toward bacteria after adhesion, these are able to multiply and colonize freely on implant surfaces.³⁴

Septic arthritis. Septic arthritis is a joint disease typified by bacterial colonization and rapid joint destruction and it manifests as a serious infection characterized by pain, fever, swelling and even loss of function in one or more affected joints.^{20,31} The most commonly involved joints are the knees and hips.³¹

In all age and risk groups, the most frequent causative organisms identified are *Staphylococcus aureus* followed by other gram-positive bacteria, including streptococci.^{40,41}

Numerous different factors have been identified for developing of septic arthritis. These factors include rheumatoid arthritis or osteoarthritis, joint prosthesis, low socioeconomic status, intravenous drug abuse, alcoholism, diabetes, previous intra-joint corticosteroid injection and cutaneous ulcers.⁴¹

The yearly incidence of septic arthritis is between 2 and 10 in 100,000 in the general population but it may be as high as 30–70 per 100,000 in rheumatoid arthritis patients or recipients of prosthetic joints⁴²⁻⁴⁴ and is more common in children than in adults, and in males rather than in females.⁴⁵ The incidence of septic arthritis seems to be rising, and this increase is linked to augmented orthopedic-related infection⁴⁶ and an aging population,

more invasive procedures being undertaken and enhanced use of immunosuppressive treatment.⁴⁶

Mortality for septic arthritis varies in different studies, but seems to be around 11% for monoarticular sepsis.⁴⁷ In view of the 11% mortality rate for septic arthritis, patients should be admitted to hospital for prompt assessment, supportive care and intravenous antibiotic treatment, along with measures to aspirate pus from the joint.

Prosthetic joint infections. The implantation of prosthetic joints along with the use of other implantable orthopedic devices (e.g., pins, screws, plates and external fixators) has improved the quality of life greatly and restored function to patients suffering from debilitating bone and joint disease or injury. Based on conservative estimates, millions of people worldwide have some form of prosthetic joint or other implantable orthopedic device. Among the possible complications associated with implantation, infection is the most serious and occurs in 1 to 13 percent of the cases; the resulting consequences include postoperative prosthesis failure, chronic pain and immobility.³²

Prosthetic joint infections (PJIs) occur less frequently than aseptic failures but represent the most devastating complication. These infections are a major threat, as therapy is difficult, resulting in a significant increase in hospitalization-related morbidity and mortality.^{48,49}

The most common agents are *Staphylococcus aureus* and *Staphylococcus epidermidis*, which account for close to 65% of PJIs. They are the most commonly reported microorganisms both in early and late infections and in total knee and hip arthroplasty.⁴⁸

Table 1 summarizes the classification of prosthetic joint infection according to the route of infection and the time of symptom onset after implantation.⁵⁰

Numerous different factors have been identified as increasing a patient's risk for developing an infection of a prosthetic joint or orthopedic implant. These factors include rheumatoid arthritis, immunocompromised states, diabetes mellitus, poor nutritional status, obesity, psoriasis, long-term urinary catheterization, extreme age, surgical site infection and human immunodeficiency virus (HIV).^{32,48}

Prosthetic joint infections (PJIs) of total hip arthroplasty (THA) or total knee arthroplasty (TKA) occur with an incidence

of 1.5–2.5% for primary THA or TKA, respectively, whereas revision THA or TKA carries a respective infection risk of 3.2% or 5.6%.⁵¹ Additionally, prosthetic joint infection is an economic burden; the estimated cost of treating an infected prosthetic joint in the US is \$50,000 to \$60,000.⁵² The attendant mortality was estimated, in the 1970s and 1980s, to be between 2.7% and 18%⁵³ in older patients. Fisman et al. have estimated the mortality attendant to surgical intervention for PJI to be 0.4–1.2% for 65-y-old patients and 2–7% for 80-y-old patients.⁵⁴ The mortality reported since 1989 has ranged between 1% and 2.7%.⁵⁵ In patients with primary joint replacement, the infection rate in the first two years is usually < 1% in hip and shoulder prostheses, < 2% in knee prostheses and < 9% in elbow prostheses.⁵⁶ In addition, infection rates after surgical revision are usually considerably higher (up to 40%) than after primary replacement.⁵⁶ In two studies in patients with prosthetic hip and knee associated infection, 29–45% had an early, 23–41% had a delayed, and 30–33% had a late infection.^{57,58}

In the future, it is expected that the incidence of prosthetic joint infections will further increase due to (1) better detection methods for microbial biofilms involved in prosthetic joint infections, (2) the growing number of implanted prostheses in the aging population and (3) the increasing residency time of prostheses, which are at continuous risk for infection during their implanted lifetime.⁵⁹

Bacterial Adhesion

The research of bacterial adhesion and its significance is a large field covering different aspects of nature and human life. Adhesion of bacteria to human tissue surfaces and implanted biomaterial surfaces is an important step in the pathogenesis of infection, whereby the bacteria can divide and colonize the surface.^{60–68}

Generally, any structures responsible for adhesive activities can be called adhesins. Bacteria may have multiple adhesins for different surfaces (different receptors). A receptor is a component on the surfaces of biomaterials or host tissue that is bound by the active site of an adhesion during the process of specific adhesion.⁶¹

During development of micro-colonies, some strains of bacteria, particularly *Staphylococcus epidermidis*, secrete a layer of

Table 1. Classification of prosthetic joint infections

Classification	Characteristic
According to the route of infection	
Perioperative	Inoculation of microorganisms into the surgical surgery or immediately thereafter
Hematogenous	Through blood or lymph spread from a distant focus of infection
Contiguous	Contiguous spread from an adjacent focus of infection (eg, penetrating trauma, pre-existing osteomyelitis, skin and soft tissue lesions)
According to the onset of symptoms after implantation	
Early infection (< 3 mo)	Predominantly acquired during implant surgery or the following 2 to 4 d and caused by highly virulent organisms
Delayed or low-grade infection (3–24 mo)	Predominantly acquired during implant surgery and caused by less virulent organisms
Late infection (> 24 mo)	Predominantly caused by hematogenous seeding from remote infections

Reproduced with permission from reference 50.

slime after adhering to the implant surface, making themselves less accessible to the host defense system and significantly decreasing antibiotic susceptibility. Slime, an extracellular substance (exopolymers composed mainly of polysaccharides) produced by the bacteria, may protect the bacteria from antibiotic therapy, physiologic shear, and possibly host cell-mediated defenses. Bacterial strains that do not produce slime are less adherent and less pathogenic.^{60-62,69}

These bacteria can remain quietly on the material surface for a long period of time until the environment allows them to overgrow, such as with decreased host immune activity or poor tissue in-growth around the prosthesis, and a clinical infection then occurs.⁶⁹

An accumulated biomass of bacteria and their extracellular materials (basically slime) on a solid surface is called a biofilm.^{61,69-71} Biofilms contain interstitial voids (water channels). Within biofilms, bacterial cells develop into organized and complex communities with structural and functional heterogeneity resembling multicellular organisms in which water channels serve as a rudimentary circulatory system. Release of cell-to-cell signaling molecules (quorum sensing) induces bacteria within a population to respond in concert by changing patterns of gene expression involved in biofilm differentiation.^{61,69,72}

Mechanisms of bacterial adhesion. Initial adhesion of bacteria to biomaterial surfaces is believed to be the critical event in the pathogenesis of foreign body infections.⁷³

Bacterial adhesion to a material surface can be described as a two-phase process including an initial, instantaneous and reversible physical phase (phase one) and a time-dependent and irreversible molecular and cellular phase (phase two).^{61,69,74}

From an overall physicochemical viewpoint, bacterial adhesion can be mediated by non-specific interaction forces, with a long-range character, and specific interactions forces acting in highly localized regions of the interacting surfaces, over distances smaller than 5 nm. Both specific and non-specific interactions may play an important role in the ability of the cell to attach to (or to resist detachment from) the biomaterial surface.^{61,69}

Physicochemical interactions between bacteria and material surfaces: phase one. Bacterial adhesion to surfaces consists of the initial attraction of the cells to the surface followed by adsorption and attachment. Bacteria move to or are moved to a material surface through the effects of physical forces, such as Brownian motion, van der Waals attraction forces, gravitational forces, surface electrostatic charge and hydrophobic interactions. These physical interactions are further classified as long-range and short-range interactions.^{61,69,75}

The long-range interactions (non-specific, distances > 50 nm) between cells and material surfaces are described by mutual forces, which are related to the distance and free energy. Short-range interactions become effective when the cell and the surface come into close contact (< 5 nm), these can be separated into chemical bonds (such as hydrogen bonding), ionic and dipole interactions and hydrophobic interactions. Bacteria are transported to the surface by the so-called long-range interactions and upon closer contact, short-range interactions become more important.^{64,69,75}

This initial attachment of bacteria to surfaces is the initial part of adhesion, which makes the molecular or cellular phase of adhesion possible.^{61,69}

Molecular and cellular interactions between bacteria and material surfaces: phase two. In the second phase of adhesion, molecular-specific reactions between bacterial surface structures and substratum surfaces become predominant. This implies a firmer adhesion of bacteria to a surface by the selective bridging function of bacterial surface polymeric structures, which include capsules, fimbriae or pili and slime. In fact, the functional part of these structures should be the adhesins, especially when the substrata are host tissues. Beyond phase two, certain bacterial strains are capable of forming a biofilm if provided with an appropriate supply of nutrients. During biofilm formation, bacteria secrete an exopolysaccharide layer that retains nutrients and protects the microorganisms from the immune response.^{61,69,75}

Factors influencing bacterial adhesion. Bacterial adhesion is an extremely complex process that is affected by many factors including the environmental factors, such as the presence of serum proteins or antibiotics, the bacterial properties and the material surface characteristics. A better understanding of the unique behavior of certain bacteria, the surface characteristics of the material and the relevant environment would make it possible for one to control the adhesion process by changing these factors.^{61,65,69,76-79}

Environment. Certain factors in the general environment, such as temperature, exposure time length, bacterial concentration, chemical treatment, the presence of antibiotics and the associated flow conditions affect bacterial adhesion.^{61,69}

Flow conditions are considered dominant factors that strongly influence the number of attached bacteria⁸⁰ as well as the biofilm structure and performance.⁸¹ The decreased bacterial adhesion at higher flow rates is clearly established. Katsikogianni et al.⁷⁴ showed the effect of flow conditions on bacterial adhesion to several substrates, and in most material, except diamond-like carbon (DLC) coated poly(vinyl chloride) (PVC) deposited by Atom Beam (A.B.), the number of adherent bacteria significantly decreased with the increase of shear rate from 150 sec⁻¹ to 1,500 sec⁻¹. DLC (A.B.) was the only material that exhibited a different behavior, and this difference appears to be associated with the significantly higher surface roughness values. Bacteria preferentially stick to rough surfaces and especially to irregularities that conform their shapes in order to maximize bacteria-surface contact area and probably protect themselves from shear forces.⁷⁴ In another study, Katsikogianni et al.⁸² also found that the number of adherent *S. epidermidis*, for several materials and for two bacterial strains, decreased with increasing shear rate, from 50 to 500 or 1,000 sec⁻¹, and especially when it reached 2,000 sec⁻¹.⁸² Therefore, it is generally considered that higher shear rates result in higher detachment forces that decrease the number of attached bacteria.^{74,82} However, there is an optimum flow rate for bacterial attachment reflecting the balance between the rate of delivery and the force acting on the attached bacteria.⁸³ Mohamed et al.⁸⁴ showed that in the case of higher number of receptors/cell *S. aureus* adhesion to collagen coated coverslips increased for shear rates between 50–300 sec⁻¹ and decreased for

shear rates above 500 sec⁻¹. However, in the case of lower number of receptors/cell this optimum flow rate was not clear.⁸⁴

Concentrations of electrolytes, such as KCl, NaCl and pH value of the culture environment also influence bacterial adhesion.^{61,69} Changes in pH can have a marked effect on bacterial growth and adhesion. Bacteria possess membrane-bound proton pumps that extrude protons from the cytoplasm to generate a transmembrane electrochemical gradient, i.e., the proton motor force.⁸⁵ The passive influx of protons in response to the proton motive force can be a problem for cells attempting to regulate their cytoplasmic pH.⁸⁶ Bacteria respond to changes in internal and external pH by adjusting the activity and synthesis of proteins associated with many different cellular processes.⁸⁶ Studies have shown that a gradual increase in acidity increases the chances of cell survival in comparison to a sudden increase by rapid addition of HCl.⁸⁷ This suggests that bacteria contain mechanisms in place which allow the bacterial population to adapt to small environmental changes in pH. However, there are cellular processes which do not adapt to pH fluctuations so easily. One such process is the excretion of exopolymeric substances (polysaccharides). Optimum pH for polysaccharide production depends on the individual species, but it is around pH 7 for most bacteria.⁸⁸ Hamadi et al.⁸⁹ investigated the adhesion of *Staphylococcus aureus* ATCC 25923 to glass at different pH values and observed that pH influenced bacterial adhesion. The images obtained by SEM showed that the adhesion behavior of *S. aureus* ATCC 25923 depended on the pH of the suspending medium and at highly acidic (pH 2 and pH 3) and alkaline conditions, the cells deposited in aggregate forms, while at pH 5 the aggregation phenomenon was absent. The quantitative adhesion (number of adhering cells to glass surface) showed that cells adhered strongly in the pH range 4 to 6 and weakly at highly acidic (pH 2 and pH 3) and alkaline conditions.⁸⁹ Kinnari et al.⁹⁰ studied whether the most common causative agents of orthopedic implant-related infections, *S. aureus* and *S. epidermidis*, can penetrate the ceramic pores and adhere particularly avidly to that surface at a slightly acidic pH, simulating conditions to which they may be exposed in vivo.⁹⁰ The isoelectric point of the materials at the surface-liquid interface changes with the decrease in pH following infection, surgery, trauma or aseptic implant loosening.^{90,91} On these occasions, the pH of the bone tissue environment often falls below pH 7, whereas in healthy tissues this pH value varies in the range 7.35 to 7.45.⁹⁰ The ceramic materials used by Kinnari et al.⁹⁰ were hydroxyapatite (HA) and biphasic calcium phosphate (BCP) that are widely employed as bone substitutes.⁹⁰ Their porosity and the decrease in surrounding pH as a result of surgical trauma may, however, pre-condition these materials to bacterial infections. The authors showed that when pH decreased from 7.4 to 6.8, the adherence of staphylococci both to HA and BCP surfaces decreased significantly. Moreover, in this study they observed that HA and BCP ceramics did not have pores large enough to allow the internalization of staphylococci. Therefore, their anti-adherent properties seemed to improve when pH value decreased, suggesting that HA and BCP bioceramics are not compromised upon orthopedic use.

The presence of antibiotics decreases bacterial adhesion depending on bacterial susceptibility and antibiotic concentration.^{69,78,92} Kohnen et al.⁹³ showed that *S. epidermidis* adhesion on catheters was reduced when catheters were impregnated with rifampin-sparfloxacin that were released slowly with time from catheter surface.⁹³ Stigter et al.⁹⁴ developed a biomimetic approach for coating titanium alloy (Ti6Al4V) implants with calcium phosphate containing an antibiotic. The authors showed that the coatings, containing tobramycin, were effective against the growth of *S. aureus* in a concentration-dependent manner. These results demonstrated the efficacy of the biomimetic coatings combined with tobramycin, to prevent local post-surgical infections in orthopedic surgery.⁹⁴ The most important fact is that bacteria normally grow as biofilms.⁹⁵ The bacteria in biofilms can be differentiated from free-floating planktonic forms by an extracellular polymeric substance, slower growth rate and the up- or down-regulation of certain genes. The extracellular polymeric substance acts as a filter and conduit for nutrients and minerals that are channeled to interior cells and protects cells from potentially harmful agents, including antibiotics.⁹⁶ The prevalence of biofilms in infections and on surfaces of medical implant devices has focused attention on the increased antibiotic resistance (10³-fold) of biofilm-resident bacteria vs. the more commonly studied planktonic (free-floating) form.⁹⁷ It is postulated that biofilms contribute to antibiotic resistance by at least three mechanisms: reduced antibiotic penetration across the extracellular polymeric substance, a favorable (e.g., anaerobic) environment within the inner layers and bacteria cell differentiation and role specialization providing increased protection.⁹⁸ Even if antibiotic therapy is effective against some of bacteria in a colony, surviving bacteria can feed themselves of left behind nutrients.⁹⁹ As a result, bacteria in biofilms survive exposure to concentrations of antibiotics 10³-fold higher than lethal values found for cells in suspension.⁹⁸ It has been suggested that if a low concentration of antibiotics or other drugs is able to prevent initial bacterial adherence to surfaces, the subsequent step of biofilm formation would also be inhibited.¹⁰⁰ However, it has previously been shown that in the case of staphylococcal strains the initial adherence and subsequent biofilm formation are two distinct phenomena.^{101,102} Cerca et al.²⁶ evaluated the adherence of several clinical isolates of coagulase-negative staphylococci (CoNS) to acrylic and the effect of sub-minimal inhibitory concentrations (sub-MICs) of vancomycin, cefazolin, dicloxacillin and combinations of these antibiotics on adherence and biofilm formation. They showed that most of these antibiotics resulted in effective reduction of bacterial adherence to acrylic, in some cases reaching over 70% adherence inhibition, and when strains with a high biofilm-forming capacity were grown in sub-MICs of those antibiotics, there existed combinations of the drugs that significantly inhibited biofilm formation. However, they also saw that most of the antibiotic combinations that inhibited adherence did not have a profound effect on biofilm formation. In general, these results indicated that the effect on adherence inhibition was greater than the effect on inhibiting biofilm formation.²⁶ Prado et al.¹⁰³ evaluated the susceptibility of planktonic and biofilm-associated organisms of *Streptococcus pneumoniae* to antibiotics. The authors

also realized that amoxicillin, erythromycin and levofloxacin were less active against biofilm-associated organisms as compared with their planktonic counterparts.¹⁰³ Thus, the most promising anti-infective strategies seek to inhibit bacterial adhesion prior to biofilm formation. Reducing bacterial adhesion during the initial 6 h period following implantation is particularly important to avoid device-associated infection.¹⁰⁴ Pagano et al.¹⁰⁵ evaluated the differences between a prophylactic and therapeutic approach to the CoNS biofilm problem. These authors showed that by adding low concentrations of linezolid or vancomycin before the bacteria could reach the surface, they were able to inhibit biofilm formation. However, if the application of the drug was delayed just by 6 h after initial adherence occurrence, the inhibition of biofilm formation was less effective.¹⁰⁵

All of these factors may influence bacterial adhesion by either changing physical interactions in phase one of adhesion or changing surface characteristics of bacteria or materials.⁶¹

Material surface characteristics. The factors influencing bacteria adherence to a biomaterial surface include chemical composition of the material, surface charge, hydrophobicity, surface roughness or physical configuration.^{61,69}

Surface chemistry influences bacterial adhesion and proliferation. Materials with different functional groups change bacterial adhesion in a manner depending on material hydrophobicity and charge.⁶⁹

Surface roughness is a 2-dimensional parameter of a material surface measured by roughness measuring systems. Biomaterials surface roughness is another relevant property for the bacterial adhesion process, with the irregularities of the material surfaces normally promoting bacterial adhesion and biofilm accumulation whereas an ultra-smooth surface does not favor bacterial adhesion and biofilm accumulation.¹⁰⁶ This is due to the increased surface area and depressions in the roughened surfaces that provide more favorable and additional sites for colonization.^{61,69} Oztürk et al. investigated the adhesion of biofilm forming *S. epidermidis* strain YT-169a on nitrogen (N) ion implanted as well as on as-polished CoCrMo alloy materials and the adhesion test results showed that *S. epidermidis* strain YT-169a adhere much more efficiently to the N implanted surfaces than to the as-polished CoCrMo alloy surface. This was attributed mainly to the rougher surfaces associated with the N implanted specimens in comparison with the relatively smooth surface of the as-polished specimen.¹⁰⁷

Teughels et al.¹⁰⁸ also found that an increase in surface roughness facilitated biofilm formation on implant surfaces.¹⁰⁸ However, the accumulation of bacteria in such locations depends largely on their size, cell dimension and division mode.¹⁰⁹ According to Katainen et al.,¹⁰⁹ surfaces may have roughness in several length scales, but due to the short range of the van der Waals interactions, roughness in the nanoscale ultimately determines the adhesion strength. This is corroborated by another study¹¹⁰ where the impact of nanometer-scale roughness on bacterial adhesion was tested and according to which, a reduction in the nanoscale roughness (of $R_a = 2.1$ nm to $R_a = 1.3$ nm) lead to a strong increase in the number of adhered bacteria. Therefore, it seems that roughness at a nanoscale can strongly influence initial attachment of bacteria, probably by providing the presence

of a greater number of contact points. Truong et al. have shown that the adhesion of bacterial cells on titanium surfaces is promoted by the presence of nanoscale topographical features.¹¹¹ Whitehead et al. have studied bacterial colonization on nanostructured titanium surfaces, and demonstrated improved colonization efficiency when surface roughness increases.¹¹² Webster et al.¹¹³ evaluated the adhesion of *Pseudomonas fluorescens* on nanophased alumina, compared with conventional grain size alumina substrates. They observed greater *P. fluorescens* attachment to nanophased as compared with conventional alumina. Moreover, the ability of a nanostructured surface to influence irreversible adhesion, attachment of *P. fluorescens* to alumina was followed after fibronectin was allowed to adsorb to the surfaces. Results of this study indicated a greater adhesion of *P. fluorescens* in this environment as well.¹¹³ Colon et al.¹¹⁴ examined the functions of *S. epidermidis* (known to be detrimental to orthopedic implant efficacy) and osteoblasts (or bone-forming cells) on ZnO and titania (TiO_2), that presented nanostructured compared with microstructured surface features. ZnO is a well-known antimicrobial agent and TiO_2 readily forms on titanium once implanted. When normalized to the projected surface area, they observed significantly decreased *S. epidermidis* colony forming units on nanophase compared with microphase ZnO as well as TiO_2 (by 60% and 69%, respectively) and osteoblast adhesion increased by 146% and 200% on nanophase compared with microphase ZnO and TiO_2 , respectively, leading to improved calcium mineral deposition on two nanophased ceramics: ZnO and TiO_2 . Although the exact mechanism is not known, some comments for why *S. epidermidis* adhesion decreased on these nanophase ceramics were made by these authors. For example, it has been suggested that ZnO reduces bacterial activity through the release of ZnO ions to the local environment, which alters protein adsorption and intracellular mechanisms pertinent to bacteria activities. Following this line of thought, two important properties may be responsible for decreasing bacterial adhesion on nanophased as compared with microphased ceramics: increased surface area and greater numbers of surface grain boundaries. Higher surface areas of nanophased as compared with microphased ZnO may result in the increased presence of soluble ZnO ions to disrupt bacteria activities. Moreover, the increased presence of soluble ZnO ions that disrupt bacterial activities may have resulted from the fact that greater material dissolution occurs at grain boundaries and more grain boundaries are present on the surfaces of nanophased compared with microphased ZnO. The aspect ratio of ZnO nanoparticles used in that study may also have influenced bacterial adhesion. Therefore, this study suggests that nanophased ZnO and TiO_2 may reduce *S. epidermidis* adhesion and increase osteoblastic performance required to promote the efficacy of orthopedic implants.¹¹⁴ Since clinically different prostheses or implant devices have different surface roughnesses that may play a role in bacterial adhesion and implant infection, more studies are needed to test the effects of a broader range of surface roughness values.

Physical configuration of a material surface is different from surface roughness and is rather complicated. It is a morphological description of the pattern of a material surface, such as a

monofilament surface, a braided surface, a porous surface or a grid-like surface, and it is a 3-dimensional parameter.^{61,69} Merritt et al.¹¹⁵ showed that porous materials had significantly higher infection rates than nonporous materials when implanted subcutaneously in mice that were challenged with *Staphylococcus aureus*. Therefore, the implant site infection rates are different between porous and dense materials with porous materials having a much higher rate. This implies that bacteria preferentially adhere and colonize on the porous surface.^{115,116} Moreover, bacteria adhere more to grooved and braided materials compared with flat ones, probably partially due to increased surface area. Physical configurations are routinely evaluated by scanning electron microscopy.^{61,69}

Metal surfaces have a high surface energy and are negatively charged and hydrophilic as shown by water contact angles, while polymers have low surface energy and are less electrostatically charged and hydrophobic.⁶¹ The structure of water in the region near any surface (such as solid material surface or bacterial surface) is perturbed over distances of up to several tens of molecular layers. Near a hydrophobic surface the water is less structured in terms of intermolecular hydrogen bonding between the water molecules, while near a hydrophilic surface water is more structured. Water contact angle (WCA) is a good example of the hydrophobic or hydrophilic nature of a surface. A high WCA represents hydrophobicity and a low WCA represents hydrophilicity.⁶¹ The hydrophobicity of a material surface has been evaluated mainly by contact angle measurement. Depending on the hydrophobicity of both bacteria and material surfaces, bacteria adhere differently to materials with different hydrophobicities.^{61,69} A microorganism may adhere to a substratum via the hydrophobic effect if the associating sites possess sufficiently high densities of apolar areas.¹¹⁷ In staphylococcal species, for instance, these hydrophobic areas are provided by proteins that are covalently bound to the cell wall.¹¹⁸ Charville et al.¹¹⁹ also showed that the pre-treatment of the PVC surface with bovine serum albumin (BSA) originated a decrease of surface hydrophobicity and reduced bacterial adhesion for each of the three species tested. Katsikogianni et al.⁷⁴ reported that diamond-like carbon coated PVC exhibited lower levels of *S. epidermidis* adhesion probably due to reduced hydrophobicity in comparison to uncoated PVC. Moreover, these authors also found that the fluorinated PVC presented a slightly higher level of *S. epidermidis* adhesion compared with the sterilized PVC, probably due to the increased hydrophobic properties of its surface.⁷⁴ In this study, Katsikogianni et al. also showed that *S. epidermidis* was a moderate hydrophobic bacterium; therefore adhesion was favored to the most hydrophobic substrate, which, in their case, was the fluorinated surface. However, the relatively small increase in *S. epidermidis* adhesion observed for the fluorinated surface may be due to the moderating effect associated with the reduction in surface roughness of the fluorinated PVC. The reduction in surface roughness would mean fewer sites for bacteria to adhere despite the more favorable hydrophobic surface.⁷⁴ The surface coating of substrates with proteins, such as BSA, bovine glycoprotein, or fatty-acid free

BSA decreases the hydrophobicity of the surface, leading to an inhibition of bacterial adhesion to surfaces.⁶¹

Bacterial characteristics. For a given material surface, different bacterial species and strains adhere differently since they have different physicochemical characteristics.^{61,69}

Surface hydrophobicity of bacteria is an important physical factor for adhesion, especially when the substrata surfaces are either hydrophilic or hydrophobic. Generally, bacteria with hydrophobic properties prefer hydrophobic material surfaces; the ones with hydrophilic characteristics prefer hydrophilic surfaces and hydrophobic bacteria adhere to a greater extent than hydrophilic bacteria.^{61,69} The hydrophobicity of bacteria varies according to bacterial species and is influenced by growth medium, bacteria age and bacterial surface structure.^{61,69} Walker et al.¹²⁰ found a decrease in adhesion and hydrophobicity of *Escherichia coli* during mid-exponential compared with the stationary phase. These observations were attributed to hydrophilic (acidic) proteins on the outer membrane of *E. coli* that decrease with the culture age, and consequently lead to a decrease in hydrophobicity and adhesion.¹²⁰ Kuntiya et al.¹²¹ also found that cell surface hydrophobicity of *Pseudomonas* sp decreased with increasing cellular age. Moreover, Kuntiya et al.¹²¹ showed that changing the medium composition by the addition of sodium chloride (0.5% w/v) resulted in a faster decrease in the cell surface hydrophobicity. The authors explained that there appear to be at least three possible reasons for the observed changes in hydrophobicity. First, the presence of salts has been reported to increase exopolysaccharide production although the mechanism is not completely understood; this may, however, account for a drop in hydrophobicity, if the exopolysaccharides are predominantly neutral or hydrophilic. Second, it has been reported that the production of exopolysaccharides is higher with aged cells. Third, nutrient starvation in the batch culture may be another reason for lowering the hydrophobicity since this also triggers the production of exopolysaccharides.¹²¹ Therefore, these results demonstrated that the presence of sodium chloride in the medium and cellular age did affect cell surface hydrophobicity and consequently biofilm formation and growth. It was reported that marked differences in both the slime production and *S. epidermidis* adhesion were observed when comparing four culture media.¹²² Slime production was notably poor in used peritoneal dialysis fluid (PUD). Adherent growth was markedly increased in a chemically defined medium (HHW) and synthetic dialysis fluid (SDF) but was poor in tryptic soy broth (TSB) and PUD when air containing 5% CO₂ was used. These findings emphasize the advantages in using chemically defined and biological fluids when studying slime production and adhesion of *S. epidermidis*.¹²²

The surface charge of bacteria may be another important physical factor for bacterial adhesion. The surface charge attracts ions of opposite charge in the medium and results in the formation of an electric double layer. Most particles acquire a surface electric charge in aqueous suspension due to the ionization of their surface groups. Bacteria in aqueous suspension are almost always negatively charged. The surface charge of bacteria varies according to bacterial species and is influenced by the growth

medium, the pH and the ionic strength of the suspending buffer, bacterial age and bacterial surface structure.^{61,69}

Serum or tissue proteins. It is well accepted that the protein adsorption is the first event following blood-material contact. The process of protein adsorption from an aqueous solution onto a solid surface is typically described in three steps. First, transportation of the protein from the solution toward the solid surface occurs. This is followed by attachment of the protein to the surface, and finally the protein structure undergoes a conformational change after adsorption.^{123,124}

When an implant is inserted into host tissue, small biomolecules including extracellular matrix (ECM) proteins adsorb onto the material surface to form a conditioned protein layer conducive to the adherence of free floating planktonic bacteria. The adhered bacteria then rapidly proliferate, recruit other cells and produce sticky secretions to form dense communities of attached cells called biofilms.^{125,126}

Serum or tissue proteins, such as albumin, fibronectin, fibrinogen, laminin, denaturated collagen and others, promote or inhibit bacterial adhesion by either binding to substrata surfaces, binding to the bacterial surface or by being present in the liquid medium during the adhesion period. Most of the bindings between bacteria and proteins are specific ligand-receptor interactions. Proteins may also change the adherent behavior of bacteria by changing bacterial surface physicochemical characteristics.^{61,69}

Fibronectin. Fibronectin (FN) is a protein that seems to promote adhesion of certain strains. FN clearly promotes *S. aureus* adhesion to the substratum surface.^{61,69} The binding of FN to a strain of *S. aureus* is specific, time-dependent and irreversible.^{61,69} Therefore, in the presence of FN, the adherence of *S. aureus* to foreign surfaces is significantly increased. Most studies showed that adsorbed FN promotes adherence of bacteria, especially *staphylococci* to biomaterials.^{61,69}

In the fibronectin molecule, two different binding sites are known for staphylococci adhesion: a first binding site in the N-terminal domain and a second near the C-terminus.¹²⁷ A study by surface plasmon resonance reported a higher affinity of *S. epidermidis* for the C-terminal fragment.¹²⁸ FN has played a crucial role in promoting bacterial adhesion to biomaterial surfaces.

In the last few decades, it has become clear that many bacteria possess fibronectin-binding proteins and that such proteins can bind to a growing number of sites in fibronectin.¹²⁹

S. aureus produces a number of surface proteins that are likely to be involved in the initial attachment to host tissues. These proteins, which have been termed MSCRAMMs (microbial surface components recognizing adhesive matrix molecules) bind specifically to components of the ECM. One such component of the ECM is fibronectin and it has binding sites for several pathogens.¹³⁰⁻¹³² *S. aureus* has been shown to specifically bind to adsorbed fibronectin. This bacterium has two fibronectin-binding proteins, FnBPA and FnBPB, encoded by the closely linked genes *fnbA* and *fnbB*, both of which contribute to the adherence to fibronectin-coated surfaces. At least one of two genes coding for the very similar surface proteins FnBPA and FnBPB is found in

almost all clinical isolates of *S. aureus*. This fibronectin-binding proteins (FnBPs) are involved in the pathogenesis of infection.¹³³⁻¹³⁵

S. epidermidis has also been reported to bind to a number of host cell extracellular matrix proteins, including fibronectin. In vitro studies have shown that *S. epidermidis* can bind to biomaterials coated with fibronectin.¹³¹ However, compared with *S. aureus* little is known about how *S. epidermidis* interacts with matrix proteins.¹³¹ It was found that in *S. epidermidis* 1585v overexpression of a 460 kDa truncated isoform of the ECM-binding protein (Embp) is necessary for biofilm formation. This *S. epidermidis* cell surface-associated protein termed Embp is a giant fibronectin-binding protein. Studies using Embp-expressing strains adhered significantly stronger to the fibronectin-coated surface compared with Embp-negative strains, indicating that Embp mediates *S. epidermidis* adherence to fibronectin. Furthermore, a quantitative association between fibronectin amounts used for plate coating and *S. epidermidis* adherence was found, indicating that here, fibronectin is essential for bacterial binding. These findings suggest that Embp plays a role during primary attachment to conditioned surfaces.^{136,137}

Albumin. Albumin adsorbed on material surfaces has shown obvious inhibitory effects on bacterial adhesion to polymer, ceramic and metal surfaces.^{61,69} An et al. showed that human serum albumin (HSA) inhibited *S. epidermidis* adhesion to cpTi surfaces by more than 95% after treatment of the cpTi sample with 200 mg/mL of HSA at 37°C for 2 h.⁶² Kinnari et al.¹³⁸ also showed that the level of adherence of both *S. aureus* and *P. aeruginosa* was significantly lower on the HSA-coated titanium surface than on the uncoated surface, with overall bacterial adhesion dependent on bacterial concentration. Adhesion of *S. aureus* on HSA-coated surfaces was significantly inhibited (from 82% to 95% depending on the concentration) and the adhesion of *P. aeruginosa* was inhibited from 29% to 37%. However, the inhibitory effects of HSA seem to depend on bacterial strain and species, as indicated by a previous study,¹³⁸ due to differences between bacterial strains in terms of their cell surface properties.¹³⁹ Albumin may inhibit adhesion through binding to the bacterial cells or by changing the substratum surface to more hydrophilic character.^{139,140}

In a study, a cross-linked albumin coating reduced the prosthetic infection rate in a rabbit model. Animals with albumin-coated implants had a much lower infection rate (3/11 animals, 27%) than those with uncoated implants (8/13 animals, 62%).¹⁴¹ This finding may represent a new method for preventing prosthetic infections.

However, in a recent study, Prado et al.¹⁴² showed that the effect of HSA on ability of *Streptococcus pneumoniae* strains to form biofilms on polystyrene plates was concentration dependent and HSA at concentrations from 40 to 25,000 µg/mL stimulated bacterial growth, while higher concentrations produced bacterial inhibition. The activity of HSA to prevent biofilm formation was concentration and strain dependent with the greater efficacy at concentrations 0.5 × minimum inhibitory concentration (MIC).¹⁴² Although the use of HSA for preventing biofilm formation on abiotic material has been proposed, these results

showing that certain concentrations of this compound produced stimulation of bacterial growth and even significantly increased biofilm formation by 2 out of the 11 strains tested could be a serious drawback of such approach.¹⁴² Naves et al.¹⁴³ also showed that HSA inhibited biofilm formation by all *E. coli* strains on polystyrene plates, but as a possible drawback, it stimulated bacterial growth.

Fibrinogen. Fibrinogen (Fg) is another important protein that mediates bacterial adhesion to biomaterials and host tissues.¹⁴⁴ Fibrinogen promotes bacterial adhesion by bridging the biomaterial surface with bacterial cell membrane receptors specific to Fg.¹⁴⁵ Such interactions are responsible for bacterial adhesion to medical devices in vivo, and bacteria possessing the ability to specifically bind surface-adsorbed Fg have been found to be responsible for significantly more clinical orthopedic device-associated infections than those without Fg-binding proteins.¹⁴⁶

Charville et al. showed that the extent of *S. aureus*, *S. epidermidis* and *Escherichia coli* adhesion was greater to PVC substrates with pre-adsorbed Fg compared with substrates without protein. However, the most significant increase was observed in the case of *S. aureus*, where adhesion to Fg-coated substrates was more than 5 times that of uncoated controls.¹¹⁹ Baumgartner et al.¹⁴⁷ also reported similar results for *S. aureus* adhesion to polyurethane surfaces with pre-adsorbed Fg. Pei et al.¹⁴⁸ found that *S. epidermidis* adhesion to control catheters without pre-adsorbed functional Fg was approximately half that observed at Fg-coated catheters. Collectively, the data indicate that the increase in bacterial adhesion in the presence of Fg is the result of specific Fg-mediated interactions between the bacterial cells and the substrate.¹⁴⁹⁻¹⁵³

Laminin. Laminin has a promoting effect on *S. aureus* and CNS adhesion to PMMA coverslips but to a lesser extent compared with the effects of FN and fibrinogen.¹⁴⁵ The presence of laminin receptors in *S. aureus* has also been reported.¹⁵⁴

Serum. The role of serum proteins in mediating bacterial adhesion has also been evaluated. Some studies have revealed a strong inhibition of adherence of bacteria to biomaterials in the presence of whole serum.^{155,156} Ardehali et al.¹⁵⁷ observed a marked, up to 5-fold, reduction in bacterial adhesion to polyurethane (PU) surfaces in the presence of bovine/human serum or plasma at 0.5% or higher concentration. Moreover, the authors reported that the inhibition of bacterial adhesion by serum is to a large extent due to apo-transferrin.¹⁵⁷

Techniques Used in Studying Bacterial-Material Interactions

Bacterial interactions are of prime importance in the many stages of the lifecycle of a bacterium.¹⁵⁸ Specific bacterial interactions are mediated by polymeric substances which are present on the outside of the cell wall. Highly diverse classes of surface constituents have been implicated in bacterial interactions, such as slime, surface proteins, lipopolysaccharides, lipoteichoic acids, capsules, lectins and fimbriae or pili.¹⁵⁸ These specific interactions between bacterial surface structures and substratum surfaces imply a firmer bacterial adhesion to a surface by the selective bridging

function of bacterial surface polymeric structures. In fact, the functional part of these structures should be the adhesins, especially when the substrata are host tissues.¹⁵⁹⁻¹⁶² Subsequently, certain bacterial strains are capable of forming a biofilm if provided with an appropriate supply of nutrients. During biofilm formation, bacteria secrete a slime layer that retains nutrients and protects the microorganisms from the host immune response.^{61,69,75} Biofilms are the most common mode of bacterial growth in nature and are also important in clinical infections, especially due to the associated high antibiotic resistance.¹⁶³⁻¹⁶⁵ Investigations of phenomena such as irreversible cell adhesion (i.e., the initial stage of the biofilm formation) to surfaces and an understanding of factors affecting spatial arrangement of biofilms, including the distribution and composition of microorganisms within the biofilm matrix and characterizing properties of this matrix, are recognized as essential in understanding the function of biofilms.^{166,167}

A fundamental aspect of the study of bacterial adhesion and attachment to surfaces is the need for reliable quantification of the microbiological population that attaches to the surface. Several experimental techniques have been developed to study and quantify bacterial adhesion on material surfaces. Since this is a very exhausting topic, only the commonly used techniques and the basic principles will be summarized in Table 2.

Metabolic assays are also excellent candidates for quantification of bacterial viability in biofilms. These assays are indirect methods based on the detection of metabolic products produced by bacteria and have the advantage of being able to assess viability without sample manipulation since these assays generally do not require the removal of the biofilm from the adherent surface.¹⁶⁸ Moreover most assays are simple, fast and perfectly suitable for high-throughput quantification of biofilms grown in a microtiter plate.¹⁶⁹ Some of these assays, including colorimetric biomass (crystal violet), Syto 9, resazurin and fluorescein diacetate (FDA), will also be summarized in Table 2.

However, it is important to mention that several conditions during the biofilm formation process can affect the results obtained including growth conditions, the cultivation medium and the surface selection. Growth conditions are very different among the available literature, namely different physiological states influence adhesion and biofilm formation. The stationary growth phase is the most common among other works from the literature. The bacterial inoculums should be determined with caution since it is known that increased inoculums increase biofilm density. So the exact size of the inoculums should be determined by adjusting to a specific optical density or absorbance. In order to avoid error in the optical reading, cell clusters should be avoided using a brief agitation and/or filtration. The medium for biofilm cultivation is also known to be crucial to the biofilm formation ability.¹⁷⁰

After the biofilm incubation step, the parameters that have been identified as being extremely important for biofilm quantification and which are not usually taken into account and/or omitted in the previously published work are: (1) bacterial removal and rinsing procedures of the wells as it assures the removal of non-adherent cells while keeping biofilm integrity. For

Table 2. Techniques to study and quantify the microorganisms attached to a surface and the bacterial viability in biofilms

Techniques	Advantages	Limitations
Colony forming units counting (CFU)	CFU plate counting is the most basic method for bacterial enumeration. ^{69,176,177} The washing is a very important part of a bacterial adhesion study using this technique, and its purpose is to remove the unattached and loosely adhered bacteria from the material surface. Methods for removing bacteria from substrata surfaces include homogenization, sonication, and the use of surfactants. According to the comparative study by McDaniel and Capone ¹⁷⁶ sonication appears to be an efficient and safe way to remove bacteria from biomaterial surfaces. There are two basic ways to perform plate counting, the pour plate method and the surface spread method. ^{176,177}	This technique is time consuming and involves tedious work, indirect and complicated procedures that give more uncertainty. ¹⁷⁷ It detects only viable bacteria. ¹⁷⁷
Light microscopy	Technique for bacterial enumeration and observation. Normally bacteria are stained with dyes like crystal violet or fuchsin. Some special staining methods allow the observation of bacterial surface structures such as capsules, or appendages. ^{176,177} Light microscopy has been combined with a bacterial flow chamber to observe living attached bacterial cells in real time. ^{176,177} A transparent material forms part of the wall of a cell flow chamber so that the bacteria attached to the inner side of the material might be directly observed. The advances in image analysis make bacterial counting by light microscopy much faster and more efficient. ^{176,177}	The substrata surfaces have to be translucent to be able to use light microscopy. ^{176,177}
Epifluorescence microscopy	It allows to differentiate between live and dead bacterial cells on the surface, if certain fluorochromes are used. ^{178,179} Image analysis systems are used for determining the number of cells adhered. ¹⁷⁸ It makes direct observation and enumeration possible for attached bacteria on an opaque surface. Relatively fast, easy method for biofilm characterization that is especially suitable for a large set of samples. ^{177,179} Wirtanen et al. ¹⁸⁰ evaluated the efficacy of various disinfectants against biofilms of <i>Pseudomonas aeruginosa</i> and <i>Pseudomonas fragi</i> on stainless steel surfaces using epifluorescence microscopy coupled with acridine orange.	Two-dimensional imaging only. ¹⁷⁹ The use of fluorochromes is necessary for viewing bacteria. ¹⁷⁹ Limited to macroscopic investigation of bacteria-surface interactions. ¹⁷⁹
Scanning electron microscopy (SEM)	SEM is a well-established basic technique to observe the morphology of bacteria adhered on a material surface, the material surface morphology, and the relationships between the two. It is also used to observe the morphology of bacterial biofilms on surfaces. ^{176,177,181} Environmental SEM or Low Vacuum SEM do not require metal or carbon sputtering and is less prone to damaging the bacteria adhered on a surface or alter the surface characteristics of the specimen, therefore overcoming the referred drawbacks. Chemical composition of samples can be determined by using energy-dispersive X-ray (EDX) for elements with $Z > 6$. ¹⁷⁹ SEM has previously been used to visualize biofilm development of <i>S. epidermidis</i> on contact lenses, ¹⁸² extensive biofilms on endoscope tubing samples that had been sent for endoscope servicing ¹⁸³ and the development of biofilms on catheters. ¹⁸⁴	SEM has been used for the enumeration of adhered bacteria, but, because of the small field and time-consuming work, it is less adequate for this purpose. ¹⁷⁷ It requires samples preparation for observation and the procedure for preparation can be tedious and labor intensive. ¹⁷⁹ It requires the specimen to be conductive (essentially “metal sputtered”). Cannot differentiate between live and dead bacterial cells. ¹⁷⁹ During sample preparation the drying step is considered to cause noticeable cell shrinkage and it exacerbates other undesirable outcomes, like damage and distortion of the biofilm. ¹⁷⁹ It also requires specialist equipment, training and extensive samples preparation. ¹⁷⁸
Confocal scanning laser microscopy (CSLM)	CSLM is a three-dimensional technique using fluorescent molecular probes and laser beams to study in situ bacterial associations with surfaces. ¹⁸⁵ It is used to visualize and count bacterial cells directly on transparent or opaque surfaces. It allows the examination of living fully hydrated biofilms in real time, and the simultaneous use of specific molecular probes allows to determine the identity (oligonucleotide probes) and the physiological state (live vs. dead) of the adherent bacterial cells. ^{186,187} This CSLM-based technique may be used to accurately assess the antibacterial properties of biofilm-resistant biomaterials. ¹⁸⁶ This technique offers several advantages, including the ability to control depth of field, elimination or reduction of background information away from the focal plane (that leads to image degradation), and the capability to collect serial optical sections from thick specimens. ¹⁸⁷⁻¹⁸⁹ Burnett et al. ¹⁹⁰ observed the attachment of <i>E. coli</i> O157:H7 to apple tissue by confocal scanning laser microscopy. Lindsay et al. ¹⁹¹ visualized co-cultured biofilms of <i>Pseudomonas fluorescens</i> M2 and <i>Bacillus cereus</i> DL5 on stainless steel surfaces.	The bacteria need to be colored or labeled with oligonucleotide probes for visualization. ^{186,187} Requirement of a CSLM to obtain the requested image quality is expensive. ¹⁹²

Table 2. Techniques to study and quantify the microorganisms attached to a surface and the bacterial viability in biofilms (continued)

Techniques	Advantages	Limitations
Atomic force microscopy (AFM)	<p>AFM has proved to be useful in imaging the morphology of individual microbial cells and bacterial biofilm on solid surfaces, both in dried and hydrated states.¹⁹³ It is used for mapping interaction forces at microbial surfaces.¹⁹⁴⁻¹⁹⁹ AFM is a non-invasive microscopic technique capable of imaging surfaces at nanometer resolutions,¹⁸⁵ and three-dimensional images at high resolution.¹⁷⁹ Furthermore, as no stains or coatings are needed in this method, biofilms may be observed in situ.¹⁸⁵ Preparation of sample surface is not required.¹⁷⁹</p> <p>AFM can be used preferentially to other methods, such as scanning electron microscopy, as the technique has several major advantages. Since the sample do not need to be electrically conductive, no metallic coating of the specimen is required. Unlike the case with the SEM, no dehydration of the sample is required, and biofilms may be viewed in their hydrated state. The resolution of AFM is higher than that of the environmental SEM, where images can also be obtained with hydrated samples, and extracellular polymeric substances may not be imaged with clarity.¹⁷⁹</p> <p>Within the medical context, AFM has been used to observe the effect of modified catheter surfaces on bacterial biofilm development.^{200,201}</p>	<p>The observation area is limited as compared with SEM.¹⁶⁴</p> <p>It cannot differentiate between live and dead bacterial cells.¹⁶⁴</p> <p>Imaging bacterial cells can be a time consuming task.^{179,202}</p>
Fourier transform infrared spectroscopy (FTIR)	<p>Spectroscopic techniques provide a wealth of qualitative and quantitative information about a given sample. FTIR spectroscopy measures the vibrations of chemical bonds within all the biochemical constituents of cells (i.e., proteins, lipids, polysaccharides and nucleic acids) and thus provides quantitative information about the total biochemical composition of the intact whole microbial cell.²⁰³⁻²⁰⁷ Differences in the structure and quantity of cell wall polysaccharide, lipids and protein are reflected in the FTIR spectra enabling differentiation between bacterial strains.²⁰⁸ The FTIR method is rapid, non-invasive, accurate, automated, inexpensive and quantitative, allowing users to collect full spectra in a few seconds per sample.^{208,209} FTIR spectroscopy has shown to be an effective tool for analyzing bacterial strains.¹⁹⁴ This technique has also been shown to have sufficient resolving power for differentiation between CNS and <i>S. aureus</i>.^{210,211} Amiali et al.²⁰⁷ observed that FTIR spectroscopy had considerable potential as a rapid (1 h) and simple method for MRSA strain typing and monitoring in clinical settings.</p>	<p>Its efficacy in differentiating metabolic changes of differentially induced bacteria or genetically identical bacterial strains on different growth substrates remains untested.²⁰⁵</p>
Radiolabelling	<p>This technique is useful in the study of bacterial adhesion to irregular material surfaces. It is very sensitive and very accurate, allowing for rapid processing of a large number of samples.^{177,212} For example, it was shown that the radiolabelling of bacteria was very useful for the studies of bacterial adhesion to irregular material surfaces, such as the surfaces of particles or spheres.²¹³</p>	<p>It requires special laboratory space and techniques for handling radioactive materials and it carries potential risk to performers.¹⁷⁷</p>
Contact angle measurements	<p>In the contact angle technique, a water droplet is applied to the surface of a dried lawn of bacteria. The angle formed where the water contacts the organisms is proportional to the surface hydrophobicity of the bacteria.²¹⁴ Analysis is very quick to perform.¹⁷⁹ Fonseca et al.⁶⁵ evaluated the hydrophobicity of <i>S. epidermidis</i> RP62A (ATCC 35984) using contact angle measurements.</p>	<p>Contamination of test surface may cause error in the obtained values.¹⁷⁹</p>
Molecular biological techniques	<p>It can identify the total community of bacteria attached to a surface. It offers a very sensitive method for detection of specific genes or species. A species of bacteria can be viewed in a heterogeneous community by fluorescently labeling by oligonucleotide probes.¹⁷⁹ Castonguay et al.²¹⁵ employed quantitative polymerase chain reaction (PCR) in their studies for confirmation of the presence of the two bacteria in a mature biofilm.</p>	<p>When using oligonucleotide probes, there is a requirement that they must bind specifically to the bacterial DNA sequence.¹⁷⁹</p>
Colorimetric biomass assay (crystal violet)	<p>This assay is used for quantification of biofilm biomass and crystal violet (CV) is frequently used. CV is a basic dye that stains both living and dead cells, by linking to negatively charge surface molecules and polysaccharides in the extra-cellular matrix.^{170,216} CV assay is cheap, straightforward and is commonly used for the quantification of biofilms formed by a broad range of microorganisms.¹⁶⁹</p>	<p>It cannot differentiate between live and dead bacterial cells.¹⁶⁹ Moreover, because both living and dead cells, as well as matrix, are stained with CV, this method provides no information about viability.²¹⁷</p>

Table 2. Techniques to study and quantify the microorganisms attached to a surface and the bacterial viability in biofilms (continued)

Techniques	Advantages	Limitations
Syto 9 assay	The fluorogenic dye Syto9 is a nucleic acid stain, which diffuses passively through cellular membranes and binds to DNA of both viable and dead cells. ²¹⁸ As DNA is also a substantial part of the extracellular matrix, ²¹⁹ this staining will provide information on total biofilm biomass. Syto9 has previously been used in CLSM studies of biofilm composition and morphology. ²²⁰ This stain has also been used for the routine quantification of bacterial and yeast biofilm biomass. ^{221,222}	This assay includes high costs of Syto9. ¹⁶⁹ It cannot differentiate between live and dead bacterial cells. ¹⁶⁹
Resazurin assay	Resazurin is a common metabolic activity indicator that has been shown to be effective in assessing bacterial viability ²²³ and in biofilm quantification. ¹⁶⁹ Resazurin, the main component of Alamar Blue, is a blue redox indicator that can be reduced by viable bacteria in the biofilm to pink resorufin, ²²⁴ thus continued growth maintains a reduced environment (pink) and the extent of conversion from blue to pink is a reflection of cell viability. ²²⁵ Peeters et al. showed that resazurin viability assay is a good alternative for quantification of microbial biofilms grown in microtiter-plates. ¹⁶⁹	It is necessary to construct a calibration curve. ²²⁶
Fluorescein diacetate (FDA) assay	Viable microbial cells are capable of converting non-colored, non-fluorescent fluorescein diacetate (FDA) into yellow, highly fluorescent fluorescein by non-specific intra- and extracellular esterases. FDA has been used for the quantification of biofilm biomass and viability. ^{221,227}	It is necessary to construct a calibration curve. ¹⁶⁴

this, special caution should be taken in terms of the number of washings (two or three times with PBS is the most often) and the washing technique, because if it is insufficient it may lead to false-positives and if it is excessive to false-negatives.¹⁷⁰ Extremina et al. recommend the three washing procedure and the careful pipetting of the wells to avoid compromising biofilm integrity. (2) Another important issue that is often omitted in the literature is the need to measure planktonic growth before washing. Extremina et al. showed that *E. faecium* 1162 Δ esp had higher planktonic index compared with the other tested strains, although being a non-biofilm producer. This procedure allows you to measure the engagement of bacteria to form biofilms by normalizing biofilms formation by the growth index, thus obtaining the biofilm formation index (BFi). For this purpose, the easiest way is to transfer the bacterial suspension to a new microtiter-plate and measure the optical density in a microtiter-plate reader. (3) It is crucial that the selection of the method takes into consideration the specific target for quantification. (4) Finally, of utmost importance is the interpretation of results and evaluation of assay quality.¹⁷⁰

In the study conducted by Extremina et al., the use of BFi confirmed that E1162 Δ esp isolate is a good negative control for biofilm quantification and demonstrates the importance of knowing the growth index of different sets of strains or conditions in order to compare biofilm formation values. Cut-off values (ODc) separate biofilm-producing from non-biofilms producing strain,¹⁷¹ which is in accordance with previously described work.^{172,173} Z' factor^{174,175} indicated high quality for the different assays during the optimization process, thus confirming a good repeatability and reproducibility of the experimental procedures. This study recognizes that parameters for classification of biofilm producers (cut-off values), evaluation of assay accuracy (BFi), and quality (Z' factor) are of utmost importance for evaluation, comparison and validation of biofilm screening assays.¹⁷⁰

Concluding Remarks and Future Perspectives

Better understanding of the interaction between microorganisms, the implant and the host may improve our current approach to the diagnosis and treatment of implant-associated infections. Despite several efforts to find medical therapies to treat biofilm infections, the physical removal of an infected medical device is often necessary, thus carrying an additional economic cost. Therefore, there is great interest in finding methods or strategies to inhibit biofilm formation. Several strategies have been proposed to achieve this on medical devices, including the use of antibiotics, development of new anti-adhesive medical surfaces and coating medical devices with several different compounds, including antibiotics. Applying antimicrobial agents is an easy and frequently used way to control biofilms. However, many antimicrobial agents that are effective against planktonic bacterial cells turn out to be ineffective against the same bacteria when growing in a biofilm. Combined use of multiple antimicrobial agents with different chemistries and modes of action may be a strategy to improve the performance of these antimicrobial agents and circumvent bacterial adaptation. However, the tremendous resistance of biofilms to conventional antibiotic therapy has prompted a great deal of research on synthetic surfaces and coatings that resist bacterial colonization.

Several biomaterials used in orthopedic surgery show different susceptibilities to infection, because adhesion and growth of infecting bacteria are controlled by biomaterial surface properties, like hydrophobicity and roughness. Controlling the topography and hydrophobic properties of materials surfaces is likewise a way to influence bacterial interaction with the surface and must be taken into account when developing novel anti-infective biomaterials.

However, since bacterial adhesion is a very complex process affected by many factors, such as bacterial and material properties and environment, further studies are required to understand the

mechanisms of bacterial adhesion and implant infection, and to provide adequate methodologies to prevent them to occur. Future research must strive to better understand the pathogenesis of implant-related infections, with a special attention on the alarming phenomenon of antibiotic resistance. Future investigations should also focus on designing animal model systems to study in vivo-grown biofilms and infections.

All the above mentioned techniques provide us with an impressive array of tools for investigating bacteria-material interactions in vitro. Each one has certain advantages and limitations with respect to the others. However, although they cannot be routinely used because of the cost, complexity of the set

up and time required to give results, are useful in studying bacteria-material interactions.

Disclosure of Potential Conflicts of Interest

No potential conflicts of interest were disclosed.

Acknowledgments

This work was financed by FEDER funds through the Programa Operacional Factores de Competitividade (COMPETE). The support of Projects NanoforBone (NORTE-01-0202-FEDER-005372) and NaNOBiofilm (PTDC/SAU-BMA/111233/2009) are greatly acknowledged.

References

1. Navarro M, Michiardi A, Castaño O, Planell JÁ. Biomaterials in orthopaedics. J R Soc Interface 2008; 5:1137-58; PMID:18667387; <http://dx.doi.org/10.1098/rsif.2008.0151>
2. Smith KR, Hunt TR, Asher MA, Anderson HC, Carson WL, Robinson RG. The effect of a stiff spinal implant on the bone-mineral content of the lumbar spine in dogs. J Bone Joint Surg Am 1991; 73:115-23; PMID:1985981
3. Paital SR, Dahotre NB. Calcium phosphate coatings for bio-implant applications: Materials, performance factors, and methodologies. Mater Sci Eng Rep 2009; 66:1-70; <http://dx.doi.org/10.1016/j.mser.2009.05.001>
4. Long PH. Medical devices in orthopedic applications. Toxicol Pathol 2008; 36:85-91; PMID:18337225; <http://dx.doi.org/10.1177/0192623307310951>
5. Chevalier J, Gremillard L. Ceramics for medical applications: A picture for the next 20 years. J Eur Ceram Soc 2009; 29:1245-55; <http://dx.doi.org/10.1016/j.jeurceramsoc.2008.08.025>
6. Vallet-Regí M. Evolution of bioceramics within the field of biomaterials. C R Chim 2010; 13:174-85; <http://dx.doi.org/10.1016/j.crci.2009.03.004>
7. Duan K, Wang R. Surface modifications of bone implants through wet chemistry. J Mater Chem 2006; 16:2309-21; <http://dx.doi.org/10.1039/b517634d>
8. Ercan B, Kummer KM, Tarquinio KM, Webster TJ. Decreased *Staphylococcus aureus* biofilm growth on anodized nanotubular titanium and the effect of electrical stimulation. Acta Biomater 2011; 7:3003-12; PMID:21515421; <http://dx.doi.org/10.1016/j.actbio.2011.04.002>
9. Zilberman M, Elsner JJ. Antibiotic-eluting medical devices for various applications. J Control Release 2008; 130:202-15; PMID:18687500; <http://dx.doi.org/10.1016/j.jconrel.2008.05.020>
10. Trampuz A, Osmon DR, Hanssen AD, Steckelberg JM, Patel R. Molecular and antibiofilm approaches to prosthetic joint infection. Clin Orthop Relat Res 2003; 414:69-88; PMID:12966280; <http://dx.doi.org/10.1097/01.blo.0000087324.60612.93>
11. Turner IG, Pilliar RM, Srichana T, Domb AJ, Lacroix D, Planell JA, et al. Sterility and Infection. In: Narayan R, ed. Biomedical Materials. New York, NY: Springer Science, 2009:239-258.
12. Davies D. Understanding biofilm resistance to antibacterial agents. Nat Rev Drug Discov 2003; 2:114-22; PMID:12563302; <http://dx.doi.org/10.1038/nrd1008>
13. Gristina AG, Naylor P, Myrvik Q. Infections from biomaterials and implants: a race for the surface. Med Prog Technol 1988-1989; 14:205-24; PMID:2978593
14. Montanaro L, Campoccia D, Arciola CR. Nanostructured materials for inhibition of bacterial adhesion in orthopedic implants: a minireview. Int J Artif Organs 2008; 31:771-6; PMID:18924088
15. Alexander H, Anderson JM, Bianco RW, Brunski JB, Chang TMS, Colas A, et al. Host Reactions to Biomaterials and Their Evaluation. In: Ratner BD, Hoffman AS, Schoen FJ, Lemons JE, eds. Biomaterials Science: An Introduction to Materials in Medicine. 2nd Edition. London, UK: Elsevier Academic Press, 2004:293-345.
16. Campoccia D, Montanaro L, Arciola CR. The significance of infection related to orthopedic devices and issues of antibiotic resistance. Biomaterials 2006; 27:2331-9; PMID:16364434; <http://dx.doi.org/10.1016/j.biomaterials.2005.11.044>
17. Kalita SJ, Verma S. Nanocrystalline hydroxyapatite bioceramic using microwave radiation: Synthesis and characterization. Mater Sci Eng C 2010; 30:295-303; <http://dx.doi.org/10.1016/j.msec.2009.11.007>
18. Harris LG, Richards RG. Staphylococci and implant surfaces: a review. Injury. Int J Care Injured 2006; 37:3-14; <http://dx.doi.org/10.1016/j.injury.2006.04.003>
19. Teterycz D, Ferry T, Lew D, Stern R, Assal M, Hoffmeyer P, et al. Outcome of orthopedic implant infections due to different staphylococci. Int J Infect Dis 2010; 14:e913-8; PMID:20729115; <http://dx.doi.org/10.1016/j.ijid.2010.05.014>
20. Wright JA, Nair SP. Interaction of staphylococci with bone. Int J Med Microbiol 2010; 300:193-204; PMID:19889575; <http://dx.doi.org/10.1016/j.ijmm.2009.10.003>
21. Ghasemzadeh-Moghaddam H, Ghaznavi-Rad E, Sekawi Z, Yun-Khoon L, Aziz MN, Hamat RA, et al. Methicillin-susceptible *Staphylococcus aureus* from clinical and community sources are genetically diverse. Int J Med Microbiol 2011; 301:347-53; PMID:21193348; <http://dx.doi.org/10.1016/j.ijmm.2010.10.004>
22. Campoccia D, Baldassarri L, Pirini V, Ravaoli S, Montanaro L, Arciola CR. Molecular epidemiology of *Staphylococcus aureus* from implant orthopaedic infections: ribotypes, agr polymorphism, leukocidal toxins and antibiotic resistance. Biomaterials 2008; 29:4108-16; PMID:18676012; <http://dx.doi.org/10.1016/j.biomaterials.2008.07.006>
23. François P, Scherl A, Hochstrasser D, Schrenzel J. Proteomic approaches to study *Staphylococcus aureus* pathogenesis. J Proteomics 2010; 73:701-8; PMID:19879388; <http://dx.doi.org/10.1016/j.jpro.2009.10.007>
24. Hudson MC, Ramp WK, Frankenburg KP. *Staphylococcus aureus* adhesion to bone matrix and bone-associated biomaterials. FEMS Microbiol Lett 1999; 173:279-84; PMID:10227156; <http://dx.doi.org/10.1111/j.1574-6968.1999.tb13514.x>
25. Arciola CR, Campoccia D, Gamberini S, Donati ME, Montanaro L. Presence of fibrinogen-binding adhesin gene in *Staphylococcus epidermidis* isolates from central venous catheters-associated and orthopaedic implant-associated infections. Biomaterials 2004; 25:4825-9; PMID:15120529; <http://dx.doi.org/10.1016/j.biomaterials.2003.11.056>
26. Cerca N, Martins S, Pier GB, Oliveira R, Azeredo J. The relationship between inhibition of bacterial adhesion to a solid surface by sub-MICs of antibiotics and subsequent development of a biofilm. Res Microbiol 2005; 156:650-5; PMID:15950124; <http://dx.doi.org/10.1016/j.resmic.2005.02.004>
27. Vuong C, Otto M. *Staphylococcus epidermidis* infections. Microbes Infect 2002; 4:481-9; PMID:11932199; [http://dx.doi.org/10.1016/S1286-4579\(02\)01563-0](http://dx.doi.org/10.1016/S1286-4579(02)01563-0)
28. Montanaro L, Campoccia D, Arciola CR. Advancements in molecular epidemiology of implant infections and future perspectives. Biomaterials 2007; 28:5155-68; PMID:17764738; <http://dx.doi.org/10.1016/j.biomaterials.2007.08.003>
29. Arciola CR, Campoccia D, Gamberini S, Donati ME, Pirini V, Visai L, et al. Antibiotic resistance in exopolysaccharide-forming *Staphylococcus epidermidis* clinical isolates from orthopaedic implant infections. Biomaterials 2005; 26:6530-5; PMID:15949842; <http://dx.doi.org/10.1016/j.biomaterials.2005.04.031>
30. Brady RA, Leid JG, Costerton JW, Shirliff ME. Osteomyelitis: Clinical Overview and Mechanisms of Infection Persistence. Clin Microbiol Newsl 2006; 28:65-72; <http://dx.doi.org/10.1016/j.clinmicnews.2006.04.001>
31. Cai XY, Yang C, Zhang ZY, Qiu WL, Chen MJ, Zhang SY. Septic arthritis of the temporomandibular joint: a retrospective review of 40 cases. J Oral Maxillofac Surg 2010; 68:731-8; PMID:19954877; <http://dx.doi.org/10.1016/j.joms.2009.07.060>
32. Aaskov JG, Abdel-Rahman SM, Aebi C, Ament ME, Anderson MS, Arnon SS, et al. Infections Related to prosthetic or artificial devices. In: Feigin RD, Cherry JD, Demmler-Harrison GJ, Kaplan SL, eds. Textbook of Pediatric Infectious Diseases. 6th Edition. Philadelphia, PA: Elsevier Inc., 2009.
33. Lidgren L, Knutson K, Stefánssdóttir A. Infection and arthritis. Infection of prosthetic joints. Best Pract Res Clin Rheumatol 2003; 17:209-18; PMID:12787522; [http://dx.doi.org/10.1016/S1521-6942\(03\)00002-0](http://dx.doi.org/10.1016/S1521-6942(03)00002-0)
34. Sawan SP, Manivannan G. In: Sawan SP, Manivannan G, eds. Antimicrobial/Anti-Infective Materials: Principles, Applications and Devices. Lancaster, LA: Technomic Publishing Company, Inc., 2000.
35. Lew DP, Waldvogel FA. Osteomyelitis. Lancet 2004; 364:369-79; PMID:15276398; [http://dx.doi.org/10.1016/S0140-6736\(04\)16727-5](http://dx.doi.org/10.1016/S0140-6736(04)16727-5)

36. Weichert S, Sharland M, Clarke NM, Faust SN. Acute haematogenous osteomyelitis in children: is there any evidence for how long we should treat? *Curr Opin Infect Dis* 2008; 21:258-62; PMID:18448970; <http://dx.doi.org/10.1097/QCO.0b013e3283005441>
37. Blyth MJ, Kincaid R, Craigen MA, Bennet GC. The changing epidemiology of acute and subacute haematogenous osteomyelitis in children. *J Bone Joint Surg Br* 2001; 83:99-102; PMID:11245548; <http://dx.doi.org/10.1302/0301-620X.83B1.10699>
38. Lazzarini L, Mader JT, Calhoun JH. Osteomyelitis in long bones. *J Bone Joint Surg Am* 2004; 86-A:2305-18; PMID:15466746
39. Gillespie WJ. Epidemiology in bone and joint infection. *Infect Dis Clin North Am* 1990; 4:361-76; PMID:2212594
40. Dubost JJ, Soubrier M, De Champs C, Ristori JM, Bussi re JL, Sauvezie B. No changes in the distribution of organisms responsible for septic arthritis over a 20 year period. *Ann Rheum Dis* 2002; 61:267-9; PMID:11830437; <http://dx.doi.org/10.1136/ard.61.3.267>
41. Mathews CJ, Weston VC, Jones A, Field M, Coakley G. Bacterial septic arthritis in adults. *Lancet* 2010; 375:846-55; PMID:20206778; [http://dx.doi.org/10.1016/S0140-6736\(09\)61595-6](http://dx.doi.org/10.1016/S0140-6736(09)61595-6)
42. Goldenberg DL. Septic arthritis. *Lancet* 1998; 351:197-202; PMID:9449882; [http://dx.doi.org/10.1016/S0140-6736\(97\)09522-6](http://dx.doi.org/10.1016/S0140-6736(97)09522-6)
43. Nade S. Septic arthritis. *Best Pract Res Clin Rheumatol* 2003; 17:183-200; PMID:12787520; [http://dx.doi.org/10.1016/S1521-6942\(02\)00106-7](http://dx.doi.org/10.1016/S1521-6942(02)00106-7)
44. Stort NS. Paediatric bone and joint infection. *J Orthop Surg* 2001; 9:83-90.
45. Levine M, Siegel LB. A swollen joint: why all the fuss? *Am J Ther* 2003; 10:219-24; PMID:12756429; <http://dx.doi.org/10.1097/00045391-200305000-00009>
46. Geirsson AJ, Statkevicius S, Vikingson A. Septic arthritis in Iceland 1990-2002: increasing incidence due to iatrogenic infections. *Ann Rheum Dis* 2008; 67:638-43; PMID:17901088; <http://dx.doi.org/10.1136/ard.2007.077131>
47. Coakley G, Mathews C, Field M, Jones A, Kingsley G, Walker D, et al. British Society for Rheumatology Standards, Guidelines and Audit Working Group. BSR & BHP, BOA, RCGP and BSAC guidelines for management of the hot swollen joint in adults. *Rheumatology (Oxford)* 2006; 45:1039-41; PMID:16829534; <http://dx.doi.org/10.1093/rheumatology/ kel163a>
48. Esposito S, Leone S. Prosthetic joint infections: microbiology, diagnosis, management and prevention. *Int J Antimicrob Agents* 2008; 32:287-93; PMID:18617373; <http://dx.doi.org/10.1016/j.ijantimicag.2008.03.010>
49. Rohde H, Burandt EC, Siemssen N, Frommelt L, Burdelski C, Wurster S, et al. Polysaccharide intercellular adhesin or protein factors in biofilm accumulation of *Staphylococcus epidermidis* and *Staphylococcus aureus* isolated from prosthetic hip and knee joint infections. *Biomaterials* 2007; 28:1711-20; PMID:17187854; <http://dx.doi.org/10.1016/j.biomaterials.2006.11.046>
50. Trampuz A, Zimmerli W. Prosthetic joint infections: update in diagnosis and treatment. *Swiss Med Wkly* 2005; 135:243-51; PMID:15965826
51. Hanssen AD, Rand JA. Evaluation and treatment of infection at the site of a total hip or knee arthroplasty. *Instr Course Lect* 1999; 48:111-22; PMID:10098033
52. Sculco TP. The economic impact of infected joint arthroplasty. *Orthopedics* 1995; 18:871-3; PMID:8570494
53. Berbari EF, Hanssen AD, Duffy MC, Steckelberg JM, Ilstrup DM, Harmsen WS, et al. Risk factors for prosthetic joint infection: case-control study. *Clin Infect Dis* 1998; 27:1247-54; PMID:9827278; <http://dx.doi.org/10.1086/514991>
54. Fisman DN, Reilly DT, Karchmer AW, Goldie SJ. Clinical effectiveness and cost-effectiveness of 2 management strategies for infected total hip arthroplasty in the elderly. *Clin Infect Dis* 2001; 32:419-30; PMID:11170950; <http://dx.doi.org/10.1086/318502>
55. Lentino JR. Prosthetic joint infections: bane of orthopedists, challenge for infectious disease specialists. *Clin Infect Dis* 2003; 36:1157-61; PMID:12715311; <http://dx.doi.org/10.1086/374554>
56. Zimmerli W, Trampuz A, Ochsner PE. Prosthetic-joint infections. *N Engl J Med* 2004; 351:1645-54; PMID:15483283; <http://dx.doi.org/10.1056/NEJMr040181>
57. Giulieri SG, Graber P, Ochsner PE, Zimmerli W. Management of infection associated with total hip arthroplasty according to a treatment algorithm. *Infection* 2004; 32:222-8; PMID:15293078; <http://dx.doi.org/10.1007/s15010-004-4020-1>
58. Laffer R, Graber P, Ochsner P, Zimmerli W. The case for differentiated orthopedic management of prosthetic knee-associated infection. 44th ICAAC, American Society for Microbiology, 2004, Washington, DC 2004; Abstract K-113.
59. Zimmerli W. Infection and musculoskeletal conditions: Prosthetic-joint-associated infections. *Best Pract Res Clin Rheumatol* 2006; 20:1045-63; PMID:17127196; <http://dx.doi.org/10.1016/j.berh.2006.08.003>
60. Vacheethasane K, Temenoff JS, Higashi JM, Gary A, Anderson JM, Bayston R, et al. Bacterial surface properties of clinically isolated *Staphylococcus epidermidis* strains determine adhesion on polyethylene. *J Biomed Mater Res* 1998; 42:425-32; PMID:9788506; [http://dx.doi.org/10.1002/\(SICI\)1097-4636\(19981205\)42:3<425::AID-JBM12>3.0.CO;2-F](http://dx.doi.org/10.1002/(SICI)1097-4636(19981205)42:3<425::AID-JBM12>3.0.CO;2-F)
61. An YH, Friedman RJ. Concise review of mechanisms of bacterial adhesion to biomaterial surfaces. *J Biomed Mater Res* 1998; 43:338-48; PMID:9730073; [http://dx.doi.org/10.1002/\(SICI\)1097-4636\(199823\)43:3<338::AID-JBM16>3.0.CO;2-B](http://dx.doi.org/10.1002/(SICI)1097-4636(199823)43:3<338::AID-JBM16>3.0.CO;2-B)
62. An YH, Friedman RJ, Draughn RA, Smith EA, Nicholson JH, John JF. Rapid quantification of staphylococci adhered to titanium surfaces using image analyzed epifluorescence microscopy. *J Microbiol Methods* 1995; 24:29-40; [http://dx.doi.org/10.1016/0167-7012\(95\)00051-8](http://dx.doi.org/10.1016/0167-7012(95)00051-8)
63. Costa F, Carvalho IF, Montelaro RC, Gomes P, Martins MCL. Covalent immobilization of antimicrobial peptides (AMPs) onto biomaterial surfaces. *Acta Biomater* 2011; 7:1431-40; PMID:21056701; <http://dx.doi.org/10.1016/j.actbio.2010.11.005>
64. Extremina CI, Granja PL, da Fonseca AF, Fonseca AP. Adhesion of staphylococcus epidermidis to a modified cellulose triacetate membrane. *Int J Antimicrob Agents* 2007; 29:S143-S144; [http://dx.doi.org/10.1016/S0924-8579\(07\)70458-2](http://dx.doi.org/10.1016/S0924-8579(07)70458-2)
65. Fonseca AP, Granja PL, Nogueira JA, Oliveira DR, Barbosa MA. *Staphylococcus epidermidis* RP62A adhesion to chemically modified cellulose derivatives. *J Mater Sci Mater Med* 2001; 12:543-8; PMID:15348271; <http://dx.doi.org/10.1023/A:1011227915575>
66. Fonseca AP, Extremina C, Fonseca AF, Sousa JC. Effect of subinhibitory concentration of piperacillin/tazobactam on *Pseudomonas aeruginosa*. *J Med Microbiol* 2004; 53:903-10; PMID:15314198; <http://dx.doi.org/10.1099/jmm.0.45637-0>
67. Ueshima M, Tanaka S, Nakamura S, Yamashita K. Manipulation of bacterial adhesion and proliferation by surface charges of electrically polarized hydroxyapatite. *J Biomed Mater Res* 2002; 60:578-84; PMID:11948516; <http://dx.doi.org/10.1002/jbm.10113>
68. Popat KC, Eltgroth M, Latempa TJ, Grimes CA, Desai TA. Decreased *Staphylococcus epidermidis* adhesion and increased osteoblast functionality on antibiotic-loaded titania nanotubes. *Biomaterials* 2007; 28:4880-8; PMID:17697708; <http://dx.doi.org/10.1016/j.biomaterials.2007.07.037>
69. Katsikogianni M, Missirlis YF. Concise review of mechanisms of bacterial adhesion to biomaterials and of techniques used in estimating bacteria-material interactions. *Eur Cell Mater* 2004; 8:37-57; PMID:15593018
70. Stewart PS, Costerton JW. Antibiotic resistance of bacteria in biofilms. *Lancet* 2001; 358:135-8; PMID:11463434; [http://dx.doi.org/10.1016/S0140-6736\(01\)05321-1](http://dx.doi.org/10.1016/S0140-6736(01)05321-1)
71. Donlan RM, Costerton JW. Biofilms: survival mechanisms of clinically relevant microorganisms[were added.]. *Clin Microbiol Rev* 2002; 15:167-93; PMID:11932229; <http://dx.doi.org/10.1128/CMR.15.2.167-193.2002>
72. Davies DG, Parsek MR, Pearson JP, Igleski BH, Costerton JW, Greenberg EP. The involvement of cell-to-cell signals in the development of a bacterial biofilm. *Science* 1998; 280:295-8; PMID:9535661; <http://dx.doi.org/10.1126/science.280.5361.295>
73. Harris LG, Tosatti S, Wieland M, Textor M, Richards RG. *Staphylococcus aureus* adhesion to titanium oxide surfaces coated with non-functionalized and peptide-functionalized poly(L-lysine)-grafted-poly(ethylene glycol) copolymers. *Biomaterials* 2004; 25:4135-48; PMID:15046904; <http://dx.doi.org/10.1016/j.biomaterials.2003.11.033>
74. Katsikogianni M, Spiliopoulou I, Dowling DP, Missirlis YF. Adhesion of slime producing *Staphylococcus epidermidis* strains to PVC and diamond-like carbon/silver/fluorinated coatings. *J Mater Sci Mater Med* 2006; 17:679-89; PMID:16897160; <http://dx.doi.org/10.1007/s10856-006-9678-8>
75. Hetrick EM, Schoenfisch MH. Reducing implant-related infections: active release strategies. *Chem Soc Rev* 2006; 35:780-9; PMID:16936926; <http://dx.doi.org/10.1039/b515219b>
76. Martins MC, Wang D, Ji J, Feng L, Barbosa MA. Albumin and fibrinogen adsorption on cibacron blue F3G-A immobilised onto PU-PHEMA (polyurethane-poly(hydroxyethylmethacrylate)) surfaces. *J Biomater Sci Polym Ed* 2003; 14:439-55; PMID:12807146; <http://dx.doi.org/10.1163/156856203766652057>
77. Grenho L, Manso MC, Monteiro FJ, Ferraz MP. Adhesion of *Staphylococcus aureus*, *Staphylococcus epidermidis*, and *Pseudomonas aeruginosa* onto nanohydroxyapatite as a bone regeneration material. *J Biomed Mater Res A* 2012; 100:1823-30; PMID:22489063; <http://dx.doi.org/10.1002/jbm.a.34139>
78. Extremina CI, Fonseca AF, Granja PL, Fonseca AP. Anti-adhesion and antiproliferative cellulose triacetate membrane for prevention of biomaterial-centred infections associated with *Staphylococcus epidermidis*. *Int J Antimicrob Agents* 2010; 35:164-8; PMID:19942411; <http://dx.doi.org/10.1016/j.ijantimicag.2009.09.017>
79. Parreira P, Magalh es A, Gon alves IC, Gomes J, Vidal R, Reis CA, et al. Effect of surface chemistry on bacterial adhesion, viability, and morphology. *J Biomed Mater Res A* 2011; 99:344-53; PMID:22021182; <http://dx.doi.org/10.1002/jbm.a.33178>
80. Isberg RR, Barnes P. Dancing with the host: flow-dependent bacterial adhesion. *Cell* 2002; 110:1-4; PMID:12150990; [http://dx.doi.org/10.1016/S0092-8674\(02\)00821-8](http://dx.doi.org/10.1016/S0092-8674(02)00821-8)

81. Klapper I, Rupp CJ, Cargo R, Purvedorj B, Stoodley P. Viscoelastic fluid description of bacterial biofilm material properties. *Biotechnol Bioeng* 2002; 80:289-96; PMID:12226861; <http://dx.doi.org/10.1002/bit.10376>
82. Katsikogianni MG, Missirlis YF. Interactions of bacteria with specific biomaterial surface chemistries under flow conditions. *Acta Biomater* 2010; 6:1107-18; PMID:19671455; <http://dx.doi.org/10.1016/j.actbio.2009.08.006>
83. Liu Y, Tay J-H. The essential role of hydrodynamic shear force in the formation of biofilm and granular sludge. *Water Res* 2002; 36:1653-65; PMID:12044065; [http://dx.doi.org/10.1016/S0043-1354\(01\)00379-7](http://dx.doi.org/10.1016/S0043-1354(01)00379-7)
84. Mohamed N, Rainier TR, Jr., Ross JM. Novel experimental study of receptor-mediated bacterial adhesion under the influence of fluid shear. *Biotechnol Bioeng* 2000; 68:628-36; PMID:10799987; [http://dx.doi.org/10.1002/\(SICI\)1097-0290\(20000620\)68:6<628::AID-BIT5>3.0.CO;2-D](http://dx.doi.org/10.1002/(SICI)1097-0290(20000620)68:6<628::AID-BIT5>3.0.CO;2-D)
85. Rowland BM. Bacterial contamination of dental unit waterlines: what is your dentist spraying into your mouth? *Clin Microbiol Newsl* 2003; 25:73-7; [http://dx.doi.org/10.1016/S0196-4399\(03\)80016-8](http://dx.doi.org/10.1016/S0196-4399(03)80016-8)
86. Garret TR, Bhakoo M, Zhang Z. Bacterial adhesion and biofilms on surfaces. *Prog Nat Sci* 2008; 18:1049-56; <http://dx.doi.org/10.1016/j.pnsc.2008.04.001>
87. Li Y, Hanna MN, Svensäter G, Ellen RP, Cvikovitch DG. Cell density modulates acid adaption in *Streptococcus mutans*. *J Bacteriol* 2001; 183:6875-84; PMID:11698377; <http://dx.doi.org/10.1128/JB.183.23.6875-6884.2001>
88. Oliveira R, Melo L, Oliveira A, Salgueiro R. Polysaccharide production and biofilm formation by *Pseudomonas fluorescens*: effects of pH and surface material. *Col Surf B: Biointerf* 1994; 2:41-6; [http://dx.doi.org/10.1016/0927-7765\(94\)80016-2](http://dx.doi.org/10.1016/0927-7765(94)80016-2)
89. Hamadi F, Latrache H, Mabrouki M, Elghmari A, Outzourhit A, Ellouali M, et al. Effect of pH on distribution and adhesion of *Staphylococcus aureus* to glass. *J Adhes Sci Technol* 2005; 19:73-85; <http://dx.doi.org/10.1163/1568561053066891>
90. Kinnari TJ, Esteban J, Martin-de-Hijas NZ, Sánchez-Muñoz O, Sánchez-Salcedo S, Colilla M, et al. Influence of surface porosity and pH on bacterial adherence to hydroxyapatite and biphasic calcium phosphate bioceramics. *J Med Microbiol* 2009; 58:132-7; PMID:19074665; <http://dx.doi.org/10.1099/jmm.0.002758-0>
91. Kontinen YT, Takagi M, Mandelin J, Lassus J, Salo J, Ainola M, et al. Acid attack and cathepsin K in bone resorption around total hip replacement prosthesis. *J Bone Miner Res* 2001; 16:1780-6; PMID:11585341; <http://dx.doi.org/10.1359/jbmr.2001.16.10.1780>
92. Ferraz MP, Mateus AY, Sousa JC, Monteiro FJ. Nanohydroxyapatite microspheres as delivery system for antibiotics: release kinetics, antimicrobial activity, and interaction with osteoblasts. *J Biomed Mater Res A* 2007; 81:994-1004; PMID:17252559; <http://dx.doi.org/10.1002/jbm.a.31151>
93. Kohnen W, Kolbenschlag C, Teske-Keiser S, Jansen B. Development of a long-lasting ventricular catheter impregnated with a combination of antibiotics. *Biomaterials* 2003; 24:4865-9; PMID:14530084; [http://dx.doi.org/10.1016/S0142-9612\(03\)00379-X](http://dx.doi.org/10.1016/S0142-9612(03)00379-X)
94. Stigter M, de Groot K, Layrolle P. Incorporation of tobramycin into biomimetic hydroxyapatite coating on titanium. *Biomaterials* 2002; 23:4143-53; PMID:12182316; [http://dx.doi.org/10.1016/S0142-9612\(02\)00157-6](http://dx.doi.org/10.1016/S0142-9612(02)00157-6)
95. Galanakis SP, Papadakis SA, Kateros K, Papakostas I, Macheras G. Biofilm and orthopaedic practice: the world of microbes in a world of implants. *Orthop Trauma* 2009; 23:175-9.
96. Donlan RM. Biofilms: microbial life on surfaces. *Emerg Infect Dis* 2002; 8:881-90; PMID:12194761; <http://dx.doi.org/10.3201/eid0809.020063>
97. Stoodley P, Sauer K, Davies DG, Costerton JW. Biofilms as complex differentiated communities. *Annu Rev Microbiol* 2002; 56:187-209; PMID:12142477; <http://dx.doi.org/10.1146/annurev.micro.56.012302.160705>
98. Stewart PS, Costerton JW. Antibiotic resistance of bacteria in biofilms. *Lancet* 2001; 358:135-8; PMID:11463434; [http://dx.doi.org/10.1016/S0140-6736\(01\)05321-1](http://dx.doi.org/10.1016/S0140-6736(01)05321-1)
99. Costerton JW, Stewart PS. Battling biofilms. *Sci Am* 2001; 285:74-81; PMID:11432197; <http://dx.doi.org/10.1038/scientificamerican0701-74>
100. Furneri PM, Garozzo A, Musumarra MP, Scuderi AC, Russo A, Bonfiglio G. Effects on adhesiveness and hydrophobicity of sub-inhibitory concentrations of netilmicin. *Int J Antimicrob Agents* 2003; 22:164-7; PMID:12927958; [http://dx.doi.org/10.1016/S0924-8579\(03\)00149-3](http://dx.doi.org/10.1016/S0924-8579(03)00149-3)
101. Cramton SE, Gerke C, Schnell NF, Nichols WW, Götz F. The intercellular adhesion (ica) locus is present in *Staphylococcus aureus* and is required for biofilm formation. *Infect Immun* 1999; 67:5427-33; PMID:10496925
102. Galdhart JO, Allignet J, Tung HS, Rydén C, El Solh N. Screening for *Staphylococcus epidermidis* markers discriminating between skin-flora strains and those responsible for infections of joint prostheses. *J Infect Dis* 2000; 182:351-5; PMID:10882623; <http://dx.doi.org/10.1086/315660>
103. del Prado G, Ruiz V, Naves P, Rodríguez-Cerrato V, Soriano F, del Carmen Ponte M. Biofilm formation by *Streptococcus pneumoniae* strains and effects of human serum albumin, ibuprofen, N-acetyl-L-cysteine, amoxicillin, erythromycin, and levofloxacin. *Diagn Microbiol Infect Dis* 2010; 67:311-8; PMID:20638597; <http://dx.doi.org/10.1016/j.diagmicrobio.2010.03.016>
104. Poelstra KA, Barekzi NA, Rediske AM, Felts AG, Slunt JB, Grainger DW. Prophylactic treatment of gram-positive and gram-negative abdominal implant infections using locally delivered polyclonal antibodies. *J Biomed Mater Res* 2002; 60:206-15; PMID:11835177; <http://dx.doi.org/10.1002/jbm.10069>
105. Pagano PJ, Buchanan LV, Dailey CF, Haas JV, Van Enk RA, Gibson JK. Effects of linezolid on staphylococcal adherence versus time of treatment. *Int J Antimicrob Agents* 2004; 23:226-34; PMID:15164962; <http://dx.doi.org/10.1016/j.ijantimicag.2003.07.012>
106. Scheuerman TR, Camper AK, Hamilton MA. Effects of substratum topography on bacterial adhesion. *J Colloid Interface Sci* 1998; 208:23-33; PMID:9820746; <http://dx.doi.org/10.1006/jcis.1998.5717>
107. Öztürk O, Sudagidan M, Türkan U. Biofilm formation by *Staphylococcus epidermidis* on nitrogen ion implanted CoCrMo alloy material. *J Biomed Mater Res A* 2007; 81:663-8; PMID:17187392; <http://dx.doi.org/10.1002/jbm.a.31037>
108. Teughels W, Van Assche N, Slieden I, Quirynen M. Effect of material characteristics and/or surface topography on biofilm development. *Clin Oral Implants Res* 2006; 17(Suppl 2):68-81; PMID:16968383; <http://dx.doi.org/10.1111/j.1600-0501.2006.01353.x>
109. Katainen J, Paajanen M, Ahtola E, Pore V, Lahtinen J. Adhesion as an interplay between particle size and surface roughness. *J Colloid Interface Sci* 2006; 304:524-9; PMID:17010358; <http://dx.doi.org/10.1016/j.jcis.2006.09.015>
110. Mitik-Dineva N, Wang J, Mocanaru RC, Stoddart PR, Crawford RJ, Ivanova EP. Impact of nano-topography on bacterial attachment. *Biotechnol J* 2008; 3:536-44; PMID:18246568; <http://dx.doi.org/10.1002/biot.200700244>
111. Truong VK, Lapovok R, Estrin YS, Rundell S, Wang JY, Fluke CJ, et al. The influence of nano-scale surface roughness on bacterial adhesion to ultrafine-grained titanium. *Biomaterials* 2010; 31:3674-83; PMID:20163851; <http://dx.doi.org/10.1016/j.biomaterials.2010.01.071>
112. Whitehead KA, Colligon J, Verran J. Retention of microbial cells in substratum surface features of micrometer and sub-micrometer dimensions. *Colloids Surf B Biointerfaces* 2005; 41:129-38; PMID:15737538; <http://dx.doi.org/10.1016/j.colsurfb.2004.11.010>
113. Webster TJ, Tong Z, Liu J, Katherine Banks M. Adhesion of *Pseudomonas fluorescens* onto nanophase materials. *Nanotechnology* 2005; 16:S449-57; PMID:21727466; <http://dx.doi.org/10.1088/0957-4484/16/7/021>
114. Colon G, Ward BC, Webster TJ. Increased osteoblast and decreased *Staphylococcus epidermidis* functions on nanophase ZnO and TiO₂. *J Biomed Mater Res A* 2006; 78:595-604; PMID:16752397; <http://dx.doi.org/10.1002/jbm.a.30789>
115. Merritt K, Shafer JW, Brown SA. Implant site infection rates with porous and dense materials. *J Biomed Mater Res* 1979; 13:101-8; PMID:429378; <http://dx.doi.org/10.1002/jbm.820130111>
116. Harris JM, Martin LF. An in vitro study of the properties influencing *Staphylococcus epidermidis* adhesion to prosthetic vascular graft materials. *Ann Surg* 1987; 206:612-20; PMID:2960278; <http://dx.doi.org/10.1097/00000658-198711000-00010>
117. Doyle RJ. Contribution of the hydrophobic effect to microbial infection. *Microbes Infect* 2000; 2:391-400; PMID:10817641; [http://dx.doi.org/10.1016/S1286-4579\(00\)00328-2](http://dx.doi.org/10.1016/S1286-4579(00)00328-2)
118. Meyer HGW, Gattermann S. Surface properties of *Staphylococcus saprophyticus*: hydrophobicity, haemagglutination and *Staphylococcus saprophyticus* surface-associated protein (Ssp) represent distinct entities. *APMIS* 1994; 102:538-44; PMID:7917223; <http://dx.doi.org/10.1111/j.1699-0463.1994.tb05203.x>
119. Charville GW, Hetrick EM, Geer CB, Schoenfish MH. Reduced bacterial adhesion to fibrinogen-coated substrates via nitric oxide release. *Biomaterials* 2008; 29:4039-44; PMID:18657857; <http://dx.doi.org/10.1016/j.biomaterials.2008.07.005>
120. Walker SL, Hill JE, Redman JA, Elimelech M. Influence of growth phase on adhesion kinetics of *Escherichia coli* D21g. *Appl Environ Microbiol* 2005; 71:3093-9; PMID:15933006; <http://dx.doi.org/10.1128/AEM.71.6.3093-3099.2005>
121. Kuntiya A, Nicoletta C, Pyle L, Poosaran N. Effect of sodium chloride on cell surface hydrophobicity and formation of biofilm in membrane bioreactor. *Songklanakarin J Sci Technol* 2005; 27:1073-82.
122. Hussain M, Wilcox MH, White PJ, Faulkner MK, Spencer RC. Importance of medium and atmosphere type to both slime production and adherence by coagulase-negative staphylococci. *J Hosp Infect* 1992; 20:173-84; PMID:1348772; [http://dx.doi.org/10.1016/0195-6701\(92\)90085-Z](http://dx.doi.org/10.1016/0195-6701(92)90085-Z)
123. Xu LC, Siedlecki CA. Effects of surface wettability and contact time on protein adhesion to biomaterial surfaces. *Biomaterials* 2007; 28:3273-83; PMID:17466368; <http://dx.doi.org/10.1016/j.biomaterials.2007.03.032>

124. Luensmann D, Jones L. Albumin adsorption to contact lens materials: a review. *Cont Lens Anterior Eye* 2008; 31:179-87; PMID:18603467; <http://dx.doi.org/10.1016/j.clae.2008.05.004>
125. Khoo X, O'Toole GA, Nair SA, Snyder BD, Kenan DJ, Grinstaff MW. *Staphylococcus aureus* resistance on titanium coated with multivalent PEGylated-peptides. *Biomaterials* 2010; 31:9285-92; PMID:20863561; <http://dx.doi.org/10.1016/j.biomaterials.2010.08.031>
126. Tang H, Wang A, Liang X, Cao T, Salley SO, McAllister JP, 3rd, et al. Effect of surface proteins on *Staphylococcus epidermidis* adhesion and colonization on silicone. *Colloids Surf B Biointerfaces* 2006; 51:16-24; PMID:16806854; <http://dx.doi.org/10.1016/j.colsurfb.2006.04.011>
127. Arciola CR, Bustanji Y, Conti M, Campoccia D, Baldassarri L, Samorì B, et al. *Staphylococcus epidermidis*-fibronectin binding and its inhibition by heparin. *Biomaterials* 2003; 24:3013-9; PMID:12895573; [http://dx.doi.org/10.1016/S0142-9612\(03\)00133-9](http://dx.doi.org/10.1016/S0142-9612(03)00133-9)
128. Holmes SD, May K, Johansson V, Markey F, Critchley IA. Studies on the interaction of *Staphylococcus aureus* and *Staphylococcus epidermidis* with fibronectin using surface Plasmon resonance (BIAcore). *J Microbiol Methods* 1997; 28:77-84; [http://dx.doi.org/10.1016/S0167-7012\(96\)00967-0](http://dx.doi.org/10.1016/S0167-7012(96)00967-0)
129. Henderson B, Nair S, Pallas J, Williams MA. Fibronectin: a multidomain host adhesion targeted by bacterial fibronectin-binding proteins. *FEMS Microbiol Rev* 2011; 35:147-200; PMID:20695902; <http://dx.doi.org/10.1111/j.1574-6976.2010.00243.x>
130. Williams RJ, Henderson B, Nair SP. *Staphylococcus aureus* fibronectin binding proteins A and B possess a second fibronectin binding region that may have biological relevance to bone tissues. *Calcif Tissue Int* 2002; 70:416-21; PMID:12055657; <http://dx.doi.org/10.1007/s00223-001-2073-z>
131. Williams RJ, Henderson B, Sharp LJ, Nair SP. Identification of a fibronectin-binding protein from *Staphylococcus epidermidis*. *Infect Immun* 2002; 70:6805-10; PMID:12438356; <http://dx.doi.org/10.1128/IAI.70.12.6805-6810.2002>
132. Buck AW, Fowler VG, Jr., Yongsunthorn R, Liu J, DiBartola AC, Que YA, et al. Bonds between fibronectin and fibronectin-binding proteins on *Staphylococcus aureus* and *Lactococcus lactis*. *Langmuir* 2010; 26:10764-70; PMID:20218549; <http://dx.doi.org/10.1021/la100549u>
133. Fowler T, Wann ER, Joh D, Johansson S, Foster TJ, Höök M. Cellular invasion by *Staphylococcus aureus* involves a fibronectin bridge between the bacterial fibronectin-binding MSCRAMMs and host cell β 1 integrins. *Eur J Cell Biol* 2000; 79:672-9; PMID:11089915; <http://dx.doi.org/10.1078/0171-9335-00104>
134. Peacock SJ, Day NP, Thomas MG, Berendt AR, Foster TJ. Clinical isolates of *Staphylococcus aureus* exhibit diversity in fmb genes and adhesion to human fibronectin. *J Infect* 2000; 41:23-31; PMID:10942636; <http://dx.doi.org/10.1053/jinf.2000.0657>
135. Schwarz-Linek U, Höök M, Potts JR. Fibronectin-binding proteins of gram-positive cocci. *Microbes Infect* 2006; 8:2291-8; PMID:16782385; <http://dx.doi.org/10.1016/j.micinf.2006.03.011>
136. Rohde H, Frankenberger S, Zähringer U, Mack D. Structure, function and contribution of polysaccharide intercellular adhesin (PIA) to *Staphylococcus epidermidis* biofilm formation and pathogenesis of biomaterial-associated infections. *Eur J Cell Biol* 2010; 89:103-11; PMID:19913940; <http://dx.doi.org/10.1016/j.ejcb.2009.10.005>
137. Christner M, Franke GC, Schommer NN, Wendt U, Wegert K, Pehle P, et al. The giant extracellular matrix-binding protein of *Staphylococcus epidermidis* mediates biofilm accumulation and attachment to fibronectin. *Mol Microbiol* 2010; 75:187-207; PMID:19943904; <http://dx.doi.org/10.1111/j.1365-2958.2009.06981.x>
138. Kinnari TJ, Peltonen LI, Kuusela P, Kivilahti J, Kõnönen M, Jero J. Bacterial adherence to titanium surface coated with human serum albumin. *Otol Neurotol* 2005; 26:380-4; PMID:15891637; <http://dx.doi.org/10.1097/01.mao.0000169767.85549.87>
139. Brokke P, Dankert J, Carballo J, Feijen J. Adherence of coagulase-negative staphylococci onto polyethylene catheters in vitro and in vivo: a study on the influence of various plasma proteins. *J Biomater Appl* 1991; 5:204-26; PMID:2013835; <http://dx.doi.org/10.1177/088532829100500305>
140. Reynolds EC, Wong A. Effect of adsorbed protein on hydroxyapatite zeta potential and *Streptococcus mutans* adherence. *Infect Immun* 1983; 39:1285-90; PMID:6301991
141. An YH, Bradley J, Powers DL, Friedman RJ. The prevention of prosthetic infection using a cross-linked albumin coating in a rabbit model. *J Bone Joint Surg Br* 1997; 79:816-9; PMID:9331043; <http://dx.doi.org/10.1302/0301-620X.79B5.7228>
142. del Prado G, Ruiz V, Naves P, Rodríguez-Cerrato V, Soriano F, del Carmen Ponte M. Biofilm formation by *Streptococcus pneumoniae* strains and effects of human serum albumin, ibuprofen, N-acetyl-L-cysteine, amoxicillin, erythromycin, and levofloxacin. *Diagn Microbiol Infect Dis* 2010; 67:311-8; PMID:20638597; <http://dx.doi.org/10.1016/j.diagmicrobio.2010.03.016>
143. Naves P, del Prado G, Huelves L, Rodríguez-Cerrato V, Ruiz V, Ponte MC, et al. Effects of human serum albumin, ibuprofen and N-acetyl-L-cysteine against biofilm formation by pathogenic *Escherichia coli* strains. *J Hosp Infect* 2010; 76:165-70; PMID:20615578; <http://dx.doi.org/10.1016/j.jhin.2010.05.011>
144. Tegoulia VA, Cooper SL. *Staphylococcus aureus* adhesion to self-assembled monolayers: effect of surface chemistry and fibrinogen presence. *Col Surf B: Biointerf* 2002; 24:217-28; [http://dx.doi.org/10.1016/S0927-7765\(01\)00240-5](http://dx.doi.org/10.1016/S0927-7765(01)00240-5)
145. Herrmann M, Vaudaux PE, Pittet D, Auckenthaler R, Lew PD, Schumacher-Perdreau F, et al. Fibronectin, fibrinogen, and laminin act as mediators of adherence of clinical staphylococcal isolates to foreign material. *J Infect Dis* 1988; 158:693-701; PMID:3171224; <http://dx.doi.org/10.1093/infdis/158.4.693>
146. Arciola CR, Campoccia D, Gamberini S, Donati ME, Montanaro L. Presence of fibrinogen-binding adhesin gene in *Staphylococcus epidermidis* isolates from central venous catheters-associated and orthopaedic implant-associated infections. *Biomaterials* 2004; 25:4825-9; PMID:15120529; <http://dx.doi.org/10.1016/j.biomaterials.2003.11.056>
147. Baumgartner JN, Cooper SL. Influence of thrombus components in mediating *Staphylococcus aureus* adhesion to polyurethane surfaces. *J Biomed Mater Res* 1998; 40:660-70; PMID:9599043; [http://dx.doi.org/10.1002/\(SICI\)1097-4636\(19980615\)40:4<660::AID-JBM18>3.0.CO;2-J](http://dx.doi.org/10.1002/(SICI)1097-4636(19980615)40:4<660::AID-JBM18>3.0.CO;2-J)
148. Pei L, Flock JI. Functional study of antibodies against a fibronectin-binding protein in *Staphylococcus epidermidis* adherence to polyethylene catheters. *J Infect Dis* 2001; 184:52-5; PMID:11398109; <http://dx.doi.org/10.1086/321003>
149. Patti JM, Allen BL, McGavin MJ, Höök M. MSCRAMM-mediated adherence of microorganisms to host tissues. *Annu Rev Microbiol* 1994; 48:585-617; PMID:7826020; <http://dx.doi.org/10.1146/annurev.mi.48.100194.003101>
150. Elgalal I, Foster HA. Comparison of adhesion of wound isolates of *Staphylococcus aureus* to immobilized proteins. *J Appl Microbiol* 2003; 94:413-20; PMID:12588550; <http://dx.doi.org/10.1046/j.1365-2672.2003.01858.x>
151. Pei L, Arvholm IL, Lonnie L, Flock JI. GST-Fbe can recognize B-chains of fibrin(ogen) on explanted materials. *J Chromatogr B Analyt Technol Biomed Life Sci* 2003; 86:319-25; [http://dx.doi.org/10.1016/S1570-0232\(02\)00744-4](http://dx.doi.org/10.1016/S1570-0232(02)00744-4)
152. Taylor FB, Jr., Wada H, Kinasewitz G. Description of compensated and uncompensated disseminated intravascular coagulation (DIC) responses (non-overt and overt DIC) in baboon models of intravenous and intraperitoneal *Escherichia coli* sepsis and in the human model of endotoxemia: toward a better definition of DIC. *Crit Care Med* 2000; 28(Suppl):S12-9; PMID:11007191; <http://dx.doi.org/10.1097/00003246-200009001-00004>
153. Tedjo C, Neoh KG, Kang ET, Fang N, Chan V. Bacteria-surface interaction in the presence of proteins and surface attached poly(ethylene glycol) methacrylate chains. *J Biomed Mater Res A* 2007; 82:479-91; PMID:17295255; <http://dx.doi.org/10.1002/jbm.a.31172>
154. Lopes JD, dos Reis M, Brentani RR. Presence of laminin receptors in *Staphylococcus aureus*. *Science* 1985; 229:275-7; PMID:3160113; <http://dx.doi.org/10.1126/science.3160113>
155. Wang IW, Anderson JM, Marchant RE. *Staphylococcus epidermidis* adhesion to hydrophobic biomedical polymer is mediated by platelets. *J Infect Dis* 1993; 167:329-36; PMID:8421167; <http://dx.doi.org/10.1093/infdis/167.2.329>
156. Benson DE, Burns GL, Mohammad SF. Effect of plasma on adhesion of biofilm forming *Pseudomonas aeruginosa* and *Staphylococcus epidermidis* to fibrin substrate. *Trans Am Soc Artif Intern Organs* 1996; 42:M655-60; <http://dx.doi.org/10.1097/00002480-199609000-00069>
157. Ardehali R, Shi L, Janatova J, Mohammad SF, Burns GL. The inhibitory activity of serum to prevent bacterial adhesion is mainly due to apo-transferrin. *J Biomed Mater Res A* 2003; 66:21-8; PMID:12833427; <http://dx.doi.org/10.1002/jbm.a.10493>
158. Ubbink J, Schär-Zammaretti P. Probing bacterial interactions: integrated approaches combining atomic force microscopy, electron microscopy and biophysical techniques. *Micron* 2005; 36:293-320; PMID:15857770; <http://dx.doi.org/10.1016/j.micron.2004.11.005>
159. Heilmann C, Schweitzer O, Gerke C, Vanittanakom N, Mack D, Götz F. Molecular basis of intercellular adhesion in the biofilm-forming *Staphylococcus epidermidis*. *Mol Microbiol* 1996; 20:1083-91; PMID:8809760; <http://dx.doi.org/10.1111/j.1365-2958.1996.tb02548.x>
160. O'Gara JP, Humphreys H. *Staphylococcus epidermidis* biofilms: importance and implications. *J Med Microbiol* 2001; 50:582-7; PMID:11444767
161. Götz F. *Staphylococcus* and biofilms. *Mol Microbiol* 2002; 43:1367-78; PMID:11952892; <http://dx.doi.org/10.1046/j.1365-2958.2002.02827.x>
162. Perrin C, Briandet R, Jubelin G, Lejeune P, Mandrand-Berthelot M-A, Rodrigue A, et al. Nickel promotes biofilm formation by *Escherichia coli* K-12 strains that produce curli. *Appl Environ Microbiol* 2009; 75:1723-33; PMID:19168650; <http://dx.doi.org/10.1128/AEM.02171-08>
163. Bagge N, Ciofu O, Skovgaard LT, Høiby N. Rapid development in vitro and in vivo of resistance to ceftazidime in biofilm-growing *Pseudomonas aeruginosa* due to chromosomal beta-lactamase. *APMIS* 2000; 108:589-600; PMID:11110047; <http://dx.doi.org/10.1034/j.1600-0463.2000.d01-102.x>
164. Xu KD, McFeters GA, Stewart PS. Biofilm resistance to antimicrobial agents. *Microbiology* 2000; 146:547-9; PMID:10746758

165. Chandra J, Mukherjee PK, Leidich SD, Faddoul FF, Hoyer LL, Douglas LJ, et al. Antifungal resistance of candidal biofilms formed on denture acrylic *in vitro*. J Dent Res 2001; 80:903-8; PMID:11379893; <http://dx.doi.org/10.1177/00220345010800031101>
166. Beech IB, Smith JR, Steele AA, Penegar I, Campbell SA. The use of atomic force microscopy for studying interactions of bacterial biofilms with surfaces. Col Surf B: Biointerf 2002; 23:231-47; [http://dx.doi.org/10.1016/S0927-7765\(01\)00233-8](http://dx.doi.org/10.1016/S0927-7765(01)00233-8)
167. Otto K. Biophysical approaches to study the dynamic process of bacterial adhesion. Res Microbiol 2008; 159:415-22; PMID:18550342; <http://dx.doi.org/10.1016/j.resmic.2008.04.007>
168. Welch K, Cai Y, Strømme M. A Method for Quantitative Determination of Biofilm Viability. J Funct Biomater 2012; 3:418-31; <http://dx.doi.org/10.3390/jfb3020418>
169. Peeters E, Nelis HJ, Coenye T. Comparison of multiple methods for quantification of microbial biofilms grown in microtiter plates. J Microbiol Methods 2008; 72:157-65; PMID:18155789; <http://dx.doi.org/10.1016/j.mimet.2007.11.010>
170. Extremina CI, Costa L, Aguiar AI, Peixe L, Fonseca AP. Optimization of processing conditions for the quantification of enterococci biofilms using microtitre-plates. J Microbiol Methods 2011; 84:167-73; PMID:21081140; <http://dx.doi.org/10.1016/j.mimet.2010.11.007>
171. Stepanović S, Vuković D, Hola V, Di Bonaventura G, Djukić S, Cirković I, et al. Quantification of biofilm in microtiter plates: overview of testing conditions and practical recommendations for assessment of biofilm production by staphylococci. APMIS 2007; 115:891-9; PMID:17696944; http://dx.doi.org/10.1111/j.1600-0463.2007.apm_630.x
172. Heikens E, Bonten MJM, Willems RJL. Enterococcal surface protein Esp is important for biofilm formation of *Enterococcus faecium* E1162. J Bacteriol 2007; 189:8233-40; PMID:17827282; <http://dx.doi.org/10.1128/JB.01205-07>
173. LaPlante KL, Mermel LA. In vitro activities of telavancin and vancomycin against biofilm-producing *Staphylococcus aureus*, *S. epidermidis*, and *Enterococcus faecalis* strains. Antimicrob Agents Chemother 2009; 53:3166-9; PMID:19451302; <http://dx.doi.org/10.1128/AAC.01642-08>
174. Kreander K, Vuorela P, Tammela P. A rapid screening method for detecting active compounds against erythromycin-resistant bacterial strains of Finnish origin. Folia Microbiol (Praha) 2005; 50:487-93; PMID:16681145; <http://dx.doi.org/10.1007/BF02931435>
175. Sandberg M, Määttänen A, Peltonen J, Vuorela PM, Fallarero A. Automating a 96-well microtitre plate model for *Staphylococcus aureus* biofilms: an approach to screening of natural antimicrobial compounds. Int J Antimicrob Agents 2008; 32:233-40; PMID:18640013; <http://dx.doi.org/10.1016/j.ijantimicag.2008.04.022>
176. An YH, Friedman RJ. Laboratory methods for studies of bacterial adhesion. J Microbiol Methods 1997; 30:141-52; [http://dx.doi.org/10.1016/S0167-7012\(97\)00058-4](http://dx.doi.org/10.1016/S0167-7012(97)00058-4)
177. An YH, Friedman RJ, Draughn RA, Smith EA, John JF, Ambrosio L, et al. Biomaterials and Biocompatibility Studies. In: Wise DL, Trantolo DJ, Altobelli DE, Yaszemski MJ, Gresser JD, eds. Human Biomaterials Applications. Totowa, NJ: Humana Press Inc., 1996:1-59.
178. Whitehead KA, Smith LA, Verran J. The detection and influence of food soils on microorganisms on stainless steel using scanning electron microscopy and epifluorescence microscopy. Int J Food Microbiol 2010; 141(Suppl 1):S125-33; PMID:20153071; <http://dx.doi.org/10.1016/j.ijfoodmicro.2010.01.012>
179. Weir E, Lawlor A, Whelan A, Regan F. The use of nanoparticles in antimicrobial materials and their characterization. Analyst (Lond) 2008; 133:835-45; <http://dx.doi.org/10.1039/b715532h>
180. Wirtanen G, Salo S, Helander IM, Mattila-Sandholm T. Microbiological methods for testing disinfectant efficiency on *Pseudomonas* biofilm. Colloids Surf B Biointerfaces 2001; 20:37-50; PMID:11084307; [http://dx.doi.org/10.1016/S0927-7765\(00\)00173-9](http://dx.doi.org/10.1016/S0927-7765(00)00173-9)
181. Bogner A, Jouneau PH, Thollet G, Basset D, Gauthier C. A history of scanning electron microscopy developments: towards "wet-STEM" imaging. Micron 2007; 38:390-401; PMID:16990007; <http://dx.doi.org/10.1016/j.micron.2006.06.008>
182. Kodjikian L, Burillon C, Lina G, Roques C, Pellon G, Freney J, et al. Biofilm formation on intraocular lenses by a clinical strain encoding the ica locus: a scanning electron microscopy study. Invest Ophthalmol Vis Sci 2003; 44:4382-7; PMID:14507883; <http://dx.doi.org/10.1167/iovs.03-0185>
183. Pajkos A, Vickery K, Cossart Y. Is biofilm accumulation on endoscope tubing a contributor to the failure of cleaning and decontamination? J Hosp Infect 2004; 58:224-9; PMID:15501338; <http://dx.doi.org/10.1016/j.jhin.2004.06.023>
184. Camargo GMPA, Pizzolitto AC, Pizzolitto EL. Biofilm formation on catheters used after cesarean section as observed by scanning electron microscopy. Int J Gynaecol Obstet 2005; 90:148-9; PMID:15964000; <http://dx.doi.org/10.1016/j.ijgo.2005.04.006>
185. Lindsay D, von Holy A. Bacterial biofilms within the clinical setting: what healthcare professionals should know. J Hosp Infect 2006; 64:313-25; PMID:17046102; <http://dx.doi.org/10.1016/j.jhin.2006.06.028>
186. Cook G, Costerton JW, Darouiche RO. Direct confocal microscopy studies of the bacterial colonization in vitro of a silver-coated heart valve sewing cuff. Int J Antimicrob Agents 2000; 13:169-73; PMID:10724020; [http://dx.doi.org/10.1016/S0924-8579\(99\)00120-X](http://dx.doi.org/10.1016/S0924-8579(99)00120-X)
187. Kazama JJ, Gejyo F, Ejiri S, Okada M, Ei I, Arakawa M, et al. Application of confocal laser scanning microscopy to the observation of bone biopsy specimens. Bone 1993; 14:885-9; PMID:8155412; [http://dx.doi.org/10.1016/8756-3282\(93\)90319-6](http://dx.doi.org/10.1016/8756-3282(93)90319-6)
188. Lemon KP, Earl AM, Vlamakis HC, Aguilar C, Kolter R, Spormann AM, et al. Biofilm Development with an Emphasis on *Bacillus subtilis*. In: Romeo T, ed. Bacterial Biofilms. Clifton Rd., NE: Springer, 2008:1-14.
189. Fett WF, Cooke PH. A survey of native microbial aggregates on alfalfa, clover and mung bean sprout cotyledons for thickness as determined by confocal scanning laser microscopy. Food Microbiol 2005; 22:253-9; <http://dx.doi.org/10.1016/j.fm.2004.03.004>
190. Burnett SL, Chen J, Beuchat LR. Attachment of *Escherichia coli* O157:H7 to the surfaces and internal structures of apples as detected by confocal scanning laser microscopy. Appl Environ Microbiol 2000; 66:4679-87; PMID:11055910; <http://dx.doi.org/10.1128/AEM.66.11.4679-4687.2000>
191. Lindsay D, Brözel VS, Mostert JF, von Holy A. Differential efficacy of a chlorine dioxide-containing sanitizer against single species and binary biofilms of a dairy-associated *Bacillus cereus* and a *Pseudomonas fluorescens* isolate. J Appl Microbiol 2002; 92:352-61; PMID:11849365; <http://dx.doi.org/10.1046/j.1365-2672.2002.01538.x>
192. Hug T, Gujer W, Siegrist H. Rapid quantification of bacteria in activated sludge using fluorescence in situ hybridization and epifluorescence microscopy. Water Res 2005; 39:3837-48; PMID:16112167; <http://dx.doi.org/10.1016/j.watres.2005.07.013>
193. Robichon D, Girard J-C, Cenatiempo Y, Cavallier J-F. Atomic force microscopy imaging of dried or living bacteria. C R Acad Sci Paris. Life Sci 1999; 322:687-93.
194. Willing GA, Ibrahim TH, Etzler FM, Neuman RD. New approach to the study of particle-surface adhesion using atomic force microscopy. J Colloid Interface Sci 2000; 226:185-8; PMID:11401364; <http://dx.doi.org/10.1006/jcis.2000.6801>
195. Fang HHP, Chan K-Y, Xu LC. Quantification of bacterial adhesion forces using atomic force microscopy (AFM). J Microbiol Methods 2000; 40:89-97; PMID:10739347; [http://dx.doi.org/10.1016/S0167-7012\(99\)00137-2](http://dx.doi.org/10.1016/S0167-7012(99)00137-2)
196. Beech IB, Smith JR, Steele AA, Penegar I, Campbell SA. The use of atomic force microscopy for studying interactions of bacterial biofilms with surfaces. Col Surf B: Biointerf 2002; 23:231-47; [http://dx.doi.org/10.1016/S0927-7765\(01\)00233-8](http://dx.doi.org/10.1016/S0927-7765(01)00233-8)
197. Boyd RD, Verran J, Jones MV, Bhakoo M. Use of Atomic Force Microscope to determine the effect of substratum surface topography on bacterial adhesion. Langmuir 2002; 18:2343-6; <http://dx.doi.org/10.1021/la011142p>
198. Alonso JL, Goldmann WH. Feeling the forces: atomic force microscopy in cell biology. Life Sci 2003; 72:2553-60; PMID:12672501; [http://dx.doi.org/10.1016/S0024-3205\(03\)00165-6](http://dx.doi.org/10.1016/S0024-3205(03)00165-6)
199. Dufrène YF. Recent progress in the application of atomic force microscopy imaging and force spectroscopy to microbiology. Curr Opin Microbiol 2003; 6:317-23; PMID:12831910; [http://dx.doi.org/10.1016/S1369-5274\(03\)00058-4](http://dx.doi.org/10.1016/S1369-5274(03)00058-4)
200. Sénéchal A, Carrigan SD, Tabrizian M. Probing surface adhesion forces of *Enterococcus faecalis* to medical-grade polymers using atomic force microscopy. Langmuir 2004; 20:4172-7; PMID:15969413; <http://dx.doi.org/10.1021/la035847y>
201. Krishna OD, Kim K, Byun Y. Covalently grafted phospholipid monolayer on silicone catheter surface for reduction in platelet adhesion. Biomaterials 2005; 26:7115-23; PMID:16009416; <http://dx.doi.org/10.1016/j.biomaterials.2005.05.023>
202. Churnside AB, King GM, Perkins TT. Label-free optical imaging of membrane patches for atomic force microscopy. Opt Express 2010; 18:23924-32; PMID:21164738; <http://dx.doi.org/10.1364/OE.18.023924>
203. Erukhimovitch V, Pavlov V, Talyshinsky M, Souprun Y, Huleihel M. FTIR microscopy as a method for identification of bacterial and fungal infections. J Pharm Biomed Anal 2005; 37:1105-8; PMID:15862692; <http://dx.doi.org/10.1016/j.jpba.2004.08.010>
204. Schmitt J, Flemming H. FTIR-spectroscopy in microbial and material analysis. Int Biodeterior Biodegradation 1998; 41:1-11; [http://dx.doi.org/10.1016/S0964-8305\(98\)80002-4](http://dx.doi.org/10.1016/S0964-8305(98)80002-4)
205. Huang WE, Hopper D, Goodacre R, Beckmann M, Singer A, Draper J. Rapid characterization of microbial biodegradation pathways by FT-IR spectroscopy. J Microbiol Methods 2006; 67:273-80; PMID:16737754; <http://dx.doi.org/10.1016/j.mimet.2006.04.009>
206. Amiali NM, Mulvey MR, Sedman J, Louie M, Simor AE, Ismail AA. Rapid identification of coagulase-negative staphylococci by Fourier transform infrared spectroscopy. J Microbiol Methods 2007; 68:236-42; PMID:17049398; <http://dx.doi.org/10.1016/j.mimet.2006.08.010>

207. Amiali NM, Mulvey MR, Sedman J, Simor AE, Ismail AA. Epidemiological typing of methicillin-resistant *Staphylococcus aureus* strains by Fourier transform infrared spectroscopy. *J Microbiol Methods* 2007; 69:146-53; PMID:17316849; <http://dx.doi.org/10.1016/j.mimet.2006.12.022>
208. Lin M, Al-Holy M, Chang SS, Huang Y, Cavinato AG, Kang DH, et al. Rapid discrimination of *Alicyclobacillus* strains in apple juice by Fourier transform infrared spectroscopy. *Int J Food Microbiol* 2005; 105:369-76; PMID:16126293; <http://dx.doi.org/10.1016/j.ijfoodmicro.2005.04.018>
209. Goodacre R, Shann B, Gilbert RJ, Timmins EM, McGovern AC, Alsberg BK, et al. Detection of the dipicolinic acid biomarker in *Bacillus* spores using Curie-point pyrolysis mass spectrometry and Fourier transform infrared spectroscopy. *Anal Chem* 2000; 72: 119-27; PMID:10655643; <http://dx.doi.org/10.1021/ac990661i>
210. Helm D, Labischinski H, Schallehn G, Naumann D. Classification and identification of bacteria by Fourier-transform infrared spectroscopy. *J Gen Microbiol* 1991; 137:69-79; PMID:1710644; <http://dx.doi.org/10.1099/00221287-137-1-69>
211. Maquelin K, Kirschner C, Choo-Smith LP, Ngo-Thi NA, van Vreeswijk T, Stämmeler M, et al. Prospective study of the performance of vibrational spectroscopies for rapid identification of bacterial and fungal pathogens recovered from blood cultures. *J Clin Microbiol* 2003; 41:324-9; PMID:12517868; <http://dx.doi.org/10.1128/JCM.41.1.324-329.2003>
212. Ofek I, Hasty DL, Doyle RJ. Methodological Approaches to Analysis of Adhesins and Adhesion. In: Ofek I, Hasty DL, Doyle RJ, eds. *Bacterial Adhesion to Animal Cells and Tissues*. Washington, DC: ASM Press, 2003:19-40.
213. Timmerman CP, Fleer A, Besnier JM, De Graaf L, Cremers F, Verhoef J. Characterization of a proteinaceous adhesin of *Staphylococcus epidermidis* which mediates attachment to polystyrene. *Infect Immun* 1991; 59:4187-92; PMID:1682256
214. Ahimou F, Paquot M, Jacques P, Thonart P, Rouxhet PG. Influence of electrical properties on the evaluation of the surface hydrophobicity of *Bacillus subtilis*. *J Microbiol Methods* 2001; 45:119-26; PMID:11311397; [http://dx.doi.org/10.1016/S0167-7012\(01\)00240-8](http://dx.doi.org/10.1016/S0167-7012(01)00240-8)
215. Castonguay MH, van der Schaaf S, Koester W, Krooneman J, van der Meer W, Harmsen H, et al. Biofilm formation by *Escherichia coli* is stimulated by synergistic interactions and co-adhesion mechanisms with adherence-proficient bacteria. *Res Microbiol* 2006; 157:471-8; PMID:16376056; <http://dx.doi.org/10.1016/j.resmic.2005.10.003>
216. Li X, Yan Z, Xu J. Quantitative variation of biofilms among strains in natural populations of *Candida albicans*. *Microbiology* 2003; 149:353-62; PMID:12624197; <http://dx.doi.org/10.1099/mic.0.25932-0>
217. Pitts B, Hamilton MA, Zelter N, Stewart PS. A microtiter-plate screening method for biofilm disinfection and removal. *J Microbiol Methods* 2003; 54:269-76; PMID:12782382; [http://dx.doi.org/10.1016/S0167-7012\(03\)00034-4](http://dx.doi.org/10.1016/S0167-7012(03)00034-4)
218. Boulos L, Prévost M, Barbeau B, Coallier J, Desjardins R. LIVE/DEAD BacLight : application of a new rapid staining method for direct enumeration of viable and total bacteria in drinking water. *J Microbiol Methods* 1999; 37:77-86; PMID:10395466; [http://dx.doi.org/10.1016/S0167-7012\(99\)00048-2](http://dx.doi.org/10.1016/S0167-7012(99)00048-2)
219. Whitchurch CB, Tolker-Nielsen T, Ragas PC, Mattick JS. Extracellular DNA required for bacterial biofilm formation. *Science* 2002; 295:1487; PMID:11859186; <http://dx.doi.org/10.1126/science.295.5559.1487>
220. Strathmann M, Wingender J, Flemming HC. Application of fluorescently labelled lectins for the visualization and biochemical characterization of polysaccharides in biofilms of *Pseudomonas aeruginosa*. *J Microbiol Methods* 2002; 50:237-48; PMID:12031574; [http://dx.doi.org/10.1016/S0167-7012\(02\)00032-5](http://dx.doi.org/10.1016/S0167-7012(02)00032-5)
221. Honraet K, Goetghebeur E, Nelis HJ. Comparison of three assays for the quantification of *Candida* biomass in suspension and CDC reactor grown biofilms. *J Microbiol Methods* 2005; 63:287-95; PMID:15936097; <http://dx.doi.org/10.1016/j.mimet.2005.03.014>
222. Honraet K, Nelis HJ. Use of the modified robbins device and fluorescent staining to screen plant extracts for the inhibition of *S. mutans* biofilm formation. *J Microbiol Methods* 2006; 64:217-24; PMID:15979176; <http://dx.doi.org/10.1016/j.mimet.2005.05.005>
223. Sarker SD, Nahar L, Kumarasamy Y. Microtitre plate-based antibacterial assay incorporating resazurin as an indicator of cell growth, and its application in the *in vitro* antibacterial screening of phytochemicals. *Methods* 2007; 42:321-4; PMID:17560319; <http://dx.doi.org/10.1016/j.ymeth.2007.01.006>
224. O'Brien J, Wilson I, Orton T, Pognan F. Investigation of the Alamar Blue (resazurin) fluorescent dye for the assessment of mammalian cell cytotoxicity. *Eur J Biochem* 2000; 267:5421-6; PMID:10951200; <http://dx.doi.org/10.1046/j.1432-1327.2000.01606.x>
225. Pettit RK, Weber CA, Kean MJ, Hoffmann H, Pettit GR, Tan R, et al. Microplate Alamar blue assay for *Staphylococcus epidermidis* biofilm susceptibility testing. *Antimicrob Agents Chemother* 2005; 49:2612-7; PMID:15980327; <http://dx.doi.org/10.1128/AAC.49.7.2612-2617.2005>
226. Unosson E, Cai Y, Jiang X, Löf J, Welch K, Engqvist H. Antibacterial properties of dental luting agents: potential to hinder the development of secondary caries. *Int J Dent* 2012; 2012:529495; PMID:22505901; <http://dx.doi.org/10.1155/2012/529495>
227. Prieto B, Silva B, Lantes O. Biofilm quantification on stone surfaces: comparison of various methods. *Sci Total Environ* 2004; 333:1-7; PMID:15364515; <http://dx.doi.org/10.1016/j.scitotenv.2004.05.003>