FEITENG **LYRA**

BRUSHED ALUMINUM DECORATIVE PANEL

FEITENG

Performance index

		PREMIUM (Alu. Thickness: 0.3mm)	
Panel thickness tolerance	**Units**	**3mm**	**4mm**
Alu thickness tolerance	mm	±0.02	
Alu grade		1100, 3003, 5005	
Composite Panel Size			
Panel weight	kg/m²	≥4.40	≥5.55
Panel length tolerance	mm	±3	
Panel width tolerance	mm	±2	
Panel thickness tolerance	mm	±0.2	
Mechanical Property			
Bending strength	MPa	≥50	
Penetration resistance	KN	≥5	
Shear strength	MPa	≥12	
Tensile strength of Alu	MPa	≥145	
Alu Proof stress(0.2%)	%	≥115	
The elongation of Alu	mm/m	≥2	
Liner thermal expansion	°C⁻¹	≤0.0004	
Thermal deformation temperature	°C	≥85	
180° peel strength	N/mm	≥5	
Heat resistance water	/	No change	
Composite Panel Core			
Core density	g/cm³	1.15~1.20	
Fire Rating Classification		EN13501-1/Class C-s1,d0	
Coating		Polyester	
Coating thickness	μm	Single avg≥16 min≥14; Double avg≥25 min≥23; Third avg≥32 min≥30	
Glossiness	%	≥25	
Coating hardness	/	≥HB	
Acoustic Performance			
Sound absorption factor	α	0.05	
Sound insulation factor	Rw (dB)	25	26
Thermal Performance			
Heat transfer coefficient	W/mK	5.65	5.54

ZHANGJIAGANG FEITENG NEW COMPOSITE MATERIALS CO., LTD.
Specialize in Producing Metal Coating Panel and Composite Panel for 30 Years
www.feitengacp.com