FEITENG **LYRA**

WHITEBOARD MAGNETIC PANEL

FEITENG

Performance index

		PREMIUM (Steel Thickness: 0.3mm)
Panel thickness tolerance	**Units**	**3mm**
Steel thickness tolerance	mm	±0.02
Steel grade		SGCC
Composite Panel Size		
Panel weight	kg/m^2	7.67
Panel length tolerance	mm	±3
Panel width tolerance	mm	±2
Panel thickness tolerance	mm	±0.2
Mechanical Property		
Bending strength	MPa	≥100
Penetration resistance	KN	≥10
Shear strength	MPa	≥30
Flexural Modulus	MPa	≥30000
Thermal expansion coefficient	$°C^{-1}$	≤$1.8x10^{-5}$
Thermal deformation temperature	°C	≥100
180° peel strength	N/mm	≥7.0
Heat resistance water		No change
Resistance to change of temperature		No change
Composite Panel Core		
Core density	g/cm^3	1.15~1.20
Fire Rating Classification		In accordance with GB8624 level B Degree Standard
Coating		Polyester
Coating thickness	μm	Double avg≥25 min≥23
Glossiness	%	≥80
Coating hardness	/	≥HB

ZHANGJIAGANG FEITENG NEW COMPOSITE MATERIALS CO., LTD.

Specialize in Producing Metal Coating Panel and Composite Panel for 30 Years

www.feitengacp.com