FEITENG **DIPPER**

FEITENG

Performance index

		Alu. Thickness: 0.5mm	
Panel thickness tolerance	**Units**	**4mm**	
Alu thickness tolerance	mm	±0.02	
Alu grade		1100, 3003, 5005	
Composite Panel Size			
Panel weight	kg/m²	≥7.5	≥8.7
Panel length tolerance	mm	±3	
Panel width tolerance	mm	±2	
Panel thickness tolerance	mm	±0.2	
Mechanical Property			
Bending strength	MPa	≥100	
Penetration resistance	KN	≥7	
Shear strength	MPa	≥22	
Tensile strength of Alu	MPa	R_m≥130	
0.2% yield stress	MPa	$R_{P0.2}$≥90	
The elongation of Alu	MPa	A_{50}≥4	
Liner thermal expansion	%	≤0.0004	
Resistance to temperature difference	°C-1	≥100	
Flexural elastic modulus	°C	≥2.0*10⁴	
Peeling force	N/mm	Average≥110, Minimum≥100	
Alloy state	/	H24	
Composite Panel Core		FR	A2
Core density	g/cm³	1.55~1.60	1.95~2.00
Fire Rating Classification		EN13501-1/Class B-s1,d0	EN13501-1/Class A2-s1,d0
Coating		PVDF	
Coating thickness	μm	Single avg≥16 min≥14; Double avg≥25 min≥23; Third avg≥32 min≥30	
Glossiness	%	≥25	
Coating hardness	/	≥HB	
Acoustic Performance			
Sound absorption factor	α	0.05	
Sound insulation factor	dB	26	
Thermal Performance			
Heat transfer coefficient	W/mK	5.53	5.8

ZHANGJIAGANG FEITENG NEW COMPOSITE MATERIALS CO., LTD.
Specialize in Producing Metal Coating Panel and Composite Panel for 30 Years
www.feitengacp.com