FEITENG **LYRA**

FR DIGITAL PRINTING & SIGNAGE PANELS

FEITENG

Performance index

		FR LITE (Alu. Thickness: 0.2mm)	
Panel thickness	**Unit**	**3mm**	**4mm**
Alu thickness tolerance	mm	±0.02	
Alu grade		1100	
Composite Panel Size			
Panel weight	Kg/m²	≥4.85	≥6.30
Panel length tolerance	mm	±3	
Panel width tolerance	mm	±2	
Panel thickness tolerance	mm	±0.2	
Mechanical Property			
Bending strength	MPa	≥60	
Penetration resistance	KN	≥5	
Shear strength	MPa	≥15	
Tensile strength of Alu	MPa	≥145	
Alu Proof stress(0.2%)	MPa	≥115	
The elongation of Alu	%	≥2	
Liner thermal expansion	mm/m/°C^{-1}	≤0.0004	
Thermal deformation temperature	°C	≥95	
180° peel strength	N/mm	≥4	
Heat resistance water	/	No change	
Composite Panel Core			
Core density		1.40~1.45	
Fire Rating Classification		EN13501-1 / Class B-s1,d0	
Coating		Polyester	
Coating thickness	μm	Single avg≥16 min≥14; Double avg≥25 min≥23; Third avg≥32 min≥30	
Glossiness	%	≥25	
Coating hardness	/	≥HB	
Acoustic Performance			
Sound absorption factor	α	0.05	
Sound insulation factor	dB	25	26
Thermal Performance			
Heat transition coefficient	W/mK	5.68	5.58

ZHANGJIAGANG FEITENG NEW COMPOSITE MATERIALS CO., LTD.
Specialize in Producing Metal Coating Panel and Composite Panel for 30 Years
www.feitengacp.com