Holograph notes on design, weight and assay of thirteen mainly German coins 1685-96.

Author: Isaac Newton

Source: MINT 19/2/185, National Archives, Kew, Richmond, Surrey, UK

<185r>

Two half Guldens of the Duke of Hannover. About S^t Andrew Sanctus Andreas Revivisceus 1692 And about the Dukes arms Ernestus Augustus D. G. Eps Osn D. BR. et Lune, And underneath Fein $\frac{1}{3}$ silb. Weight of one 4^{dw^t} 4^{gr} of the other 4^{dwt} 6^{gr} of both together 8^{dwt} 10^{gr} . No worn. Better $17\frac{1}{2}^{dw^t}$.

A $\frac{1}{2}$ Gulden of Brandenburgh 1692. The Electors head & about it. Frid. III D. G. M. B. S. R. I. AC & E. And about his arms crownd Moneta nova $\frac{1}{3}$ Brandenb. Weight 5^{dw^t} 13^{gr} . Not worn. Worse 2^{oz} . 3^{dwt} . Standard 4. 12. 5.

A coyn of the Duke of Zell. On on side XVI Guite Grosch I.I.I & about it Georg. Wilh. D. G. Dux Bruns & Lun. And on the Reverse a Running horse & about him Quo fas et Gloria Ducunt 1694. Weight 11^{dw} 1^{gr} . Not worn. Worse 2^{oz} . 4^{dw} . Standard 8^{dwt} 20. 10.

A coyn I think of the Bishop of Hildesheim. On one side 24 Marien Grosch 1684 & about it HILDESHEIMISCHSTADTGELT. On the other side about a coat of Arms Da pacem domine in diebus nostris. Weight $11^{\text{dw}^{\text{t}}}$ 21^{gr} . Worn 1^{gr} . Standard 9. 17. 16 Worse 2^{oz} $\frac{1}{2}^{\text{dw}^{\text{t}}}$.

About the Elector of Brandenburgs head Frid. Wilh. D. G. M. B. Elec. 1661 & about his arms Moneta nova Arg. Reins. $\frac{2}{3}$ Weight $12^{\text{dw}^{\text{t}}}$ $3\frac{1}{2}$ gr. Worn 0 gr $\frac{1}{2}$. Worse 2 ounces 3 dwt. standard 9. 19. 9.

About the gate of a city with two towers — is Magdeburg 1675. On the other side Verbum Domini manet in æternum $\frac{2}{3}$ Worn 3 or 4^{gr} Weight 11^{dw^t} 14^{gr} . Worse 2^{oz} . 1^{dwt} . Standard 9. 11. 2

Two pieces of the Bishop of Leige. About his head Ioan. Lud. D. G. EP. et Prin. Leo. About his arms Dux Bull. Mar. Fra, Comes Los. Hor. $16\frac{90}{93}$. Weight $\frac{17.21}{17.21\frac{1}{2}}$. Worn $\frac{2}{2\frac{1}{2}}$. grains. Assay $\frac{11\frac{1}{2}}{13}$ dwt worse

A four Marck piece of Sweden 1693. Weight $13^{\mathrm{dw}^{\mathrm{t}}}$ 5^{gr} . worse 2^{oz} $18^{\mathrm{dw}^{\mathrm{t}}}$. standard 9. 18. 5

Another 169{illeg} Weight 13. $5\frac{1}{3}$ gr. standard 9. 18. 12.

28 Styvers of Groiningen 1699 Weight 11^{dwt} 6^{gr}. Worse 2^{oz} 9^{dwt}.

A Doller or two Gulden piece of the Duke of Hannover. On one side about S^t Andrew Sanctus Andreas revivisceus. On the other side about the Dukes arms Ern. Aug. D. G. BR et L S R I. El. Ep. {O}. Worse 07^{dw} . Weight 18^{dw} . 18^{gr} .

A Gulden of the Duke of Saxony 1696. About his head Frider. Augustus D. G. Dux Sax. I. C. M. A & W. About his arms Sac. Rom. Imp. Archim. & Elector 1696. $\frac{2}{3}$ Weight $11^{\text{dw}^{\text{t}}}$. 3^{gr} . Worse 2^{oz} . $1^{\text{dw}^{\text{t}}}$. Standard 9. 1. 14.