

GPT

Buyer Name: C&A

TEST	TEST METHOD	MINIMUM STANDARD
STRENGTH		
Seam force	ISO 13935-2 : 1999	260 N for $\geq 340 \text{ g/m}^2$ 200 N for $\geq 200 \text{ g/m}^2$ and $< 340 \text{ g/m}^2$ 200 N for all corduroy trousers 140 N for $< 200 \text{ g/m}^2$ 80 N for lining
Seam slippage	ISO 13936-1 : 2004	max. opening 6 mm at load of 160 N for $\geq 340 \text{ g/m}^2$ max. opening 6 mm at load of 120 N for $\geq 200 \text{ g/m}^2$ and $< 340 \text{ g/m}^2$ max. opening 6 mm at load of 100 N for $< 200 \text{ g/m}^2$ and for all corduroy trousers max. opening 6 mm at load of 80 N for lining
Tear force	ISO 13937-1: 2000	20 N for $\geq 340 \text{ g/m}^2$ 15 N for $\geq 200 \text{ g/m}^2$ and $< 340 \text{ g/m}^2$ 12 N for $< 200 \text{ g/m}^2$ and for all corduroy trousers 8N for lining
Tensile force	ISO 13934-2: 1999	300 N for $\geq 340 \text{ g/m}^2$ 230 N for $\geq 200 \text{ g/m}^2$ and $< 340 \text{ g/m}^2$ 200 N for all trousers $< 200 \text{ g/m}^2$ and for all corduroy trousers 140 N for lining

Buyer Name: Varner

Attachment strength EN 71-1	Children's wear size 50 - 128 Accessories $\geq 6\text{mm}$	90N	Under maximum force for 10 sec.
	Children's wear size 134 - 164 Accessories $\geq 6\text{mm}$	70N	
	Children's wear size 50 - 164 Accessories $< 6\text{mm}$	50N	
	General, fabric weighing $< 100\text{g/m}^2$	50N	
	General, fabric weighing $> 100\text{g/m}^2$	70N	
Tensile strength ISO 13934-2	$< 160\text{g/m}^2$	120N	Minimum Force before breakage. Test applied to woven garments
	160-250g/m2	150N	
	$> 250\text{g/m}^2$	200N	
Tear strength ISO 13937-2	Woven tops / blouses / dresses / fancy jackets	$> 10\text{N}$	The requirement applies to lowest received value, not the mean value.
	Woven fabrics, bottoms	$> 15\text{N}$	
	Woven fabrics, jackets, coats & outerwear	150 – 200gsm: $> 15\text{N}$ 200 – 400gsm: $> 20\text{N}$	
	Denim, General	$> 20\text{N}$	
	Denim, Treated (test before and after wash)	$> 15\text{N}$	
Bursting strength ISO 13938-2	Test applied to jersey garments	250kPa	Minimum force before bursting.
Seam slippage ISO 13936-2	Woven fabrics $\leq 220\text{g/m}^2$ - load applied 60N	Seam opening $\leq 6\text{mm}$	Applied to the garment
	Woven fabrics $\geq 220\text{g/m}^2$ - load applied 120N		

GPT

GPT

GPT